INFORMATION TO USERS

This was produced from a copy of a document sent to us for microfilming. While the most advanced technological means to photograph and reproduce this document have been used, the quality is heavily dependent upon the quality of the material submitted.

The following explanation of techniques is provided to help you understand markings or notations which may appear on this reproduction.

1. The sign or "target" for pages apparently lacking from the document photographed is "Missing Page(s)". If it was possible to obtain the missing page(s) or section, they are spliced into the film along with adjacent pages. This may have necessitated cutting through an image and duplicating adjacent pages to assure you of complete continuity.
2. When an image on the film is obliterated with a round black mark it is an indication that the film inspector noticed either blurred copy because of movement during exposure, or duplicate copy. Unless we meant to delete copyrighted materials that should not have been filmed, you will find a good image of the page in the adjacent frame.
3. When a map, drawing or chart, etc., is part of the material being photographed the photographer has followed a definite method in "sectioning" the material. It is customary to begin filming at the upper left hand corner of a large sheet and to continue from left to right in equal sections with small overlaps. If necessary, sectioning is continued again—beginning below the first row and continuing on until complete.
4. For any illustrations that cannot be reproduced satisfactorily by xerography, photographic prints can be purchased at additional cost and tipped into your xerographic copy. Requests can be made to our Dissertations Customer Services Department.
5. Some pages in any document may have indistinct print. In all cases we have filmed the best available copy.

**University
Microfilms
International**

300 N. ZEEB ROAD, ANN ARBOR, MI 48106
18 BEDFORD ROW, LONDON WC1R 4EJ, ENGLAND

7919601

KIRKPATRICK, JOHN PAXTON
DYNAMIC RHEOLOGICAL STUDIES OF COAGULATION
AND FIBRINOLYSIS.

RICE UNIVERSITY, PH.D., 1979

University
Microfilms
International

300 N. ZEEB ROAD, ANN ARBOR, MI 48106

PLEASE NOTE:

In all cases this material has been filmed in the best possible way from the available copy. Problems encountered with this document have been identified here with a check mark ☒.

1. Glossy photographs _____
2. Colored illustrations _____
3. Photographs with dark background _____
4. Illustrations are poor copy _____
5. Print shows through as there is text on both sides of page _____
6. Indistinct, broken or small print on several pages ☒ throughout

7. Tightly bound copy with print lost in spine _____
8. Computer printout pages with indistinct print _____
9. Page(s) _____ lacking when material received, and not available
from school or author _____
10. Page(s) _____ seem to be missing in numbering only as text
follows _____
11. Poor carbon copy _____
12. Not original copy, several pages with blurred type _____
13. Appendix pages are poor copy _____
14. Original copy with light type _____
15. Curling and wrinkled pages _____
16. Other _____

RICE UNIVERSITY

DYNAMIC RHEOLOGICAL STUDIES OF
COAGULATION AND FIBRINOLYSIS

by

John Paxton Kirkpatrick

A THESIS SUBMITTED
IN PARTIAL FULFILLMENT OF THE
REQUIREMENTS FOR THE DEGREE

DOCTOR OF PHILOSOPHY

APPROVED, THESIS COMMITTEE:

L. V. McIntire, Chairman
Professor in Chemical Engrg.

J. D. Hellums, Professor of
Chemical Engineering

W. G. Characklis, Professor of
Environmental Sci-Engrg.

*J. L. Moake, M.D.
Adjunct Professor of Medicine

*Dept. of Hematology, Univ. of
Texas Medical School-Houston

Houston, Texas
May, 1979

ABSTRACT

DYNAMIC RHEOLOGICAL STUDIES OF COAGULATION AND FIBRINOLYSIS

by

John Paxton Kirkpatrick

Dynamic measurements of the mechanical properties of recalcified plasma were performed using a Weissenberg rheogoniometer in the oscillatory mode with a parallel platen geometry. This technique yields the dynamic shear storage and loss moduli (G' , G'') of the material.

Coagulation occurred earlier and the maximum storage modulus ($G'_{\max}$) was an order of magnitude greater for recalcified PRP than PFP. While $G'_{\max}$ was linearly proportional to fibrinogen concentration in PFP, a 50 percent decrease in fibrinogen concentration in PRP resulted in a 20-25 percent reduction in $G'_{\max}$.

$G'_{\max}$ of PRP was depressed in the presence of agents which inhibit platelet metabolism (KCN + 2-deoxy-D-glucose), elevate intraplatelet cyclic AMP levels (Dibutyryl cAMP), or disrupt the contractile mechanism (cytochalasin B). Cytochalasin B inhibited clot retraction, also.

At concentration of cytochalasin B where $G'_{\max}$ and clot retraction were reduced, ADP-induced and collagen-induced platelet aggregation and serotonin release were not impaired. It appears that the release reaction is not

absolutely dependent on cytochalasin B - sensitive microfilaments.

Fibrinogen degradation products (FDP) were produced by incubation of PFP with streptokinase (SK). Equal volume mixtures of fresh PFP and PFP incubated with 100 u/ml SK exhibited increased thrombin times. Fibrin monomer aggregation tests indicated that FDP inhibit the thrombin-fibrinogen interaction. The mixtures containing the 3 minute incubation digest showed significantly higher $G'_{\max}$ than control samples. The decrease in $G'_{\max}$ or thrombin time was seen at 10 u/ml SK.

Equal volume mixtures of fresh PRP and PFP incubated previously with 100 u/ml of SK showed decreased $G'_{\max}$ for all incubation periods. The reduction in $G'_{\max}$ (60-70%) was significantly greater than that caused by a decreased fibrinogen concentration. Tests with cytochalasin B and FDP suggest the decrease in clot strength was due to an inhibition of the fibrin-platelet interaction. Platelet aggregation to ADP, thrombin, and polymerizing fibrin was not impaired in the presence of FDP.

SK added to coagulating plasma had little effect at a concentration of 10 u/ml SK but resulted in complete and rapid lysis at 20 u/ml. Poorly crosslinked clots were more susceptible to SK-induced lysis than normal fibrin clots.

Prothrombin and partial thromboplastin times and the time between recalcification and the onset of coagulation

were prolonged in plasma from subjects receiving warfarin. A mathematical model of coagulation fitted to the data gave values for kinetic parameters consistent with the experimental results.

An increased rate of coagulation and a decreased $G'_{\max}$ were found in frozen and lyophilised PFP compared to fresh plasma.

ACKNOWLEDGEMENTS

It is impossible to express adequately the gratitude and appreciation I feel toward my friends, colleagues, and teachers at Rice University and the Texas Medical Center. Nonetheless, I would like to thank:

My advisor, Professor Larry V. McIntire for the direction, goading, and enlightening discussions he provided on this dissertation,

Dr. J. L. Moake, for the suggestions on experiments and the excellent advice on the biochemical aspects of this study,

Professors J. D. Hellums and W. G. Characklis for serving on the Oral Examination Committee,

Professor Murty Kuntamukkula for introducing me to the art of rheometry and the idiosyncracies of the Weissenberg Rheogoniometer,

Ms. Joy Pirsch, Ms. Marcella Estrella, and Mr. Hardy Bourland of the Biomedical Engineering Laboratory,

The staff of the Department of Hematology, Baylor College of Medicine, and in particular Ms. Patsy D. McPherson for their "painless venipuncture" and technical skill,

Mr. Joe Troll, Ms. Susan Ferber, Christie Rudi, and Carol Emory of the Department of Hematology, University of Texas Medical School at Houston, for performing the collagen-induced platelet aggregation and serotonin release assays and preparing the electrophoretic gels,

Mr. David Nystrom of the Space Physics Department, Rice University, for invaluable assistance with the data reduction process,

Ms. Beverley McCabe for drawing the figures,

My fellow graduate students for their friendship, and

My family for their support.

TABLE OF CONTENTS

	<u>Page</u>
CHAPTER I. INTRODUCTION	1
1. Coagulation	2
2. Platelets	10
3. Fibrinolysis	17
4. Experimental Methods for the Measurement of Coagulation	23
5. Modelling of Coagulation	27
CHAPTER II. EXPERIMENTAL METHOD AND APPARATUS	31
1. Dynamic Viscoelastic Measure- ments with the Rheogoniometer	31
CHAPTER III. MATERIALS AND EXPERIMENTAL PROCEDURE	44
1. Plasma Preparation and Treatment	44
2. Dynamic Rheological Testing	52
3. Additional Testing	55
CHAPTER IV. RESULTS	61
1. Normal Plasma	61
2. Inhibitors of Platelet Function	69
3. Fibrinolysis	82
4. Anticoagulation Therapy	123
5. Lypholisation	128
CHAPTER V. DISCUSSION	135
1. Rubber Elasticity Theory and Coagulation Kinetics Modelling	135
2. Platelet Function	165
3. Fibrinolysis	170
CHAPTER VI. SUMMARY	182
BIBLIOGRAPHY	186

	<u>Page</u>
APPENDIX A. DETERMINATION OF DYNAMIC SHEAR MODULI	206
APPENDIX B. COMPUTER DETERMINATION OF DYNAMIC SHEAR MODULI FROM DIGITAL DATA	212
APPENDIX C. NON-LINEAR PARAMETER ESTIMATION	232
APPENDIX D. DIFFUSION INTO THE REGION BETWEEN PARALLEL PLATENS	242
APPENDIX E. SUMMARY OF THE DATA	249

LIST OF FIGURES

<u>Figure No.</u>		<u>Page</u>
I-1.	The cascade system for blood coagulation	5
I-2.	Schematic representation of the fibrinogen molecule	7
I-3.	Enzymatic polymerization of fibrinogen and fibrin crosslinking	8
I-4.	Plasmin activation by streptokinase and fibrinolysis	20
II-1.	Schematic representation of the test section of the Weissenberg Rheogoniometer	33
II-2.	Schematic diagram of the data reduction process	42
IV-1.	Shear storage and loss moduli of recalcified normal PFP and PRP	62
IV-2.	Shear storage and loss moduli of recalcified normal PFP and PRP	63
IV-3.	Normalized maximum shear storage modulus of clots formed from PFP diluted with normal saline	66
IV-4.	Normalized maximum shear storage modulus of PRP diluted with isotonic buffer	67
IV-5.	Thrombin times of PFP diluted with imidazole buffered saline	68
IV-6.	Dynamic shear storage modulus of PRP incubated with 2×10^{-5} , 2×10^{-4} , 2×10^{-3} M monoiodoacetic acid or PBS	71
IV-7.	Dynamic shear storage modulus of PRP incubated with 10^{-3} M, 10^{-2} M 2-deoxy-D-glucose or normal saline	72

<u>Figure No.</u>		<u>Page</u>
IV-8.	Dynamic shear storage modulus of PRP incubated with PBS, 10^{-5} M KCN, or 5×10^{-3} M KCN + 5×10^{-3} M 2-deoxy-D-glucose	73
IV-9.	Dynamic shear storage modulus of PRP or PFP incubated with 5×10^{-3} M KCN + 5×10^{-3} M 2-deoxy-D-glucose or PBS	74
IV-10.	ADP-induced platelet aggregation in the presence of PBS/EtOH, 0.1 mg/ml cytochalasin B, 5×10^{-3} M KCN, 10^{-2} M 2-deoxy-D-glucose, or 5×10^{-3} M KCN + 5×10^{-3} M 2-deoxy-D-glucose	75
IV-11.	Dynamic shear storage modulus of PRP or PFP incubated with IBS or 5×10^{-3} M DBcAMP	78
IV-12.	Dynamic shear storage modulus of PRP incubated with 0.01, 0.05, 0.1 mg/ml cytochalasin B or PBS/EtOH	79
IV-13.	Dynamic shear storage modulus of PRP or PFP incubated with 0.1 mg/ml cytochalasin B or PBS/EtOH	80
IV-14.	Dilute PRP clot retraction in the presence of 0.01, 0.05, 0.1 mg/ml cytochalasin B or PBS/EtOH	81
IV-15.	Dynamic shear storage modulus of PFP incubated with 0, 0.025, 0.05, or 0.1 mg/ml SBTI	84
IV-16.	Dynamic shear storage modulus of PRP incubated 0, 3, or 10 minutes with 100 u/ml SK	88
IV-17.	Thrombin times of 1:1 mixtures of fresh PFP and PFP incubated previously with 100 u/ml SK	90
IV-18.	Normalized maximum shear storage modulus of clots formed from 1:1 mixtures of fresh PFP and PFP incubated previously with 100 u/ml SK	94

<u>Figure No.</u>		<u>Page</u>
IV-19.	Normalized maximum shear storage modulus of clots formed from 1:1 mixtures of fresh PFP and PFP incubated previously with 50 u/ml SK	95
IV-20.	Normalized maximum shear storage modulus of clots formed from 1:1 mixtures of fresh PFP and PFP incubated previously with 10 u/ml SK	96
IV-21.	Polyacrylamide gels of clots formed from 1:1 mixtures of fresh PFP and PFP incubated previously with 100 u/ml SK	101
IV-22.	Normalized maximum shear storage modulus of clots formed from 1:1 mixtures of fresh PRP and PFP incubated previously with 100 u/ml SK	102
IV-23.	ADP-induced platelet aggregation in 1:1 mixtures of PRP and PFP incubated previously with 100 u/ml SK	105
IV-24.	Thrombin-induced platelet aggregation in 1:1 mixtures of PRP and PFP incubated previously with 100 u/ml SK	106
IV-25.	Platelet aggregation to polymerizing fibrin in 1:1 mixtures of PRP and PFP incubated previously with 100 u/ml SK	107, 108
IV-26.	Dynamic shear storage modulus of 1:1 mixtures of PRP and PFP incubated 0 or 3 minutes with 100 u/ml SK and containing 0 or 0.1 mg/ml cytochalasin B	110
IV-27.	Dynamic shear storage modulus of 1:1 mixtures of PRP and PFP incubated 0 or 3 minutes with 100 u/ml SK and containing 0 or 0.1 mg/ml cytochalasin B	111
IV-28.	Dynamic shear storage modulus of 1:1 mixtures of PRP and PFP incubated 0 or 30 minutes with 100 u/ml SK and containing 0 or 0.1 mg/ml cytochalasin B	112

<u>Figure No.</u>		<u>Page</u>
IV-29.	Dynamic shear storage modulus of 1:1 mixtures of PRP and PFP incubated 0 or 30 minutes with 100 u/ml SK and containing 0 or 0.1 mg/ml cytochalasin B	113
IV-30.	Dynamic shear storage modulus of 1:1 mixtures of fresh PFP or PRP and fibrin clot digest or serum control	117
IV-31.	Dynamic shear storage modulus of recalcified PFP containing 0, 10, or 20 u/ml SK	119
IV-32.	Dynamic shear storage modulus of recalcified PRP containing 0, 10, or 20 u/ml SK	120
IV-33.	Dynamic shear storage modulus of PFP containing 0 or 10 u/ml SK and 10% 0.1 M NH ₂ OH or an isoosmotic control	121
IV-34.	Dynamic shear storage modulus of PFP containing 20 u/ml SK and 10% 0.1 M NH ₂ OH or an isoosmotic control	122
IV-35.	Thrombin time, prothrombin time, and activated partial thromboplastin time as per cent of control for PFP from patients undergoing warfarin therapy . . .	125
IV-36.	Dynamic shear storage modulus of PFP from a subject undergoing warfarin therapy	126
IV-37.	Dynamic shear storage modulus of PFP from a subject undergoing warfarin therapy	127
IV-38.	Dynamic shear storage modulus of fresh, frozen, and lypholised PFP	129
IV-39.	Dynamic shear storage modulus of fresh and lypholised pooled PFP	130

<u>Figure No.</u>		<u>Page</u>
IV-40.	Evolution of chromophore from fresh, frozen and lypholised PFP containing Factor Xa orthochromogenic substrate	133
V-1.	A crosslinked network	135
V-2.	Defects in polymer networks	137
V-3.	Experimental dynamic shear storage modulus and fitted values obtained from the coagulation model for PFP from a subject undergoing warfarin therapy	158
V-4.	Thrombin time versus the product of SK incubation time and SK concentration for 10, 50, and 100 u/ml SK	175
A-1.	Schematic representation of parallel platen geometry and motion	207
D-1.	Radial concentration profiles for a species diffusing into the region between parallel plates	247
D-2.	Dimensionless bulk average concentration versus dimensionless time for a species diffusing into the region between parallel plates	248

LIST OF TABLES

<u>Table No.</u>		<u>Page</u>
I-1	International nomenclature for blood coagulation factors	4
III-1	Platelet inhibitor concentra- tions and incubation periods	51
IV-1	The effect of 5×10^{-3} M KCN + 5×10^{-3} M 2-deoxy-D-glucose on the mechanical properties of PRP clots	70
IV-2	The effect of 5×10^{-3} M DBcAMP on the mechanical properties of PRP clots	76
IV-3	The effect of cytochalasin B on the mechanical properties of PRP clots	77
IV-4	The effect of cytochalasin B on collagen-induced platelet aggre- gation and ^{14}C -serotonin release	82
IV-5	The effect of SBTI on the thrombin time of normal PFP	83
IV-6	Fragment D and E levels in PFP in- cubated with 100 u/ml SK	86
IV-7	Thrombin times of 1:1 mixtures of fresh PFP and PFP incubated with 100 u/ml SK	91
IV-8	Thrombin times of 1:1 mixtures of fresh PFP and PFP incubated with 100 u/ml SK	92
IV-9	Thrombin times of 1:1 mixtures of fresh PFP and PFP incubated with 50 u/ml SK	93

<u>Table No.</u>		<u>Page</u>
IV-10	Thrombin times of 1:1 mixtures of fresh PFP and PFP incubated with 10 u/ml SK	93
IV-11	Fibrin monomer aggregation times for 1:1 mixtures of fresh PFP and PFP incubated with 100 u/ml SK	97
IV-12	Clot initiation times for 1:1 mixtures of fresh PFP and PFP incubated with 100, 50, or 10 u/ml SK	99
IV-13	Clot initiation times for 1:1 mixtures of fresh PRP and PFP incubated with 10 u/ml SK	104
IV-14	Normalized $G_{\max}^I$ of 1:1 mixtures of fresh PRP and PFP incubated with 100 u/ml SK and containing 0 or 0.1 mg/ml cytochalasin B	114
IV-15	The ratio of $G_{\max}^I$ of 1:1 mixtures of fresh PRP and PFP incubated with 100 u/ml SK containing 0.1 mg/ml cytochalasin B to those containing PBS/EtOH	115
IV-16	Thrombin times of 1:1 mixtures of fresh PFP and PFP incubated with 10 u/ml SK and 10% 0.1 M NH_2OH or 10 u/ml SK alone	123
IV-17	Drug regimen for patients undergoing warfarin therapy	124
IV-18	The effect of freezing and lypholisation on the initiation and extent of PFP coagulation	131
IV-19	Coagulation test times for fresh, frozen, and lypholised PFP	132
V-1	Rheological parameters for recalcified PFP, $n = 1$	154
V-2	Rheological parameters for recalcified PFP, $n = 2$	156
E-1	The effect of DBcAMP on the dynamic rheological characteristics of PRP clots	250

<u>Table No.</u>		<u>Page</u>
E-2	The effect of KCN and 2-deoxy-D-glucose on the dynamic rheological characteristics of PRP clots	251
E-3	The effect of IDA on the dynamic rheological characteristics of PRP clots	252
E-4	The effect of cytochalasin B on the dynamic rheological characteristics of PRP clots	253
E-5	The dynamic rheological characteristics of 1:1 mixtures of fresh PFP and PFP incubated previously with 100 u/ml SK	254
E-6	The dynamic rheological characteristics of 1:1 mixtures of fresh PFP and PFP incubated previously with 50 u/ml SK	255
E-7	The dynamic rheological characteristics of 1:1 mixtures of fresh PFP and PFP incubated previously with 10 u/ml SK	256
E-8	The dynamic rheological characteristics of 1:1 mixtures of fresh PRP and PFP incubated previously with 100 u/ml SK	257
E-9	The dynamic rheological characteristics of 1:1 mixtures of fresh PRP and PFP incubated previously with 100 u/ml SK and PBS/EtOH or 0.1 mg/ml cytochalasin B	258, 259
E-10	The dynamic rheological characteristics of PFP and PRP containing 0, 10, or 20 u/ml SK in the presence or absence of 0.01 M hydroxylamine	260
E-11	The dynamic rheological characteristics and coagulation times of PFP from subjects undergoing warfarin therapy	261

<u>Table No.</u>		<u>Page</u>
E-12	Dynamic rheological characteristics of fresh, frozen, and lypholised PFP clots	262

I. INTRODUCTION

In the study of blood coagulation, accurate and quantitative measurements of the biochemical and physical properties of forming clots have been difficult to obtain. The introduction of the Weissenberg rheogoniometer and linear viscoelastic theory provides a method of measuring the dynamic mechanical properties in vitro of coagulating plasma. From this quantitative data, it is possible to predict and explain some of the in vivo effects of trauma or chemical agents on the human coagulation system.

The primary objective of this work is to study the effects of an activated fibrinolytic system or the products formed by the enzymatic degradation of fibrinogen or fibrin on coagulating plasma.

Dynamic rheological measurements will be employed to determine the rate and extent of clot formation in these systems. The effect of these degradation products on platelet function and the platelet-mediated contractile force will also be investigated.

While the induction of fibrinolysis is desirable if clots are to be dissolved, the degradation products have been implicated as inhibitors of coagulation. Thus, fibrinolysis

and its interaction with the hemostatic mechanism are of clinical importance.

In addition, this work will present data from experiments on

1. The effect of inhibitors of platelet function (3;5'-dibutyryl cyclic AMP, 2-deoxy-D-glucose, cyanide, cytochalasin B) on the coagulation of platelet-rich plasma.
2. The coagulation of platelet-free plasma from subjects receiving warfarin anticoagulant therapy.
3. The effect of freeze drying platelet-free plasma on the rate and extent of clot formation.

Besides the rheological measurements, the results of biochemical and clinical assays will be employed to provide a more complete understanding of the effects of these agents and treatments.

In the remainder of this chapter, a brief review of coagulation, fibrinolysis, platelet structure and function, experimental methods for the study of coagulation, and the models proposed for the clotting process will be presented.

I.1 Coagulation

Coagulation is essentially the polymerization and crosslinking of a protein monomer, fibrin, formed from the

circulating blood protein, fibrinogen. In this section, the initial enzymatic activation of coagulation known as the coagulation cascade, fibrinogen, fibrin polymerization and crosslinking, and anticoagulation will be discussed.

Coagulation Cascade

Coagulation proceeds by the sequential activation of circulating zymogens in the blood and results ultimately in the conversion of fibrinogen to fibrin (1,2). The enzymes of the "coagulation cascade" along with calcium and fibrinogen are termed coagulation factors and denoted by Roman numerals (Table I.1). Coagulation which occurs because of surface contact proceeds by the intrinsic system and when initiated by Factor VII and tissue activator takes place through the extrinsic system (Figure I.1). The term "cascade" results from the observation that enzyme activation occurs sequentially (3). For example, in the intrinsic system, Factor XIIa, initially activated by surface contact, catalyzes the conversion of Factor XI to XIa, which in turn converts Factor IX to IXa. In the presence of Factor VIII, Factor IXa activates Factor X and so on. Thus, the coagulation cascade may act as a biological amplifier, and activation of a small quantity of enzyme initially may result in significant fibrin polymerization (3).

In the control of the coagulation cascade, feedback

Factor	Synonyms
I	Fibrinogen
II	Prothrombin, prethrombin
III	Tissue factor, tissue thromboplastin
IV	Calcium
V	Proconvertin, SPCA, autoprothrombin I
(VI)	Not assigned
VII	Proconvertin, SPCA, autoprothrombin I
VIII	Antihemophilic globulin (AHG), antihemophilic factor (AHF), platelet cofactor I
IX	Christmas factor, plasma thromboplastin component (PTC), autoprothrombin II, platelet cofactor I
X	Stuart-Prower factor, Stuart factor, autoprothrombin III
XI	Plasma thromboplastin antecedent (PTA)
XII	Hageman factor
XIII	Fibrin-stabilizing factor, Laki-Lorand factor, fibrinase

Table I.1 International nomenclature for blood coagulation factors. Activated factors are designated by an "a" after the Roman numeral.

(From: Williams, W. J., E. Beutler, A. J. Erslev, and R.W. Rundles, Hematology, p. 1226, McGraw-Hill, New York, 1977.)

Figure I-1. The cascade system for blood coagulation. Solid lines without arrowheads indicate a catalytic function. Solid arrows denote a conversion of substrate or reactant product. Broken lines with arrows indicate the enhancement of Factors VIII and V activity by thrombin. Ca = calcium; PL = phospholipid. (Modified from: Williams, W.J., E. Beutler, A.J. Erslev, and R.S. Rundles, Hematology, p.1266, McGraw-Hill, New York, 1977).

effects are important (4). Thrombin may act in an autocatalytic role and alter Factor V and VIII such that prothrombinase and Factor X activation are stimulated (5,6). Inhibition also significantly affects the rate of coagulation. The principal inhibitors in the circulation are antithrombin III, an inhibitor of the serine proteases, thrombin (7), Factor Xa (7), Factor IXa (8), Factor XIa (10), XIIa (11), and α_2 -macroglobulin, a thrombin inhibitor (12). In addition, circulating activated coagulation factors are removed by the liver (4).

Fibrinogen

The circulating precursor of the fibrin monomer is fibrinogen, a protein of approximately 340,000 MW (13). The fibrinogen molecule is composed of three pairs of chains - α A, β B and γ - having molecular weights of about 64,000, 57,000 and 48,000, respectively (14). These peptide chains are linked by 28-29 disulfide bridges (15) and by electrostatic interactions and hydrogen bonding (16). At physiological pH (7.4-7.9) the fibrinogen molecule is globular with a diameter of 22-23 nm and a radius of gyration of 11 nm (16,17). The conformation is determined primarily by the strong electrostatic attraction between the negatively-charged N-terminal disulfide knot (18) and the positively-charged C-terminal end of the α A, β B, and γ chains (Figure I.2).

Figure I-2 (From: Hudry-Clergeon, C. Marguerie, L. Pouit, and M. Suscillon, "Models proposed for the fibrinogen molecule and for the polymerization process," Thromb. Res., 6, 533-541 (1975).)

Figure I-2.

Schematic representation of the fibrinogen molecule. The molecule is 22 nm in diameter, of spherical shape with a two-fold axis of symmetry. The chain length is approximately represented according to their molecular weight ($A\alpha$: 63,000, $B\beta$: 55,000, γ : 48,000). The C-terminal parts of these chains are folded around the N-terminal disulfide knot (close-dotted area). This morphology is stabilized by intermolecular interactions of electrostatic nature in the A and B peptide region in particular. A large portion of the crosslinking sites is masked.

- o , crosslinking sites (acceptors and donors): the chain sites are placed arbitrarily.
- , interchain disulfide bridges in the N-terminal disulfide knot.
- , disulfide bridges of Fragment D, arbitrarily placed.

Figure I-3.
Enzymatic polymerization of fibrinogen and fibrin crosslinking. The cleavage of fibrinopeptides A and B reduces the C- and N-terminal interactions. The structural changes that follow expose the sites involved in the formation of the linear fibrin array (hydrogen and electrostatic bonding and hydrophobic interactions) and crosslinking (covalent bonding).

(From: Hudry-Clergeon, G., C. Marguerie, L. Pouit, and M. Suscillon, "Models proposed for the fibrinogen molecule and the polymerization process," Thromb. Res., 6, 533-541 (1975).)

Fibrin Polymerization and Crosslinking

Fibrinogen is converted to fibrin by the cleavage of fibrinopeptides A and B (the negatively charged N-terminal ends of the A α and B β chains) by thrombin (19,20). With the electrostatic interaction between the C- and N-terminals no longer present, the molecule unfolds to yield a "squashed T-shaped" structure (see Figure I.3). These fibrin monomers then associate electrostatically to yield a fibrin gel consisting of linear arrays of these "T-shaped" molecules (21).

Factor XIIIa is a thrombin-activated transamidase which catalyzes the formation of ϵ -(γ -glutamyl) lysine bonds between the α and γ chains of fibrin to yield α polymers and γ dimers (22-26). A total of 6 covalent crosslinks are formed per fibrin monomer (24). The formation of these crosslinks yields a clot of increased mechanical strength (27-30) which is insoluble in 1 percent monochloroacetic acid and 5M urea. Crosslinking can be inhibited by clotting plasma in a calcium-free environment (27,28) or by the use of an inhibitor of transamidation such as hydroxylamine (29). Clots formed in this manner will dissolve in urea or monochloroacetic acid.

Anticoagulation

To prevent the clotting of blood, anticoagulants are employed which have various modes of action. For most in vitro studies, a calcium chelator, such as trisodium

citrate, acid citrated dextrose, or EDTA, is used. Because calcium is a necessary cofactor in the coagulation cascade, the chelation of this divalent cation prevents activation of the coagulation factors. If blood is anticoagulated with 3.8 percent tridosium citrate, a weak calcium chelator, it may later be recalcified to reactivate the coagulation system and allow clotting to proceed.

For in vivo anticoagulation therapy, heparin and dicumarol are the drugs principally administered. In concert with antithrombin III, heparin inhibits thrombin and Factors IXa, Xa, XIa, and XIIa (8-11). The coumarin anticoagulants inhibit the production of the vitamin K-dependent clotting factors, prothrombin and Factors VII, IX, and X, by the liver (33-34). While for in vitro studies coumarin is useless, it is often administered to patients with prosthetic heart valves over periods of years with excellent results.

I.2 Platelets

In this section, a brief overview is given of platelet morphology and the role of platelets in hemostasis and thrombosis. Platelet aggregation and the inhibition of platelet function are also discussed.

Morphology

Platelets are disc-shaped blood cells with an average volume of 5 to 7.5 μm^3 (35). In whole human blood, the normal

range of platelet concentration is considered to be 150-400,000 platelets/mm³. Carbohydrates are metabolized by platelets via the Krebs' cycle and aerobic glycolysis (36,37).

Essentially, platelets consist of three structural zones (38). The peripheral zone consists of a unit membrane with an exterior glycoprotein coat. It is primarily involved with adhesion (the attachment of a platelet to a blood vessel wall or a foreign surface) and as a catalytic surface for the activation of coagulation factors (39). A second zone (termed the "sol-gel" zone by White (38)) is composed of fibrous elements, the microfilaments and microtubules. The first system of fibers, the microfilaments, are 50-70 Å in diameter (40) and resemble those fibers found in smooth muscles (41,42). These filaments are believed to represent the F-actin component of platelet actomyosin or "thrombos-thenin" (43-46). Thus, the microfilaments are most probably responsible for platelet contractile properties such as clot retraction (38,44). Microtubules, 250 Å in diameter, form a circumferential bundle beneath the unit membrane (38,41,47). Chemical agents which depolymerize microtubules do not inhibit platelet-mediated clot retraction or contractile force, and therefore, contractility does not depend on the presence of microtubules (44,47,48). The role of microtubules remains unclear, though it has been suggested that they may serve as a cytoskeleton for the maintenance of platelet shape (38,44).

The organelle zone contains mitochondria, granules, and dense bodies (47). The dense bodies, primarily containing serotonin, ADP, and calcium (49) are released when platelets become exposed to aggregating agents (50). This release reaction in turn stimulates platelet aggregation and accelerates coagulation (51).

Aggregation

Platelet aggregation is simply the attachment of platelets to one another. In vitro platelet aggregation is measured using the turbidimetric technique of Born (52,53). In this method, a beam of light is passed through a sample of platelet-rich plasma (PRP) and the optical density or light transmission measured. Addition of an aggregating agent to the initially cloudy plasma causes platelets to cohere to each other with a consequent increase in the transmissivity. In vivo aggregating agents and the ones most commonly used in vitro are ADP, thrombin, and collagen.

Aggregation of platelets to the addition of exogenous ADP may be either primary, biphasic, or irreversible (54). At concentrations of ADP sufficiently low that primary aggregation occurs, platelets cohere in response to exogenous ADP then spontaneously disaggregate. In biphasic aggregation, addition of ADP yields an initial aggregation of platelets shortly followed by a second wave of aggregation. This second wave is in response to ADP secreted from the dense

granules during the release reaction (49,55). At higher concentrations of ADP ($\sim 2\mu\text{M}$ ADP for normal PRP), a single irreversible wave of aggregation is seen. Also, a small amount of normal fibrinogen must be present for ADP-induced aggregation to occur (56,57).

Addition of collagen to PRP results in an "all-or-nothing" response i.e., either irreversible aggregation occurs or there is no effect (58,59). This is because collagen induces the release reaction which in turn stimulates aggregation (59). Thrombin-induced aggregation proceeds by a mechanism which remains unclear, though it probably involves the release reaction (60). Platelet aggregation to polymerizing fibrin, but not fibrinogen or fibrin polymer, has also been demonstrated (61).

Role in Hemostasis and Thrombosis

In vivo platelets perform two major functions--hemostatic and thromboplastic (62). The former relates to the formation of a hemostatic plug by platelets, and the latter to platelets role in the acceleration of clotting and the strengthening of the clot. When a blood vessel is injured, subendothelial tissue (similar to collagen) is exposed. Platelets adhere to this surface due to the presence of this collagen-like material and the release of ADP from damaged cells (63). The platelet plug continues to grow after the initial adhesion by the aggregation of platelets. Presumably

this aggregation is potentiated by the collagen-induced release reaction. Whether these aggregated platelets release ADP, thus recruiting still more platelets is unclear (60). In the circulation, the hemostatic function is affected by blood flow which generates wall shear stress and removes aggregating agents from the site of injury (64).

In their thromboplastic role, platelets accelerate the formation of fibrin clots by the release of platelet factors (51,65). The activation of Factors XI and XII may be enhanced by platelets, and Factor XIa protected from inactivation (66). Also, the phospholipid-rich platelet membrane possibly acts as a catalytic surface for factor activation (67). In turn, thrombin and polymerizing fibrin induce platelet aggregation (60,70), and thrombin's action on platelets causes the release reaction (49). Thus, platelets and the coagulation cascade exhibit a synergistic effect in the formation of thrombi.

Platelets interact with and attach to polymerizing fibrin (68-70), and in vitro clot retraction occurs (71,72). This decrease in clot size is a consequence of platelet contraction and shortened fibrin chain length. In systems in which PRP is constrained so that a change in volume of the clot is not permitted, an increase in the isometric tension (73,74) or the dynamic rigidity (75-77) of the clot is found. This is the result of tightening of the network by platelet contraction (75-77). While in the presence of flowing blood,

platelets are not distributed homogeneously throughout the fibrin network, it is likely that the retraction mechanism still plays a significant role in hemostasis. In vivo, tightening of the platelet-fibrin matrix probably serves to close a wound, and decreasing the size of a clot prevents occlusion of blood vessels (63).

Control and Inhibition of Platelet Function

Cyclic AMP is believed to play an important role in the control of platelet aggregation and contractility (78-81). Addition of dibutyryl cyclic AMP (a derivative of cyclic AMP which more easily crosses the platelet membrane) inhibits platelet aggregation (82-84), clot retraction (85,86), and yields platelet-fibrin clots of decreased dynamic rigidity (86). Prostaglandin E_1 (PGE_1), elevates the level of cyclic AMP in the platelet (80,84,86,87) and inhibits aggregation (82,85,87,88) and clot retraction (85,86). The effect of PGE_1 on the contractile force generated in clots formed by recalcification of normal platelet-rich plasma is confusing, but studies using Factor-VIII deficient PRP in which only a small amount of thrombin is generated, indicate that PGE decreases the dynamic modulus (86). Agents such as caffeine, which inhibit phosphodiesterase and thus raise the level of cyclic AMP, also inhibit platelet function (78,80,82). Conversely, epinephrine which decreases the intraplatelet cyclic AMP concentration, promotes platelet aggregation (80,87). In

short, a rise in cyclic AMP level inside the platelet inhibits aggregation and contraction, a decrease promotes these functions.

An inhibitor of platelet function in wide use (though not for this purpose) is acetylsalicylic acid, more commonly known as aspirin. Aspirin inhibits the release reactions and, thus, prevents collagen-induced platelet aggregation (89,90). This effect is thought to be a result of blocking of prostaglandin synthesis (91,92).

Cytochalasin B has been shown to inhibit those cell movements and processes which require contractile microfilaments (93). When platelets are incubated with cytochalasin B, clot retraction (42,93-95) and adherence to collagen (96) are inhibited, and platelet aggregation may be reduced (42, 95). Fibroblast-mediated clot retraction is also inhibited by cytochalasin B (97). Although Halsam states that the primary effect of cytochalasin B is the inhibition of glucose metabolism (95), more convincing evidence indicates that cytochalasin B interferes with F actin (of which microfilaments are composed) and prevents its binding to myosin (98).

Less subtle inhibitors of platelet function are those chemicals which interfere with the metabolism of the platelet. Monoiodoacetic acid and 2-deoxy-D-glucose, inhibitors of glycolysis, reduce platelet aggregation and induce platelet shape change (99,100). In addition clot retraction is

decreased when glycolysis is inhibited with 3,5-dinitrobenzoyl-glucosamine (101). Chemical agents which prevent oxidative phosphorylation, such as cyanide or Antimycin A (cytochrome oxidase inhibitors (102)), have been shown to induce platelet shape changes (99) though they have little effect on platelet aggregation (100,103). When both inhibitors of glycolysis and respiration are employed, e.g., antimycin + deoxyglucose (100,104), KCN + deoxyglucose (105), or moniodoacetate + cyanide (99,103), normal platelet function may be totally suppressed.

I.3 Fibrinolysis

The enzymatic degradation of fibrinogen or fibrin is termed fibrinolysis (106,107). The lysis of clots is often beneficial as in the treatment of phlebitis. However, the products of fibrinolysis may interfere with the coagulation process. Some aspects of the fibrinolytic system and the relationship of the products of fibrinolysis to coagulation are discussed in this section.

Plasmin and Plasmin Activators

The enzyme principally responsible for the lysis of fibrin clots or fibrinogen is plasmin, an endopetidase of M.W. 80,000 (108). Plasmin is formed from its circulating zymogen, plasminogen (MW 88,000 (108)), by the action of activators released from the tissue or present in the plasma.

An example of a tissue activator is urokinase (purified from urine) which has been the subject of extensive study (108-113). Urokinase directly converts plasminogen to plasmin and, thus, is termed a "direct activator."

Indirect activators require the presence of a proactivator if plasminogen is to be converted to plasmin. The indirect activator most widely employed clinically and for in vitro experimentation is streptokinase (SK), a molecule of MW 45,000 produced by streptomyces (114). In this case, the proactivator is plasminogen or plasmin itself which combines in a 1:1 molar ratio with SK to form an active complex (110,115-119). It is this complex which catalyzes the conversion of plasminogen to plasmin. The numerous studies of streptokinase-induced fibrinogen degradation or fibrin clot lysis are consistent with the concept of an SK-plasmin(ogen) activator (110,120-123).

Fibrinogen and Fibrin Degradation Products

When plasmin attacks fibrinogen or fibrin, the fragments produced are termed fibrin(ogen) degradation products (FDP). This process was recognized as occurring sequentially, and those products evolved by the enzymatic degradation of fibrin(ogen) were classed at first as early or late FDP (depending on the length of the incubation period with plasmin or plasmin activator). With further investigation, these degradation products have been characterized, and a generally

accepted explanation for the fibrinolytic mechanism set forth by Marder et al. (124-126). In this scheme, fibrin or fibrinogen undergoes sequential degradation to yield the FDP, fragments X,Y,D, and E. Initially, plasmin digests fibrinogen to produce a high molecular weight fragment, X (MW 240,000 vs. 340,000 for fibrinogen), and some small peptides. Fragment X is then split by plasmin to yield fragment Y (MW 155,000) and fragment D (MW 83,000). While the D fragment is stable, fragment Y is further digested by plasmin to yield another D fragment and fragment E (MW 50,000). Thus, the end products of the digestion of one mole of fibrinogen by plasmin are one mole fragment E, two moles fragment D, and several moles assorted small peptides (see Figure I.4). When crosslinked fibrin is degraded by plasmin, one D dimer (MW 184,000) and one fragment E moiety are produced per monomer subunit of fibrin polymer (126,127). An alternative model for fibrinogenolysis has been advanced by Mosesson et al. (128,129) in which the end products are one fragment D and one E per fibrinogen molecule. However, Ferguson and coworkers have presented evidence which strongly supports the mechanism proposed by Marder (127).

The FDP have several properties of interest. It should be noted that each fragment is actually a heterogeneous population of fragments. For example, fragment D is several similar molecules with molecular weights ranging from 76,000 to 94,000 (127). The higher molecular weight

Figure I-4. Streptokinase-induced fibrinogen degradation by plasmin. Streptokinase (SK) combines with plasminogen (Pg) or plasmin (Pm) to form an active complex (SK-Pg or SK-Pm). This complex promotes plasmin formation from plasminogen. Plasmin attacks fibrinogen (fg) or fibrin (fn) to yield a series of degradation products denoted X, Y, D, and E. The end product of the plasminic digestion of 1 mole of fibrinogen is two moles D, 1 mole E, and several moles of small peptides.

fragment is the end product of plasmin digestion of fibrinogen in the presence of calcium, and the lower molecular weight species is produced in chelated systems (130). While fragment X (or more precisely stage 1 and stage 2 fragment X) are less potent promoters of ADP-induced platelet aggregation than intact fibrinogen, fragments Y, D, and E will not support aggregation by ADP (56). With regard to the structure of the end product fragments, the fragment D consists of three chains--one each of portions of the $A\alpha$, $B\beta$, and γ chains, and E represents the "N-terminal disulfide knot" (126,127).

Fibrinolysis and the Coagulation Mechanism

One of the fundamental purposes in studying the fibrinolytic system is to be able to design therapy that will permit dissolution of clots or inhibit excessive fibrinolysis without interfering with normal hemostatic function. To this end, the interactions of plasmin and FDP with fibrin polymerization and platelet function have been investigated.

Fibrinogen degradation products have been shown to lengthen thrombin times significantly (125,131-133). Marder and Shulman have determined that of the fragments, Y is the most potent inhibitor of the clotting of fibrinogen by thrombin (125). Apparent impairment of fibrin polymerization in the presence of FDP has been demonstrated through observation of thin fibrin gels by electron microscopy (134) and by

increased "fragility" of fibrin clots during thromboelastography (135).

Studies on the effects of FDP on platelet function are contradictory. Kowalski et al. reported that FDP inhibit ADP-, thrombin-, and collagen-induced aggregation (136). A study by Hirsh and coworkers indicated that clot retraction and ADP-induced platelet aggregation are not influenced by early or late FDP, and only late FDP inhibit thrombin-induced aggregation (135). Jerushalmy and Zucker found that early FDP impaired thrombin-induced aggregation and serotonin release (137). In contrast, the results of Barnhart et al. show that fragments D and E have the ability to aggregate platelets (138): Wilson et al. purified FDP produced by trypsin or plasmin and found some inhibited while others enhanced platelet aggregation (139). Larrieu and colleagues have observed that low molecular weight FDP inhibit platelet adhesion and spreading on a glass slide, but fragments X, Y, D, and E have little or no effect (140). After infusion of SK in vivo, Cronberg noted decreased platelet adhesiveness to glass, though he saw no effect of purified fragments D and E on ADP--on collagen-induced aggregation (141). The results of Niewiarowski and coworkers show that a dialysable low molecular weight moiety produced early in the digestion of fibrinogen inhibits the first phase of ADP-induced aggregation (142). In studies by Prentice et al. and Kwaan et al., ADP-induced platelet aggregation was impaired

in plasma with elevated FDP levels as a result of Arvin therapy (143,144).

The coagulation mechanism may in turn influence plasmin generation and function. Factor XIIa may directly convert plasminogen to plasmin and, thus, the first enzyme in the extrinsic system of the coagulation cascade also activates the fibrinolytic mechanism (145). The effect of crosslinking of fibrin clots on fibrinolysis is controversial. Increased susceptibility of poorly crosslinked clots to digestion by plasmin has been demonstrated using plasma from patients with congenital Factor XIII deficiency as well as plasma in which transamidation was inhibited by chemical agents (146-150). Other studies have found no effect of the extent of fibrin crosslinking on fibrinolysis (151,152).

I.4 Experimental Methods for the Measurement of Coagulation

Coagulation tests may be divided into two main categories--"end-point" and dynamic tests (153). In the "end-point" tests, the time at which blood is clotted is obtained. The criteria for this "end-point" may be the formation of the first fibrin strand (the fibrometer time), the point when blood or plasma will no longer flow, or the time when the rate of change of the optical density of a clotting sample is a maximum. While these tests are quick, easy, and may be performed with unsophisticated equipment, they provide only a

single measurement of a property of a forming clot. Thus, these methods provide rapid screening for coagulation disorders, but they reveal little information on the extent or development of the physical properties of coagulating blood.

Dynamic methods measure continuously the physical properties of clots as they are forming. By monitoring of these properties over the course of clot formation, the kinetics of coagulation may be studied and with the more advanced rheological techniques the extent of clotting may be determined quantitatively. Perhaps the methods which yield the most useful data are those which provide a measurement of the mechanical properties (as elasticity and viscosity) of the forming clot. The principal instruments for the dynamic measurement of mechanical properties are similar in design and conceptually simple. In these systems, a test sample is placed between two test members. A forced oscillation is applied to one member and this motion is transmitted to the other member by the test material. By comparing the motions of the two surfaces, the "modulus" of the sample may be determined.

The instrument most widely used to study clot formation is Hartert's thromboelastograph (153). This device consists of a stainless steel cup containing a concentric cylinder suspended by a torsion wire. A sample is placed in the 1 mm gap between cup and cylinder, and a $4^{\circ} 45'$ oscillation applied to the cup. The oscillation is rather peculiar

in that the cup moves from maximum positive to maximum negative deflection for 3.5 seconds and then rests for 1 second (a period of 9 seconds). The motion of the inner cylinder is recorded continuously, the amplitude of deflection increasing as the clot becomes more rigid. Von Kaulla provides an analysis of the resulting thromboelastogram in terms of the delay time between initiation of clotting and first clot formation, rate of change of amplitude of deflection, and the maximum deflection of the inner cylinder (153). By characterizing the blood clots as an ideal elastic material, Hartert and Schaefer have obtained the approximate shear storage modulus, G' , of a sample from the amplitude of deflection (154).

Dintenfass et al have employed the variable-frequency thrombo-viscometer for the study of blood coagulation. This device is very similar to the thromboelastograph with the exceptions that it uses a cone-and-cone geometry (35° and 40°) and as the name implies, permits testing at various frequencies (1 to 3 cps). The 110° amplitude of oscillation of the outer cone imposes very large strains on the clot structure and probably disrupts the fibrin network. With this apparatus, Dintenfass has performed extensive studies on the effects of velocity gradient, hypertension, and vascular disease on clot formation (156-158).

A device more sophisticated than the previous two is the viscoelastorecorder of Kaibara and Fukada (158). Like

the thromboelastograph, the test section of this apparatus consists of a concentric cup and rod. However, a small amplitude sinusoidal axial oscillation is applied to the cup and the amplitude ratio and phase difference between the cylinder and rod strains detected. From these measurements, the dynamic shear storage or elastic modulus, G' , and the shear loss or viscous modulus, G'' , were determined, where G' is the in-phase component or real part of the complex modulus G^* and G'' is the out-of-phase or imaginary part of G^* . This method has been employed to study the effects of thrombin concentration, fibrin network formation, and various diseases on the viscoelasticity of plasma and purified fibrin clots (158-163).

When operated in the oscillatory shear mode, the Weissenberg Rheogoniometer is capable of determining G' and G'' , also. It is the instrument employed in this study, and its principle and method of operation are explained in Chapters II and III. A broad range of factors affecting blood coagulation have been examined with this device by Roberts (164), Glover (75), Kuntamukkula (77) and their respective colleagues. Among these factors are calcium ion concentration (30,164), crosslinking of fibrin (29,30,75,164, 165) platelet concentration (75,76) abnormal platelets (75, 76,166) antiplatelet agents (48,77,86), and the coagulation of factor-deficient-plasma (75,77).

Cohen et al. have employed a much different apparatus

for the study of platelets. In this device a platelet-rich clot is held rigidly between two platens, and the tensile force generated by the isometric tightening of the fibrin network due to platelet contraction is measured. With this technique, the effect of platelet and fibrinogen concentration on the contractile force and clot retraction has been studied (73,74).

I.5 Modeling of Coagulation

To say that the quantitative modeling of the development of the mechanical properties in coagulation blood is difficult would be a considerable understatement. The coagulation cascade consists of better than a dozen factors and cofactors whose various interactions leading to the polymerization of fibrin have not been fully elucidated. It is not possible at this time to obtain quantitative dynamic measurements of these factors in a realistic system. As a result, a detailed model can not be constructed from experimental kinetic data. Indeed, if such a model could be devised, it would contain so many parameters that to fit a clotting curve to this equation (or set of equations) would require an enormous amount of high quality data as well as computing time.

To circumvent this problem, most models, which are based on measurements of the rigidity or loss modulus of clots, lump parameters and obtain equations of relatively simple form. These equations are generally empirical in

nature and are valid for only a portion of the clotting process. It should be noted that only the coagulation of platelet-free plasma or the purified thrombin-fibrinogen system has been modelled. The presence of platelets introduces a complexity which precludes the use of these simple models.

Scott-Blair and Burnett (167,168) have set forth a model for the initial stages of coagulation of the form

$$G = G_{\infty} \exp(-\tau/t) \quad (I.1)$$

and for later stages

$$G = A \left(\frac{1}{t} - \frac{1}{t'} \right) \quad (I.2)$$

where G is the rigidity of the completely clotted sample and A, t' , and τ are constants determined by fitting of experimental data. G , which corresponds to the magnitude of the complex shear modulus, was obtained by U-tube gelometer (167) and by thromboelastograph (168).

In modeling the development of the storage and loss moduli, Kaibara and Fukada have proposed two models:

$$G = at^{\beta} \quad (I.3)$$

and

$$G = G_{\infty}(1 - e^{-kt}) \quad (I.4)$$

where G is either G' or G'' , G_{∞} is the ultimate G' or G'' , and k , α , and β are empirical constants. These equations are fit to a portion of the G versus time data, and thus, several sets of parameters are required to model the total clotting process.

By assuming that G' is proportional to the crosslink density of the fibrin network, Kaibara (160) represents the rate of change of G' by the following expression:

$$\frac{dG'}{dt} = k(G_{\infty}' - G')^n \quad (I.5)$$

where k is constant and n is the order of the reaction. This approach resembles that of Mussati and Macosko which relates the modulus to the crosslink density and the rate of crosslink formation to the number of crosslinks to be formed (169). Kaibara also models the formation of a fibrin network as occurring by two simultaneous first-order reactions.

Glover incorporates the idea of available crosslinks into his model and allows a dependence on enzyme concentration to yield the equation:

$$\frac{dN}{dt} = k(N_{\infty} - N)^a (t - t_0) \quad (I.6)$$

where N is the number of crosslinks formed, N_{∞} is the possible number of crosslinks, and a , c , k , and t_0 are constants. The magnitude of the complex modulus, $|G^*|$, is related to N by the expression

$$|G^*| = k_1 N^m + |G_0^*| \quad (I.7)$$

where $|G_0^*|$ is the magnitude of the complex modulus for the nonclotted plasma at t_0 . For the region in which only a small fraction of crosslinks have formed (small values of $t-t_0$), the modulus is described by

$$G_e = k_2 (t-t_0)^{k_1} \quad (I.8)$$

where k_1 and k_2 are constants and G_e is the excess modulus:

$$G_e = \frac{|G^*| - |G_0^*|}{|G_\infty^*|} \quad (I.9)$$

Glover (33) and Kuntamukkula (77) have applied this model to an extensive number of normal and abnormal plasma with great success.

II. EXPERIMENTAL METHOD AND APPARATUS

This chapter deals with the use of the Weissenberg Rheogoniometer in the dynamic measurement of mechanical properties. With some minor modifications, it is essentially the system outlined by Glover (75) and Kuntamukkula (77).

II.1 Dynamic Viscoelastic Measurements with the Rheogoniometer

Weissenberg Rheogoniometer

A Weissenberg Rheogoniometer (Model R-18), (Sangamo-Weston Controls) was employed in the measurement of the dynamic mechanical properties of coagulation plasma. This device permits normal force or torque measurements in the oscillatory or steady rotational mode. In order to determine the complex dynamic modulus only oscillatory shear experiments were performed and only the torque was measured. As this is a standard instrument, the mechanics of the device will not be discussed.

For performing dynamic rheological studies, the necessary components of the rheogoniometer were:

1. Torsion bar.
2. Upper and lower stainless steel platens.

3. Air-bearing rotor.
4. Multispeed gear box and variable sine wave generator for sinusoidal oscillation of the bottom platen assembly.
5. Transducers, amplifiers, and analog filters for monitoring upper and lower platen motion.
6. Transducer and amplifier for setting the gap between platens.
7. Magnetic tape recorder.

To make dynamic rheological measurements with this instrument, a test sample is placed on the bottom platen. The upper platen which is held by the air-bearing rotor and whose movement is restricted by a torsion bar, is next lowered until the desired distance between the platens is obtained. This distance is determined using the gap-set transducer system. A forced oscillation is then applied to the bottom platen and its motion monitored by a displacement transducer. Stresses developed by this movement are transmitted to the upper platen assembly by the test material, and the resultant shear strain on the upper platen is monitored by another transducer.

If the amplitude of oscillation is sufficiently small, the test sample will behave as a linear viscoelastic material, and the analysis of Walters and Kemp (170,171) can be employed to obtain the complex dynamic modulus. This

Figure II-1. Schematic representation of the test section of the Weissenberg Rheogoniometer.

requires determination of the amplitude ratio and phase difference between the signals from the upper and lower platen displacement transducers. From this data, the dynamic shear storage and loss moduli (G' and G'' , respectively) may be found.

In practice, the measurement of rheological properties of "thin" viscoelastic fluids is difficult. When the shear modulus of the materials is less than 10 dyne/cm^2 , the signal-to-noise ratio is low for the analog signal corresponding to the upper platen motion. The small amplitudes of deflection required when working in the linear viscoelastic range must also be measured accurately. In thixotropic materials, it is necessary that the period of oscillation be sufficiently small such that the material properties are approximately constant over the course of several cycles. In the following paragraphs, the specific test system chosen to overcome these problems is described in detail.

Test Geometry

For this study, parallel 5 cm stainless steel platens were employed. In comparison to the cone-and-plate system, the solution for the dynamic moduli from the amplitude ratio and phase difference of the motions of the upper and lower platens (171) more rapidly converges for thin fluids. In addition, the surface-to-volume ratio may be altered simply by changing the gap between the platens. To provide

a frictionless air-bearing, a working pressure of 15 psig was supplied by compressed air to the upper platen assembly rotor. The movement of this assembly was restricted by a torsion bar with a constant of 9.6×10^{-6} dyne-cm/radian.

The frequency of oscillation of the bottom platen was chosen to be 6 Hertz which differs significantly from the resonance frequency of the upper platen assembly (~ 15 Hz). In all experiments, an amplitude of oscillation of .0028 radians was applied to the bottom platen and the gap between the platens set at 578 microns. These values represent a maximum of 12 percent shear strain at the outer edge of the platens. Under these conditions, Glover (75) has found that the effects of varying the surface-to-volume and aspect ratio are negligible. In addition, by varying the shear strain he has determined that in this system the clot is not disrupted and linear viscoelasticity theory is applicable.

Electronics

The motion of the upper and lower platens was monitored by linear voltage differential transducers which converted movements to analog signals. These signals were then amplified, subjected to analog filtration, and recorded on magnetic tape for further processing.

In this study, two generations of transducer-transducer meter systems were employed. Initially, the

transducers supplied with the R18 system were used (Sangamo F.51/M for the torsion head signal in conjunction with Sangamo EP. 597 transducer meters). By selecting the meter range, full scale outputs corresponding to ± 5 , 20, 50, 200, 500, or 2000 microns movement of the transducer armature are attainable. In the measurement of the motion of the upper and lower platens, one micron movement of the transducer armature is equivalent to 10^{-5} and 3.075×10^{-5} radians, respectively. These transducers and meters were later replaced by more reliable transducers (Sangamo NA 1/2.5 mm) and a solid-state transducer meter system (Sangamo C 56/3/AL). Full-scale outputs of ± 2.5 , 10, 25, 100, 250, and 1000 microns of transducer armature movement were selectable with these meters.

The analog signals from the transducer meters were filtered and full-scale output set accurately using a variable-gain low-pass analog filter designed and built by the Department of Electrical Engineering at Rice University. The filtered analog data were then recorded on magnetic tape by a 4 channel FM tape recorder (Tandberg TIR 115).

For monitoring of the distance between the upper and lower platens, a gap-set transducer (Sangamo F. 13/B/M) and transducer meter (Sangamo EP.597) were employed at first. These were later replaced by the Sangamo C 56/3/AL system (Sangamo NBR/2.5 mm transducer and NT 9 transducer amplifier). A Simpson 2700 digital voltmeter was used in

calibration, setting full-scale outputs, making transducer meter adjustments and monitoring the temperature in the rheogoniometer environmental chamber. Oscillations of the platens were continually displayed on a dual trace oscilloscope (Tektronix 561A) and on the CRT monitor of the magnetic tape recorder.

Environmental Control

For experimental consistency, temperature, humidity and partial pressures of O_2 , CO_2 and N_2 were controlled in the environmental chamber. Temperature was regulated by circulating water from a temperature-controlled water bath (Lauda Brinkman type K-4 R-D) through the jacket surrounding the platens. The temperature was monitored using a thermistor (YSI, series 400) and kept within $\pm 0.1^\circ C$ of $37^\circ C$.

By means of a mixing manifold consisting of three rotameters in parallel, a mixture of oxygen, nitrogen and carbon dioxide was obtained. This mixture was then bubbled through distilled water at $37^\circ C$ and the humidified gas admitted to the environmental chamber. The flow rates of the gases were set such that $pO_2 = pCO_2 = 45$ mm Hg (approximately the same partial pressures found in venous blood). The atmosphere largely influenced only events occurring at the air-plasma interface. Times much longer than those over which rheological experiments were carried out would be required to propagate changes in dissolved gas concentration

(and, hence, pH) from the interface to the interior of the plasma (Appendix D).

Data Collection and Reduction

In principle, the determination of the shear modulus merely requires the determination of the attenuation and phase shift of the sinusoidal oscillation of the lower platen by the test material as measured by the motion of the upper platen. In practice, however, determination of the amplitude ratio and phase difference is non-trivial. While the signal from the lower platen is a sine wave of constant amplitude (mechanical imperfection in the variable sine wave generator cause slight deviations from ideality), in the rheological testing of coagulating plasma or other thixotropic materials the amplitude of oscillation of the upper platen is time-dependent. Furthermore, the signal is contaminated with noise and by the resonant vibration of the torsion head. This is particularly a problem during the early stages of coagulation when G^* is small. In the measurement of the mechanical properties of forming clots, it is necessary to obtain the "clean" signal at the fundamental frequency (6 Hz) over a period less than 1 second in duration from an output often of low S/N ratio and containing a 15 Hz resonance.

This dilemma of real-time data analysis is obviated by recording the data on magnetic tape and at a later time

converting it to digital form and subjecting it to band pass digital filtration. After amplification and analog filtration, the signals from the transducers monitoring the motion of the upper and lower platen were recorded on the first and second channels of the tape recorder. Since only those data which were unaffected by the starting and stopping of the tape drive were to be used, it was necessary to generate a sample window. This was done by recording a + 1.0 D.C. voltage or "flag" (from a Kepco power supply, ABC 40-0.5) on the third channel. During those periods in which the data were meaningless the flag was off (0 volt signal), and at the time the data were meaningful, the flag was on (+1.0 volts). This resulted in the eventual formation of a data block. As a label for each block of data, a voice record of the time of the sample and the range of the upper transducer amplifier was made on the fourth channel.

At the beginning of each experiment, the tape recorder was placed in the record mode with the tape drive idled. To record a data sample the following procedure was employed:

1. The tape drive was set in motion and allowed to stabilize (~3 seconds).
2. A voice record of the time after initiation of the experiment and the range of the upper transducer amplifier was made.

3. The +1.0 volt flag was turned on for two seconds.
4. One second after the flag was turned off, the tape drive was idled.
5. The data in step 2 were recorded in a notebook.

The two part procedure for digitization of the data was developed and programmed by David Nystrom of the Department of Space Physics, Rice University, and employed an SDS model 92 computer. In the first pass, all the analog signals on the three data channels were digitized to produce a binary-coded-decimal intermediate tape. Simultaneous sampling of each channel occurred at a rate of 200 samples/second (or 33.3 samples/cycle for a 6Hz signal). During the course of the first pass, a count of the flags appeared on a LED display, and this count was continuously compared against the voice and notebook records. By this means, it was possible to detect the appearance of spurious flag signals or the absence of samples.

In the second step of the digitization procedure, the digital form of the transducer signals from those periods in which the flag was on were written as a file to another BCD tape. The first logical record (eighty bytes) of each file was used as a label and read from a card reader. Each label contained the time after recalcification (minutes and seconds), Gregorian date, Julian date, experiment number, input oscillation frequency (radians), amplitude of

oscillation (microns), and the range for the lower and upper platen transducer amplifiers, sequentially written. The sample rate as determined by the program comprised the next logical record. Following records contained five samples each of the digital form of the signals from the transducers arranged in an alternating manner. The closure of a file was indicated by a tape mark written after the last record. Thus, a data sample of exactly two seconds duration would yield a file of 82 logical records and a total of 800 data points. This method permits the processing of each data file independently of other files on the tape and the addition of more files at a later date.

The data on the final BCD tape then underwent data reduction on an IBM 370/155 system (ICSA, Rice University) to give the components of the complex dynamic modulus (G' , G''). To produce the fundamental 6 hertz sinusoidal waves free from noise and determine the amplitude ratio and phase difference between the signals, it was necessary to filter the data by employing a narrow digital bandpass filter. This was accomplished using the program "Amplitude and Phase Analysis" from the University of California Biomedical Computer Programs (172). The dynamic shear storage and loss moduli were then computed from the amplitudes and phase angle using the analysis of Walters and Kemp (170,171) as programmed by Glover (75). The computer program for data reduction may be found in Appendix B.

Figure II-2. Schematic diagram of data reduction process.

To perform testing at frequencies other than 6 hz, it is necessary to change the sample rate such that 33.3 samples/cycle are taken. Thus, to digitize 9.48 Hz oscillatory data, the sample rate is set to 316 cps. With this method, the same filter parameters used in the digital filtration of 6 hz data may be employed. Caution is advised when the frequency of oscillation is near the resonance frequency of the upper platen assembly (15 hz). In this range, aberrant behavior of G' has been observed (171).

III. MATERIALS AND EXPERIMENTAL PROCEDURE

This chapter describes the materials and experimental procedures employed in the study of coagulation and fibrinolysis. The first section details the handling of blood and the preparation of plasma used in the experiments. Dynamic testing of coagulating plasma with the rheogniometer is outlined in the second section. In the third section, biochemical and clinical assays are described which further characterize coagulation and fibrinolysis of plasma in a variety of systems.

III.1 Plasma Preparation and Treatment

Blood Collection

In the collection of blood samples, only healthy adult male donors between the ages of 21 and 30 were used. All donors were non-smokers, and had fasted at least 8 hours prior to blood donation. Blood was drawn by venipuncture into siliconized glass tubes containing 3.8 percent trisodium citrate (9 parts blood: 1 part anticoagulant) at Methodist Hospital. The anticoagulated blood was transported immediately to the Biomedical Engineering Laboratory, Rice University, for preparation of plasma and hematocrit determination.

Plasma Handling

Platelet-rich plasma (PRP) prepared by centrifugation of whole blood at 170 g for 10 minutes in a GLC-1 centrifuge (Sorvall). Platelet-free plasma was produced by centrifuging whole blood in the GLC-1 at 1000 g for 15 minutes and centrifugation of the resultant platelet-poor plasma in a Beckman J21-B centrifuge for an additional 15 minutes at 11,000 g.

Platelet counts were performed with a Coulter Counter (Model ZBI, Coulter Electronics, Hialeah, Florida). Typical platelet counts obtained were 350,000 to 600,000 platelets/ mm^3 for PRP and < 2000 platelets/ mm^3 for PFP. If platelet concentration was greater than desired in PRP, PFP was used as a diluent.

In all handling, preparation, and treatment of blood and plasma, only siliconized glassware or plastic was allowed to contact the samples. Platelet-rich plasma was stored in tightly capped tubes at room temperature (21-25°C) prior to testing since studies indicate platelet function is more deleteriously affected by refrigeration or by incubation at 37°C (173). In tests involving PRP, experiments were completed within 10 hours of drawing the blood. No change in either the rate or extent of clotting or platelet aggregability was noted over this period. PFP was used within 12 hours of blood without noticeable deterioration.

Materials

Unless otherwise noted all stock solutions were prepared daily and stored at 4°C.

Streptokinase (SK, Varidase, Lederle, Pearl River, New York) was prepared in distilled water as a stock solution of 5000 units/ml.

Soybean trypsin inhibitor (SBTI, Sigma Chemicals, St. Louis, Missouri) was dissolved in distilled water. SBTI concentration was adjusted so that 1 ml of stock solution was capable of inhibiting 2.4 mg of trypsin with an activity of 8500 BAEE units/mg (1.6 - 2.0 mg SBTI/ml).

The hydroxylamine solution was 0.1 M NH_2OH in 0.05 M TRIS buffer, pH 7.4.

N-2-Hydroxyethylpiperazine-N¹-2-ethanesulfonic acid (HEPES, Calbiochem) was added directly to plasma. The pH of plasma containing HEPES was 6.5.

Phosphate buffered saline (PBS) was prepared by addition of 7.15 gm KH_2PO_4 , 3.195 gm Na_2HPO_4 , and 4.38 gm NaCl to 1 liter distilled water. This yielded a 0.027 M Na_2HPO_4 , .053 M KH_2PO_4 , .075 M NaCl solution of pH 7.4.

PBS-EtOH buffer was prepared by mixing 9 parts PBS to 1 part 95 percent ethanol.

Imidazole buffered saline (IBS) was 0.017 M imidazole and .12 M NaCl in distilled water, pH 7.4.

Michaelis buffer, pH 0.9, was prepared by mixing 10 ml .14 M sodium acetate buffer + 4 ml NaCl + 24 ml.

.5 N HCl + 11 ml distilled water. Michaelis buffer, pH 9.6, was made by mixing 98.5 ml 0.1 M barbital sodium and 1.5 ml 0.1 N HCl.

Hirudin (Sigma) was prepared as a stock solution of 50 units/ml in Michaelis buffer, pH 9.6.

3',5'-Dibutyryl cyclic adenosine monophosphate (DBcAMP, Sigma) was dissolved in PBS to give a 0.05 M stock solution.

Potassium cyanide (KCN, Baker), 2-deoxy-D-glucose (Sigma), and monoiodoacetic acid (IDA, Sigma) were prepared as 0.1 M stock solutions in PBS.

Cytochalasin B (Sigma) was dissolved in PBS/EtOH to yield a 1.0 mg/ml stock solution.

Human thrombin solution was prepared by dissolving 50 units Fibrindex (OrthoDiagnostics) in 6 ml of IBS.

Bovine thrombin (Dade) was prepared as a 200 u/ml stock solution in IBS or glycerine.

Thromboplastin reagent (Hyland) and cephaloplastin reagent were reconstituted with distilled water immediately before testing.

Adenosine diphosphate (ADP, Sigma) was prepared as a 1 mM stock solution in distilled water and stored at -20°C. On the day of use, the solution was thawed and diluted with distilled water to the appropriate concentration (typically 10 μ M).

Collagen reagent (Hormon-Chemie Munschen) was prepared as 0.1 mg/ml working solution.

The solution in which washed clots were dissolved prior to polyacrylamide gel electrophoresis was composed of 10 percent glycerol, 3 percent mercaptoethanol, and 2 percent sodium dodecyl sulfate (SDS).

Orthochromogenic substrate (S2222, OrthoDiagnostics) for assaying Factor Xa activity was dissolved in distilled water at a 5×10^{-4} M concentration. This compound is a specific substrate for Factor Xa and has the formula:

where R is 50 percent H and 50 percent CH_3 .

Fibrinogen Degradation Products

FDP were produced by incubation of fresh PFP with streptokinase, a plasmin activator. 0.1 ml Of 1500, 750, or 150 u/ml SK solution was added per 1.4 ml of fresh PFP to yield a final SK concentration of 100, 50, or 10 u/ml, respectively. These SK-PFP mixtures were allowed to incubate at 37°C for various lengths of time, and at the end of the incubation period 0.1 ml of SBTI solution was added per 1.5 ml plasma mixture to inhibit fibrinolysis. For those samples labeled as "0" minute, SBTI was added to PFP immediately prior to the addition of SK. 1.0 ml aliquots of the SBTI-PFP mixture were then transferred to plastic tubes, the tubes

tightly capped, and the samples quick frozen at -70°C in a dry ice-ethanol or dry ice-acetone bath. These frozen samples were stored at -20°C for later analysis. In some preliminary tests PRP was treated with 100 u/ml SK, and at the end of the incubation period SBTI added. The PRP was then recalcified and dynamic rheological measurements performed.

Fibrin Degradation Products

Fibrin degradation products were prepared by streptokinase treatment of clots formed from PFP. Recalcified fresh PFP was incubated at 37°C until the plasma was fully clotted (45-60 minutes). 0.1 ml of 1500 or 750 u/ml SK solution was then added to 1.4 ml of coagulated plasma, and the samples incubated for an additional 20-60 minutes at 37°C with agitation. At the end of this period, 0.1 ml of the SK-PFP clot mixtures and the samples centrifuged for 10 minutes at 8000 g to remove any undigested fibrin. The resulting supernatant was used immediately in dynamic rheological experiments or stored for biochemical analysis at a future time. The production of the control samples was identical except that SBTI was added simultaneously with the SK solution.

Inhibition of Crosslinking

Hydroxylamine (NH_2OH) was used as the crosslinking

inhibitor in a procedure identical to that of Glover (29,75). To 1.7 ml of PFP, 0.2 ml of 0.1 M NH_2OH solution or 0.2 ml 0.5 M NaCl (as an isoosmotic control) and 0.1 ml of 0.5 M NaCl were added. The mixture was then incubated 2 minutes at 37°C before undergoing further treatment or dynamic testing.

Induction of Fibrinolysis in Coagulating Plasma

As in the production of fibrinogen or fibrin degradation streptokinase was employed to induce fibrinolysis in coagulating plasma. One minute after recalcification of 2.0 ml fresh PFP, PRP, or PFP containing hydroxylamine or an isoosmotic control, 0.1 ml of 420 or 210 u/ml of SK or distilled water (as a control) was added to the plasma. The mixture containing 20, 10, or 0 u/ml SK was placed immediately between the platens of the rheogoniometer, and dynamic rheological measurements performed.

Inhibition of Platelet Function

Solutions of DBcAMP, KCN, 2-deoxy-D-glucose, IDA, and cytochalasin B were used to inhibit platelet function. In all cases, 0.2 ml of the inhibitor solution added to 1.8 ml of PRP ($\sim 200,000$ platelets/ mm^3) and the mixture incubated at 37°C prior to testing. Final concentrations of inhibitor and incubation periods may be found in Table III.1.

COMPOUND	BUFFER	INCUBATION PERIOD (Min)	FINAL CONCENTRATION
DBcAMP	PBS	50	5×10^{-5} M
KCN	PBS	30,60	10^{-3} , 5×10^{-3} M
2 deoxy-D-glucose	PBS	60	10^{-3} , 5×10^{-3} , 10^{-2} M
IDA	PBS	15	2×10^{-5} , 2×10^{-4} , 2×10^{-3} M
Cytochala-sin B	PBS/EtOH	60	10^{-2} , 5×10^{-2} , 10^{-1} mg/ml

Table III.1 Platelet inhibitor concentrations and incubation periods.

Warfarinized Plasma

Plasma from subjects undergoing anticoagulant therapy was a gift of Dr. C. P. Alfrey, Baylor College of Medicine. These samples were collected and PFP prepared as previously described. Blood for this study was drawn prior to the initiation of warfarin therapy and 5 and 12 days after therapy had begun. The drug regimen may be found in Table IV.16.

Freeze Drying of Plasma

To regulate the pH of freeze-dried plasma after reconstitution, 0.01 g HEPES per ml of fresh PFP was added. After centrifugation of the HEPES-containing PFP for 5

minutes at 1500 g to remove any debris, the HEPES-PFP was divided into 1 or 2 ml aliquots among plastic tubes, and the tubes tightly capped. The tubes (held in a wire rack) were then immersed in an acetone-dry ice bath for 30 minutes. After transferring a portion of the tubes to a -20°C freezer, the remaining tubes were uncapped and placed in a chamber of a lyophilisation unit (model 2001, Refrigeration for Science). The samples were subsequently lyophilised for 24 hours at -40°C. The resultant freeze-dried plasma was stored in tightly capped tubes at -20°C for future use.

III.2 Dynamic Rheological Testing

Recalcification

To replace the plasma calcium chelated by trisodium citrate and, thus, activate the coagulation mechanism, CaCl_2 at 37°C was added to the plasma. The amount of 0.25 M CaCl_2 required to recalcify the plasma was calculated using the formula (174):

$$x = \frac{(.2)v}{(1-\text{HCT})(3.9)}$$

where HCT is the hematocrit of the citrated blood, v is the volume of plasma to be recalcified and x is the volume of CaCl_2 to be added.

Preparation of Samples for Testing

In the testing of plasma containing fibrinogen degradation products, the frozen SK-treated 1 ml PFP samples were thawed 5 minutes in a 37°C water bath. To these samples, 1 ml of PFP or PRP ($\sim 4 \times 10^5$ platelets/mm³) was added and the mixture incubated 2 minutes at 37°C before recalcification. Similarly, one-to-one mixtures of serum containing fibrin degradation products (or the control) and PFP or PRP were incubated 2 minutes at 37°C before addition of calcium. Samples treated with anti-platelet agents were recalcified immediately following the incubation period. Normal plasma, PFP from subjects receiving warfarin, and freeze-dried PFP reconstituted with distilled water were incubated at 37°C for two minutes before recalcification.

Procedure

For all rheological testing with the Weissenberg Rheogoniometer, the following procedure was employed:

1. The transducer amplifiers were zeroed and the input oscillation amplitude adjusted to ± 90 microns, if necessary.
2. The platen temperature, flow rate of gases to the environmental chamber, and flag voltage were checked and, if required, adjusted.
3. The gain of the analog filter was adjusted so that

the full scale filtered outputs of the transducer amplifiers were ± 5.000 volts.

4. The gap-set transducer was zeroed. This was accomplished by allowing the torsion head to vibrate freely and gently lowering the upper assembly while observing the oscillation on an analog meter. Oscillation ceased upon contact of the upper and lower platen. At this point, the transducer amplifier was set to 0.0 microns.
5. The plasma or plasma mixture was recalcified and the stop watch started simultaneously.
6. The well-mixed recalcified sample was poured carefully on the bottom platen.
7. The upper assembly was lowered until the desired gap was achieved (578 microns).
8. A thin film of silicone oil (Dow Corning 200 fluid, 5 centistokes) was applied to the air-plasma interface.
9. The environmental chamber was closed about the platens.
10. The forced oscillation to the bottom platen was started.

The combination of silicone oil and a humidified atmosphere greatly reduced protein denaturation and drying at the gas-plasma interface.

From the time of recalcification to the oscillation start-up required less than two minutes. Data collection began with the first noticeable changes in the output waveform. The time between data points was approximately inversely proportional to the log rate of change of the modulus. In experiments with normal or rapidly clotting plasma, the moduli were measured for 90 minutes after recalcification. With abnormally slowly coagulating samples, the experiments lasted up to 200 minutes.

Platen Cleaning

After each experiment, the stainless steel surfaces of the platens were cleaned thoroughly. Before any contact with the platens, air pressure to the air bearing was increased to 45 psig, and the upper assembly held rigidly by a cable plate to prevent damage to the rotor. The clotted plasma was then gently removed, and the platen surfaces washed with detergent followed by distilled water. The washing was repeated several times, and to insure an uncontaminated surface the platens were rinsed with distilled water 3 times after the final application of detergent.

III.3 Additional Testing

Coagulation Tests

Standard clinical assays for the thrombin time (175),

prothrombin time (176), and activated partial thromboplastin time (177) were performed with a Coagulation Profiler (Model CP-7, Bio-Data) using solutions of human thrombin, thromboplastin, and cephaloplastin and 0.02 M CaCl_2 , respectively. A test for the time required for the polymerization of fibrin monomer in the presence of FDP was also carried out using a modification of the technique of Forman, Ratnoff, and Boyer (178). In this test, fibrin monomers are produced by thrombin at low pH (5.5), and because of the acidic environment they do not polymerize. By adding an alkaline buffer which contains hirudin, an inhibitor of thrombin, the fibrin monomer aggregation occurs. From this method, a fibrin monomer aggregation time is determined independently of the thrombin time (which is a measure of thrombin-fibrinogen interaction as well as the aggregability of fibrin monomer). To initiate the test, 0.1 ml bovine thrombin (200 u/ml) was added to 0.6 ml fresh PFP, 0.6 ml thawed SK-treated PFP from the same donor, and 0.3 ml pH 0.9 Michaelis buffer. At 20 seconds, 2, 4, 8, and 16 minutes after the addition of thrombin, 0.1 ml of hirudin solution (50 u/ml) in pH 9.6 Michaelis buffer). The tube was gently rocked, and the fibrin monomer aggregation time taken as the instant when the first clotting appeared.

Fibrinogen

Samples of fresh or treated PFP were frozen and

stored at -20°C for determination of fibrinogen concentration. In this measurement, either the V_{max} assay (179) or the biuret test (180) were employed.

Fibrinogen Degradation Products

FDP levels were measured using anti-D and -E antibody coated latex particles (181, Thrombo Wellcotest, Burroughs Wellcome). In this assay, thrombin is added to a plasma sample to clot all fibrinogen and "early" fragments (X + Y). After centrifuging down the clot, the serum is diluted with buffer and mixed with the antibody-coated latex particles. Aggregation of the particles indicates a concentration of fragment D + E in excess of $2\text{ }\mu\text{g/ml}$. By testing various dilutions of the serum an approximate range for the fragment D + E concentration may be established.

Crosslinking

The presence or absence of crosslinking in fibrin was tested by incubation of a clot in 5 M urea overnight at 37°C . At this urea concentration covalently crosslinked clots are insoluble while non-crosslinked clots will dissolve (182).

Platelet Function

The aggregation of platelets by the addition of exogenous ADP, thrombin, or collagen to PRP was measured by the

turbidimetric technique of Born (52,53). Either a Chronolog Platelet Aggregometer Recorder (Model 300, Chronolog) or a Platelet Aggregation Profiler (Model PAP-2, Bio/Data) was employed in this assay. Platelet aggregation in response to polymerizing fibrin monomer was also studied. In a method similar to the fibrin monomer aggregation test, fibrin monomer was generated by incubation of 0.6 ml fresh PFP, 0.6 ml of PFP previously incubated with 100 u/ml SK, 0.3 ml pH 0.9 Michaelis buffer, and 0.1 ml 50 u/ml bovine thrombin for 12 minutes at 37°C. At the end of this incubation period, 0.25 ml of this solution was added to 0.05 ml hirudin solution (100 u/ml). The pH was still sufficiently low that no polymerization occurred. 0.1 ml of the resultant mixture and 0.1 ml of pH 9.6 Michaelis buffer were then added simultaneously to an aggregation cuvette containing PRP (0.15-0.25 ml). Platelet aggregation was followed using the aggregometer for 10-12 minutes.

In addition, PRP was incubated with cytochalasin B for 60 minutes at 37°C, and dilute PRP clot retraction (71) and ¹⁴C-serotonin release (183) studies performed by methods previously described.

Factor Xa Activity

The activity of Factor Xa was assayed using an orthochromogenic substrate, S2222. When Factor Xa attacks S2222 a p-nitroaniline group is liberated, and this product

concentration may be measured spectrophotometrically. Employing a modification of the method of Aurell et al. (184), 2.0 ml pH 8.3 Tris buffer, 0.2 ml PFP, and 0.2 ml S2222 solution were placed in one cuvette of an Acta II spectrophotometer (Beckman Instruments). After allowing the cuvette to reach thermal equilibrium with the spectrophotometer heating block (37°C), 0.1 ml of 0.043 M CaCl_2 was added to the sample. Simultaneously, a stopwatch was started, and readings of the absorbance taken for the next 90 minutes. As a blank, an identical cuvette containing 2.1 ml pH 8.3 Tris, 0.2 ml S2222, and 0.2 ml PFP was used. By measuring the slope of the absorbance versus time curve, Factor Xa activity could be determined.

Gel Electrophoresis

Crosslink formation of clots formed in the presence of FDP was analyzed by electrophoresis in polyacrylamide gels as described by Glover et al. (29) and Weber and Osborn (185). Mixtures of the PFP treated with 100 u/ml SK and fresh PFP were clotted by recalcification for two hours at 37°C. The clots were then centrifuged, the supernatant removed, and the clots washed with PBS. After twice repeating the centrifugation and PBS wash, the clots were transferred to 5 ml of the SDS- β -mercaptoethanol-glycerol solution and incubated overnight at 37°C. Following incubation, 10 μ l samples were electrophoresed 4 hours in 7.5 percent

polyacrylamide gels. These gels were stained with Coomassie blue and destained in a Slab Gel Diffusion Destainer (SE 530, Hoefer Scientific Instruments).

pH

Measurements of pH were made with a Beckman pH meter at 37°C (Model #1019, Beckman Instruments).

IV. RESULTS

In this chapter, experimental results of rheological, biochemical and clinical assays are presented. These findings are grouped into five sections:

1. Normal plasma systems.
2. The effect of anti-platelet agents on platelet function and the coagulation of platelet-rich plasma.
3. Fibrinolysis of plasma and the effects of fibrin(ogen) degradation products on clotting.
4. Freeze-drying of PFP.
5. The effect of anti-coagulation therapy on the rate and extent of coagulation.

The significance of these results is discussed in Chapter V.

IV.1 Normal Plasma

Typical rheological measurements of the mechanical properties of PRP and PFP are shown in Figures IV-1 and IV-2. There are several interesting features of these normal clotting curves. Initially, the modulus of the plasma is too low to be measured with the rheogoniometer in the oscillatory

Figure IV-1. Shear storage or loss moduli (G' , G'') of recalcified normal PRP (2.0×10^5 platelets/ mm^3) or PFP (< 2000 platelets/ mm^3).

Figure IV-2. Shear storage and loss moduli (G' , G'') of recalcified normal PRP (2.0×10^5 platelets/ mm^3) and PFP (< 2000 platelets/ mm^3).

mode. However, with the onset of fibrin polymerization, there is a very rapid rise in the values of G' and G'' . In both PFP and PRP, G' is approximately an order of magnitude greater than G'' after the initial steep rise in clot strength. Thus, in the later stages of clot formation the magnitude of the complex dynamic modulus, $|G^*|$, is approximately equal to G' ($|G^*| = ((G')^2 + (G'')^2)^{1/2}$). Also, the phase angle, c , is close to 0° at these times, and small errors in its measurement have a relatively greater effect on G'' than G' because G' is proportional to $\cos(c)$ and G'' to $\sin(c)$. Consequently, there is more scatter in the shear loss modulus data. For these reasons, the graphs presented in later sections consist of G' data exclusively.

In comparing PFP and PRP clotting curves, it can be seen that the lag time between the addition of calcium and the sudden increase in the modulus was greater for PFP than PRP. The presence of platelets also greatly increased clot strength--observe that the plasma with 200,000 platelets/mm³ had a maximum G' ($G'_{\max}$) an order of magnitude greater than $G'_{\max}$ for the platelet-free plasma. In addition, note that the shape of the curves was different. While G' reaches a plateau for PFP, in the platelet rich system it attains a maximum at about 30 minutes and then slowly declines. The implications of this behavior will be fully discussed in the next chapter.

In order to determine the effect of decreased

fibrinogen concentration on the mechanical properties of PFP or PRP clots, plasma was diluted with normal saline or IBS. Figure IV-3 shows the effect of dilution of PFP on $G'_{\max}$ normalized with respect to the $G'_{\max}$ of an undiluted sample from the same donor. A linear least squares fit of the data indicates that the extent of clot formation, as measured rheologically, is directly proportional to the fibrinogen concentration. This agrees with Glover's finding that $G'_{\max}$ increases linearly with concentration of fibrinogen (29,75). When PRP was diluted and the platelet concentration held constant, a different relationship was observed (Figure IV-4). At a 50 percent decrease in plasma concentration, $G'_{\max}$ decreased 20-25 percent. Hence, at these platelet concentrations (160,000-200,000 platelets/mm³), clot strength was less dependent on fibrinogen concentration than in PFP. Cohen et al. have found similar results for their system of varying platelet and fibrinogen concentrations (73,74).

Thrombin time is chosen arbitrarily as the time at which the rate of change of optical density for a plasma-thrombin mixture is a maximum. The thrombin times of diluted PFP are graphed in Figure IV-5. For this typical plasma sample with a 10.3 second thrombin time for undiluted PFP, a 50 percent dilution resulted in an increase in thrombin time to 13.6 seconds.

Figure IV-3. G'_{MAX} of clots from PPP diluted with 0.9% saline. All values normalized with respect to G'_{MAX} of undiluted sample from the same donor.

Figure IV-4. Maximum shear storage modulus (G'_{max}) of PRP diluted with an isotonic buffer. Data normalized with respect to G'_{max} of an undiluted sample from the same donor.

Figure IV-5. Thrombin times of PFP diluted with imidazole buffered saline.

IV.2 Inhibitors of Platelet Function

This section presents data on the effects of chemical agents which prevent normal platelet function by inhibition of metabolism (moniodoacetic acid, KCN, 2-deoxy-D-glucose), by elevation of intraplatelet cyclic AMP (dibutyryl cAMP) and by interference with the microfilaments (cytochalasin B). In all cases, one volume of the inhibitor solution or a control buffer was added to nine volumes PRP with a platelet count of approximately $200,000/\text{mm}^3$.

Metabolic Inhibitors

In Figure IV-6, G' of clotting PRP, incubated 15 minutes with 2×10^{-5} , 2×10^{-4} , and 2×10^{-3} M final concentrations of sodium moniodoacetic acid (IDA) prior to recalcification, is shown. With increased IDA concentration, G'_{max} was depressed proportionately. At a 2×10^{-3} M IDA concentration, the "relaxation" of the clot resulted in a G' at 90 minutes of about 260 dynes/cm^2 . This is substantially below the maximum shear storage modulus of a clot formed from the PFP of this donor (400 to 600 dynes/cm^2 for recalcified PFP diluted 10 percent with a suitable buffer). Thus, it appears that IDA may have effects in this system apart from the inhibition of platelet metabolism.

The addition of 2-deoxy-D-glucose in final concentrations as high as 10^{-2} M had little effect on the G' of recalcified PRP (Figure IV-7). At a concentration of 10^{-2} M,

2-deoxy-D-glucose results in a $G'_{\max}$ of 3200 dynes/cm² compared to a control value of 4200 dynes/cm², approximately a 25 percent reduction. While a 10^{-3} M final concentration of KCN had no significant effect on the clotting of PRP (Figure IV-8), a combination of 5×10^{-3} M KCN and 5×10^{-3} M 2-deoxy-D-glucose incubated 60 minutes with PRP prior to recalcification decreased $G'_{\max}$ markedly (Figure IV-8 and IV-9). In addition, the magnitude of the decrease in G' between $G'_{\max}$ and G' at 90 minutes ($\Delta G'$) is reduced by these agents working in concert. The results for 5×10^{-3} M KCN and 5×10^{-3} M 2-deoxy-D-glucose are summarized in Table IV-1.

Number of Observations	$\frac{G'_{\max}}{(G'_{\max})_c}$	$\frac{\Delta G'}{(\Delta G')_c}$
5	$0.253 \pm .045$	0.217 ± 0.113

Table IV-1. Effect of 5×10^{-3} M KCN and 5×10^{-3} M 2-deoxy-D-glucose on the mechanical properties of PRP clots. $\Delta G' = G'_{\max} - G'$ at 90 minutes. Subscript "c" signifies control value. Results are $\pm$ one standard deviation.

While pre-incubation for 60 minutes with 10^{-2} M 2-deoxy-D-glucose did not affect the aggregation of platelets to 2 μ M ADP, 5×10^{-3} M KCN and 5×10^{-3} M KCN + 5×10^{-3} M 2-deoxy-D-glucose inhibited ADP-induced platelet aggregation

Figure IV-6. Dynamic shear storage modulus (G') of PRP incubated with 2×10^{-5} , 2×10^{-4} , 2×10^{-3} M monoiodoacetic acid (IDA), or PBS for 15 min.

Figure IV-7. Dynamic shear storage modulus (G') of PRP incubated with 10^{-3} M, 10^{-2} M 2-deoxy-D-glucose or 0.14 M NaCl for 60 minutes.

Figure IV-8. Dynamic shear storage modulus (G') of PRP incubated for 60 minutes with PBS, 10^{-3} M KCN, or 5×10^{-3} M KCN + 5×10^{-3} M 2-deoxy-D-glucose.

Figure IV-9. Dynamic shear storage modulus of PRP or PFP incubated for 60 minutes with PBS or 5×10^{-3} M KCN + 5×10^{-3} M 2-deoxy-D-glucose before recalcification.

Figure IV-10. ADP-induced platelet aggregation induced by addition of $0.1 \text{ ml } 10 \mu\text{M}$ ADP to 0.4 ml PRP (2.0×10^5 platelets/ mm^3) incubated 60 minutes with a) PBS/EtOH, b) 0.1 mg/ml cytochalasin B, c) $5 \times 10^{-3} \text{ M KCN}$, and d) (i) $5 \times 10^{-3} \text{ M } 2\text{-deoxy-D-glucose} + 5 \times 10^{-3} \text{ M KCN}$ or (ii) $10^{-2} \text{ M } 2\text{-deoxy-D-glucose}$.

(Figure IV-10).

Dibutyryl Cyclic AMP

The study of the effect of DBcAMP on the dynamic mechanical properties of clotting PRP was undertaken to supplement Kuntamukkula's data (77,86). A typical set of results for PRP incubated 50 minutes with 5×10^{-3} M DBcAMP is shown in Figure IV-11. As in Kuntamukkula's work, DBcAMP was found to reduce $G'_{\max}$ and the decline of G' . In Table IV-2, the effects of DBcAMP on PRP clots are summarized for the experiments of this study. Platelet concentrations before dilution of PRP were 200,000 to 222,000 platelets/mm³.

n	$\frac{G'_{\max}}{(G'_{\max})_c}$	$\frac{\Delta G'}{(\Delta G')_c}$	$\frac{t_{\max}}{(t_{\max})_c}$
4	$0.478 \pm .108$	$0.512 \pm .172$	$0.989 \pm .114$

Table IV.2. Effect of 5×10^{-3} M DBcAMP on coagulating PRP, 50 minute incubation before recalcification. $t_{\max}$ is the time after the addition of calcium at which $G'_{\max}$ is attained. Results $\pm$ one standard deviation.

Cytochalasin B

Typical results for rheological measurements of recalcified PRP pre-incubated with cytochalasin B in final

concentrations of 0.01, 0.05, and 0.1 mg/ml may be found in Figures IV-12 and IV-13. As the concentration of cytochalasin B was increased, it can be seen that $G'_{\max}$ and $\Delta G'$ decreased. This decrease appeared only in PRP; G' of PFP was not significantly affected by the presence of 0.1 mg/ml cytochalasin B (Figure IV-13). The results of the rheological studies are summarized in Table IV-3.

n	Cytochalasin B Concentration	$\frac{G'_{\max}}{(G'_{\max})_c}$	$\frac{\Delta G'}{(\Delta G')_c}$	$\frac{t_{\max}}{(t_{\max})_c}$
4	0.01 mg/ml	0.669 $\pm$.110	0.761 $\pm$.241	0.971 $\pm$.133
3	0.05 mg/ml	0.434 $\pm$.039	0.388 $\pm$.023	1.131 $\pm$.010
7	0.1 mg/ml	0.367 $\pm$.030	0.264 $\pm$.097	1.190 $\pm$.222

Table IV-3. The effect of cytochalasin B on the rheological properties of PRP clots. All values $\pm$ one standard deviation.

Cytochalasin B was also found to decrease clot retraction in dilute PRP. Platelet mediated retraction was totally inhibited at a concentration of 0.1 mg/ml. The results for a typical donor are pictured in Figure IV-14.

In all experiments, pre-incubation of PRP for 60 minutes with 0.01, 0.05, and 0.1 mg/ml cytochalasin B did not affect aggregation of platelets to 2 μ M ADP. The effect of cytochalasin B on collagen-induced platelet aggregation

Figure IV-11. Dynamic shear storage modulus (G') of re-calcified PRP or PFP incubated 50 minutes with IBS or 5×10^{-3} M DBcAMP.

Figure IV-12. Shear storage modulus of recalcified PRP incubated 0' in the presence of PBS/EtOH or 0.01, 0.05 or 0.1 mg/ml cytochalasin B.

Figure IV-13. Shear storage modulus (G') of recalcified PRP or PFP incubated 60 minutes in the presence of PBS/EtOH or 0.1 mg/ml cytochalasin B.

Figure IV-14. Dilute PRP clot retraction. PRP + a) PBS/EtOH (no thrombin added) b) PBS/EtOH; c) 0.01 mg/ml Cytochalasin B; d) 0.05 mg/ml cytochalasin B; e) 0.1 mg/ml cytochalasin B.

and ^{14}C -serotonin release were somewhat less clear. In the PRP from some donors, aggregation and release were nearly prevented in the presence of 0.1 mg/ml cytochalasin B, while no decrease and even some enhancement of these functions was found in others. Thus, at this concentration, the data exhibited a large standard deviation (Table IV-14). At the lower cytochalasin B concentrations, 0.05 and 0.01 mg/ml, collagen-induced aggregation and ^{14}C -serotonin release were affected little if at all (though recall at these levels, G'_{max} , $\Delta G'$, and clot retraction were significantly decreased).

Cytochalasin B Concentration	$\frac{\% \text{ Aggregation}}{(\% \text{ Aggregation})_c}$	$\frac{\% \text{ Release}}{(\% \text{ Release})_c}$
0.01 mg/ml	1.071 $\pm$.132	1.030 $\pm$.077
0.05 mg/ml	0.942 $\pm$.267	0.884 $\pm$.222
0.1 mg/ml	0.724 $\pm$.421	0.723 $\pm$.413

Table IV-4. The effect of cytochalasin B on collagen-induced platelet aggregation and ^{14}C -serotonin release. Seven observations. All results $\pm$ one standard deviation.

IV.3 Fibrinolysis

In this section, fibrinolysis and its effects on coagulation are studied. Results are reported for the effects of fibrinogen and fibrin degradation products on the coagulation of platelet-free and platelet-rich plasma and for

streptokinase-induced lysis of crosslinked and non-crosslinked clots. In addition, data is presented on the effects of FDP on platelet aggregation, thrombin time, and fibrin monomer aggregation.

Soybean Trypsin Inhibitor

Because SBTI was to be used as an anti-plasmin agent in these experiments, tests were initially carried out to determine its effects on the thrombin time and mechanical properties of coagulating PFP. The results for the addition of SBTI to recalcified PFP may be found in Figure IV-15. It is apparent that SBTI does not decrease the extent of clot formation. However, the time between recalcification and the sudden increase in G' lengthens with increasing SBTI concentrations. This is not unexpected as SBTI is an inhibitor of Factor Xa (186). Thrombin time is not affected by SBTI in the concentration range employed in this study (0.05 - 0.1 mg/ml) as can be seen in Table IV-5.

SBTI Concentration mg/ml	Thrombin Time (sec)
0.0	19.2 + .3
0.1	19.3 + .4
0.2	19.1 + .4
0.4	19.4 + .1
0.8	20.8 + .3

Table IV-5. SBTI concentration and thrombin time. Results $\pm$ one standard deviation.

Figure IV-15. Dynamic shear storage modulus (G') of recalcified PFP containing 0, 0.025, 0.05, or 0.1 mg/ml SBTI.

Fibrinogen Degradation Products

Fibrinogen degradation products were produced in normal PFP by the method described in the previous chapter. Fragment D and E levels in PFP incubated for various lengths of time with 100 u/ml were measured by the anti-D and E antibody-coated latex particle tests, and the results may be found in Table IV-6. At incubation times of 15 minutes and longer, there is a substantial concentration ($> 40 \mu\text{g/ml}$) of these end products of fibrinolysis.

The concentration of fibrinogen in PFP incubated with streptokinase proved more difficult to determine. Many assays such as the Biuret test simply measure the concentration of protein clottable by thromboplastin reagent or thrombin. Thus, if a clottable derivative of fibrinogen is present (such as fragment X) the fibrinogen concentration will appear greater than its actual value. Using the Biuret test or V_{max} assay, the clottable protein content was found to decrease with the length of 100 u/ml SK treatment, although approximately 50 percent remained even after 120 minutes incubation.

A measure of the ability of digested fibrinogen to form clots can be obtained by employing rheological techniques. In this series of experiments, 9 parts PRP were incubated with 1 part SK such that the final SK concentration was 100 u/ml. Nine parts of this mixture was then added to 1 part SBTI (final concentration .1 mg/ml) and the resulting

SK Incubation Time (min)	D & E Levels	
	> 10 $\mu\text{g/ml}$	> 40 $\mu\text{g/ml}$
Donor: JK		
0	-	-
3	-	-
10	+	-
15	+	+
20	+	+
30	+	+
45	+	+
120	+	+
Donor: JG		
0	-	-
3	-	-
10	+	-
15	+	+
20	+	+
30	+	+
45	+	+
120	+	+

Table IV-6. Fragment D & E levels for PFP incubated with 100 $\mu\text{g/ml}$ of SK. "+" indicates agglutination of anti-D and -E antibody coated latex particles.

PRP-SBTI-SK mixture recalcified. Comparing the clotting curves of these samples (Figure IV-16), PRP incubated for 10 minutes with SK yields a clot with a $G'_{\max}$ less than 10 percent that of a clot formed from the 0' control PRP (SK and SBTI added simultaneously). No change in platelet count was found due to SK incubation. PRP samples incubated with SK for periods longer than 15 minutes showed an inability to coagulate.

Results of the thrombin time assays for 1:1 mixtures of PFP incubated with 100 u/ml SK and fresh PFP from the same donor are shown in Figure IV-17 and Tables IV-7 and IV-8. From 0 minutes to 15 minutes incubation period, the thrombin increased rapidly. At 15 minutes, a plateau was attained, the thrombin time roughly twice that of the control value. This behavior was similar for both the 10 and 20 second thrombin time control series. For mixtures of fresh PFP and PFP incubated with 50 and 10 u/ml SK, thrombin times may be found in Tables IV-9 and IV-10, respectively. It can be seen that thrombin times increased with the length of incubation with 50 u/ml SK but did not change significantly from the control value for the PFP incubated with 10 m/ml of SK even for a 150 minute incubation period.

Fibrin monomer aggregation tests were performed employing modification of the method of Forman and colleagues (178) as described in the previous chapter. Results of this assay are given in Table IV-11. Since the aggregating

Figure IV-16. Dynamic shear storage modulus (G') of PRP incubated for 0, 3, or 10 minutes with 100 u/ml SK.

fibrin monomer was diluted to a great extent by the Michaelis buffers, it was difficult to ascertain the exact point when gelation occurred. Nonetheless, it is clear that with increased FDP and decreased fibrinogen concentration, the fibrin monomer aggregation time increased. To determine whether this effect was due to the presence of FDP or merely a consequence of decreased fibrinogen concentration, the test was repeated for a sample containing IBS in place of the SK-treated PFP. The fibrin monomer aggregation times for this mixture (50 percent control in Table IV-11) were lengthened to as great or greater extent than those samples containing FDP. Thus, it appears that the increase in aggregation times was due to a decrease in fibrinogen concentration rather than an effect of FDP.

Rheological measurements of recalcified 1:1 mixtures of fresh PFP and PFP previously incubated with SK were performed using the technique outlined in Chapters II and III. Maximum shear storage moduli normalized with respect to the $G'_{\max}$ of the sample containing the 0' digest (from the same donor) are shown in Figures IV-18, 19, and 20 for SK concentrations of 100, 50, and 10 u/ml, respectively. In the set of experiments with 100 u/ml of SK (Figure IV-17), the $G'_{\max}$ of the mixture containing the 3' digest was significantly greater (~ 30 percent) than that of the mixture composed of the 0' control. With longer SK incubation, the PFP digests caused a decrease in $G'_{\max}$ to approximately 50 percent of the

Figure IV-17. Thrombin times of 1:1 mixtures of fresh PFP previously incubated with 100 u/ml SK.

Incubation Period (min)	Thrombin time (sec)			
	Donor:	JG	JK	GA
0		10.3 $\pm$.2	10.8 $\pm$.2	10.1 $\pm$.1
3		11.4 $\pm$.2	11.8 $\pm$.2	10.2 $\pm$.1
6				13.1 $\pm$.2
10		19.1 $\pm$.4	17.1 $\pm$.4	16.9 $\pm$.3
15		22.3 $\pm$.6	18.5 $\pm$.2	18.2 $\pm$.2
20		24.7 $\pm$.5	18.5 $\pm$.2	19.7 $\pm$.3
26				19.8 $\pm$.3
30		22.5 $\pm$.1	18.5 $\pm$.3	
34				19.8 $\pm$.3
45		22.3 $\pm$.1	18.8 $\pm$.2	20.6 $\pm$.4
120		24.4 $\pm$.6	19.0 $\pm$.5	21.0 $\pm$.2

Table IV-7. Thrombin times of 1:1 mixtures of fresh PFP and PFP incubated with 100 u/ml SK. Results $\pm$ one standard deviation.

Incubation Period (min)	Donor:	Thrombin Time (sec)	
		JG	JK
0		21.4	22.4
3		21.1	24.7
10		39.0	27.0
15		29.6	34.5
20		42.9	34.7
30		46.6	35.9
45		45.7	44.7
120		47.7	37.2

Table IV-8. Thrombin times for 1:1 mixtures of PFP and PFP incubated with 100 u/ml SK.

Incubation Period (min)	Thrombin Time (sec)	
	Donor:	
	JG	JK
0	10.2 $\pm$.1	10.7 $\pm$.2
3	10.4 $\pm$.1	10.8 $\pm$.1
6	10.4 $\pm$.1	10.5 $\pm$.2
10	10.8 $\pm$.2	11.1 $\pm$.3
15	12.4 $\pm$.3	13.2 $\pm$.3
20	13.9 $\pm$.1	15.3 $\pm$.2

Table IV-9. Thrombin times for 1:1 mixtures of fresh PFP and PFP incubated with 50 u/ml SK. Results $\pm$ one standard deviation.

Incubation Period (min)	Thrombin Time (sec)		
	Donor:		
	JG	JK	JK
0	10.2 $\pm$.2	10.4 $\pm$.1	10.3 $\pm$.1
30	10.3 $\pm$.1		10.3 $\pm$.2
50		10.3 $\pm$.1	
60	10.3 $\pm$.1		10.3 $\pm$.1
100	10.3 $\pm$.1	10.5 $\pm$.1	10.2 $\pm$.1
150	10.3 $\pm$.1	10.5 $\pm$.1	10.2 $\pm$.2

Table IV-10. Thrombin times for 1:1 mixtures of fresh PFP and PFP incubated with 10 u/ml SK. Results $\pm$ one standard deviation.

Figure IV-18. Maximum shear storage modulus (G'_{MAX}) of clots formed from 1:1 mixtures of fresh PFP and PFP previously incubated with 100 u/ml SK. Data normalized with respect to G'_{MAX} of sample containing the 0 minute digest.

Figure IV-19. Maximum shear storage modulus (G'_{MAX}) of clots formed from 1:1 mixtures of fresh PFP and PFP previously incubated with 50 u/ml SK. Data normalized with respect to G'_{MAX} of sample containing the 0 minute digest.

Figure IV-20. Maximum shear storage modulus (G'_{MAX}) of clots formed from 1:1 mixtures of fresh PFP and PFP previously incubated with 10 u/ml SK. Data normalized with respect to G'_{MAX} of sample containing the 0 minute digest.

SK Incubation Time (min):	Donor:	DVK			
	<u>0</u>	<u>3</u>	<u>6</u>	10	15
				20	26
				34	45
					120

Thrombin incubation time	Fibrin monomer aggregation time (sec)				
20 sec	23	24	20	23	17
2 min	21	23	16	19.5	17
4 min	14	15	17	17	15
8 min	16	16	14	18	14
16 min	14	14	14	21	16

SK Incubation Time (min):	Donor: GA	50% Control
0	6	120
3	10	45
15	15	34
20	20	26
26	34	45
34	45	120

Thrombin incubation																			
time		14	16	25	30	20	22	23	23	23	18	20							
20 sec	∞																		
2 min	12	13.5	--	21	23	16	19	30	17	17	17	19							
4 min	13	17.5	25	18	16.5	16	19	23	22	16	22	22							
8 min	11.5	14	17	24	16	18	19	23	14	18	20	20							
16 min	11	18	24.5	13	17	14	25	17	12	18	17	17							

Table IV-11. Fibrin monomer aggregation times for 1:1 mixtures of fresh PFP and PFP incubated with 100 u/ml SK. Fibrin monomer produced at pH 5.5 with 13 u/ml bovine thrombin. 50% control is 1:1 mixture of fresh PFP and IBS rather than PFP digest.

control value. For plasma incubated with 50 u/ml SK, similar results were obtained. The presence of the 3' digest resulted in an increased clot strength compared to the control mixture, and as the incubation time increased, $G'_{\max}$ decreased, albeit somewhat more slowly than the 100 u/ml SK case. When dynamic measurements of G' were performed for mixtures of fresh PFP and PFP incubated with 10 u/ml SK up to 150 minutes, with one exception $G'_{\max}$ did not deviate from the control value more than 10 percent. This is an insignificant amount by this method. Fitting this data to a straight line by the method of least squares and forcing the curve to intercept the y-axis at 1.0 (as indeed it must since all values are normalized with respect to the 0' control) gave a slope of -0.03 min^{-1} . Thus, from the $G'_{\max}$ and thrombin time data, there appears to be no fibrinogen degradation in PFP incubated with 10 u/ml SK.

The lag time, t_0 , between recalcification and the beginning of the sudden increase in G' (arbitrarily chosen as the time at which $|G^*| = 15 \text{ dynes/cm}^2$) was lengthened for those mixtures containing PFP incubated with 100 or 50 u/ml SK for 15 minutes or longer (Table IV-12). However, this increase in t_0 did not exceed 50 percent and, indeed, was relatively small compared to the increases seen in plasma from hemophiliacs (75,77) or from subjects undergoing anticoagulation therapy (IV-5). No significant increase in t_0

Incubation Period (min)	t_o (min)			$\frac{t_o}{(t_o)_{o'}}$
	<u>100 u/ml SK</u>			
	(JG)	(JK)	(GA)	
0	16.0	18.0	16.7	1.00
3	15.4	19.7	15.0	1.00
6			15.8	0.94
10	16.3	19.2		1.04
15	19.8	23.4	18.6	1.22
20	17.1	23.8	19.8	1.19
30	15.6	21.5		1.09
45	15.8	26.8		1.24
120	19.4	31.2		1.47
	<u>50 u/ml</u>			
	(JG)		(JK)	
0	13.5		14.4	1.00
3	16.7		15.8	1.17
6	17.4		12.8	1.09
10	17.2		12.9	1.09
15	17.7		16.3	1.22
20	19.0			
	<u>10 u/ml</u>			
	(JG)		(JK)	
0	33.5		24.3	1.00
30			29.5	
50	23.0			
60			24.3	
100	23.5		25.8	
150	28.7		25.0	

Table IV-12. Clot initiation times for 1:1 mixtures of fresh PFP and PFP incubated with 100, 50, or 10 u/ml SK. $(t_o)_{0'}$ is t_o for mixture containing the 0 minute digest. t_o is the time after recalcification at which $|G^*| = 15 \text{ dynes/cm}^2$.

was noted for PFP incubated for up to 150 minutes with 10 u/ml SK.

To examine qualitatively if the presence of fibrinogen degradation products influences the α -polymerization and γ -dimerization of fibrin, electrophoretic gels were made of washed clots formed from recalcified mixtures of fresh PFP and PFP incubated with 100 u/ml of SK. In particular, the clot formed from fresh PFP and the 3' digest was of interest, since a higher $G'_{\max}$ was found for this sample. The excellent gels (produced by Joe Troll and Christie Rudi, Department of Hematology, University of Texas Medical School at Houston) showed the presence of α polymer and no apparent decrease in the concentration of these moieties when FDP were present (Figure IV-21). From these patterns, it appears that fibrinogen degradation products do not significantly alter the formation of interfibrin covalent crosslinks.

Results of the rheological measurements of the moduli for mixtures of equal parts fresh PRP and PFP incubated with 100 u/ml SK may be found in Figure IV-22 and Table IV-13. Platelet counts in the PRP before mixing were $4.0 \times 10^5/\text{mm}^3$ (donors JG and PN) or $3.5 \times 10^5/\text{mm}^3$ (donor GA). PRP was only added to SK-treated PFP from the same donor. It can be seen from the graph of normalized $G'_{\max}$ (Figure IV-21) that increased SK incubation time progressively decreased the maximum clot rigidity for times up to 30 minutes. While a 3 minute incubation sample yielded a higher $G'_{\max}$ for PFP when

Figure IV-21. SDS-polyacrylamide gels of washed clots formed from 1:1 mixtures of fresh PFP and PFP incubated previously with 100 u/ml SK.

Figure IV-22. Maximum shear storage modulus (G'_{MAX}) of clots formed from recalcified 1:1 mixtures of fresh PRP ($\sim 4 \times 10^5$ platelets/mm³) and PFP incubated with 100 u/ml SK. Data normalized with respect to G'_{MAX} of sample containing 0 minute digest.

compared to its control, in PRP a similar SK-treated sample resulted in a significant decrease. From the results of plasma dilution runs in PRP (Figure IV-4), a 25 percent reduction in $G'_{\max}$ would be expected if all the fibrinogen were degraded in the SK-treated PFP and the degradation products inert. However, for SK incubation times 10 minutes and greater $G'_{\max}$ was less than 60 percent the control value, and in the neighborhood of 30 minutes was less than 40 percent. Thus, the decrease was at least twice as great as would have been found if FDP had only a passive effect. The curve of $G'_{\max}$ versus SK incubation time also appeared to have a minimum in the half-hour range though the statistical significance is doubtful. The lag times for initial clot formation after recalcification were slightly increased for the mixtures containing FDP (Table IV-13).

For 1:1 mixtures of the fresh PRP and the PFP incubated with 100 u/ml of SK, no effect on ADP-induced or thrombin-induced platelet aggregation was found (Figures IV-23 and IV-24, respectively). Tests on polymerizing-fibrin-induced aggregation indicated that platelets may aggregate somewhat sooner in the presence of FDP, though the extent of aggregation did not significantly differ (Figure IV-25). When the SK-incubated PFP was used as an aggregating agent in normal PRP, no detectable platelet aggregation or response was elicited. In this system, the concentrations of FDP employed failed to promote or inhibit the extent of

SK Incubation Period (min)	Donor:			t_o (min)	$\frac{t_o}{(t_o)_{o'}}$
	JG	PN	GA		
0	7.5	11.2	9.9		1.00
3	12.5	12.3	8.7		1.22
6			8.5		.86
10	12.0	10.2	11.0		1.21
15	15.0	13.7	11.2		1.29
20	12.5	9.8	9.9		1.12
26		11.2	8.8		.94
30	14.5				1.93
34		12.8	10.5		1.10
45	13.0	12.8	9.8		1.29
120	14.0	13.6	10.8		1.39

Table IV-13. Clot initiation times for 1:1 mixtures of fresh PRP and PFP digested with 100 u/ml SK. t_o is time at which $|G^*| = 15$ dynes/cm². $(t_o)_{o'}$ is t_o for mixture containing PFP incubated 0 minutes with SK before addition of SBTI.

Figure IV-23. ADP-induced platelet aggregation. 0.1 ml of 10 μ M ADP added at 0 min (+) to 0.2 ml fresh PRP 3.5×10^5 platelets/mm³ + 0.2 ml PRP incubated previously with 100 u/ml SK for a) 0 minutes, b) 3 minutes, c) 25 minutes and d) 50 minutes.

Figure IV-24. Aggregation profiles of 0.1 ml 2 units/ml thrombin + 0.2 ml PRP (4×10^5 platelets/mm³) + 0.2 ml PFP incubated with 100 u/ml SK for a) 0 minutes, b) 3 minutes, c) 20 minutes, d) 50 minutes. Thrombin added at 0 minutes (+).

Figure IV-25. Platelet aggregation to polymerizing fibrin. See text for method. To 0.25 ml PRP (4.0×10^5 platelets/mm³), 0.1 ml pH 9.6 Michaelis buffer and 0.1 ml the PFP mixture containing a) 0 minutes, b) 5 minutes, c) 26 minutes, or d) 120 minutes digest were added.

platelet aggregation to a variety of aggregating agents.

To determine if FDP caused the decrease in $G'_{\max}$ of platelet-rich clots by interfering with events exterior or interior to the platelet, an agent which interferes with intra-platelet function, cytochalasin B, was employed in conjunction with SK-treated PFP. In these experiments, fresh PRP was mixed in a 1:1 ratio with PFP previously incubated for 0, 3, and 30 minutes with 100 u/ml of SK. Nine parts of this mixture were then incubated with 1 part of 1.0 mg/ml cytochalasin B solution or PBS/EtOH for 60 minutes before recalcification and dynamic rheological testing. Typical results for these experiments are shown in Figures IV-26-IV-29. As before, decreased $G'_{\max}$ was associated with increased length of the SK-incubation period, $G'_{\max}(30') < G'_{\max}(3') < G'_{\max}(0')$. This was also seen in the mixtures containing cytochalasin B (Table IV-14). In addition, cytochalasin B invariably results in a decreased $G'_{\max}$ for a particular mixture, eg. $G'_{\max}$ for a mixture of fresh PRP and PFP incubated 30 minutes with 100 u/ml SK will be higher when the mixture contains PBS/EtOH rather than 0.1 mg/ml cytochalasin B (Table IV-15). However, the effect of cytochalasin B was diminished for increased SK-incubation time. From Table IV-15 the addition of 0.1 mg/ml cytochalasin B to a PRP-0 minute PFP digest mixture resulted in a $G'_{\max}$ 38 percent that of the same mixture containing PBS/EtOH. The same concentration of cytochalasin B added to the mixtures composed of

Figure IV-26. Shear storage modulus of recalcified 1:1 mixtures of PRP previously incubated with 100 u/ml SK for 0 or 3 minutes. Mixtures incubated with PBS/EtOH or .1 mg/ml cytochalasin B for 60 minutes before addition of CaCl_2 .

Figure IV-27. Shear storage modulus of recalcified 1:1 mixtures of PRP (4×10^5 platelets/mm³) and PFP previously incubated with 100 u/ml SK for 0 or 3 minutes. Mixtures incubated with PBS/EtOH or 0.1 mg/ml cytochalasin B for 60 minutes before addition of CaCl₂.

Figure IV-28. Shear storage modulus of recalcified 1:1 mixtures of PRP (4×10^5 platelets/mm³) and PFP previously incubated with 100 u/ml SK for 0 or 30 minutes. Mixtures incubated with PBS/EtOH or 0.1 mg/ml cytochalasin B for 60 minutes before addition of CaCl_2 .

Figure IV-28. Shear storage modulus of recalcified 1:1 mixtures of PRP (4×10^5 platelets/mm³) and PFP previously incubated with 100 u/ml SK for 0 or 30 minutes. Mixtures incubated with PBS/EtOH or 0.1 mg/ml cytochalasin B for 60 minutes before addition of CaCl₂.

SK-Incubation Period (min)	$\frac{G'_{\max}}{(G'_{\max})_c}$	
	PBS/EtOH	0.1 mg/ml Cytochalasin B
0	1.00	0.38 $\pm$.10
3	0.67 $\pm$.20	0.32 $\pm$.15
30	0.27 $\pm$.17	0.17 $\pm$.07

Table IV-14. Data from 4 donors for normalized $G'_{\max}$ of 1:1 mixtures of PRP (380,000-400,000 platelets/mm³) and PFP incubated with 100 u/ml SK and containing PBS/EtOH or 0.1 mg/ml Cytochalasin B. $(G'_{\max})_c$ is the maximum shear storage modulus of a mixture containing the 0 minute digest and PBS/EtOH. Values $\pm$ one standard deviation.

SK Incubation Period (min)	$\frac{G'_{\max}(0.1 \text{ mg/ml Cyt B})}{G'_{\max}(\text{PBS/EtOH})}$
0	0.38 $\pm$.10
3	0.50 $\pm$.19
30	0.70 $\pm$.18

Table IV-15. Experimental results from 4 donors on the effect of cytochalasin B on the $G'_{\max}$ of 1:1 mixtures of fresh PRP (380,000-400,000 platelets/mm³) and PFP incubated with 100 u/ml SK. $G'_{\max}(0.1 \text{ mg/ml Cyt B})/G'_{\max}(\text{PBS/EtOH})$ is calculated using rheological data for samples containing identical PRP and the indicated PFP digest, only differing in the concentration of cytochalasin B (0.0 or 0.1 mg/ml). Data $\pm$ one standard deviation.

3 and 30 minute digests decreased $G'_{\max}$ to 50 percent and 70 percent respectively, of their PBS/EtOH values.

Fibrin Degradation Products

As a preliminary test of the effect of fibrin degradation products on the coagulation of plasma, fresh PRP or PFP was mixed with an equal part of serum from normal clotted PFP or from a PFP clot incubated with 100 u/ml of SK for 20 minutes (see Chapter III). The resultant mixture was then recalcified and rheological testing performed. Dynamic shear storage moduli for a typical series of experiments may be found in Figure IV-30. It is evident that in both PRP and PFP, fibrin degradation products decrease $G'_{\max}$ and increase the lag time between recalcification and the onset of coagulation.

Because the clots did not fully lyse during the SK incubation period, the concentration of D-dimer and E in the digest serum were unknown relative to the original fibrinogen concentration. Thus, the results of this section are qualitative.

SK-Induced Clot Lysis

The effects of 10 u/ml, 20 u/ml SK, or a distilled water control on the mechanical properties of coagulation PFP or PRP are presented in Figures IV-31 and IV-32, respectively. In both platelet-rich and platelet-free plasma, the

Figure IV-30. Shear storage modulus (G') of recalcified 1:1 mixtures of fresh PRP or PFP and fibrin clot digest or control. Fibrin clot digest produced by incubation of a PFP clot with 100 u/ml SK for 20 minutes.

addition of 10 u/ml SK yields a clot of only marginally lower $G'_{\max}$ which declines rapidly as fibrin is digested by plasmin.

The effect of hydroxylamine is shown in Figure IV-33. In normal PFP, the $G'_{\max}$ of fibrin clots containing 10 percent (by volume) 0.1 M NH_2OH was approximately 40 percent the $G'_{\max}$ of normal crosslinked clots. This agrees well with Glover's findings for the identical system (29,75). $G'_{\max}$ for PFP fibrin clots containing both NH_2OH and 10 u/ml SK was less than half that of the $G'_{\max}$ for PFP containing NH_2OH alone. In addition, the G' of fibrin clots formed from PFP containing both NH_2OH and 10 u/ml SK slowly decreased beginning 15-20 minutes after recalcification, indicating fibrinolysis. In contrast, G' values for PFP fibrin clots produced in the presence of 10 u/ml SK were only slightly less than values of G' for the control samples. PFP fibrin clots attained a lower $G'_{\max}$ and lysed more rapidly in the presence of 20 u/ml SK alone (Figure IV-34).

Incubation of PFP with 10 u/ml SK or 10 percent 0.1 M NH_2OH + 10 u/ml SK for up to 15 minutes did not significantly alter the thrombin times of these samples (Table IV-16).

Figure IV-31. Shear storage modulus (G') of recalcified PFP containing 0, 10, or 20 u/ml SK.

Figure IV- 32. Shear storage modulus (G') of recalcified PRP (2.0×10^5 platelets/mm³) containing 0, 10, or 20 u/ml SK.

Figure IV- 33. Shear storage modulus (G') of PFP containing 0 or 10 u/ml SK and 10% 0.1 M NH₂OH or an isotonic buffer.

Figure IV-34. Shear storage modulus (G') of recalcified PFP containing 20 u/ml SK and 10% 0.1 M NH₂OH or an isotonic control.

SK Incubation Period (min)	Thrombin Time (sec)	
	10 u/ml SK	10 u/ml SK + 10% 0.1 M NH_2OH
0	10.3 $\pm$.1	10.3 $\pm$.1
30	10.3 $\pm$.1	10.3 $\pm$.1
60	10.3 $\pm$.1	10.4 $\pm$.1
100	10.2 $\pm$.1	10.3 $\pm$.2
150	10.2 $\pm$.1	10.3 $\pm$.1

Table IV-16. Thrombin times for 1:1 mixtures of fresh PFP and PFP incubated with 10 u/ml SK and 10 percent 0.1 M NH_2OH or 10 u/ml SK alone. All results $\pm$ one standard deviation.

IV.4 Anticoagulation Therapy

Courtesy of Baylor College of Medicine PFP was obtained from volunteers undergoing anticoagulant therapy with sodium warfarin. The drug regimen for the 4 donors used in this study is given in Table IV-17. Six days prior to the start of dicoumarol therapy (4-11-78), thrombin, prothrombin, and activated partial thromboplastin times were determined, and rheological tests of coagulating PFP performed. All clinical coagulation tests proved normal (Figure IV-35). Typical results of the rheological tests may be found in Figure IV-36 and IV-37. It is evident that coagulation of recalcified PFP proceeded normally with a clot initiation time, t_0 , for the group of $12.0 \text{ min} \pm 1.3 \text{ min}$ (s.d.). Four days after therapy was begun (4-21-78) thrombin times remained normal while prothrombin and partial thromboplastin

		Warfarin Doses (mg/day)			
Day	Donor:	DB	RB	PJ	ET
1978					
4-17	1	15	15	15	15
4-18	2	10	10	10	10
4-19	3	5	5	5	5
4-20	4	10	15	15	10
4-21	5	12.5	25	30	12.5
4-22	6	12.5	25	30	12.5
4-23	7	12.5	20	20	12.5
4-24	8	12.5	20	20	12.5
4-25	9	12.5	15	15	10
4-26	10	10	15	15	10
4-27	11	10	12.5	12.5	5
4-28	12	10	12.5	12.5	5
4-29	13	10	12.5	12.5	5
4-30	14	10	12.5	12.5	5
5-1	15	10	12.5	12.5	5

Table IV-17. Drug regimen for subjects undergoing warfarin therapy.

Figure IV- 35. Thrombin time, prothrombin time, and activated partial thromboplastin time as % of control for PFP from patients undergoing warfarin therapy. See text for drug regimen.

Figure IV-36. Shear storage modulus (G') of recalcified PFP from a subject undergoing warfarin therapy.

Figure IV- 37. Shear storage modulus (G') of recalcified PFP from a subject undergoing warfarin therapy.

times were significantly prolonged. In addition, the mean clot initiation time was lengthened to 18.7 ± 4.1 min, though no significant change in $G'_{\max}$ or fibrinogen concentration was noted. Further prolongation of the clinical coagulation test times was found after another 7 days of warfarin administration (4-28-78), and clot initiation times increased to 101.9 ± 16.3 min (approximately 8 times the pre-warfarin value). No experimental $G'_{\max}$ could be determined for these samples because of the length of time required to allow coagulation to proceed to completion. Nonetheless, the fibrinogen concentration was not significantly different for these PFP samples.

IV.5. Lypholisation

Frozen and freeze-dried plasma showed significantly decreased $G'_{\max}$ and clot initiation times, t_0 , compared to fresh plasma (Figures IV-38 and IV-39, Table IV-18). Freeze-drying and lypholisation did not alter fibrinogen concentration as measured by the Biuret assay. Clots formed from fresh, frozen, and lypholised PFP were insoluble in 5 M urea, indicating that covalent crosslinking by Factor XIIIa was not seriously impaired.

The results of coagulation tests for a typical donor are presented in Table IV-19. While thrombin and prothrombin times were essentially the same for all samples, partial thromboplastin times were slightly though significantly less

Figure IV- 38 Dynamic shear storage modulus (G') of fresh, frozen, and lyophilised PFP.

Figure IV-39. Dynamic shear storage modulus (G') of fresh and lyophilised pooled PFP.

PFP	n	$\frac{t_o}{(t_o)_c}$	$\frac{G'_{max}}{(G'_{max})_c}$
Frozen	3	.499 $\pm$.119	.645 $\pm$.057
Lypholised	5	.551 $\pm$.057	.496 $\pm$.092

Table IV-18. The effect of freezing and lypholisation on the initiation and extent of PFP coagulation. Values normalized with respect to those of fresh PFP from the same donor. All data $\pm$ one standard deviation.

PFP	Thrombin Time (sec)	Prothrombin Time (sec)	Partial Thromboplastin Time (sec)
Fresh	10.3 $\pm$.1	11.6 $\pm$.2	32.6 $\pm$.2
Frozen	10.3 $\pm$.1	11.5 $\pm$.2	31.1 $\pm$.2
Lypholized	10.3 $\pm$.1	11.3 $\pm$.1	30.0 $\pm$.5

Table IV-19. Coagulation test times for PFP (donor: WK).
Results $\pm$ one standard deviation.

Figure IV-40. Absorbance at 405 nm of mixtures of S-2222 orthochromogenic substrate, TRIS buffer (pH 8.4) and recalcified fresh, frozen or lypholised PFP.

for the lypholised plasma compared to fresh PFP. Tests for the total potential Factor Xa conducted using a specific orthochromogenic substrate for this enzyme showed similar Factor Xa activity in recalcified fresh and lypholised PFP from the same donor (Figure IV-40).

V. DISCUSSION

This chapter is divided into three sections. In the first, rubber elasticity theory as applied to fibrin networks is discussed, and a mathematical model of coagulation kinetics derived. This model is then applied to some normal and abnormal platelet-free systems. The second section deals with the role of normal and drug-altered platelets in clot formation. Finally, explanations for the actions of fibrin(ogen) degradation products and plasmin on coagulating PFP and PRP are presented. Throughout this chapter, the attempt is made to integrate the results of this study with the current body of knowledge on hemostasis, thrombosis, and fibrinolysis.

V.1 Rubber Elasticity Theory and Coagulation Kinetics Modeling

In the first part of this section, the applicability of rubber elasticity theory to fibrin networks will be critically examined. The basic assumptions which underlie the theory will be outlined and the structure of fibrin clots discussed briefly. It will be seen that the fibrin network may not fall entirely within the framework of these assumptions, and, thus, the application of the theory may be

somewhat questionable.

For a crosslinked network (Figure V-1) the fundamental assumptions of the theory of rubber elasticity as presented by Flory (187) and Treloar (188) are:

1. Every chain in the network is terminated by a point of crosslinking, i.e. there are no free ends.
2. The chains in the network have a random coil configuration as if they were free in space.
3. The effect of deformation is to change the components of the vector length of each chain in the same ratio as the corresponding dimensions in the rubber network (the "affine deformation" assumption).
4. In either the strained or the unstrained state, each junction point may be regarded as fixed to within a small element of volume which is independent of the state of strain at its mean position within the material coordinate system.

For these assumptions, Gaussian statistical theory may be applied to each chain to calculate the entropy change and work of deformation. Doing so, the elastic shear modulus, G , of the network is found to be (188):

$$G = R T N$$

where R is the gas constant, T the absolute temperature, and

• crosslinkage

• 1 chain

Figure V-1. A crosslinked network.

N the "effective" crosslink density. Thus, if the number of crosslinks per unit volume is known, the modulus may be predicted. Conversely, the determination of G will yield the crosslink density. It remains to define the term "effective" crosslink. In keeping with the fundamental precepts of the theory, an effective crosslink is taken to mean a chemical (covalent) bond between chains which contributes to the modulus. In contrast to effective crosslinks, there may exist ineffective crosslinks which do not increase G , and pseudo-crosslinks that while they are not covalent crosslinks, nevertheless, contribute to G . These two deviations may arise as a result of network defects or molecular interactions.

Flory (187) specifies three basis types of network defects--molecular entanglements, loop linkages, and free chain terminations (Figure V-2). The first of these (Figure V-2a) acts as a pseudo-crosslink since it restricts the number of possible chain configurations. While chemically crosslinked chains will remain permanently bound under moderate stress, entangled segments of molecules will slip past each other if the network is subjected to constant strain for a sustained period. Hence, these pseudo-crosslinks give rise to stress relaxation, while the chemical (covalent) crosslinks do not. The second network defect occurs when a chain segment loops back on itself and forms an intramolecular crosslink (Figure V-2.b). In this case,

Figure V-2. Network defects: (a) entanglement, (b) intra-chain loop linkage, (c) free end. ● = crosslinkage, ○ = free end.
 (From: Treloar, L.R.G., The Physics of Rubber Elasticity, p. 80, Oxford University Press, London, 1958).

it is obvious that the crosslink is ineffective and will make no contribution to the modulus. If a chain terminates in a free end (Figure V-2.c), the configuration of that chain will not be restricted, and the adjacent crosslink will not increase the modulus.

Intra or intermolecular forces may significantly alter the modulus. If there is a substantial degree of hydrogen or electrostatic bonding between chains or adjacent units of a chain, the molecule may take on a preferred configuration. As a result, the random coil model and, hence, the Gaussian statistics leading to the modulus will be inappropriate. Along with the solvent interaction (e.g. hydrophobic interactions in protein-water solutions), these non-covalent bondings may cause steric hindrances resulting in restricted chain mobility and increased modulus. In particular, the conformation of proteins is dictated strongly by these interactions (see Dickerson and Geis (189)). Even isolated protein molecules are rarely random coils in their entirety. The bonds formed electrostatically or by hydrogen bonding, while not as strong as covalent chemical crosslinks, may be capable of significantly adding to G . It is conceivable that hydrogen bonding or electrostatic bonds could far outnumber the intermolecular covalent bonds (especially in a system of large biopolymers), and thus, there would appear to be a greater number of effective crosslinks owing to these pseudo-crosslinks.

When the system consists of x primary molecules, then Flory (187) indicates that a threshold number of crosslinks must be formed before a network is established. Additional crosslinks contribute to the modulus, and, therefore, the number of effective crosslinks, v_e , may be found from

$$v_e = v - 2x$$

where v is the total number of crosslinkages. This states that two crosslinks per primary molecule are ineffective.

Glover has applied the theory of rubber elasticity to fibrin networks in order to determine the crosslink density. The complex dynamic shear modulus G^* , was found for PFP clots using the Weissenberg rheogoniometer in the oscillatory mode. Recalling that $G^* = G' + G''$, and $G' \gg G''$ then $|G^*| = G$. By applying the formula

$$N = \frac{|G^*|}{RT}$$

to recalcified PFP which contained a known concentration of fibrinogen and for which $|G^*|$ had been determined, Glover calculated that there are 3 effective crosslinks or a total of 5 crosslinks per fibrin monomer (29). This compares favorably with the 6 crosslinks per molecule measured chemically by Pisano et al. (24). However, if the structure of the fibrin network is examined in light of the basic assumptions of rubber elasticity theory, the reason for this

agreement is not readily apparent.

On the molecular level, fibrin polymer is not randomly dispersed, but rather it is packed regularly in fibers. Even at the level which may be resolved with the light microscope, one sees these fibrin strands (166). Because of the regular structure of the fibrin polymer in these fibers, it is doubtful that there would be many entanglements or loop kinkages on the molecular level. The great length of fibrin polymers (21) indicates a relatively small number of free ends. Therefore, network defects on a molecular level do not increase or decrease greatly the number of effective crosslinks. Almost certainly, the fibrin chains do not assume a "random coil" configuration, and, thus, the second fundamental assumption of rubber elasticity theory is violated. In addition, electrostatic and hydrogen bonding undoubtedly account for a significant portion of the clot strength. Recall that $G'_{\max}$ for non-crosslinked clots was 30-40 percent that of crosslinked. This residual modulus may have been the result of these non-covalent interactions. It is possible that the electrostatic and hydrogen bonds serve the same function as crosslinks albeit somewhat weaker than covalent bonds. Thus these interactions restrict the configurations and movements of the molecules and along with hydrophobic interactions result in fiber formation.

Another aspect of fibrin polymer structure which merits attention is the structure of the fibrin monomer.

Briefly reviewing its structure, the fibrin molecule consists of three pairs of chains linked by 28-29 disulfide bridges (15,16). Formation of the ϵ -(γ -glutamyl) lysine crosslinks occurs between α and γ chains to yield α polymers and γ dimers (16,22-25). The question arises as to which of these crosslinks effectively contributes to the modulus. Because the disulfide bridges are intramolecular in nature, they primarily serve a structural role in maintaining the integrity of the molecule. For example, twelve disulfide bridges link the γ and β chains of the fibrin molecule and consequently do not contribute to the long range network structure. Nonetheless, the disulfide bridges do restrict the configuration of fibrin molecule and, thus, affect the modulus. While the crosslinks which form the α polymer obviously act as effective crosslinks, the contribution to the modulus by the covalent bonds between γ dimers is unclear. Glover's studies with hydroxylamine (29), (which completely inhibited α -polymer formation and slightly reduced the number of γ dimers) indicate that the α -polymer bonds which form the three-dimensional network are more important in maintaining the modulus than the γ -dimer bonds between fibrin monomers in the same linear array. Thus, γ -dimer covalent linkages while structurally important are not fully effective in the development of clot rigidity.

Despite the deviation of fibrin network from an "ideal rubber," rubber elasticity theory still provides an

acceptable first approximation for the modulus of PFP clots as a function of fibrinogen concentration and crosslink density. Indeed, at the present time it provides the only prediction of G' . Data from this and Glover's study (29) on $G'_{\max}$ as a function of fibrinogen concentration support the theory's contention that G' is directly proportional to crosslink density. With its limitations in this system recognized, a modified rubber elasticity theory will continue to be employed.

Models for Coagulation Kinetics

In modeling the coagulation process, there are two major objectives. First, the equation or set of equations must predict observed behavior. Second the set of equations must be sufficiently tractable such that necessary parameters may be obtained using the existing data base and a reasonable amount of computation time. To determine the form of the equations, the basic processes leading to clot formation in PFP will be discussed.

As described in the first chapter, thrombin catalyzes the conversion of fibrinogen monomer. This fibrin monomer associates electrostatically to form a linear fibrin array. In the presence of Factor XIIIa, the linear polymer undergoes crosslinking to yield a three-dimensional network. The shear storage modulus, G , is a result of the crosslinks and the electrostatic and hydrogen bonding. Therefore, fibrin

network formation and the development of G may be considered a two-step process consisting of fibrinogen-to-fibrin-monomer conversion and subsequent fibrin monomer polymerization and crosslinking.

If the thrombin-catalyzed fibrinogen conversion is taken as a first-order reaction in fibrinogen and thrombin, an expression for the rate of change of fibrinogen in an isothermal system may be written

$$\frac{dFg}{dt} = -k_1(Fg)(Th) \quad (V.1)$$

where k_1 is a rate constant, Fg is the fibrinogen concentration, and Th is the thrombin concentration (as yet unspecified). Fibrin monomer is formed by this process and is assumed to polymerize by an m-th order reaction in fibrin monomer concentration, Fb. The equation describing this process is:

$$\frac{dFb}{dt} = k_1(Fg)(Th) - k_2(Fb)^m \quad (V.2)$$

where k_2 and m are constants.

The evolution of effective crosslinks may be expressed:

$$\frac{dN}{dt} = ak_2(Fb)^m \quad (V.3)$$

where "a" is a constant relating polymer concentration to crosslink density and N is the concentration.

Applying the theory of rubber elasticity, the shear storage modulus, G' , may be found at a given temperature from

$$G' = k_3 N \quad (V.4)$$

or

$$\frac{dG}{dt} = ak_3 k_2 (Fb)^m \quad (V.5)$$

where k_3 is the gas constant times temperature.

Alternatively, the production of the fibrin network can be considered a one-step process where the appearance of crosslinks is assumed directly proportional to the disappearance of fibrinogen:

$$\frac{dN}{dt} = -a \frac{dFg}{dt} \quad (V.6)$$

Assuming this process has a first-order dependence of thrombin and an n -th order dependence on fibrinogen, an expression for the rate of change of fibrinogen concentration may be written:

$$\frac{dFg}{dt} = -k_1 (Th) (Fg)^n \quad (V.7)$$

Hence, the shear modulus may be obtained from the equation:

$$\frac{dG'}{dt} = ak_1 k_3 (Th) (Fg)^n \quad (V.8)$$

While the two-step model is perhaps slightly more

realistic, the system of equations on the one-step model is much less tedious to solve, and one less parameter is involved. Thus the one-step model will be employed as a first approximation.

Applying the initial condition:

$$F_g = F_0, \quad t = 0 \quad (V.9)$$

Equation (V.7) may be rearranged to yield:

$$\int_{F_0}^{F_g} \frac{dF_g}{(F_g)^n} = -k_1 \int_0^t (Th) dt \quad (V.10)$$

which may be integrated to give:

$$\ln \left[\frac{(F_g)}{(F_0)} \right] = -k_1 T, \quad n = 1 \quad (V.11)$$

or

$$\frac{1}{n-1} \left[\left(\frac{1}{F_0} \right)^{n-1} - \left(\frac{1}{F_g} \right)^{n-1} \right] = -k_1 T, \quad n \neq 1 \quad (V.12)$$

where

$$T = \int_0^t (Th) dt \quad (V.13)$$

Equation (V.11) and (V.12) may be rearranged to obtain expressions explicit in the fibrinogen concentration

$$F_g = F_0 \exp[-k_1 T], \quad n = 1 \quad (V.14)$$

$$F_g = \frac{F_o}{[1+(n-1)k_1F_o^{n-1}T]^{1/n-1}}, \quad n \neq 1 \quad (V.15)$$

If there are no crosslinks present at $t = 0$ then

$$\int_0^N dN = -a \int_{F_o}^{F_g} dF_g \quad (V.16)$$

which obviously yields

$$N = a(F_o - F_g) \quad (V.17)$$

$$= aF_o(1 - \exp[-k_1T]), \quad n = 1 \quad (V.18)$$

$$= aF_o\left(1 - \frac{1}{[1+(n-1)k_1F_o^{n-1}T]^{1/n-1}}\right), \quad n \neq 1 \quad (V.19)$$

Thus, the shear modulus G may be found from

$$G' = ak_3F_o(1 - \exp[-k_1T]), \quad n = 1 \quad (V.20)$$

$$= ak_3F_o\left(1 - \frac{1}{[1+(n-1)k_1F_o^{n-1}T]^{1/n-1}}\right), \quad n \neq 1 \quad (V.21)$$

An equation for the thrombin concentration must be chosen such that the model system exhibits the following behavior

$$(1) \quad F_g \rightarrow 0 \quad \text{as} \quad t \rightarrow \infty$$

$$(2) \quad G' \rightarrow G_{\max}^i \quad \text{as} \quad t \rightarrow \infty$$

- (3) After some initial period during which $G' \approx 0$, G' suddenly increases.

These criteria and physical intuition suggest that after some lag period in which $Th = 0$, the thrombin concentration rises rapidly to some steady state value.

To satisfy these requirements the conversion of prothrombin (Pr) to thrombin is modelled by the equation:

$$\frac{dPr}{dt} = -k'_0(t)(Pr) \quad (V.22)$$

where

$$k'_0(t) = 0 \quad 0 \leq t \leq t_i \quad (V.23)$$

$$= k'_0 \text{ [a constant]} \quad t > t_i \quad (V.24)$$

Thus, in this approximation, $k'_0(t)$, which is a function of Factor Xa, Factor V, phospholipid, and Ca^{++} concentration as well as time, is zero for $0 \leq t \leq t_i$ and some constant value when $t > t_i$. In reality, $k'_0(t)$ is some continuous function of time rather than a step function. However, the arbitrary introduction of a more complex function in the absence of quantitative data on prothrombin conversion cannot be justified.

An initial condition for the prothrombin concentration and an expression relating the thrombin and prothrombin concentration can be written:

$$Pr = T_0, \quad 0 \leq t \leq t_i \quad (V.25)$$

$$T_0 = Pr + Th \quad (V.26)$$

Using this initial condition, Equation (V.22) may be integrated to yield:

$$Pr = T_0, \quad 0 \leq t \leq t_i \quad (V.27)$$

$$= T_0 \exp[-k'_0(t-t_i)], \quad t > t_i \quad (V.28)$$

From Equation (V.26), the thrombin concentration is found to be:

$$Th = 0, \quad 0 \leq t \leq t_i \quad (V.29)$$

$$= T_0(1-\exp[-k'_0(t-t_i)]), \quad t > t_i \quad (V.30)$$

Using Equations (V.29) and (V.30), the integration in Equation (V.13) may be carried out to yield T:

$$T = \int_0^t (Th) dt \quad (V.13)$$

$$= 0, \quad 0 \leq t \leq t_i \quad (V.31)$$

$$= T_0 \int_{t_i}^t (1-\exp[-k'_0(t-t_i)]) dt, \quad t > t_i \quad (V.32)$$

$$= T_0 \left[(t-t_i) - \frac{1-\exp[-k'_0(t-t_i)]}{k'_0} \right], \quad t > t_i \quad (V.33)$$

To reduce the number of parameters the following definitions are made:

$$F_g^* = F_g/F_0 \quad (V.34)$$

$$k_1' = k_1 F_0^{n-1} T_0 \quad (V.35)$$

In addition, it may be recognized that:

$$G_{\max}' = a k_3 F_0 \quad (V.36)$$

Substituting the expression for T, Equations (V.14, 15, 20, and 21) become for $t > t_i$:

$$F_g^* = \exp(k_1'[(t-t_i) - \frac{(1-\exp[-k_0'(t-t_i)])}{k_0'}]), \quad n = 1 \quad (V.37)$$

$$= \frac{1}{(1+k_1'(n-1)[(t-t_i) - \frac{(1-\exp[-k_0'(t-t_i)])}{k_0'}])^{1/n-1}}, \quad n \neq 1 \quad (V.38)$$

$$G' = G_{\max}' [1 - \exp(k_1'[(t-t_i) - \frac{(1-\exp[-k_0'(t-t_i)])}{k_0'})]), \quad n = 1 \quad (V.39)$$

$$= G'_{\max} \left[1 - \frac{1}{(1+k'_1(n-1)) \left[(t-t_i) - \frac{(1-\exp[-k'_0(t-t_i)])}{k'_0} \right]^{1/n-1}} \right],$$

$$n \neq 1 \quad (V.40)$$

Of course, G^* is zero, and Fg^* is one over the interval 0 to t_1 .

Before proceeding to fit the data to the model, it is important to discuss the physical significance of each of the parameters. The lag time, t_i , is a measure of the early coagulation cascade. In it is lumped the concentrations and rates of activation of Factors XII through IX. The constant k'_0 contains the prothrombinase concentration and the rate constant for the conversion of prothrombin to thrombin. k'_1 relates to final thrombin concentration (T_0), the rate constant for the formation of fibrin monomer from fibrinogen, and the aggregation, polymerization and crosslinking of fibrin. Both k'_0 and k'_1 have dimensions of time^{-1} . The maximum shear modulus, $G_{\max}$, is proportional to crosslink density, temperature, and the gas constant as in rubber elasticity theory. It has units of force/length^2 (pressure). The constant, n , is the order of the overall fibrinogen to fibrin network reaction with respect to fibrinogen concentration.

To determine the parameters which best fit the rheological data, an algorithm for the least-squares estimation of non-linear parameters was employed (190). This iterative

technique uses the Gauss method and the method of steepest descent to obtain a least-squares estimate of the model parameters. A computer program of the method was provided by Dr. Keicli Aoyogi and modified subsequently to run more efficiently with this mathematical model. Typically, 4 to 20 seconds of CPU time was required to fit ~ 30 data points. A printout of the FORTRAN program may be found in Appendix C.

Initially, the program was used to fit the five parameters, t_i , k_0 , k_1 , $G'_{\max}$, and n to the G' data for PFP, where the independent variable is the time after recalcification and G' is the dependent variable. However, unique solutions were difficult to obtain when n was left as a free parameter. Therefore, n was specified as a constant and the other parameters obtained by fitting the data. The results of these estimations when $n = 1$ or 2 may be found in Tables V-1 and V-2. In addition the standard deviation (the square root of the variance of residuals) is given for each fitted set of data.

Comparing the ability of the model to fit the experimental results in the case where $n = 1$ or 2 , it is apparent that only for those samples containing HEPES (the fresh-frozen-lyophilized series) does $n = 2$ give a better fit. Neither case yields consistently or significantly smaller standard deviations for the normal, warfarinized, SBTI containing or $\text{NH}_2\text{OH}/\text{NaCl}$ -treated PFP. For both cases, the parameters $G'_{\max}$ and t_i are very close. With $n = 2$, $G'_{\max}$ is

Sample	Date (min.)	t_i (min.)	k'_O (min. ⁻¹)	k'_I (min. ⁻¹)	G'_{max} (dynes/cm ²)	s.d.
JKPFP (normal)	9-26-78	9.79	0.155	0.090	419.1	14.18
DFPFP (normal)	7-18-78	11.38	0.073	0.515	543.9	6.05
DBPFP (normal)	4-11-78	9.22	0.0894	0.420	874.7	25.18
RPFP (normal)	4-11-78	10.79	0.077	0.371	758.8	26.85
PJPFP (normal)	4-11-78	12.71	0.775	0.117	629.9	16.03
ETPFP (normal)	4-11-78	11.35	0.072	0.520	545.2	19.19
DBPFP (warfarin)	4-21-78	23.04	0.155	0.117	565.6	6.01
RPFP (warfarin)	4-21-78	18.53	1.150	0.088	585.5	22.65
PJPFP (warfarin)	4-21-78	13.88	0.439	0.082	839.9	21.18
ETPFP (warfarin)	4-21-78	15.18	0.171	0.075	571.5	5.83
DBPFP (warfarin)	4-28-78	76.27	0.00086	0.755	358.9	3.87
RPFP (warfarin)	4-28-78	80.88	0.026	0.0034	708.9	2.84
PJPFP (warfarin)	4-28-78	110.7	0.018	0.039	310.4	4.45
ETPFP (warfarin)	4-28-78	71.92	0.00094	0.037	1417.0	2.97
JKPFP (H ₂ O control)	9-27-78	11.59	0.948	0.109	431.5	10.33
JKPFP (0.025 mg/ml SBTI)	9-27-78	13.32	0.246	0.059	503.8	9.00
JKPFP (0.05 mg/ml SBTI)	9-27-78	17.05	0.099	0.078	454.2	5.51
JKPFP (0.1 mg/ml SBTI)	9-27-78	22.77	0.086	0.027	637.7	3.37
JLPFP (fresh + HEPES)	11-10-77	8.33	3.823	0.108	457.5	20.09
JLPFP (frozen)	11-11-77	5.36	20.80	0.245	312.0	19.88
JLPFP (lypholised)	11-11-77	4.37	8.01	0.392	260.9	18.49
WKPFP (fresh + HEPES)	1-30-78	12.86	1.606	0.102	1072.0	25.12
WKPFP (frozen)	1-31-78	6.13	8.181	0.153	677.7	49.57
WKPFP (lypholised)	2-01-78	6.18	1.893	0.292	473.4	25.78
WKPFP (lypholised)	2-01-78	6.25	17.52	0.197	624.6	42.18
PopFP (fresh pooled)	2-17-78	9.46	0.291	0.149	1415.0	34.67
PopFP (lyph pooled)	2-21-78	6.06	14.18	0.373	558.9	39.89
PopFP (lyph pooled)	2-21-78	5.23	3.288	0.289	563.9	38.91

Table V-1 (Con't)

Sample	Date (min.)	t _i (min.)	k _o ['] (min. ⁻¹)	k _o ['] (min. ⁻¹)	G _{max} ['] (dynes/cm ²)	s.d.
WKPPF (NaCl Control)	11-22-77	12.92	0.337	0.146	775.4	16.34
WKPPF (10% NH ₂ OH)	11-22-77	10.21	5.317	0.276	268.6	12.10
WKPPF (NaCl Control)	11-28-77	9.60	0.036	0.364	605.3	18.80
WKPPF (10% NH ₂ OH)	11-28-77	11.63	0.842	0.179	272.1	11.80

Table V-1. Rheological parameters for recalified PFP, n = 1. Standard deviation (s.d.) is the square root of the variance of residuals. See text for explanation of parameters and mathematical model.

Sample	Date (min.)	t_i (min.)	k_o' (min. ⁻¹)	k_i' (min. ⁻¹)	G_{max}' (dynes/cm ²)	s.d.
JKPFP (normal)	9-26-78	9.78	0.0075	1.42	443.5	12.83
DFPFP (normal)	7-18-78	12.07	.00040	146.4	563.7	13.87
DBPFP (normal)	4-11-78	10.02	.0020	31.3	898.8	38.37
RBPFP (normal)	4-11-78	11.62	0.0018	26.37	780.8	36.40
PJPFP (normal)	4-11-78	12.60	0.219	0.248	685.9	8.75
ETPFP (normal)	4-11-78	12.06	0.0039	15.08	565.5	14.05
DBPFP (warfarin)	4-21-78	23.16	0.0063	2.43	599.8	6.56
RBPFP (warfarin)	4-21-78	18.44	0.447	0.118	682.5	15.63
PPFP (warfarin)	4-21-78	13.74	0.154	0.149	945.8	14.98
ETPFP (warfarin)	4-21-78	14.85	0.0112	0.766	607.3	6.01
DBPFP (warfarin)	4-28-78	77.64	0.0012	0.480	503.6	5.31
RBPFP (warfarin)	4-28-78	80.13	0.0166	0.0031	930.6	2.84
PJPFP (warfarin)	4-28-78	110.0	0.0049	0.111	399.7	4.45
ETPFP (warfarin)	4-25-78	71.70	0.00090	0.0195	2797	9.41
JKPFP (dist H ₂ O)	9-27-78	11.40	0.256	0.210	475.0	6.40
JKPFP (0.025 mg/ml SBTI)	9-27-78	13.0	0.075	0.129	565.7	7.44
JKPFP (0.05 mg/ml SBTI)	9-27-78	17.07	0.0663	0.094	493.7	5.61
JKPFP (0.1 mg/ml SBTI)	9-27-78	22.48	0.0506	0.0307	829.8	3.27
JLPFP (fresh + HEPES)	11-10-77	8.497	1.198	0.147	522.1	10.37
JLPFP (frozen)	11-11-78	5.52	2.348	0.424	336.4	11.22
WKPFP (fresh + HEPES)	1-30-78	12.80	0.513	0.155	1209	10.69
WKPFP (frozen)	1-31-78	6.38	3.059	0.224	753.6	30.44
WKPFP (lypholised)	2-01-78	6.29	0.808	0.558	628.7	16.44
WKPFP (lypholised)	2-01-78	6.40	2.759	0.314	596.0	26.14

Table V-2 (Con't)

Sample	Date (min.)	t _i (min.)	k' ₀ (min. ⁻¹)	k' ₁ (min. ⁻¹)	G' _{max} (dynes/cm ²)	s.d.
PopPP (fresh)	2-17-78	9.48	0.041	8.278	1456	44.17
PopPP (lypholised)	2-21-78	6.15	3.338	0.629	600.5	21.33
PopPP (lypholised)	2-21-78	5.34	1.487	0.483	610.5	24.18
WKPPF (NaCl control)	11-22-77	12.93	0.013	2.786	801.9	13.91
WKPPF (10% NH ₂ OH)	11-22-77	10.01	0.557	0.649	284.1	8.91
WKPPF (NaCl Control)	11-28-77	10.81	0.029	7.283	642.1	24.73
WKPPF (10% NH ₂ OH)	11-28-77	11.78	0.326	0.370	293.8	8.40

Table V-2. Rheological parameters for recalcified PFP, n = 2. Standard deviation (s.d.) is the square root of the variance of residuals. See text for explanation of parameters and mathematical model.

Figure V-3. Dynamic shear storage modulus (G') of PFP from a subject undergoing dicoumarol therapy. Open figures are experimental values of G' ; solid figures are fitted values obtained from the model.

approximately 5 percent higher on the average than when $n = 1$. The lag time t_i , differs by no more than 3 percent. However the rate constants are quite different for these reaction orders while k'_0 is nearly always greater when $n = 1$ than when $n = 2$, the opposite is true for k'_1 . Nonetheless, these parameters exhibit similar trends. For example the PFP samples containing SBTI (9-27-78) showed progressively decreased k'_0 and k'_1 with increased SBTI concentration for both $n = 1$ and $n = 2$. The only exception is the sample with 0.05 mg/ml SBTI in which k'_1 seemed abnormally large in both cases.

The model appears to fit the data reasonably well. In most systems, the standard deviation is less than 5 percent at $G'_{\max}$ and always less than 10 percent. In Figure V.3, experimental values at G' and G' calculated from the model ($n = 1$) are plotted against time after recalcification for PFP from a subject receiving warfarin. The agreement of the experimental and fitted values are very good, even when the G' from experiment attains a maximum and then declines slightly (4-11-78).

To facilitate discussion only the values of the parameters when $n = 1$ will be considered, although the remarks are also applicable to the $n = 2$ case. For normal plasma, the lag time, t_i , was between 9 and 13 minutes, and $G'_{\max}$ ranged between 400 and 900 dynes/cm². In contrast k'_0 and k'_1 were as low as .073 and .090 min⁻¹ and as high as .775 and .520 min⁻¹, respectively, for normal PFP. Also, high

values of one parameter appeared associated with low values of the other. This poses a dilemma. Either there was extreme donor variation, or it is difficult to uniquely determine values for these parameters. Evidence will be presented which supports the former possibility in some instances and the latter in others.

Looking first at the data from the warfarin study, it is obvious that t_i increased with the length of anticoagulant therapy. The mean t_i of the PFP from the donors after 12 days of receiving warfarin (4-28-78) was approximately a factor of 8 that of the control plasma (4-11-78). In general, k'_0 and k'_1 declined over the course of treatment for a particular donor. The most glaring exception is donor DB who showed k'_0 and k'_1 of .0894, .155, and .00086 min^{-1} and .420, .117, and .755 min^{-1} on 4-11, 4-21, and 4-28-78. Because the entire G' curve was not obtained on 4-28, the parameters were difficult to estimate accurately, and, thus, may not be uniquely determined. Nevertheless, the parameters do yield some information. The increase in t_i indicates a decrease in the concentration of enzymes composing the early coagulation cascade. The apparent decrease in k'_0 and k'_1 imply that the conversion of prothrombin to thrombin and fibrinogen to fibrin polymer were depressed. For the experiments of 4-11-78 and 4-21-78, G'_{max} were not significantly different. Because the runs of 4-28-78 ended long before G'_{max} was attained, this value could not be predicted with confidence. Nonetheless, G'_{max} did not appear dramatically

reduced on that date. This indicates that fibrinogen concentration is not directly affected.

The rheological data and the behavior of the model parameters agree favorably with the results of the clinical assays. Recall that the activated partial thromboplastin time and the prothrombin time increased 125 percent and 100 percent after 12 days of warfarin. Thus, the prothrombinase and prothrombin levels were depressed (176,177). The thrombin time was unchanged indicating that thrombin inhibitor and fibrinogen concentration were not markedly affected by warfarin therapy. In addition, the clottable protein level was not altered.

These results are consistent with the known effects of warfarin. Administration of this drug inhibits the synthesis of vitamin K-dependent coagulation factors--VII, IX, X, and prothrombin (31-34). Because t_i depends on the rate of activation and concentration of Factors IX and X, the lag time was lengthened by warfarin. Similarly, the activated partial thromboplastin time which is a measure of the formation of prothrombinase was increased. The parameter k'_0 and the prothrombin time are dependent on the prothrombinase level and on the conversion of prothrombin to thrombin, and, consequently, they decreased and increased, respectively over the course of therapy. Because k'_1 and prothrombin time are related to the concentration of normal prothrombin, these values were decreased and increased, respectively. Since

fibrinogen concentration is not reduced by warfarin, $G'_{\max}$ and thrombin time were not affected. Thus, the parameters obtained by fitting the rheological data and the results of the standard clinical assays are in qualitative agreement with the expected action of warfarin.

The results of applying the model to the G' data for PFP containing SBTI were also encouraging. The lag time, t_i , increased and the kinetic parameters, k'_0 and k'_1 , decreased progressively with SBTI concentration. No reduction in $G'_{\max}$ was found. Because SBTI inhibits Factor Xa (186), the doubling of t_i and the order of magnitude decrease in k'_0 are not unexpected. Also, it appears that even at levels of SBTI where thrombin time was not increased (see Table IV.1), k'_1 was depressed. Therefore, in recalcified PFP, SBTI seems to inhibit the rate of thrombin-mediated fibrin monomer formation and/or polymerization, although the extent of clot formation is not impaired.

The analysis of the lypholisation series of experiments reveals some interesting effects. In the fresh PFP containing HEPES, k'_0 is much greater than that of normal PFP for two of the samples (WK and JL) and slightly above average for the third (Po). Neither t_i nor k'_1 differ significantly from that of normal plasma. This implies that the formation of thrombin from prothrombin is accelerated in the presence of HEPES. Both freezing and lypholisation decrease t_i and increase k'_0 dramatically. Also, k'_1 is increased by a

factor of 2 to 3. It appears that the predominant effect of freezing and lypholisation on the rate of coagulation is an enhancement of the activation of the enzymes in the early coagulation cascade and prothrombin. The clinical assays for thrombin time and prothrombin time (Table IV-18) showed no difference between the fresh, frozen, and lypholised samples. A slight though significant increase in the activated partial thromboplastin time of the lypholised sample compared to fresh plasma was found. Thus, the parameters obtained from the analysis of the rheological data seem more sensitive in the detection of abnormalities of coagulation kinetics.

The fibrinogen concentration and fibrin crosslinking (as assessed by incubation of the clot in 5 M urea) were not reduced by lypholisation. In contrast, $G'_{\max}$ was decreased approximately 50 percent in the frozen and lypholised samples. Hence, freezing induced a subtle change in fibrinogen such that clot strength was reduced. The most probable cause of this effect is a conformational change in the fibrinogen molecule.

The addition of 10 percent by volume 0.1 M hydroxylamine (11-22 and 11-27-78) to PFP did not change either t_i or k_i' consistently compared to the isotonic NaCl control. However k_o' was increased an order of magnitude by NH_2OH . It appears that the conversion of prothrombin to thrombin is stimulated in the presence of hydroxylamine. Because the

ionic strengths of PFP samples containing NH_2OH and NaCl were the same, this factor is not responsible for the differing rates. The effect may be due to the nucleophilic properties of hydroxylamine, though the basic mechanism is unclear. The thrombin times of PFP incubated with hydroxylamine (Table IV-16) did not differ from those of control samples. This data is consistent with the relatively small difference in values of k'_1 for PFP containing NaCl or NH_2OH .

Overall, the model has some attractive features. Unlike previous models, it is able to complete fit the curve using a single set of parameters, and this fit appears acceptable. The parameters obtained from the application of the model agree qualitatively with the results of clinical assays and the expected behavior of the system. Unfortunately, the parameters k'_0 and k'_1 are not uniquely determined when the data are incomplete as in the warfarin study. As a result, the ability of the model to extrapolate the data to G'_{max} is limited. In addition, the kinetic parameters may take on a wide range of values for even normal plasma. However, abnormal coagulation yields parameter values orders of magnitude outside the normal range and, thus, normal and abnormal kinetics may be distinguished. Finally, if good rheological data is available, this technique may prove useful in the analysis and determination of the kinetics of the clotting process.

V.2. Platelet Function

From the results of rheological experiments involving normal platelet-rich and platelet-free plasma, it is obvious that platelets profoundly affect the initiation, rate of generation, and extent of clot formation. The presence of platelets in coagulating plasma decreases the lag time between recalcification and the onset of the sudden increase in G' , increases the rate at which the modulus is generated, and increases the maximum shear storage modulus, $G'_{\max}$. Rheological and biochemical studies of PRP containing inhibitors of platelet function may provide useful insights into the mechanisms which underlie these thromboplastic effects.

Platelets have been shown to play an important role in the stimulation of coagulation by contributing platelet factors (51,65), by promoting the formation of Factors XII, XI, and X (66,192-194) specifically and by the platelet membrane acting as a catalytic surface (67). Rheological studies of recalcified PRP indicated that chemical agents that inhibit platelet metabolism (KCN + 2-deoxy-D-glucose), depolymerize microtubules (colchicine and vinblastine (48)) elevate cAMP levels (DBcAMP (86)), and disrupt the contractile microfilaments (cytochalasin B) do not prolong the time between recalcification and catastrophic rise in G' . In the presence of these agents, this lag time was always shorter in PRP than in PFP. Thus, it appears that the procoagulant role of platelets is neither affected by decreased metabolism nor the

absence of structural or contractile proteins. These results also imply that an active metabolism and viable contractile proteins are not required for platelet membranes to perform their catalytic function.

The finding that ADP-and collagen-induced platelet aggregation as well as collagen-induced ^{14}C -serotonin release were not significantly affected by cytochalasin B concentrations (0.01-0.05 mg/ml), at which profound decreases in G'_{max} occur ($\sim$ 30-55 percent) indicates that the contractile microfilaments are not of primary importance in the release reaction. Similar results have been found in studies involving cytochalasin B-treated leukocytes. Hoffstein et al. (195-197) have demonstrated that lysosomal release in polymorphonuclear leukocytes is not impaired in the presence of this agent. Hoffstein and Weissman (197) postulate that lysosomal enzyme secretion occurs by the movement of the plasma membrane to the lysosomes by some cytochalasin B-insensitive process.

The order of magnitude increase in G'_{max} of PRP compared to PFP observed in this study agrees with previously reported data (48,75-77,86,198). Niewiarowski et al. (68, 69) have shown an interaction of platelets with polymerizing fibrin (though not with fibrinogen or polymerized fibrin) and an apparent contraction of the platelet. It has been suggested that the enhancement of clot strength in the presence of platelets is a result of "improved" fibrin polymerization

(193) or platelets serving as contractile crosslinks between fibrin fibers (73-76). While the first hypothesis is difficult to verify by the rheological technique employed in this study, the second is supported strongly by comparison of the normal and inhibited PRP data. Platelet-rich clots formed in the presence of cytochalasin B have a significantly lower $G'_{\max}$ than those containing PBS/EtOH. Since cytochalasin B interferes with the contractility, it is clear that the enhanced $G'_{\max}$ in normal PRP results from a tightened fibrin network. Furthermore, the decrease in $G'_{\max}$ found in PRP clots incubated with inhibitors of platelet metabolism (2-deoxy-D-glucose + KCN) indicate that this process requires energy. Though PRP clots exhibit reduced rigidity in the presence of these inhibitors, $G'_{\max}$ is still much greater than that of PFP. For example, at a cytochalasin B concentration of 0.1 mg/ml $G'_{\max}$ of PRP is approximately three-fold that of PFP even though clot retraction is almost totally inhibited and $G'_{\max}$ is reduced by more than 60 percent compared to the control samples.

An increased $G'_{\max}$ of PRP over PFP is also found in plasma from subjects with Glanzmann's thrombasthenia in which clot retraction is minimal (76) and in plasma incubated with the metabolic inhibitors KCN + 2-deoxy-D-glucose. Because the ability of platelets to tighten the network through contraction is nearly totally inhibited in the presence of these agents, this enhancement of $G'_{\max}$ must result from a mechanism

apart from the contractile process. The observation that platelets interact with the fibrin network implies that they are acting as mechanical crosslinks as well as contracting the network. Thus, in a manner analogous to the covalent crosslinking of rubber elasticity theory, fibrin fibers "stick" to the platelet membrane, thereby increasing the apparent crosslink density and restricting the possible conformations of the polymer chains. This change in the entropy of the network results in an elevated modulus.

The decline in $G'_{\max}$ of PRP beginning approximately 30 minutes after recalcification is consistent with the hypothesis that the enhanced modulus is developed through the tightening of the fibrin network by an energy-dependent platelet contractile mechanism. If the contractile process does require energy, then the metabolic stores of the clot-contracting platelet must eventually near depletion. At this time, the network will relax and the modulus decline. Inhibitors of the contractile mechanism or metabolism reduce the magnitude of the decrease in G' indicating again that increased clot strength is a result of a platelet-mediated tightening of the network. It is unlikely that relaxation of the clot is primarily due to an unrecoverable strain of fibrin network or a retraction of the clot from the platen surface induced by the test itself. Glover has shown that G' of recalcified PRP is independent of the maximum shear strain as long as this strain does not exceed 12 percent

(75). In addition, examination of the clot formed between the platens revealed no noticeable tears or detachments. The facts that PFP clots did not show this decline and fragment D + E levels in normal PRP clots were $< 10 \mu\text{g/ml}$ (75,77) dismiss the possibility that fibrinolysis is responsible for the relaxation phenomenon.

The results of rheological studies of clots formed from platelet-rich plasma diluted with isotonic buffer show G'_{max} is not linearly dependent on fibrinogen concentration, e.g. a 50 percent reduction in plasma concentration with constant platelet gave a clot with $G'_{\text{max}} = 75$ percent that of undiluted samples. Thus, it appears that the maximum shear storage modulus in PRP is only weakly dependent on fibrinogen concentration, certainly much less so than in PFP. The more extensive studies of Cohen and colleagues (73,74) on the isometric contractile force generated in platelet-rich clots with varied fibrinogen concentrations indicate that this force is nearly independent of fibrinogen concentrations above 0.1 mg/ml . This behavior is ascribed to saturation of fibrin receptor sites on the platelet membrane during fibrin polymerization.

In summary, platelets have three primary thromboplastic functions. First, they promote coagulation by contributing clotting factors and by serving as a catalytic surface for activation of the early coagulation factors. Second, they serve as crosslinks, thereby increasing clot rigidity.

Third, by contracting the fibrin network platelets they further enhance clot strength. These first two functions appear unaffected by the metabolic state, the condition of the microfilaments, and cAMP levels of platelets while the tightening of the three-dimensional fibrin network is strongly dependent on these factors.

V.3 Fibrinolysis

In this section, the implications of the results of this study dealing with fibrinolysis and the products of fibrinolysis will be discussed. While this work is not the final word in this area, an attempt will be made to draw some conclusions on the behavior of platelets and polymerizing fibrin in the presence of FDP or plasmin.

FDP and Fibrin Polymerization

Equal volume mixtures of PFP incubated with 100 u/ml SK and fresh PFP, showed markedly increased thrombin times longer than could be expected from a simple decrease in fibrinogen concentration. These results are in agreement with those of other investigators who measured thrombin times in plasma or purified fibrinogen systems containing FDP (125, 131, 133). It is difficult to compare directly the results of this study with those of previous studies since most of the researchers used systems composed of purified fibrinogen (125,131,133). Marder and Shulman (125) found potent

anticoagulant effects (as assessed by thrombin times) for mixtures of purified fibrinogen and fibrinogen incubated with 100 u/ml SK. The maximal prolongation of thrombin time occurred in the 20 minute digest mixture which contained the highest concentration of fragment Y (a thrombin time of 76 seconds versus 5 seconds for the control). With longer incubation periods, thrombin times decreased (10 seconds for the mixture containing the 120 minute digest). In contrast, the thrombin times in this study increased from 10 seconds for a 0 minute digest mixture to 20 seconds for mixtures of fresh PFP and PFP incubated with 100 u/ml of streptokinase for 15 minutes. For longer incubation periods, thrombin times remained near 20 seconds. Because Marder's mixtures contained high ratios of FDP to fibrinogen and the level of fragments X and Y were not determined in this study, no quantitative comparison of the results can be made. Nonetheless, this difference shows that fibrinogen-olysis proceeds differently in PFP than in a purified fibrinogen solution.

The increase in thrombin times has been attributed to an inhibition of thrombin binding to fibrinogen and to an interference with fibrin polymerization (133). The results of the fibrin monomer aggregation test--an assay which measures the rate at which fibrin polymerizes--indicated that while aggregation times were increased, this increase was largely due to a decrease in fibrinogen concentration. Thus, in this particular system, it appears that the inhibition of

the thrombin-fibrinogen interaction by FDP was responsible for the increased thrombin times. A likely mechanism for this effect would be a competition of fragments E and Y with fibrinogen for thrombin (133). This is logical since thrombin attacks fibrinopeptides A and B located in the N-terminal disulfide knot and fragments X, Y, and E contain this N-terminal portion (126,127).

FDP had relatively less effect on the rate of G' generation in PRP and PFP (Tables IV-12 and IV-13) than they did on thrombin times. For example, 1:1 mixtures of PFP incubated with 100 u/ml SK for 45 minutes and fresh PFP or PRP showed mean increases in the clot initiation time of 24 percent and 29 percent respectively. In contrast, thrombin times for the same PFP mixture were increased an average in excess of 100 percent. It is possible that the anticoagulant properties of FDP are masked by the presence of SBTI, a known inhibitor of Factor Xa (186). If this is the case, then the coagulation rate may be Factor Xa limited rather than limited by the ability of thrombin to attack fibrinogen. In addition, the inhibitory action of FDP may be overwhelmed by the huge amounts of thrombin produced during recalcification (199). On the other hand some increase in t_0 is to be expected since plasmin degrades various coagulation factors and reduces the fibrinogen concentration. Despite this possible obscuration, it still appears that FDP has a minimal anticoagulant effect

when t_0 in these mixtures is compared to those of PFP from factor-deficient or warfarin individuals. While the mean increase in t_0 was less than 50 percent for all mixtures containing FDP, t_0 was increased 100 to 300 percent for factor-deficient plasma (75,77) and approximately 700 percent for plasma from subjects receiving warfarin. Thus, while thrombin time data indicate that FDP may be potent antithrombins, their anticoagulant effect in recalcified plasma (as assessed by rheological techniques) is not of great importance.

The increase in $G'_{\max}$ for the recalcified mixture of fresh PFP and PFP incubated three minutes with 100 or 50 v/ml SK ($\sim$ 30 percent greater than the 0 minute control) indicates that early FDP (most likely fragment X or a pre-X fragment) increase clot strength. No change in α polymer, γ dimer, or β bands was detectable upon examination of the electrophoretic gels of washed clots formed from the recalcified fresh PFP-SK-treated PFP mixtures. Hence, the FDP do not appear to prevent the formation of crosslinks or promote crosslinking at any new sites. This suggests that the increased clot strength in the presence of early FDP is due to formation of a modified fibrin polymer formed in the presence of an early FDP. The conformation of this monomer is altered such that electrostatic and hydrogen bonding are increased, resulting in a higher $G'_{\max}$. The later FDP appear to slightly depress $G'_{\max}$, probably by interfering with the non-covalent

bonding of the fibrin polymer. These later fragments do not appear to be incorporated into the fibrin network.

PFP incubated with 10 u/ml of SK did not show any evidence of fibrinogenolysis. No change in thrombin times or significant decrease in $G'_{\max}$ for PFP incubated up to 150 minutes with this SK concentration was found. These results reveal the presence of inhibitors which prevent plasminogen-to-plasmin conversion and the enzymatic degradation of fibrinogen by plasmin. Earlier studies have demonstrated the presence of various plasmin inhibitors in human plasma (200-202).

It may be clearly seen that there is not a simple linear relationship between SK concentration and plasmin action if thrombin time is plotted against the product of SK incubation time and SK concentration (Figure V-4) for various SK concentrations. If active plasmin is directly proportional to the SK concentration the curves should be superimposable. Figure V-4 shows this not to be the case--with decreasing SK concentration the curves become flatter. Since the mechanisms by which SK induces plasmin activation and plasmin degrades fibrinogen make higher order relationships unlikely, the most logical explanation is again plasmin inhibitors. In this case, the concentration of plasmin would be roughly proportional to SK concentration minus inhibitor concentration.

Figure V-4. Thrombin time versus the product of SK incubation period and SK concentration for 100, 50, and 10 u/ml SK.

FDP and Platelet Function

Fibrinogen degradation products were found to markedly depress the $G'_{\max}$ in clots formed from 1:1 mixtures of fresh PRP ($\sim 4 \times 10^5$ platelets/mm³) and PFP incubated with 100 u/ml SK. In the 20 to 34 minute incubation period range, $G'_{\max}$ was less than 40 percent the $G'_{\max}$ of the 0 minute control sample. This is approximately half the maximum shear storage modulus expected if all the fibrinogen in the PFP was degraded to inert fragments. That the decrease in $G'_{\max}$ in the platelet-rich system is not due to a weaker network alone can be seen by examining the effect of the 3 minute digest on coagulating PFP and PRP. While in mixtures of fresh PFP and PFP incubated with 100 u/ml SK for 3 minutes $G'_{\max}$ is increased by approximately 30 percent, this digest decreased the $G'_{\max}$ of PRP by nearly 35 percent. Thus, FDP adversely affected the dynamic rigidity generated by the platelet-fibrin interaction.

To test if platelet function was inhibited grossly by FDP, platelet aggregation studies were carried out. For 1:1 mixtures of PRP and SK-incubated PFP aggregation to 2 μ M ADP (final concentration), 0.2-0.4 units of thrombin, and polymerizing fibrin monomer were not impaired. In fact, polymerizing fibrin aggregation appeared to occur slightly sooner in the presence of FDP. These results indicate that the inhibitory effect of FDP must occur by a subtler mechanism. However, they do not preclude the possibility that FDP

may adversely affect events occurring in the interior of the platelet. For example, cytochalasin B disrupts the platelet contractile mechanism decreasing $G'_{\max}$, yet this agent does not inhibit ADP-induced platelet aggregation or collagen-induced platelet aggregation and ^{14}C -serotonin release at fairly high concentrations ($\leq 50 \mu\text{g/ml}$).

Two possible mechanisms by which FDP inhibit the generation of the contractile force may be postulated. The first is an inhibition of the platelet-fibrin interaction. This would occur by competitive inhibition of platelet binding to polymerizing fibrin in the presence of the large fragments or small peptides produced during plasminic degradation of fibrinogen. Thus, less fibrin strands would be bound to the platelet membrane, and the effective platelet crosslink density and $G'_{\max}$ would be decreased. The second possibility is an inhibition of the platelet contractile mechanism by FDP. Because even the smallest fragments of fibrinogenolysis are several thousand daltons, it is unlikely that these moieties would diffuse through the platelet membrane. Therefore, these fragments must bind to receptor sites on the exterior of the platelet membrane if they are to affect the interior microfilament system.

To determine which of these two mechanisms is responsible for the decreased modulus rheological measurements were performed on recalcified PRP containing FDP and PBS/EtOH or cytochalasin B (0.1 mg/ml). Cytochalasin B was chosen because

it has been shown to disrupt the contractile proteins (98, 191) and at this concentration to decrease $G'_{\max}$ and prevent clot retraction in PRP. In addition, it did not affect G' in platelet-free plasma, and ADP-induced aggregation was not inhibited implying that the effect of cytochalasin B is specific. If the primary action of FDP is an inhibition of contractility, then a combination of FDP and cytochalasin B should have little more effect on the $G'_{\max}$ of PRP than cytochalasin or FDP alone (after accounting for the decreased fibrinogen concentration). A greater effect would be found if FDP inhibit the platelet-fibrin interaction.

The results of these tests (Figures IV-35 to IV-38, Tables IV-14,15) indicate a further reduction in $G'_{\max}$ is seen in PRP containing both cytochalasin B and FDP as opposed to that containing only FDP. The $G'_{\max}$ of PRP containing cytochalasin B and PFP incubated with 100 u/ml SK for 3 minutes was on the average 50 percent lower than the $G'_{\max}$ of PRP incubated with the 3 minute digest alone. In comparison, the $G'_{\max}$ of the 0 minute control mixture is decreased by 62 percent in the presence of cytochalasin B, and the PRP-3 minute digest mixture (no cytochalasin B) had a $G'_{\max}$ 67 percent that of the 0 minute control mixture (without cytochalasin B). The fact that cytochalasin B depressed $G'_{\max}$ of the undigested control more than the $G'_{\max}$ of PRP is not surprising. $G'_{\max}$ of PRP was already decreased by the early FDP in the 3 minute sample while $G'_{\max}$ of PFP mixtures were increased by the 3

minute digest. In short, $G'_{\max}$ can fall farther in the PRP-0 minute control mixture.

Note that while cytochalasin B decreased, the decline in G' after $G'_{\max}$ was attained, FDP exacerbated this phenomenon. When FDP were present, it seemed as if the energy necessary for the operation of the contractile mechanism was rapidly expended as the platelets futilely attempted to contract the fibrin network. Going one step further, it is possible that this tightening resulted in a failure of the network at the junction of fibrin and platelet membrane. In contrast, cytochalasin B acts as a "governor" on the contractile process--it permits only a weak contractile force to be generated yet this state can be maintained for longer periods since less energy must be used. More importantly, the decreased contraction would preserve the integrity of the platelet membrane-fibrin fiber attachment.

The data are more consistent with the hypothesis that FDP inhibit the interaction of fibrin and platelets. The decrease in $G'_{\max}$ and the magnitude of the decline in G' from $G'_{\max}$ in the PRP-SK-treated PFP -cytochalasin B mixtures suggest that an inhibition of the contractile mechanism is not responsible for the adverse effects of FDP. The decreased binding of fibrin to the platelet membrane resulted in an apparent decrease in platelet concentration. Consequently, the platelet-mediated contractile force is less in the presence of these degradation products.

The inhibitory role of the specific high molecular weight fragments and small peptides produced during the degradation of fibrinogen by plasmin remains unclear. However, the observation that a marked inhibition of clot rigidity occurs in PRP mixtures containing the early digest and this effect persists for digests produced during long incubation periods suggests that a small peptide formed during the production of fragment X is responsible. This agrees with Niewiarowski's finding that a low molecular weight dialysable fragment interfered with platelet aggregation (142,200). Additional rheological studies on the coagulation of PRP containing purified FDP must be performed before this question can be resolved.

Fibrinolysis of Crosslinked and Uncrosslinked Clots

While the moduli of clots formed from PFP or PRP containing 10 u/ml SK were only slightly less than those formed without SK, the presence of 20 u/ml SK resulted in the formation of clot with much lower $G'_{\max}$ and which rapidly degraded. Thus, as in the plasmin degradation of fibrinogen, there appears to be a plasmin inhibitor(s) in human plasma (201-203). This inhibitor or inhibitors prevent the lysis of cross-linked fibrin clots by plasmin for streptokinase concentrations up to 10 u/ml. At higher SK concentration, enough active plasmin is generated to totally lyse the clot.

At a level of streptokinase (10 u/ml) at which fibrinogen or crosslinked fibrin clots did not exhibit significant degradation, Factor XIII-inhibited clots slowly lysed. With 20 u/ml SK, uncrosslinked clots attained lower $G'_{\max}$ and lysed more rapidly than clots formed with the same concentration of SK but without hydroxylamine. The increased susceptibility of uncrosslinked clots to fibrinolysis is in accord with studies that have used Factor XIII deficient plasma (149) or inhibitors of transamidation (146-148,150). In these reports fibrinolysis was measured by the release of radioactivity from clots formed from ^{131}I -labelled fibrinogen (146), by visual inspection (147-149), thromboelastography (148), or immunoassay (150). The finding that no fibrinogenolysis occurred in PFP incubated with 10 u/ml SK and 10 percent 0.1 M NH_2OH (measured by thrombin time, Table IV-16) and those of other studies employing related amines (146,148) indicate that hydroxylamine does not affect the plasmin plasminogen, or anti-plasmin systems significantly.

However, the results of this study are in contrast to those of Haverkate (151) and Rampling (152). The latter investigator evaluated fibrinolysis by measuring the total protein associated with clots and the protein released into the supernatant during the fibrinolysis of normally or poorly crosslinked fibrin. This technique is not as sensitive as the rheological method described in this dissertation.

VI. SUMMARY

Normal Plasma

The maximum shear storage moduli ($G'_{\max}$) for recalcified PFP and PRP (2.0×10^5 platelets/mm³) were on the order of 500 and 5000 dynes/cm², respectively. The lag time, t_0 , between the addition of calcium and the sudden rise in G' was 10 to 14 minutes in PFP and 6 to 9 minutes in PRP. While in PRP, G' decreased after $G'_{\max}$ was attained (approximately 30 minutes after recalcification), this decline did not occur in PFP.

By dilution of PFP with an isotonic buffer the $G'_{\max}$ of PFP was found to be linearly proportional to fibrinogen concentration as predicted by rubber elasticity theory. In contrast, a 50 percent dilution of PRP resulted in a $G'_{\max}$ 75-80 percent that of an undiluted control having the same platelet concentration. The thrombin time of an equal volume mixture of buffer and PFP was approximately 14 seconds versus 10 seconds for the control.

Platelet Function

Agents which inhibit platelet metabolism (KCN + 2-deoxy-D-glucose), elevate the intraplatelet cAMP level (DBcAMP), and interfere with contractile microfilaments

(cytochalasin B) decreased $G'_{\max}$ of PRP significantly. In addition, platelet-mediated clot retraction was inhibited by cytochalasin B. None of these agents altered t_0 or the time after recalcification at which $G'_{\max}$ was attained.

The results of the experiments involving normal PRP and inhibitors of platelet function indicate two primary hemostatic functions of platelets. First, the rate of clot formation is accelerated in the presence of platelets. Second, the clot strength is increased by the interaction of platelets and polymerizing fibrin. Platelets act also as crosslinks and tighten the fibrin network. This tightening proceeds via a cAMP-regulated contractile mechanism which requires energy.

At levels of cytochalasin which depressed markedly $G'_{\max}$ and clot retraction, ADP-induced and collagen-induced platelet aggregation and ^{14}C -serotonin release were unaffected. It appears that the release reaction is not absolutely dependent on cytochalasin B-sensitive microfilaments.

Fibrinolysis

PFP clots formed from a 1:1 mixture of fresh PFP and PFP incubated previously with 50 or 100 u/ml SK for 3 minutes showed increased $G'_{\max}$ compared to control samples. For PFP mixtures composed of PFP incubated for longer periods with SK, $G'_{\max}$ was depressed with respect to the control. At 100 u/ml SK, incubation periods of 15 minutes or longer resulted

in a $G'_{\max}$ 40-50 percent that of the control. Electrophoretic gels of washed clots formed from fresh and SK-treated PFP revealed no gross difference in γ -dimerization or α -polymerization. Thrombin times for the mixtures were approximately double the control value when the incubation periods were 15 minutes or more. However, the lag time was increased 50 percent at most. The results of the fibrin monomer aggregation tests indicate that FDP interfere primarily with the thrombin-fibrin interaction rather than fibrin polymerization. No change in either the $G'_{\max}$ or thrombin time was found for mixtures of fresh PFP and PFP incubated with 10 u/ml SK.

$G'_{\max}$ was decreased significantly in equal volume mixtures of PRP and PFP incubated previously with 100 u/ml of SK. The maximum depression in $G'_{\max}$ (30-40 percent the control value) occurred in those mixtures containing the 20-34 minutes digests. The lag time also was increased no more than an average of 40 percent for the PRP mixtures. The additional decrease of the $G'_{\max}$ in PRP containing both FDP and dytochalasin B suggests that FDP inhibit the interaction of platelets and fibrin polymer as opposed to interfering with the contractile apparatus of the platelet. Aggregation to 2 μ M ADP, thrombin, and polymerizing fibrin was not impaired in the presence of FDP.

Clots formed from PFP or PRP lysed rapidly in the presence of 20 u/ml SK. At an SK concentration of 10 u/ml,

only slight fibrinolysis was observed. Clots in which cross-linking was inhibited by hydroxylamine were more susceptible to SK-induced lysis than normally crosslinked fibrin clots. Thus, covalent crosslinking inhibits fibrinolysis.

Warfarin Plasma

The activated partial thromboplastin and prothrombin times and t_0 were prolonged greatly for plasma from patients undergoing warfarin therapy. The kinetic parameters k'_0 and k'_1 which are related to the rate of thrombin generation and the conversion of fibrinogen to fibrin polymer, respectively, were decreased. $G'_{\max}$ and thrombin time were not affected significantly. The results were consistent with the role of warfarin as an inhibitor of the production of coagulation Factors X, IX, VII and prothrombin.

Lypholisation

$G'_{\max}$ and t_0 of lypholised PFP were decreased approximately 50 percent and 45 percent respectively, compared to fresh PFP. No change in the thrombin or prothrombin times were found. The activated partial thromboplastin time was decreased slightly though significantly in the lypholised sample. The kinetic parameter k'_0 was increased dramatically by lypholisation. It appears that processes early in the coagulation cascade leading to thrombin formation are stimulated by freeze-drying.

BIBLIOGRAPHY

1. MacFarlane, R. G., "The theory of blood coagulation," in Human Blood Coagulation, Haemostasis, and Thrombosis, R. Biggs, ed., p. 1-31, Blackwell Scientific Publications, London, 1976.
2. Williams, W. J., "Mechanisms of coagulation," in Hematology, W. J. Williams, E. Beutler, A. J. Erslev, and R. W. Rundles, eds., p. 1266-1275, McGraw-Hill, New York, 1977.
3. MacFarlane, R. G., "An enzyme cascade in the blood clotting mechanism and its function as a biochemical amplifier," Nature, 202, 498-499 (1964).
4. Williams, W. J., "Control of coagulation reactions" in Hematology, W. J. Williams, E. Beutler, A. J. Erslev, and R. W. Rundles, eds., p. 1276-1285, McGraw-Hill, New York (1976).
5. Prentice, C. R. M., O. D. Ratnoff, and R. T. Breckenridge, "Experiments on the nature of the prothrombin converting principle: alteration of proaccelerin by thrombin," Br. J. Haematol., 13, 898-914 (1967).
6. Rapaport, S. I., S. Schiffman, M. F. Patch, and S. B. Ames, "The importance of activation of antihemophilic globulin and proaccelerin by traces of thrombin in the generation of intrinsic prothrombin activity," Blood, 21, 221-236 (1963).
7. Abildgaard, U., "Inhibition of the thrombin-fibrinogen reaction by antithrombin III studied by N-terminal analysis," Scand. J. Clin. Lab. Invest., 20, 207-216 (1967).
8. Yin, E. T., S. Wessler, and P. J. Stoll, "Identity of plasma-activated Factor X inhibitor with antithrombin III and heparin cofactor," J. Biol. Chem., 24, 3694-3702 (1973).

9. Rosenberg, J. S., P. W. McKenna, and R. D. Rosenberg, "Inhibition of human factor IXa by human antithrombin," J. Biol. Chem., 250, 8883-8888 (1975).
10. Rosenberg, R. D., "The effect of heparin on factor XIa and plasmin," Thromb. Diath. Haemorrh., 33, 51-62 (1974).
11. Stead, N., A. P. Kaplan, and R. D. Rosenberg, "Inhibition of activated factor XII by antithrombin heparin cofactor," J. Biol. Chem., 251, 6481-6488 (1976).
12. Abildgaard, U., "Inhibition of the thrombin-fibrinogen reaction by α_2 -macroglobulin, studied by N-terminal analysis," Thromb. Diath. Haemorrh., 21, 173-180 (1969).
13. Caspary, E. A. and R. A. Kekwick, "Some physicochemical properties of human fibrinogen," Biochem. J., 67, 41-48 (1957).
14. McDonagh, J., H. Messle, R. P. McDonagh, C. Murano, and B. Blomback, "Molecular weight analysis of fibrinogen and fibrin chains by an improved sodium dodecyl sulfate gel electrophoresis," Biochem. Biophys. Acta, 257, 135-142 (1972).
15. Henschen, A., "Number and reactivity of disulfide bonds in fibrinogen and fibrin," Arkiv. Kemi., 22, 355-373 (1964).
16. Hudry-Clergeon, G., G. Marguerie, L. Pouit, and M. Suscillon, "Models proposed for the fibrinogen molecule and for the polymerization process," Thromb. Res., 6, 533-541 (1975).
17. Koppel, G., "Morphology of the fibrinogen molecule," Thromb. Diath. Haemorrh. Suppl., 39, 71-84 (1970).
18. Blomback, B., "The N-terminal disulfide knot of human fibrinogen," Brit. J. Haemat., 77, 145-157 (1969).
19. Bailey, K., F. R. Bettelheim, L. Lorand, and W. Middlebrook, "Action of thrombin in the clotting of fibrinogen," Nature, 167, 233-234 (1951).
20. Blomback, B. M. Blomback, P. Edman, and B. Heyssel, "Human fibrino-peptides: Isolation, characterization and structure," Biochem. Biophys. Acta, 115, 371-396 (1966).

21. Pouit, M. L., G. Hudry-Clergeon, and M. Scullion, "Electron Microscopy study of positive charges on fibrin fibers," Biochem. Biophys. Acta, 317, 99-105 (1973).
22. Chen, R. and R. T. Doolittle, "Isolation, characterization, and location of a donor-acceptor unit from cross-linked fibrin," Proc. Nat. Acad. Sci., 66, 472-479 (1970).
23. McKee, P. A., P. Mattock, and R. L. Hill, "Subunit structure of human fibrinogen, soluble fibrin and crosslinked, insoluble fibrin." Proc. Nat. Acad. Sci., 66, 738-744 (1970).
24. Pisano, J. J., T. J. Bronzert, M. P. Peyton, and J. S. Finlayson, " ϵ -(γ -glutamyl) lysine crosslinks determination in fibrin from normal and Factor XIII-deficient individuals," Ann. N.Y. Acad. Sci., 202, 98-113 (1972).
25. Kanaide, H., and J. R. Shainoff, "Crosslinking of fibrinogen and fibrin by fibrin-stabilizing factor (Factor XIIIa) J. Lab. Clin. Med., 85, 574-597 (1975).
26. Schwartz, M. L., S. V. Pizzo, R. L. Hill, and P. A. McKee, "Human factor XIII from plasma and platelets," J. Biol. Chem., 248, 1395-1407 (1973).
27. Shen, L. L., R. P. McDonagh, J. McDonagh, and J. Hermans, "Fibrin gel structure: influence of calcium and covalent crosslinking on the elasticity," Biochem. Biophys. Res. Comm., 56, 793-798 (1974).
28. Shen, L. L., J. Herman, J. McDonagh, R. P. McDonagh, and M. Carr, "Effects of calcium ion and covalent crosslinking on formation and elasticity of fibrin gels," Thromb. Res., 6, 255-265 (1975).
29. Glover, C., L. V. McIntire, C. H. Brown, and E. A. Natelson, "Rheological properties of fibrin clots. Effects of fibrinogen concentration, Factor XIII deficiency and Factor XIII inhibition," J. Lab. Clin. Med., 86, 644-656 (1975).
30. Roberts, W. W., L. Lorand, and L. F. Mockros, "Viscoelastic properties of fibrin clots," Biorheology, 10, 29-42, 1973.
31. Weiner, M., S. Shapiro, J. Axelrod, J. R. Cooper, and B. B. Brodie, "The physiological disposition of dicoumarol in man," J. Pharmacol. Expt. Ther., 99, 409-420 (1950).

32. O'Reilly, R. A., P. M. Aggeler, M. S. Hoag, and L. Leong, "Studies on the coumarin anticoagulants: The assay of warfarin and its biologic applications," Thromb. Diath. Haemorrh., 8, 83-94 (1962).
33. Hemker, H. C., J. J. Veltkamp, and E. A. Loeiger, "Kinetic aspects of the interaction of blood clotting enzymes. III Demonstration of an inhibitor of pro-thrombin conversion in vitamin K deficiency," Thromb. Diath. Haemorrh., 19, 346-363 (1968).
34. Hemker, H. C., and A. D. Muller, "Kinetic aspects of the interaction of blood-clotting enzymes. VI. Localisation of the site of blood-coagulation inhibition by the protein induced by vitamin K absence," Thromb. Diath. Haemorrh., 20, 78-87 (1968).
35. Karpatkin, S., "Heterogeneity of human platelets. I. Metabolic and kinetic evidence suggestive of young and old platelets," J. Clin. Invest., 47, 1073-1082 (1969).
36. Karpatkin, S., and R. M. Langer, "Biochemical energetics of simulated platelet plug formation: Effect of thrombin, adenosine diphosphate and epinephrine on intra and extra-cellular adenine nucleotide kinetics," J. Clin. Inv., 47, 2158-2168 (1968).
37. Kitchens, C. S., and T. F. Newcomb, "Human platelet respiration," J. Appl. Physiol., 25, 581-585 (1968).
38. White, J. G., "Platelet morphology and function," in Hemostasis, W. J. Williams, E. Beutler, A. J. Erslev, and R. W. Rundles, eds., p. 1159-1175, McGraw-Hill, New York, 1977.
39. Marcus, A. J., D. Zucker-Franklin, L. B. Safier, and H. L. Ullman, "Studies on human platelet granules and membranes," J. Clin. Invest., 45, 14-28 (1966).
40. Sixma, J. J., and I. Molenaar, "Microtubules and microfibrils in human platelets," Thromb. Diath. Haemorrh., 16, 153-162 (1966).
41. Zucker-Franklin, D., R. L. Nachman, and A. J. Marcus, "Ultra-structure of thrombosthenin, the contractile protein of human blood platelets," Science, 157, 945-946 (1967).

42. White, J. G., "Platelet microtubules and microfilaments: effects of cytochalasin B on structure and function," in Platelet Aggregation, J. Caen, ed., p. 15-52, Maison et Cie, Paris 1970.
43. Bettex-Galland, M., and E. F. Luscher, "Extraction of an actomyosin-like protein from human thrombocytes," Nature, 184, 276-277 (1959).
44. Zucker-Franklin, D., and N. Bloomberg, "Microfibrils of blood platelets: their relationship to microtubules and the contractile protein," J. Clin. Invest., 48, 165-175 (1969).
45. Abramowitz, J. W., A. Stracher, and T. C. Detwiler, "A second form of actin: platelet microfilaments depolymerized by ATP and divalent cations," Arch. Biochem. Biophys., 167, 230-237 (1975).
46. Clarke, M., and J. A. Spudich, "Nonmuscle contractile proteins: the role of actin and myosin in cell motility and shape determination," Ann. Rev. Biochem., 46, 797-822 (1977).
47. White, J. G., "Effects of colchicine and vinca alkaloids on human platelets," Am. J. Pathol., 53, 281-291 (1968).
48. Kuntamukkula, M. S., J. L. Moake, L. V. McIntire, and P. L. Cimo, "Effects of colchicine and vinblastine on platelet contractility and release," Thromb. Res. (Spring 1979).
49. Day, H. J. and H. Holmsen, "Concepts of the blood platelet release reaction," Ser. Haemat., 4, 3-27 (1967).
50. Mustard, J. F., D. W. Perry, R. L. Kinlough-Rathbone, and M. A. Packham, "Factors responsible for ADP-induced release reaction of human platelets," Am. J. Physiol., 228, 1757-1765 (1975).
51. Neiwirowski, S., A. Poplawski, B. Lipinski, and R. Farbiszewski, "The release of platelet clotting factors during aggregation and viscous metamorphosis," Exp. Biol. Med., 3, 121-126 (1968).
52. Born, G. V. R., "Aggregation of blood platelets by adenosine diphosphate and its reversal," Nature, 194, 927-929 (1962).

53. Born, G. V. R., and M. Hume, "Effects of the numbers and sizes of platelet aggregates on the optical density of plasma," Nature, 215, 1027-1029 (1967).
54. Zucker, M. B., "Platelet function," in Hematology, W. J. Williams, E. Beutler, A. J. Erslev, and R. W. Rundles, eds., p. 1200-1209 (1968).
55. Mills, D. C. B., I. A. Robb, and G. C. K. Roberts, "The release of nucleotides, 5-hydroxytryptamine, and enzymes from human blood platelets during aggregation," J. Physiol., 195, 715-729 (1968).
56. Niewiarowski, S., A. Z. Budzynski, and B. Lipinski, "Significance of the intact polypeptide chains of human fibrinogen in ADP-induced platelet aggregation," Blood, 49, 635-644 (1977).
57. Mustard, J. F., and M. A. Packham, "Factors influencing platelet function: Adhesion, release, and aggregation," Pharmacol. Rev., 22, 97-187 (1970).
58. Wilner, G. D., H. L. Nossel, and E. C. LeRoy, "Aggregation of platelets by collagen," J. Clin. Inv., 47, 2616-2621 (1968).
59. Jaffe, R., and D. Deykin, "Evidence for a structural requirement for the aggregation of platelets by collagen," J. Clin. Invest., 53, 875-883 (1974).
60. Davey, M. F., and E. F. Luscher, "Release reactions of human platelets by thrombin and other agents," Biochem. Biophys. Acta, 165, 490-5061 (1968).
61. Niewiarowski, S., V. R. Ream and D. P. Thomas, "Effect of fibrinogen derivatives on platelet aggregation," Thromb. Diath. Haemorrh., 42, 49-59 (1970).
62. Williams, W. J., E. Beutler, A. J. Erslev, and R. W. Rundles, Hematology, p. 1158, McGraw-Hill, New York, 1977.
63. Born, G. V. R., "Functional physiology of platelets," in Human Blood Coagulation, Haemostasis, and Thrombosis, R. Biggs, ed., p. 168-187, Blackwell Scientific Publications, London, 1976.
64. Baumgartner, H. R., "The role of blood flow in platelet adhesion, fibrin deposition, and formation of mural thrombi," Microvas. Res., 5, 167-172 (1973).

65. Hardisty, R. M., and R. A. Hutton, "Platelet aggregation and the availability of platelet factor 3," Br. J. Haematol., 12, 764-776 (1966).
66. Schiffman, S., S. I. Rapaport, and M. M. Y. Chong, "Platelets and the initiation of intrinsic clotting," Br. J. Haematol., 24, 633-647 (1973).
67. Silver, M. J., "Role of calcium ions and phospholipids in platelet aggregation," Am. J. Physiol., 209, 1128-1132 (1965).
68. Niewiarowski, S., E. Regoeczi, and J. F. Mustard, "Platelet interaction with fibrinogen and fibrin: comparison of the interaction of platelets with that of fibroblasts, leukocytes, and erythrocytes," Ann. N.Y. Acad. Sci., 201, 72-83 (1972).
69. Niewiarowski, S. E. Regoeczi, G. Stewart, A. Senyi, and J. Mustard, "Platelet interaction with polymerizing fibrin," J. Clin. Invest., 51, 685-703 (1972).
70. DeClerck, F., M. Borgers, G. deGaetano, and J. Vermynen, "Dissociation of clot retraction from platelet granule fusion and degranulation: an ultrastructural study of reptilase-human platelet-rich plasma clots," Brit. J. Haematol., 29, 341-348 (1975).
71. Widmer, K. and J. L. Moake, "Clot retraction in dilute suspensions of platelet-rich plasma and gel-separated platelets," J. Lab. Clin. Med., 87, 49-57 (1976).
72. Niewiarowski, S., G. J. Stewart, N. Nath, A. J. Sha, and G. E. Lieberman, "ADP, thrombin, and Bothrops atrox thrombin-like enzyme in platelet-dependent fibrin retraction," Am. J. Physiol., 229, 737-745 (1975).
73. Cohen, I., and A. deVries, "Platelet contractile regulation in an isometric system," Nature, 246, 36-37 (1973).
74. Cohen, I., J. Gabray, T. Glaser, and A. Oplatka, "Fibrin-blood platelet interaction in a contracting clot," Brit. J. Haematol., 31, 45-50 (1975).
75. Glover, C. J., "Dynamic shear moduli during normal and abnormal plasma clot formation," Ph.D. thesis, Rice University (1975).

76. Glover, C. J., L. V. McIntire, C. H. Brown, and E. A. Natelson, "Dynamic coagulation studies: influence of normal and abnormal platelets on clot formation," Thromb. Res., 7, 185-198 (1975).
77. Kuntamukkula, M. S., "Dynamic rheological studies of coagulation and fibrinolysis," Ph.D. thesis, Rice University (1977).
78. Salzman, E. W., and L. L. Neri, "Cyclic 3;5'-adenosine monophosphate in human blood platelets," Nature, 224, 609-610 (1969).
79. Salzman, E. W., and H. Weisenberger, "Role of cyclic AMP in platelet function," Ad. Cyc. Nuc. Res., 1, 231-247 (1972).
80. Salzman, E. W., P. C. Kensler, and L. Levine, "Cyclic 3;5'-adenosine monophosphate in human blood platelets. IV. Regulatory role of cyclic AMP in platelet function," Ann. N.Y. Acad. Sci., 201, 61-71 (1972).
81. Cole, B., G. A. Robison, and R. C. Hartman, "Studies on the role of cyclic AMP in platelet function," Ann. N.Y. Acad. Sci., 201, 477-487 (1972).
82. Marquis, N. R., R. L. Vigdahl, and P. A. Tavormina, "Platelet aggregation. I. Regulator by cyclic AMP and prostaglandin E₁," Biochem. Biophys. Res. Comm., 36, 965-972 (1969).
83. Salzman, E. W., and L. Levine, "Cyclic 3;5'-adenosine monophosphate in human blood platelets. II. Effect of N⁶-2¹-O-dibutyryl cyclic 3;5'-adenosine monophosphate on platelet function," J. Clin. Inv., 50, 131-141 (1970).
84. Minkes, M., N. Stanford, M. M. Y. Chi, G. J. Roth, A. Raz, P. Needleman, and P. W. Majerus, "Cyclic adenosine 3;5'-prostaglandin synthetase in human platelet suspensions," J. Clin. Inv., 59, 449-454 (1977).
85. Moake, J. L., P. L. Cimo, K. Widmer, D. M. Peterson, and J. R. Gum, "Clot retraction. II. Effects of prostaglandins, derivatives of cyclic 3;5'-AMP, theophylline, cholinergic agents and colchicine on clot retraction in dilute platelet-rich plasma and gel-separated test systems," Thromb. Hemostas., 38, 420-428 (1977).

86. Kuntamukkula, M. S., L. V. McIntire, J. L. Moake, D. M. Peterson, and W. J. Thompson, "Rheological studies of the contractile force within platelet fibrin clots: Effects of prostaglandin E₁, dibutyryl-cAMP and dibutyryl c-GMP," Thromb. Res. (Fall, 1978).
87. Robison, G. A., A. Arnold, and R. C. Hartman, "Divergent effects of epinephrine and prostaglandin E₁ on the level of cyclic AMP in human blood platelets," Pharm. Res. Comm., 1, 325-332 (1969).
88. Kinlough-Rathbone, R. L., M.A. Packham, and J. F. Mustard, "The effect of prostaglandin E₁ on platelet function in vitro and in vivo," Brit. J. Haematol., 19, 559-571 (1970).
89. Evans, G., M. A. Packham, E. F. Nishizawa, J. F. Mustard, and E. A. Murphy, "The effect of acetylsalicylic acid on platelet function," J. Exp. Med., 128, 877-894 (1968).
90. Weiss, H. J., L. M. Aledort, and S. Kochwa, "The effect of salicylates on the hemostatic properties of platelets in man," J. Clin. Inv., 47, 2169-2180 (1968).
91. Smith, J. B., and A. L. Willis, "Aspirin selectively inhibits prostaglandin production in human platelets," Nature, 231, 235-237 (1971).
92. Roth, G. J., and P. W. Majerus, "The mechanism of the effect of aspirin on human platelets. I. Acetylation of a particulate fraction protein," J. Clin. Inv., 56, 624-632 (1975).
93. Wessells, N. K., B. S. Spooner, J. F. Ash, M. O. Bradley, M. A. Luduena, E. L. Taylor, J. T. Wrenn, and K. M. Yamada, "Microfilaments in cellular and developmental processes," Science, 171, 135-143 (1971).
94. Shepro, D. F., F. A. Belamarich, L. Robblee, and F. C. Chao, "Antimotility effect of cytochalasin B observed in mammalian clot retraction," J. Cell Biol., 47, 544-547 (1972).
95. Halsam, R. J., "Inhibition of blood platelet function by cytochalasins: effects on thrombosthenin and on glucose metabolism," Biochem. J., 127, 34P (1972).

96. Cazenave, J.-P., M. A. Packham, M. A. Guccione, and J. F. Mustard, "Inhibition of platelet adherence to a collagen-coated surface by agents that inhibit platelet shape change and clot retraction," J. Lab. Clin. Med., 84, 483-493 (1974).
97. Niewiarowski, S., and S. Goldstein, "Interaction of cultured human fibroblasts with fibrin: modification by drugs and aging in vitro," J. Lab. Clin. Med., 82, 605-610 (1973).
98. Spudich, J. A., and S. Lin, "Cytochalasin B, its interaction with actin and actomyosin from muscle," Proc. Nat. Acad. Sci., 69, 442-446 (1972).
99. Behnke, O., "Effects of some chemicals on blood platelet microtubules, platelet shape and some platelet functions in vitro," Scand. J. Haemat., 7, 123-140 (1970).
100. Holmsen, H., C. A. Setkowsky, and H. J. Day, "Effects of antimycin and 2-deoxyglucose on adenine nucleotides in human platelets," Biochem. J., 144, 385-396 (1974).
101. Bettex-Galland, M., and E. F. Luscher, "Studies on the metabolism of human blood platelets in relation to clot retraction," Thromb. Diath. Haemorrh., 4, 178-195 (1960).
102. Lehninger, A. L., Biochemistry, p. 379, Worth, New York, 1970.
103. Zucker, M. B. and Z. Jerushalmy, "Studies on platelet shape and aggregation: effect of inhibitors on these and other platelet characteristics," in Physiology of Hemostasis and Thrombosis, S. A. Johnson and W. H. Seegers, eds., 249-265, Charles C. Thomas, Springfield, Ill., (1967).
104. Chao, F. C., D. Shepro, J. L. Tullis, F. A. Bellamarich, and W. A. Curry, "Similarities between platelet contraction and cellular motility during mitosis: role of platelet microtubules in clot retraction," J. Cell. Sci., 20, 569-588 (1976).
105. Kattlove, H. E., "Platelet ATP in ADP-induced aggregation," Am. J. Physiol., 226, 325-329 (1974).

106. Fletcher, A. P., N. Alkjaersig, and S. Sherry, "Fibrinolytic mechanisms and the development of thrombolytic therapy," Am. J. Med., 33, 738-749 (1962).
107. Sherry, S., "Fibrinolysis," in Hematology, W. J. Williams, E. Beutler, A. J. Erslev, and R. W. Rundles, eds., p. 1294-1305, McGraw-Hill, New York, 1977.
108. Walther, P. J., H. M. Steinman, R. L. Hill, and P. S. McKee, "Activation of human plasminogen by urokinase: Partial characterization of a pre-activation peptide," J. Biol. Chem., 249, 1173-1181 (1974).
109. Lesuk, A., L. Terminello, and H. Traver, "Crystalline human urokinase: some properties," Science, 147, 880-881 (1965).
110. Chesterman, C. N., M. J. Allington, and A. A. Sharp, "Relationship of plasminogen activator to fibrin," Nature, 238, 15-17 (1972).
111. Prentice, C. R. M., K. M. Rogers, and G. P. McNicol, "Evaluation of a new preparation of urokinase," Thromb. Diath. Haemorrh., 30, 114-122 (1973).
112. Caprini, J. A., H. C. Kwaan, L. Zuckerman, and A. C. Franklin, "Thromboelastographic pattern of anocrod and thrombin fibrin formation and thrombin fibrin formation and dissolution," Thromb. Res., 4, 199-217 (1974).
113. Soberano, M. E., E. B. Ong, A. J. Johnson, M. Levy, and G. Schoellman, "Purification and characterization of two forms of urokinase," Biochem. Biophys. Acta, 445, 763-773 (1976).
114. Sieftring, G. E., and F. J. Castellino, "Interaction of streptokinase with plasminogen: isolation and characterization of a streptokinase degradation products," J. Biol. Chem., 251, 3913-3920 (1976).
115. Markus, G., and W. C. Werkheiser, "The interaction of streptokinase with plasminogen. I. Functional properties of the activated enzyme," J. Biol. Chem., 239, 2637-2643 (1964).
116. Davies, M. C., M. E. Englert, and E. G. deRenzo, "Interaction of streptokinase and human plasminogen. I. Combining of streptokinase and plasminogen observed in the ultracentrifuge under a variety of experimental conditions," J. Biol. Chem., 239, 2651-2656 (1964).

117. Reddy, K. N. N., and G. Markus, "Mechanism of activation of human plasminogen by streptokinase. Presence of active center in streptokinase-plasminogen complex," J. Biol. Chem., 247, 1683-1691 (1972).
118. Schick, L. A., and F. J. Castellino, "Interaction of streptokinase and human plasminogen," Biochemistry, 12, 4315-4321 (1973).
119. Wohl, R. L., L. Summaria, L. Arzadon, and K. C. Robbins, "Steady state kinetics of activation of human and bovine plasminogens by streptokinase and its equimolar complexes with various activated forms of human plasminogen," J. Biol. Chem., 253, 1402-1407 (1978).
120. Martin, M., "Studies on activator formation in human plasma with streptokinase," Thromb. Diath. haemorrh., 30, 381-392 (1973).
121. Martin, M., "Indirect measurement of streptokinase concentration in the plasma of patients undergoing fibrinolytic treatment," Thromb. Diath. haemorrh., 32, 633-650 (1974).
122. Martin, M., "Quantitative streptokinase determination in plasma of patients undergoing thrombolytic therapy," Sem. Thromb., 2, 33-41 (1975).
123. Nowak, A., and V. Gurewich, "Thrombolysis with streptokinase in rabbits. Dose response, fibrin-clot specificity, and laboratory evaluation of fibrinolytic effect," Thromb. Diath. haemorrh., 31, 265-272 (1974).
124. Marder, V. J., N. R. Shulman, and W. R. Carroll, "High molecular weight derivatives of human fibrinogen produced by plasmin. I. Physicochemical and immunological characterization," J. Biol. Chem., 244, 2111-2119 (1969).
125. Marder, V. J., and N. R. Shulman, "High molecular weight derivatives of human fibrinogen produced by plasmin. II. Mechanism of their anticoagulant activity," J. Biol. Chem., 244, 2120-2124 (1969).
126. Marder, V. J., A. Z. Budzynski, and H. L. James, "High molecular weight derivatives of human fibrinogen produced by plasmin. III. Their NH₂-terminal amino acids and comparison with the NH₂-terminal disulfide knot," J. Biol. Chem., 247, 4775-4781 (1972).

127. Ferguson, E. W., L. J. Fretto, and P. A. McKee, "A re-examination of the cleavage of fibrinogen and fibrin by plasmin," J. Biol. Chem., 250, 7210-7218 (1975).
128. Mosesson, M. W., J. S. Finlayson, and D. K. Galankis, "The essential covalent structure of human fibrinogen evinced by analysis of derivatives formed during plasmic hydrolysis," J. Biol. Chem., 248, 7913-7929 (1973).
129. Mosesson, M. W., "Fibrinogen catabolic pathways," Sem. Thromb. Hemostas., 1, 63-84 (1974).
130. Purves, L. R., G. G. Lindsey, G. Brown, and J. Franks, "Stabilization of the plasmin digestion products of fibrinogen and fibrin by calcium ions," Thromb. Res., 12, 473-484 (1978).
131. Triantaphyllopoulous, D. C., "Nature of the thrombin-inhibiting effect of incubated fibrinogen," Am. J. Physiol., 197, 575-579 (1959).
132. Alkjaersig, N., A. P. Fletcher, and S. Sherry, "Pathogenesis of the coagulation defect developing during pathological plasma proteolytic ('fibrinolytic') states. I. The significance, mechanism, and consequences of defective fibrin polymerization," J. Clin. Inv., 41, 917-934 (1962).
133. Larrieu, M. J., C. Rigollot, and V. J. Marder, "Comparative effects of fibrinogen degradation fragments D and E on coagulation," Brit. J. Haematol., 22, 719-733 (1972).
134. Bang, N. V., A. P. Fletcher, N. Alkjaersig, and S. Sherry, "Pathogenesis of the coagulation defect developing during pathological plasma proteolytic ('fibrinolytic') states. III. Demonstration of abnormal clot structure by electron microscopy," J. Clin. Inv., 41, 935-948 (1962).
135. Hirsh, J., A. P. Fletcher, and S. Sherry, "Effect of fibrin and fibrinogen degradation products on clot physical properties," Am. J. Physiol., 209, 415-424 (1965).
136. Kowalski, E., M. Kopec, and Z. Wegrzynowicz, "Influence of fibrinogen degradation products (FDP) on platelet aggregation, adhesiveness, and viscous metamorphosis," Thromb. Diath. haemorrh., 10, 406-423 (1964).

137. Jerushalmy, Z., and M. B. Zucker, "Some effects of fibrinogen degradation products (FDP) on blood platelets," Thromb. Diath. haemorrh., 15, 413-419 (1966).
138. Barnhart, M. I., D. C. Cress, R. L. Henry, and J. M. Riddle, "Influence of fibrinogen split products on platelets," Thromb. Diath. haemorrh., 17, 78-97 (1967).
139. Wilson, P. A., G. P. McNicol, and A. S. Douglas, "Effect of fibrinogen degradation products on platelet aggregation," J. Clin. Path., 21, 147-153 (1968).
140. Larrieu, M. J., S. Inceman, and V. J. Marder, "Action des produits de degradation du fonctions plaquettaires," Nouv. Rev. Franc. Hemat., 7, 691-704 (1967).
141. Cronberg, S., "Effect of fibrinolysis on adhesion and aggregation of human platelets," Thromb. Diath. Haemorrh., 19, 474-480 (1968).
142. Niewiarowski, S., V. R. Ream, and D. P. Thomas, "Effect of fibrinogen derivatives on platelet aggregation," Thromb. Diath. haemorrh., Suppl., 42, 49-59 (1970).
143. Prentice, C. R. M., A. G. G. Turpie, A. A. Hassanein, G. P. McNicol, and A. S. Douglas, "Changes in platelet behavior during Arvin therapy," Lancet, 644-647 (1969).
144. Kwaan, H. C., and G. H. Barlow, "The mechanism of action of Arvin and reptilase," Thromb. Diath. haemorrh., Suppl., 47, 361-369 (1971).
145. Kaplan, A. P., and K. F. Austen, "The fibrinolytic pathway of human plasma: Isolation and characterization of the plasminogen proactivator," J. Exp. Med., 136, 1378-1393 (1972).
146. Gormsen, J., A. P. Fletcher, N. Alkjaersig, and S. Sherry, "Enzymic lysis of plasma clots: the influence of fibrin stabilization on lysis rates," Arch. Biochem. Biophys., 120, 654-665 (1967).
147. Lorand, L., and A. Jacobsen, "Accelerated lysis of blood clots," Nature 195, 911-912 (1962).
148. Henderson, K. W., and M. Nussbaum, "The mechanism of enhanced streptokinase-induced clot lysis following *in vitro* Factor XIII inactivation," Brit. J. Haemat., 17, 445-453 (1969).

149. McDonagh, R. P., J. McDonagh, and F. Duckert, "The influence of fibrin crosslinking on the kinetics of urokinase-influenced clot lysis," Brit. J. Haemat., 21, 323-332 (1971).
150. Gormsen, J., and C. Feddersen, "Degradation of stabilized and non-stabilized fibrin clots by plasmin: an immunologic study," Ann. N.Y. Acad. Sci., 202, 329-334 (1972).
151. Haverkate, F., "Lysis of crosslinked and non-cross-linked purified fibrin," Thromb. Diath. haemorrh., 34, 584 (1975).
152. Rampling, M. W., "Factor XIII cross-linking and the rate of fibrinolysis induced by streptokinase and urokinase," Thromb. Res., 12, 287-295 (1978).
153. Von Kaulla, K. N., "Quantitative methods for measuring blood coagulation: theoretical and practical aspects," Prog. Hematol., 3, 218-243 (1962).
154. Hartert, H., and J. A. Schaefer, "The physical and biological constants of thromboelastography," Biorheology, 1, 31-39 (1962).
155. Dintenfass, L., "Effect of velocity gradient on the clotting time of blood and on the consistency of clots formed in vitro," Circ. Res., 18, 349-356 (1966).
156. Dintenfass, L., and G. E. Bauer, "Dynamic blood coagulation, thrombus formation and degradation in patients with peripheral vascular disease (arteriosclerosis, including diabetic): an in vitro study," Ann. Surg., 170, 984-995 (1969).
157. Dintenfass, L., and G. E. Bauer, "Dynamic blood coagulation and viscosity and degradation of artificial thrombi in patients with hypertension," Cardiovas. Res., 4, 50-60 (1970).
158. Kaibara, M., and E. Fukada, "Non-Newtonian viscosity and dynamic viscoelasticity of blood during clotting," Biorheology, 6, 73-84 (1969).
159. Kaibara, M., and E. Fukada, "The influence of the concentration of thrombin on the dynamic viscoelasticity of clotting blood and fibrinogen-thrombin systems," Biorheology, 8, 139-147 (1971).

160. Kaibara, M., "Dynamic viscoelastic study of the formation of fibrin networks in fibrinogen-thrombin systems," Biorheology, 10, 61-73 (1973).
161. Kaibara, M., and E. Fukada, "Dynamic viscoelastic study for the structure of fibrin networks in the clots of blood and plasma," Biorheology, 6, 329-339 (1970).
162. Fukada, E., and M. Kaibara, "The dynamic rigidity of fibrin gels," Biorheology, 10, 129-138 (1973).
163. Isogai, Y., A. Iida, I. Chikatsu, M. Mochizuki, and M. Abe, "Dynamic viscoelasticity of blood during clotting in health and disease," Biorheology, 10, 411-424 (1973).
164. Roberts, W. W., "Viscoelastic properties of fibrin clots," Ph.D. thesis, Northwestern U. (1970).
165. Mockros, L. F., W. W. Roberts, and L. Lorand, "Viscoelastic properties of ligation-inhibited fibrin clots," Biophys. Chem., 2, 164-169 (1974).
166. Glover, C. J., L. V. McIntire, L. B. Leverett, J. D. Hellums, C. H. Brown and E. A. Natelson, "Effect of shear stress on clot structure formation," Trans. Amer. Soc. Artif. Int. Organs, XX, 463-468 (1974).
167. Scott Blair, G. W., and J. Burnett, "An equation to describe the rate of setting of blood and milk," Biorheology, 1, 183-191 (1963).
168. Scott Blair, G. W., and J. Burnett, "On the rates of coagulation and subsequent softening of bovine and human blood and of thrombin-fibrinogen," Biorheology, 5, 163-176 (1968).
169. Mussati, F. G., and D. W. Macosko, "Rheology of network forming systems," Polymer. Eng. Sci., 13, 236-240 (1973).
170. Walters, K., and R. A. Kemp, "On the use of a rheogoniometer, part III--Oscillatory Shear between parallel plates," Rheologica Acta, 7, 1-8 (1968).
171. Walters, K., Rheometry, Wiley, New York, 1975.
172. Dixon, W. J., ed., "Amplitude and Phase Analysis," Biomedical Computer Programs, p. 435, University of California Press, Berkeley, 1971.

173. Gardner, F. H., "Preservation and clinical use of platelets," in Hematology, W. J. Williams, E. Beutler, A. J. Erslev, and R. W. Rundles, eds., p. 1553-1561, McGraw-Hill, 1977.
174. Biggs, R., ed., Human Blood Coagulation, Thrombosis, and Haemostasis, p. 611, Blackwell Scientific Publications, Oxford, 1972.
175. Hougie, C., "Methods for estimating fibrinogen concentration," in Hematology, W. J. Williams, E. Beutler, A. J. Erslev, and R. W. Rundles, eds., p. 1650, McGraw-Hill, New York, 1977.
176. Hougie, C., "One-stage prothrombin time," in Hematology, W. J. Williams, E. Beutler, A. J. Erslev, and R. W. Rundles, eds., p. 1645-1647, McGraw-Hill, New York, 1977.
177. Hougie, C., "Recalcification time test and its modifications (partial thromboplastin time, activated partial thromboplastin time, and expanded partial thromboplastin time)," in Hematology, W. J. Williams, E. Beutler, A. J. Erslev, and R. W. Rundles, eds., p. 1642-1645 McGraw-Hill, 1977.
178. Forman, W. B., O. D. Ratnoff, and M. H. Boyer, "An inherited qualitative abnormality in plasma fibrinogen: Fibrinogen Cleveland," J. Lab. Clin. Med., 72, 455-472 (1968).
179. Natelson, E. A. and D. F. Doolittle, "Rapid determination of fibrinogen by thrombokinetis," Am. J. Clin. Pathol., 61, 828-833 (1974).
180. Brewer, J. M., A. J. Pesce, and R. B. Ashworth, Experimental Techniques in Biochemistry, p. 328, Prentice-Hall, Englewood Cliffs, N.J., 1974.
181. Garvey, M. B., and J. Black, "The detection of fibrinogen/fibrin degradation products by means of a new antibody-coated latex article," J. Clin. Pathol., 25, 680-682 (1972).
182. Alami, S. Y., J. W. Hampton, G. J. Race, and R. J. Speer, "Fibrin Stabilizing factor (Factor XIII), Am. J. Med., 44, 1-13 (1968).

183. Weiss, H. J., T. B. Tschopp, J. Rogers, and H. Brand, "Studies of platelet 5-hydroxytryptamine (serotonin) in storage pool disease and albinism," J. Clin. Invest., 54, 421-434 (1974).
184. Aurell, L., P. Friberger, G. Karlsson, and G. Claeson, "A new and highly specific chromogenic peptide substrate for Factor Xa," Thromb. Res., 11, 595-609 (1977).
185. Weber, K., and M. Osborn, "The reliability of molecular weight determinations by dodecyl sulfate-polyacrylamide gel electrophoresis," J. Biol. Chem., 244, 4406-4412 (1969).
186. Esnouf, M. P. and W. J. Williams, "The isolation and purification of a bovine-plasma protein which is a substrate for the coagulant fraction of Russel's viper venom," Biochem. J., 84, 62-68 (1962).
187. Flory, P. J., Principles of Polymer Chemistry, Cornell University Press, Ithaca, New York, 169.
188. Treloar, L. R. G., The Physics of Rubber Elasticity, Oxford University Press, London, 1958.
189. Dickerson, R. E., and I. Geis, The Structure and Action of Proteins, W. A. Benjamin, New York, 1969.
190. Marquardt, D. W., "An algorithm for least-squares estimation of non-linear parameters," J. SIAM, 11, 431-441 (1963).
191. Spudich, J. A., "Effects of cytochalasin B on actin filaments," Cold Spring Harbor Symp. Quant. Biol., 37, 585-593 (1972).
192. Walsh, P. N., and R. Biggs, "The role of platelets in intrinsic factor Xa formation," Brit. J. Haemat., 22, 743-760 (1972).
193. Walsh, P. N., "Platelet coagulant activities and hemostasis: a hypothesis," Blood, 43, 597-605 (1974).
194. Vecchione, J., and M. B. Zucker, "Procoagulant activity of platelets in recalcified plasma," Brit. J. Haemat., 31, 423-428 (1975).
195. Zurier, R. B., S. Hoffstein, and G. Weissman, "Cytochalasin B: Effect on lysosomal enzyme release from human leukocytes," Proc. Nat. Acad. Sci., 70, 844-848 (1973).

196. Hoffstein, S., I. M. Goldstein, and G. Weissman, "Role of microtubule assembly in lysosomal enzyme secretion from polymorphonuclear leukocytes," J. Cell Biol., 73, 242-256 (1977).
197. Hoffstein, S., and G. Weissman, "Microfilaments and microtubules in calcium ionophore-induced secretion of lysosomal enzymes from human polymorphonuclear leukocytes," J. Cell Biol., 78, 769-781 (1978).
198. deGaetano, G., D. Bottechia, and J. Vermynen, "Effects on platelets on clot structuration. A thromboelastographic study," Thromb. Res., 3, 425-435 (1973).
199. Ware, A. G., and W. H. Seegers, "Two-stage procedure for the quantitative determination of prothrombin concentration," Am. J. Clin. Pathol., 19, 471-482 (1949).
200. Stachurska, J., Z. S. Latallo, and M. Kopec, "Inhibition of platelet aggregation by dialysable fibrinogen degradation products (FDP)," Thromb. Diath. Haemorrh., 23, 91-98 (1970).
201. Mehl, J. W., W. O'Connell, and J. Degroot, "Macroglobulin from human plasma which forms an enzymatically active compound with trypsin," Science, 145, 821-822 (1964).
202. Rimon, A., Y. Shamash, and B. Shapiro, "The plasmin inhibitor of human plasma. IV. Its action on plasmin trypsin, chymotrypsin, and thrombin," J. Cell Biol., 241, 5102-5107 (1966).
203. Hedner, U., "Fibrinolytic inhibitors," in Thrombosis: Pathogenesis and Clinical Trials, E. Deutsch, K. Lechner, and K. M. Brindous, eds., p. 287, Shattaver, Stuttgart, 1974.
204. Butkov, E., Mathematical Physics, p. 307, Addison-Wesley, Reading, Massachusetts, 1968.
205. Lightfoot, E. N., Transport Phenomena and Living Systems, p. 316, Wiley-Interscience, New York, 1974.

APPENDICES

APPENDIX A

DETERMINATION OF DYNAMIC SHEAR MODULI

Walters and Kemp (170) have derived a useful mathematical method for the determination of linear viscoelastic properties of a material subjected to a small amplitude oscillatory shear strain. A brief summary of their technique is presented in this appendix.

Using the amplitude ratio and the phase difference, between the motions of the upper and lower platens, G^* , the complex dynamic shear modulus ($G^* = G' + G''$) may be calculated. The real part of G^* , G' , is the dynamic shear storage modulus which represents the elasticity of the material. G'' , the dynamic shear loss modulus, is the imaginary part of G^* , and this quantity is proportional to the frequency of oscillation times the viscosity. The computer program employed to determine the dynamic moduli may be found in Appendix B.

The test system is assumed to consist of two parallel plate radius a which sinusoidally oscillate about a common axis, $r = 0$, with frequency ω (Figure A.1). The upper platen ($z = h$) has an amplitude of oscillation of e_1 , and the amplitude of the lower platen is e_2 . The phase angle, c , is the

Figure A-1. Schematic representation of test system geometry and platen motions. Amplitudes of upper and lower platen are θ_2 and θ_1 , respectively, and phase difference, c .

amount the motion of the upper platen lags behind that of the lower platen.

If edge effects are neglected, the velocity distribution is assumed to have the form:

$$V_r = 0$$

$$V_z = 0$$

$$V_\theta = \text{Re}\{rF(z)e^{i\omega t}\} \quad (\text{A.1})$$

where $\text{Re}\{ \}$ denotes the real part. Thus, the angular velocity, V_θ , is proportional to an oscillatory motion and an angular amplitude.

The only non-vanishing component of the stress tensor is $\tau_{\theta z}$ which is written:

$$\tau_{\theta z} = \text{Re} \left\{ \frac{G^*}{i\omega} r \frac{\partial}{\partial z} F(z) e^{i\omega t} \right\} \quad (\text{A.2})$$

if the test material exhibits linear viscoelastic behavior.

For the motion of the platens, the sole non-trivial equation of motion is

$$\frac{\partial \tau_{\theta z}}{\partial z} = \text{Re}\{\rho r F(z) i \omega e^{i\omega t}\} \quad (\text{A.3})$$

where ρ is the density of the fluid.

Substitution of the expression for $\tau_{\theta z}$ in Equation (A.2) into Equation (A.3) yields

$$\operatorname{Re}\left\{ \frac{G^*}{i\omega} + \frac{\partial^2 F(z)}{\partial z^2} e^{i\omega t} \right\} = \operatorname{Re}\{\rho r F(z) i\omega e^{i\omega t}\} \quad (\text{A.4})$$

which may be rearranged to give

$$\frac{\partial^2 F(z)}{\partial z^2} + \alpha^2 F = 0 \quad (\text{A.5})$$

where

$$\alpha^2 = \frac{\omega^2 \rho}{G^*}$$

Assuming a "no-slip" condition at the platen-sample interface, the boundary conditions for this system are:

$$F(0) = i\omega\theta_2 e^{ic} \quad (\text{A.6})$$

$$F(h) = i\omega\theta_1 \quad (\text{A.7})$$

Applying these conditions, the solution to Equation (A.5) is

$$F(z) = A \sin(\alpha z) + B \cos(\alpha z) \quad (\text{A.8})$$

where

$$A = i\omega[\theta_1 \csc(\alpha h) - \theta_2 e^{ic} \cot(\alpha h)]$$

$$B = i\omega\theta_2 e^{ic}$$

From the velocity profile, the shear stress on the upper platen may be used to calculate the torque, T . The

expression for the torque is written

$$T = -r \int_0^r dr \int_0^{2\pi} \text{Re}\{\tau_{\theta z}^*(z=h)\} r d\theta \quad (\text{A.9})$$

Performing the integration in Equation (A.9) yields

$$T = - \frac{\pi a^4 \omega^2 \rho}{2} \text{Re}\left\{ \frac{e^{-i\omega t}}{\alpha} (\theta_2 e^{ic} \csc(\alpha h) - \theta_1 \cot(\alpha h)) \right\} \quad (\text{A.10})$$

In terms of torque on the upper platen, the torsion bar constant (K), and the rotational inertia of the upper assembly (I), the equation of motion of the upper platen is written:

$$T = \text{Re}\{(K - I\omega^2) \theta_1 e^{i\omega t}\} \quad (\text{A.11})$$

Equation (A.10) may be substituted for T to give

$$(K - I\omega^2) \theta_1 = - \frac{\pi a^4 \omega^2 \rho}{2\alpha} [\theta_2 e^{ic} \csc(\alpha h) - \theta_1 \cot(\alpha h)] \quad (\text{A.12})$$

This expression may be rearranged to yield

$$\frac{e^{ic}}{v} = \cos(\alpha h) + S\alpha h \sin(\alpha h) \quad (\text{A.13})$$

where

$$v = \theta_1 / \theta_2$$

$$S = \frac{2(K - I\omega^2)}{\omega^2 \rho \pi a^4 h}$$

The quantity α (and hence G^*) was evaluated using an iterative scheme proposed by Walters and Kemp (170). A first approximation to α was obtained using the form of Equation (A.12) when fluid inertia is small ($\rho = 0$)

$$\frac{e^{ic}}{v} = 1 + S\alpha^2 h^2$$

Under the experimental conditions of this study the approximate and "exact" values were virtually identical.

APPENDIX B

COMPUTER DETERMINATION OF DYNAMIC SHEAR MODULI FROM DIGITAL DATA

The digital form of the analog signals from the transducers monitoring the motion of the upper and lower platens was analysed using the FORTRAN program TFILT listed in this appendix. In the first section of the program the data were digitally filtered, and the amplitude ratio and phase difference between the signals were determined using the University of California Biomedical Computer Program BMD01T (172). The dynamic shear moduli were calculated in the second section from these values by the method of Walters and Kemp (170) as programmed by Glover (75).

```

/*SETUP    TAPE9,SER=R90386,NP,SL=R90386,NSH
// EXEC FTG1C
//FORT.SYSLIN,DD UNIT=TAPE9,DISP=(NEW,KEEP),LABEL=(1,SL),
// VOL=SER=R90386,DSN=RHEO.OBJ,DCB=BLKSIZE=80
//FORT.SYSLIN DD *

```

PROGRAM TFILT USES BND01T TO DETERMINE THE RATIO OF AMPLITUDES OF TWO DIGITAL, SINUSOIDAL SIGNALS (REPRESENTING THE MOTIONS OF THE UPPER AND LOWER PLATENS IN THE RHEOGONIOMETER) AND THE PHASE BETWEEN THEM AND CONVERTS THESE TO THE DYNAMIC STORAGE AND LOSS MODULI. INPUT DATA IS FOR A NUMBER OF RUNS (EXPERIMENTS) AND EACH RUN MAY HAVE DATA AT A NUMBER OF TIME POINTS IN ORDER TO DESCRIBE CURVES OF MODULUS VERSUS TIME FOR EACH RUN. THE INPUT DATA CONSISTS OF:

1. CONTROL CARDS
2. PHYSICAL CONSTANTS FOR THE SYSTEM THAT PRODUCED THE TWO OSCILLATORY SIGNALS.
3. INFORMATION LABELING THE TWO SIGNALS AS TO DATE, TEST NUMBER, TIME, TEST FREQUENCY, TEST AMPLITUDE, AND INPUT AND OUTPUT AMPLIFIER RANGE SETTINGS.
4. THE TWO OSCILLATORY SIGNALS IN DIGITAL FORM.

ITEMS 1 AND 2 ARE ON CARDS.

ITEMS 3 AND 4 MAY BE EITHER FROM CARDS OR TAPE (PREPARED BY THE SPACE SCIENCE DEPARTMENT FROM AN ANALOG RECORDING OF THE TWO SIGNALS).

FOR ALL DATA ON CARDS THE INPUT IS AS FOLLOWS:

CARD NO.	TYPE OF CARD
1	PROBLEM
2 (SEE BELOW)	FORMAT
3 TO N	INPUT SIGNAL DATA
N+1	PROBLEM
N+2 (SEE BELOW)	FORMAT
N+3 TO N+M	OUTPUT SIGNAL DATA
N+M+1	TIME, ETC.
N+M+2	SYSTEM CONSTANTS

'YES' MUST APPEAR IN CARD COLUMNS 22-24 IN THE FIRST PROBLEM CARD. A 'FORMAT' CARD MUST APPEAR IF AND ONLY IF THE PRECEDING 'PROBLEM' CARD HAS A YES IN CC 22-24. THE PROGRAM WILL ASSUME THAT IF YES (CC22-24) IS ABSENT IN ANY PROBLEM CARD THAT ALL THE PROBLEM PARAMETERS IN CC 25-80 ARE THE SAME AS THE LAST 'YES' PROBLEM CARD AND THAT THE HEAD FORMAT FOR THE DATA IS THE SAME AS THAT USED FOR THE FIRST 'YES' PROBLEM CARD.

REPEAT CARDS 1 TO N+M+1 FOR ADDITIONAL TIME POINTS IN A RUN. ADDITIONAL RUNS ARRANGED SIMILARLY MAY FOLLOW. AFTER THE FINAL RUN PLACE A FINISH CARD AND A /* CARD. PROBLEM, FORMAT, AND DATA CARDS ARE EXPLAINED IN 'BIOMEDICAL COMPUTER PROGRAMS' BY W. J. DIXON, UNIV. OF CAL. PRESS, 1971. THE TIME, ETC. CARD HAS THE FOLLOWING INFORMATION:

PARAMETER	FORMAT	CARD COL.
MINUTES	I3	1-3
SECONDS	I3	4-6
JULIAN DATE	I5	27-31
DATE (MONTH, DAY, YEAR)	5A5	7-26
RUN NUMBER	I3	32-34

C	FREQUENCY (RADIAN/SEC)	F9.4	35-43
C	INPUT AMPLITUDE	F7.1	44-50
C	AMPLIFIER RANGE (INPUT)	F9.1	51-59
C	AMPLIFIER RANGE (OUTPUT)	F9.1	60-68
C	TIME BETWEEN SAMPLES (SEC)	F9.3	69-77

NOTE: THE LAST ITEM (TIME BETWEEN SAMPLES) IS TO BE PUNCHED ONLY FOR THE SIGNAL DATA ON CARDS. IF THE SIGNAL DATA IS ON TAPE, THE TIME CARD INFORMATION IS PUNCHED ON A CARD FOLLOWING THE SAME FORMAT AS ABOVE (EXCEPT FOR THE TIME BETWEEN SAMPLES) AND WRITTEN ON THE DATA TAPE AS PART OF THE DIGITIZATION. THE TIME BETWEEN SAMPLES IS ALSO WRITTEN ON THE TAPE AT THIS TIME.

THE SYSTEM CONSTANTS CARD HAS THE FOLLOWING INFORMATION (FOR PARALLEL PLATE GEOMETRY):

PARAMETER	FORMAT	CARD COL.
TORSION BAR CONSTANT	1PE10.3	1-10
UPPER ASSEMBLY INERTIA	P10.4	13-22
PLATEN RADIUS	F5.2	25-29
GAP SIZE	F8.5	32-39
TEST MATERIAL DENSITY	F5.2	42-46
PHASE CORRECTION	F5.2	50-54
AMPLITUDE CORRECTION	F6.3	58-63

FOR THE DATA SIGNALS AND THE TIME, ETC. INFORMATION ON TAPE THE CARD INPUT IS:

CARD NO.	TYPE OF CARD	PUNCH
0		
1	PROBLEM	
2 (SEE BELOW)	FORMAT	
3	RECORDS SKIPPED	
4	PROBLEM	
5 (SEE BELOW)	FORMAT	
6	SYSTEM CONSTANTS	

PUNCH IS AN OPTIONAL CARD WHICH SPECIFIES THAT DATA IS TO BE PUNCHED FOR THE CALCOMP PLOTTER. 'YES' MUST APPEAR IN CARD COLUMNS 22-24 IN THE FIRST PROBLEM CARD. A 'FORMAT' CARD MUST APPEAR IF AND ONLY IF THE PRECEDING 'PROBLEM' CARD HAS A YES IN CC 22-24. THE PROGRAM WILL ASSUME THAT IF YES (CC22-24) IS ABSENT IN ANY PROBLEM CARD THAT ALL THE PROBLEM PARAMETERS IN CC 25-80 ARE THE SAME AS THE LAST 'YES' PROBLEM CARD AND THAT THE READ FORMAT FOR THE DATA IS THE SAME AS THAT USED FOR THE FIRST 'YES' PROBLEM CARD.

REPEAT CARDS 1 TO 5 FOR ADDITIONAL TIME POINTS IN A RUN. ADDITIONAL RUNS, SIMILARLY ARRANGED MAY FOLLOW. AFTER THE FINAL RUN PLACE A FINISH CARD AND A /* CARD. CARDS 1,2,4,5, AND 6 ARE AS DESCRIBED ABOVE. THE RECORDS SKIPPED CARD HAS THE NUMBER OF RECORDS TO BE SKIPPED IN A DATA FILE IN CARD COLUMNS 1-3 (FORMAT I3). JCL CARDS, OF COURSE, ARE NEEDED FOR THE TAPE INPUT.

FOR FURTHER INFORMATION SEE COMMENTS IN SUBROUTINES REDUCE, CMPLXG, AND RDDATA.

BMD01T

00000000

```

C      THIS IS A SIFTED VERSION OF BMD01T ORIGINALLY WRITTEN IN      00000010
C      FORTRAN II. SOME MODIFICATIONS WERE MADE TO MAKE IT OPERABLE  00000020
C      AND SLIGHTLY MORE EFFICIENT THAN THE SIFTED VERSION.          00000030
      DIMENSION AMPI(1000),AMPO(1000),Z2I(1000),Z2O(1000)
      DIMENSION X(5000),FMT(180),YSQ(500),Y(1500),SYM(15),YP(15),  00000040
      1A(1000),B(1000),XX(5000),YY(5000)                             00000050
      DIMENSION INDR(4),HOR(9)
      COMMON Y , FMT , YSQ , Y , SYM , YP      00000060
      COMMON A , B , XX , YY , AMPL , PHASE    00000070
      COMMON TG , FILTER , KPROB , NDATA , FTRI , NTRI 00000080
      COMMON M , FM , NPOINT , POINT , NO , ANS      00000090
      COMMON PI , H                                  00000100
C      DIMENSION X(5000),FMT(120),YSQ(500),Y(1500),SYM(15),YP(15),  00000110
C      1A(1000),B(1000),XX(5000),YY(5000)         00000120
C      COMMON X,FMT,YSQ,Y,SYM,YP,A,B,XX,YY,AMPL,PHASE,TG,FILTER,KPROB, 00000130
C      1NDATA,FTRI,NTRI,M,FM,NPOINT,POINT,NO,ANS,PI,H 00000140
C      00000150
CC305 FORMAT(49H1BMD01T - AMPLITUDE AND PHASE ANALYSIS - REVISED , 00000160
CC 1 13HJULY 16, 1970/                                           00000170
CC 2 41H HEALTH SCIENCES COMPUTING FACILITY, UCLA///           00000180
CC 3 14H PROBLEM CODE A6/                                         00000190
CC 4 16H PROBLEM NUMBER I3/                                       00000195
CC 5 23H NUMBER OF DATA POINTS I5/                               00000200
CC 6 12H INPUT UNIT I2///)                                       00000205
C      REAL*8 A123/'FINISH '/,B123/'PROBLEM '/,TODE,CODE,PUNCH    00000210
      DATA Q002HL/4HYES /                                         00000220
      DATA Q003HL/4H*000/                                         00000230
      DATA PUNCH/'PUNCH'/                                         00000240
      YES = (+Q002HL)                                              00000250
      NTAPP=5                                                       00000260
      IEND = -1
      LCTJ = 1
      NTP = -1
      JSKIP = 0
      INS=0
      PUN=0.
304 FORMAT('CONTROL CARD WAS INCORRECTLY ORDERED OR PUNCHED. IT IS', 00000270
1' PRINTED BELOW AND PROGRAM HAS BEEN TERMINATED.')             00000280
5001 FORMAT(2A6,4A3,I3,I4,I3,I4,I3,F5.0,22X,2I2)                 00000290
5002 FORMAT(1H0,2A6,4A3,I3,I4,I3,I4,I3,F5.0,22X,2I2)            00000300
500 READ (5,5001) TODE,CODE,XG,ZDATA,ELTER,XOOL,KPROX,NDATX,NTXI,MX, 00000310
1NPOINT,XX,INFORX,KVX                                           00000320
      IF (TODE.EQ.PUNCH) PUN=1.
      IF (TODE.EQ.PUNCH) GO TO 500
      IF (XOOL.NE.YES) GO TO 501
      KPROB = KPROX
      NDATA = NDATX
      NTRI = NTXI
      M = MX
      NPOINT = NPOINT
      NO = NO
      INFORM = INFORX
      KVR = KVX
501 IF (TODE.EQ.B123) GO TO 20                                     00000330
      IF (TODE.EQ.A123) GO TO 303                                  00000340
302 CONTINUE                                                       00000350
      WRITE (6,3040)                                                00000360
3040 FORMAT ( 'QA 'PROBLEM' OF 'FINISH' CARD WAS EXPECTED.' )    00000370
      WRITE (6,304)                                                 00000380
      WRITE (6,5002) TODE,CODE,XG,ZDATA,ELTER,XOOL,KPROB,NDATA,NTRI,M, 00000390

```

```

1 NPOINT,WO,INFORM,KVR                                00000400
303 IEND=1
    CALL REDUCE (KPERM,AMPI,AMEO,Z2I,Z2O,IEND,IHDR,HDR,FMT,SR,JSKIP,
1    KVR,NTAPE,NDATA,NTRI,M,WO,INS,PUN)
    IF (NTAPE-5) 371,372,371                                00000420
371 REWIND NTAPE
372 CONTINUE                                00000430
CC372 WRITE(6,3722)                                00000440
C3722 FORMAT (1H0 / / 'O FINISH CARD ENCOUNTERED.' )      00000450
    STOP
    20 IF (NTP.EQ.INFORM) GO TO 23
    CALL TPWD(INFORM,NTAPE)
    NTP = INFORM
    23 CONTINUE
CC    WRITE(6,305) CODE,KPROB,NDATA,NTAPE                00000470
    IF (-NTRI) 25,302,302                                00000480
    25 PTRI=NTRI                                          00000490
    IF (M-4000) 255,255,302                              00000500
    255 PM=M                                              00000510
    PI=3.14159265                                         00000520
    CRIT=(PM-2.0)/2.0                                    00000530
    IF (CRIT-PTRI) 11,11,12                              00000540
    11 DO 90 I=1,6                                       00000550
    90 WRITE (6,2000)                                    00000560
    WRITE (6,1011) KPROB                                  00000570
1011 FORMAT(10X,5H* * */10X,23HBANDWIDTH CHOSEN IN PROBLEM I3,
1    50H LARGER THAN PI, PROGRAM GOES TO NEXT PROBLEM CARD/10X,5H* * *00000580
    2)                                                    00000590
    PI=-4000                                              00000600
    12 IF (XOOL.NE.YES) GO TO 214                        00000610
    IF (KVR.GT.0.AND.KVR.LE.10) GO TO 210
    WRITE (6,4000)                                00000630
4000 FORMAT(1H0,23X,71HNUMBER OF VARIABLE FORMAT CARDS INCORRECTLY SPEC00000640
    XIFIED, ASSUMED TO BE 1.)                        00000650
    KVR = 1                                              00000660
    210 KVR=KVR*18                                        00000670
    READ (5,5003) (FMT(I),I=1,KVR)                  00000680
5003 FORMAT(18A4)                                        00000690
CC    WRITE (6,5005) (YMT(I),I=1,KVR)                  00000700
C5005 FORMAT ('O VARIABLE FORMAT USED IS PRINTED BELOW.'/(1H0, 18A4)) 00000710
    214 IF ((NDATA-49)*(NDATA-5001)) 215,302,302      00000720
    215 MISTAK=0                                         00000730
    IF (NTAPE.EQ.5) GO TO 26
    CALL RDATA (INFORM,NDATA,FMT,IHDR,HDR,X,LCTJ,JSKIP,SR,INS)
    GO TO 27
    26 READ (NTAPE,FMT) (X(I),I=1,NDATA)              00000740
    27 IF (-PI) 40,500,500                              00000750
    40 IF (XG.NE.YES) GO TO 30                          00000760
    45 CALL TRANS( MISTAK)                              00000770
    IF( MISTAK) 500,30,500                             00000780
    30 IF (XDATA.NE.YES) GO TO 60                       00000790
    65 WRITE (6,2000)                                    00000800
    WRITE (6,1017) KPROB                                  00000810
1017 FORMAT(10X,25HORIGINAL DATA OF PROBLEM I3//)      00000820
    WRITE (6,1018) (X(I),I=1,NDATA)                  00000830
1018 FORMAT(10F12.6)                                    00000840
    60 IF (ELTER.NE.YES) GO TO 126                     00000850
    95 POINT=NPOINT                                     00000860
    IF (50-NPOINT) 951,951,302                        00000870
    951 IF (WO*(WO-PI)) 955,955,96                    00000880
    955 H=PI/POINT                                       00000890

```

```

G= (FTRI+1.0) *2.0*PI/PM                                00000900
BONE=WO-.5*G                                              00000910
IF (BONE) 96,96,97                                         00000920
96 WRITE (6,1019)KPROB                                     00000930
1019 FORMAT(10X,49H*****THE MAIN LOBE OF THE FILTER OF THIS PROBLEM(13,00000940
166H) IS NOT BETWEEN 0 AND PI,PROGRAM GOES TO THE NEXT PROBLEM, IF 00000950
2ANY)                                                       00000960
GO TO 500                                                  00000970
97 NONE= (BONE/H) +0.5                                     00000980
WRITE (6,1000)                                             00000990
1000 FORMAT(1H1)                                           00001000
CALL LANAI (NONE,0.0,0)                                    00001010
AA=ANS                                                     00001020
100 WRITE (6,2000)                                         00001030
2000 FORMAT(1H0)                                           00001040
ZERO=0.0                                                  00001050
WRITE (6,1002)ZERO,BONE,AA                                00001060
1002 FORMAT(10X,38HVALUE OF INTEGRAL OF F(X) SQUARE FROM F10.5, 00001070
14H TO F10.5,3H = F10.5//)                                00001080
BTWO=WO+.5*G                                              00001090
IF (BTWO-PI) 101,101,102                                  00001100
102 WRITE (6,1019)KPROB                                    00001110
GO TO 500                                                  00001120
101 NTWO= (G/H) +0.5                                       00001130
CALL LANAI (NTWO,BONE,NONE)                               00001140
BE=ANS                                                     00001150
105 WRITE (6,2000)                                         00001160
WRITE (6,1002)BONE,BTWO,BB                                00001170
NTHREE= ((PI-BTWO)/H) +0.5                                00001180
KK=NONE+NTWO                                              00001190
CALL LANAI(NTHREE,BTWO,KK)                                00001200
CC=ANS                                                     00001210
110 WRITE (6,2000)                                         00001220
WRITE (6,1002)BTWO,PI,CC                                   00001230
PC=(AA+CC)*100.0/(AA+BB+CC)                               00001240
WRITE (6,1006)                                             00001250
1006 FORMAT(1H0,9X,10HRESOLUTION7X,16HNO. OF TRIANGLES9X,11HCENTERED AT00001260
18X,9HBANDWIDTH,10X,19HLEAKAGE IN PER CENT//)            00001270
WRITE (6,1008)M,NTRI,WO,G,PC                             00001280
1008 FORMAT(13X,I3,18X,I3,15X,F11.8,8X,F10.7,12X,F12.8)  00001290
115 WRITE (6,2000)                                         00001300
WRITE (6,1005)                                             00001310
1005 FORMAT(1H0,9X,34HTHESE ARE THE VALUES OF THE FILTER//) 00001320
NPOINT=NONE+NTWO+NTHREE                                   00001330
POINT=NPOINT-1                                            00001340
WRITE (6,1007) (Y(I),I=1,NPOINT)                         00001350
1007 FORMAT(7F12.6)                                       00001360
WRITE (6,1010)                                             00001370
1010 FORMAT(1H1,20X,19HGRAPH OF THE FILTER//)            00001380
YMAX=-10**10                                              00001390
YMIN=10**10                                               00001400
DO 120 I=1,NPOINT                                         00001410
YMAX=AMAX1(Y(I),YMAX)                                     00001420
120 YMIN=AMIN1(Y(I),YMIN)                                  00001430
SYM(1)=(+0003HL)                                          00001440
DO 125 I=1,NPOINT                                         00001450
PI=I-1                                                    00001460
XX(1)=PI*PI/POINT                                         00001470
YP(1)=Y(I)                                                00001480
125 CALL PLOTB (XX,0.0,PI,YP,SYM,YMIN,YMAX,1,-1)          00001490
CALL PLOTR (XX,0.0,PI,YP,SYM,YMIN,YMAX,-1,-1)            00001500

```

```

126 IF (XOOL.NE.YES) GO TO 131
127 CALL COEVV
      BZERO=2.0*PTRI/FM
CC    WRITE (6,1003)
C1003 FORMAT(1H1,9X47HB IS THE COEFFICIENT OF COS J.OMEGA IN C(OMEGA)/
CC    1 10X,75HAND A IS THE COEFFICIENT OF SIN J.OMEGA IN S(OMEGA) IN SEC
CC    2TIGN FOUR STEP 2 ///)
CC    WRITE (6,1009)BZERO
C1009 FORMAT(10X16HA( 0) = 0.024X9HB( 0) =F11.5)
CC    DO 130 I=1,M
C1130 WRITE (6,1004)I,A(I),I,B(I)
C1004 FORMAT (10X,2HA(I4,4H) = F10.5,20X,2HB(I4,4H) = F10.5)
131 DO 140 K=1,NDATA
      L=M+K
      XX(K)=BZERO*X(L)
      YY(K)=0.0
      DO 155 J=1,M
        JS=L+J
        KS=L-J
        IF (JS-NDATA) 145,145,150
145   YY(K)=YY(K)+A(J)*X(JS)-X(KS)
155   XX(K)=XX(K)+B(J)*X(JS)+X(KS)
C
C
140 CONTINUE
150 CONTINUE
CC150 WRITE (6,1020)
C1020 FORMAT(1H1,31X,56HGRAPH OF THE FILTERED INPUT AT THE INDICATED DAT
CC    1A POINTS//)
      K=K-1
      YMAX=-10.0**10
      YMIN= 10.0**10
      DO 157 I=1,K
        YMAX=AMAX1(XX(I),YMAX)
157   YMIN=AMIN1(XX(I),YMIN)
      IF (YMAX-YMIN-1.0) 1575,1575,158
1575 DIV=(YMAX-YMIN)/3.0
      YMAX=YMAX+DIV
      YMIN=YMIN-DIV
158 FK=M
      FMAX=NDATA-M
      DO 159 I=1,K
        FK=FK+1.0
        YP(I)=XX(I)
159 CONTINUE
CC159 CALL PLOTB(FK,FM,FMAX,YP,SYM,YMIN,YMAX, 1,-1)
CC    CALL PLOTB(FK,FM,FMAX,YP,SYM,YMIN,YMAX,-1,-1)
CC    WRITE (6,1023)KPF0B
C1023 FORMAT(1H1,20X,72HAVERAGE FREQUENCY, AMPLITUDE, PHASE AND FINITE M
CC    10VING AVERAGES OF SERIES I4/J2X,53H(FREQUENCY IN RADIAN/UNIT TIME
CC    2 AND PHASE IN RADIAN)///)
CC    WRITE (6,1025)
C1025 FORMAT(2X,4HDATA,7X,9HFFREQUENCY,11X,9HAMPLITUDE,13X,5HPHASE,7X,38H
CC    1FINITE MOVING AVERAGES USING CONSTANTS/1X,5HPOINT,68X,4HB(J),16X,
CC    24HA(J)///)
      CALL PHAZE(XX(1),YY(1),Z1)
      J=M+1
      DO 165 I=2,K
        J=J+1
        AMPL =SORT(XX(I)**2+YY(I)**2)
        CALL PHAZE(XX(I),YY(I),Z2)

```



```

      FRFQ=22-Z1
      IF (ABS(FREQ).GT.PI) FREQ=FREQ-2.*SIGN(PI,FREQ)
00002090
00002100
164 CONTINUE
CC164 WRITE (6,1024)J,FREQ,AMPL,Z2,XX(I),YY(I)
00002160
C1024 FORMAT(1H 15,4XF12.6,4(8X,F12.6))
00002170
      IF (LCTJ-2) 11000,10000,11000
10000 AMPO(I-1) = AMPL
      Z2O (I-1) = Z2
      GO TO 165
11000 AMPI(I-1)=AMPL
      Z2I (I-1) = Z2
00002180
165 Z1=Z2
      IF (LCTJ -2) 13000,14000,13000
13000 LCTJ = 2
      GO TO 500
14000 IF (NTAPE.NE.5) GO TO 12000
      READ(NTAPE,14001) (IHDP(I1),I1=1,2), (HDR(J1),J1=5,9),
1 (IHDR(I2),I2=3,4), (HDR(J2),J2=1,4),SR
14001 FORMAT (I3,I3,5A4,I5,I3,F9.4,F7.1,F9.1,F9.1,F9.3)
      IF (SR.EQ.0.0) GO TO 12000
      SR = 1.0 / SR
12000 KPERM = K-1
      CALL REDUCE (KPERM,AMPI,AMPO,Z2I,Z2O,IEND,IHDR,HDR,FMT,SR,JSKIP,
1 KVR,NTAPE,NDATA,NTRI,H,WO,INS,PUN)
      LCTJ = 1
      GO TO 500
      END
00002190
00002200
00002210
00002220
00002230
00002240
00002250
00002260
00002270
00002280
00002290
00002300
00002310
00002320
00002330
00002340
00002350
00002360
00002370
00002374
00002380
00002390
00002400
00002410
00002420
00002430
00002440
00002450
00002460
00002470
00002480
00002490
00002500
00002510
00002520
00002530

```

CCOEVV SUBROUTINE COEVV FOR BMD01T AUGUST 9, 1965

SUBROUTINE COEVV

DIMENSION Z(5000),FMT(180),YSQ(500),Y(1500),SYM(15),YP(15),

1A(1000),B(1000),XX(5000),YY(5000)

C S IS NOT AN ARRAY IN THIS REVISION, THUS SAVING SPACE

COMMON X , FMT , YSQ , Y , SYM , YP

COMMON A , B , XX , YY , AMPL , PHASE

COMMON TG , FILTER , KPROB , NDATA , FTRI , NTRI

COMMON M , FM , NPOINT , POINT , WO , ANS

COMMON PI , H

C DIMENSION X(5000),FMT(120),YSQ(500),Y(1500),SYM(15),YP(15),

C 1A(1000),B(1000),XX(5000),YY(5000)

C DIMENSION S(1000)

C COMMON X,FMT,YSQ,Y,SYM,YP,A,B,XX,YY,AMPL,PHASE,TG,FILTER,KPROB,

C 1NDATA,FTRI,NTRI,H,FM,NPOINT,POINT,W0,ANS,PI,H

MMO=M-1

ARG=FM*WO

C SEE STEP 2, TERMS A(M) AND B(M), IN COMPUTATIONAL PROCEDURE

AA=FTRI*(.54+.46*COS(PI))*SIN(ARG)/FM

BB=FTRI*(.54+.46*COS(PI))*COS(ARG)/FM

KT=NTRI/2

IF (NTRI-KT*2) 20,10,20

20 A(M)=-AA

B(M)=BB

GO TO 30

10 A(M)=AA

B(M)=-BB

30 DO 120 J=1,MMO

FJ=J

ARGA=FJ*PI/FM

ARGB=FJ*FTRI*PI/FM

S=2.0*(.54+.46*COS(ARGA))*SIN(ARGB)/(FM*SIN(ARGA))

C

C

```

ARG=FJ*WO
A(J)=-S*SIN(ARG)
120 B(J)=S*COS(ARG)
RETURN
END
CDINT SUBROUTINE DINT FOR BMD01T
SUBROUTINE DINT(YSQ,NN,H,ANS)
DIMENSION YSQ(500),CONS(4)
C DIMENSION YSQ(500),CONS(4)
C
CONS(1)=0.34861111
CONS(2)=1.24583333
CONS(3)=0.87916667
CONS(4)=1.02638889
X=0.0
J=NN
DO 10 I=1,4
X=X+(YSQ(I)+YSQ(J))*CONS(I)
J=J-1
10 CONTINUE
DO 20 I=5,J
X=X+YSQ(I)
20 CONTINUE
ANS=X*H
RETURN
END
CLANAI SUBROUTINE LANAI FOR BMD01T
SUBROUTINE LANAI(NH,BASE,KIT)
DIMENSION X(5000),FMT(180),YSQ(500),Y(1500),SYM(15),YP(15),
1A(1000),B(1000),XX(5000),YY(5000)
COMMON X , FMT , YSQ , Y , SYM , YP
COMMON A , B , XX , YY , AMPL , PHASE
COMMON TG , FILTER , KPROB , NDATA , FTPI , NTRI
COMMON M , FM , NPOINT , POINT , NO , ANS
COMMON PI , H
C DIMENSION X(5000),FMT(120),YSQ(500),Y(1500),SYM(15),YP(15),
C 1A(1000),B(1000),XX(5000),YY(5000)
C COMMON X,FMT,YSQ,Y,SYM,YP,A,B,XX,YY,AMPL,PHASE,TG,FILTER,KPROB,
C 1NDATA,FTPI,NTRI,M,FM,NPOINT,POINT,NO,ANS,PI,H
DO 100 I=1,NN
PI=I
OMEGA=PI*H+BASE
CALL TABBY(OMEGA)
L=I+KIT
Y(L)=YY(1)
100 YSQ(I)=YY(1)**2
CC WRITE(6,1000)
C1000 FORMAT(1H0,21HVALUES OF F(X) SQUARE//)
CC WRITE(6,1001)(YSQ(I),I=1,NN)
C1001 FORMAT(7F12.6)
CALL DINT(YSQ,NN,H,ANS)
RETURN
END
CTABBY SUBROUTINE TABBY FOR BMD01T
SUBROUTINE TABBY(OMEGA)
DIMENSION X(5000),FMT(180),YSQ(500),Y(1500),SYM(15),YP(15),
1A(1000),B(1000),XX(5000),YY(5000)
COMMON X , FMT , YSQ , Y , SYM , YP
COMMON A , B , XX , YY , AMPL , PHASE
COMMON TG , FILTER , KPROB , NDATA , FTPI , NTRI
COMMON M , FM , NPOINT , POINT , NO , ANS

```

```

00002540
00002550
00002560
00002570
00002580
00002590
00002600
00002610
00002620
00002630
00002640
00002650
00002660
00002670
00002680
00002690
00002700
00002710
00002720
00002730
00002740
00002750
00002760
00002770
00002780
00002790
00002800
00002810
00002820
00002830
00002840
00002850
00002860
00002870
00002880
00002890
00002900
00002910
00002920
00002930
00002940
00002950
00002960
00002970
00002980
00002990
00003000
00003010
00003020
00003030
00003040
00003050
00003060
00003070
00003080
00003090
00003100
00003110
00003120
00003130
00003140

```

```

COMMON PI , H
DIMENSION X(5000),FMT(120),YSQ(500),Y(1500),SYM(15),YP(15),
1A(1000),B(1000),XI(5000),YY(5000)
COMMON X,FMT,YSQ,Y,SYM,YP,A,B,XX,YY,AMPL,PHASE,TG,FILTER,KPROB,
INDATA,FTRI,NTRI,M,FM,NPOINT,POINT,WO,ANS,PI,H
SUM=0.0
MMO=M-1
DO 100 J=1,MMO
FJ=J
P=FJ*PI/FM
Q=FJ*WO
R=FTRI*FJ*PI/FM
ARG=FJ*OMEGA
100 SUM=SUM+ (.54+.46*COS(P))*COS(Q)*SIN(R)*COS(ARG)/SIN(P)
SUM=4.0*SUM/FM
S=FM*WO
T=FM*OMEGA
NIT=NTRI/2
IF(NTRI-NIT*2) 200,300,200
200 YY(1) = (2.0*FTRI/FM)+SUM+2.0*FTRI*(.54+.46*COS(PI))*COS(S)*COS(T)/
1FM
GO TO 400
300 YY(1) = (2.0*FTRI/FM)+SUM-2.0*FTRI*(.54+.46*COS(PI))*COS(S)*COS(T)/
1FM
400 RETURN
END
CTPWD SUBROUTINE TPWD FOR BMD01T VERSION OF SEPT. 26, 1963
SUBROUTINE TPWD(NT1,NT2)
IF(NT1) 40,10,12
10 NT1=5
12 IF(NT1-NT2) 14,19,14
14 IF(NT2-20.5) GO TO 19
REWIND NT2
19 IF(NT1-5) 18,24,18
18 IF(NT1-6) 22,40,22
22 REWIND NT1
24 NT2=NT1
28 RETURN
40 WRITE(6,49)
STOP
49 FORMAT(25H ERROR ON TAPE ASSIGNMENT)
END
CTRANS SUBROUTINE TRANS FOR BMD01T JUNE 2, 1964
SUBROUTINE TRANS (MISTAK)
DIMENSION X(5000),FMT(180),YSQ(500),Y(1500),SYM(15),YP(15),
1A(1000),B(1000),XX(5000),TT(5000)
DIMENSION IBIN(10),CON(10)
COMMON X , FMT , YSQ , Y , SYM , YP
COMMON A , B , XX , YY , AMPL , PHASE
COMMON TG , FILTER , KPROB , INDATA , FTRI , NTRI
COMMON M , FM , NPOINT , POINT , WO , ANS
COMMON PI , H
C DIMENSION X(5000),FMT(120),YSQ(500),Y(1500),SYM(15),YP(15),
C 1A(1000),B(1000),XX(5000),YY(5000)
C DIMENSION IBIN(10),CON(10)
C COMMON X,FMT,YSQ,Y,SYM,YP,A,B,XX,YY,AMPL,PHASE,TG,FILTER,KPROB,
C INDATA,FTRI,NTRI,M,FM,NPOINT,POINT,WO,ANS,PI,H
EQUIVALENCE(ITG,SPECTG)
ASN(Q000FL)=ATAN(Q000FL)/SQRT(1.0-Q000FL**2)
REAL*8 SPECTG/'SPECTG '/,AODE
READ(5,1002)KODE,NTRAN,(IUTR(I),CON(I),I=1,NTRAN)

```

```

1002 FORMAT(A6,I1,8(I2,P6.0))                                00003760
      IF (KODE-ITG) 900,400,900                                00003770
400 DO 500 I=1,NTRAN                                           00003780
      IF (IBIN(I)-17) 605,600,605                               00003790
605 JESUS=IBIN(I)                                              00003800
      IF (JESUS-6) 610,905,610                                   00003810
600 JESUS=6                                                    00003820
610 CC=CON(I)                                                  00003830
      IF (JESUS*(JESUS-11)) 620,905,905                         00003840
620 DO 150 K=1,NPOINT                                          00003850
      GO TO (10,20,30,40,50,60,70,80,90,100) ,JESUS           00003860
10 IF (X(K)) 200,150,14                                         00003870
14 X(K)=SQRT(X(K))                                              00003880
      GO TO 150                                                  00003890
20 IF (X(K)) 200,22,23                                          00003900
22 X(K)=1.0                                                     00003910
      GO TO 150                                                  00003920
23 X(K)=SQRT(X(K))+SQRT(X(K)+1.0)                               00003930
      GO TO 150                                                  00003940
30 IF (X(K)) 200,200,31                                         00003950
31 X(K)=.434294481E+00*ALOG(X(K))                             00003960
      GO TO 150                                                  00003970
40 X(K)=EXP(X(K))                                              00003980
      GO TO 150                                                  00003990
50 IF (X(K)) 200,150,53                                         00004000
53 IF (X(K)-1.0) 54,55,200                                     00004010
54 ARG=SQRT(X(K))                                              00004020
      Y(K)=ASN(ARG)                                             00004030
      GO TO 150                                                  00004040
55 X(K)=PI/2.0                                                  00004050
      GO TO 150                                                  00004060
60 IF (X(K)) 200,200,61                                         00004070
61 X(K)=ALOG(X(K))                                             00004080
      GO TO 150                                                  00004090
70 IF (X(K)) 71,200,71                                         00004100
71 X(K)=1.0/X(K)                                               00004110
      GO TO 150                                                  00004120
80 X(K)=X(K)+CC                                                 00004130
      GO TO 150                                                  00004140
90 X(K)=X(K)*CC                                                 00004150
      GO TO 150                                                  00004160
100 IF (X(K)) 200,200,101                                       00004170
101 X(K)=X(K)**CC                                              00004180
      GO TO 150                                                  00004190
200 WRITE (6,1001)K,IBIN(I)                                    00004200
1001 FORMAT(11HODATA POINT IS,57H VIOLATES THE RESTRICTION FOR TRANSGEN00004210
      1ERATION OF THE TYPEI3,52H. THE PROGRAM CONTINUES LEAVING THE VALUE00004220
      2 UNCHANGED.)                                           00004230
150 CONTINUE                                                  00004240
500 CONTINUE                                                  00004250
300 RETURN                                                    00004260
900 WRITE (6,1003)KODE                                           00004270
      WRITE (6,1006) KODE,NTRAN,(IBIN(I),CON(I),I=1,NTRAN)    00004280
1006 FORMAT(1H0,A6,I1,8(I2,P6.0))                             00004290
901 WRITE (6,1004)                                              00004300
      MISTAK=17                                                 00004310
      GO TO 300                                                  00004320
1003 FORMAT(58H0CONTROL CARD ERROR. PROGRAM EXPECTED A SPECTG CARD BUT 00004330
      1A A6,16H CARD WAS FOUND.)                             00004340
1004 FORMAT(42H0PROGRAM WILL GO TO THE NEXT PROBLEM CARD.)    00004350
905 WRITE(6,1005) KODE, NTRAN, (IBIN(I), CON(I), I=1,NTRAN)  00004360

```

```

1005 FORMAT('OILLEGAL TRANSGENERATION CODE SPECIFIED. CARD IS PRINTED', 00004370
1'D BELOW.' / (1H0, A6, I1, 8(I2,P6.0))) 00004380
GO TO 901 00004390
END 00004400
CPHAZE SUBROUTINE PHAZE FOR BMD01T AUGUST 9, 1965 00004410
SUBROUTINE PHAZE(X,Y,Z) 00004420
PI=3.14159265 00004430
PI2=2.0*PI 00004440
IF (X.EQ.0.0) GO TO 12 00004445
AB=ABS(Y/X) 00004450
PHI=ATAN(AB) 00004460
IF (X) 11,12,13 00004470
11 IF (Y) 17,30,18 00004480
17 Z=PI+PHI 00004490
GO TO 50 00004500
30 Z=PI 00004510
GO TO 50 00004520
18 Z=PI-PHI 00004530
GO TO 50 00004540
12 IF (Y) 35,15,40 00004550
35 Z=0.75*PI2 00004560
GO TO 50 00004570
15 Z=0.0 00004580
GO TO 50 00004590
40 Z=PI/2.0 00004600
GO TO 50 00004610
13 IF (Y) 14,15,16 00004620
14 Z=PI2-PHI 00004630
GO TO 50 00004640
16 Z=PHI 00004650
50 RETURN 00004660
END 00004670
C SUBROUTINE PLOTR (IBM 360) AUGUST 13, 1966 00004680
SUBROUTINE PLOTR(X,ZMIN,ZMAX,Y,SYM,WMIN,WMAX,NC,NP) 00004690
C 00004700
DIMENSION Y(15),CLAB(12),SYM(15),GF(10),FMT(12),XY(51,101) 00004710
INTEGER*2 XY,BLANKS 00004720
INTEGER SYM,SYMB 00004730
DATA NCC/2/ 00004740
DATA TC,TP,BLANKS/1H.,1H+,1H / 00004750
DATA GF/ 4H 1X,,4H 2X,,4H 3X,,4H 4X,,4H 5X,,4H 6X,, 00004760
14H 7X,,4H 8X,,4H 9X,,4H 10X/ 00004770
DATA FMT/'(17X',' ','5(P1','2.3','8X)'/','7X',' ','4(P1','2.3',' 00004780
1'8X) ','F12.','3) '/ 00004790
C 00004800
100 FORMAT(1H 6X5(F12.3,8X),F12.3/17X,5(F12.3,8X)) 00004810
101 FORMAT(1H F12.3,1X,103A1,F12.3) 00004820
102 FORMAT(1H 13X,103A1) 00004830
1000 FORMAT(1H 14X,101A1) 00004840
1001 FORMAT(15X,20(5H+....),1H+) 00004850
C 00004860
C NCC ON THE INITIAL ENTRY TO PLOTR IS ASSUMED TO BE SOMETHING 00004870
C OTHER THAN ZERO. 00004880
C 00004890
C 00004900
IF (NCC) 50,48,50 00004910
50 KL=0 00004920
CALL SCALE(WMIN,WMAX,100.0,JY,YMIN,YMAX,YIS) 00004930
YR=YMAX-YMIN 00004940
230 J=JY 00004950
IF (J*(J-10)) 204,201,201 00004960
201 IF (KL) 220,220,231

```

```

231 WRITE (6,1001)                                00004970
    IF (KL) 250,250,220                            00004980
220 CLAB(1)= YMIN                                   00004990
    DO 222 I=2,11                                   00005000
222 CLAB(I)=CLAB(I-1)+YIJ                           00005010
    WRITE (6,100) (CLAB(I),I=1,11,2), (CLAB(J),J=2,10,2) 00005020
    IF (KL) 231,231,14                              00005030
204 IF (J-5) 205,221,207                            00005040
207 J=J-5                                             00005050
205 JYT=5-J                                           00005060
221 CONTINUE                                         00005070
226 FMT(2)=GF(JY)                                    00005080
    IF (KL) 225,225,227                             00005090
225 FMT(7)=GF(JY)                                    00005100
    TT=JY                                             00005110
    TT=TT*YIJ/10.0                                   00005120
    CLAB(1)= YMIN+TT                                00005130
    DO 223 I=2,10                                    00005140
223 CLAB(I)=CLAB(I-1)+YIJ                           00005150
    WRITE (6,FMT) (CLAB(I),I=2,10,2), (CLAB(JJJ),JJJ=1,9,2) 00005160
    IF (KL) 227,227,14                              00005170
227 IF (JY-5) 208,209,208                          00005180
208 WRITE (6,1000) (TC,I=1,J), (TP, (TC ,I=1,4), K=1,19), TP, (TC,I=1,JYT) 00005190
    IF (KL) 250,250,225                             00005200
209 WRITE (6,1001)                                   00005210
    IF (KL) 250,250,225                             00005220
250 CONTINUE                                         00005230
    NCC=0                                             00005240
    ICC=0                                             00005250
    IF (NP) 80,11,11                                00005260
11 DO 1 I=1,51                                       00005270
    DO 1 J=1,101                                     00005280
1  XY(I,J)=BLANKS                                    00005290
    CALL SCALE (ZMIN,ZMAX,50.0,JX,XMIN,XMAX,YIJ)    00005300
    XR=XMAX-XMIN                                     00005310
    ENTRY PLOTS                                      00005320
48 IF (NC) 52,13,49                                  00005330
49 IF (NP) 80,10,10                                  00005340
10 DO 9 N=1,NC                                       00005350
    SYMB=SYM(N)                                       00005360
    XDIFFR=XMAX-X                                     00005370
    IF (XDIFFR) 105,106,106                         00005380
105 XDIFFR=0.0                                       00005390
106 YDIFFR=YMAX-Y(N)                                00005400
    IF (YDIFFR) 107,108,108                         00005410
107 YDIFFR=0.0                                       00005420
108 L=51.0-(50.0*XDIFFR)/XR+.5                     00005430
    K=101.0-(100.0*YDIFFR)/YR+.5                   00005440
    CALL FORM2(SYMB,XY(L,K))                        00005450
9  CONTINUE                                         00005460
    GO TO 15                                         00005470
80 DO 86 I=1,101                                    00005480
86 XY(I,I)=BLANKS                                    00005490
    L=1                                              00005500
    DO 95 N=1,NC                                    00005510
    SYMB=SYM(N)                                       00005520
    YDIFFR=YMAX-Y(N)                                00005530
    IF (YDIFFR) 860,865,865                         00005540
860 YDIFFR=0.0                                       00005550
865 K=101.0-(100.0*YDIFFR)/YR+.5                  00005560
95 CALL FORM2(SYMB,XY(L,K))                        00005570

```

```

      IF (MOD(IC,5)) 97,96,97
96  W=TP
      GO TO 98
97  Z=TC
98  WRITE (6,101) Z,W,(XY(1,N),N=1,101),W,X
      IC=IC+1
      GO TO 15
13  M=6-JX
      LL=50+M
      T=JX
      IF (5-JX) 131,131,135
131 T=0.0
135 RLAB=XMAX-(T*XIJ)/5.0
      W=TC
      K=52
      DO 31 L=N,LL
      K=K-1
      I=MOD(L,5)
      IF (I-1) 2,3,2
3  W=TP
      WRITE (6,101) RLAB,W,(XY(K,N),N=1,101),W,RLAB
      RLAB=RLAB-XIJ
      W=TC
      GO TO 31
2  WRITE (6,102) W,(XY(K,N),N=1,101),Z
31 CONTINUE
52 KL=1
      GO TO 230
14 NCC=1
15 RETURN
      END
C      SUBROUTINE SCALE FOR PLOT
      JUNE 21, 1966
      SUBROUTINE SCALE(YMIN,YMAX,YINT,JY,TYMIN,TYMAX,YIJ)
      DIMENSION C(10)
      DATA C /1.0,1.5,2.0,3.0,4.0,5.0,7.5,10.0,15.0,20.0/
      TEST=1.0/(2.0**20)
50 YR=YMAX-YMIN
      TT=YR/YINT
      J = ALOG10(TT)+TEST
      E=10.0**J
      TT=TT/E
      I=0
      IF (TT-1.0+TEST) 205,201,201
205 TT=TT*10.0
      E=E/10.0
201 I=I+1
      IF (9-I) 1,2,2
1  E=E*10.0
      I=1
2  IF (TT-C(I)) 233,202,201
233 YIJ=C(I)*E
      GO TO 203
202 Y=YMIN/C(I)
      J=Y
      T=J
      IF (0.0001-ABS(T-Y)) 204,233,233
204 YIJ=C(I+1)*E
203 X=((YMAX+YMIN)/YIJ-YINT)/2.0+.00001
      K=X
      IF (K) 235,240,240
235 Y=K

```

```

      IF (X-Y) 236, 240, 236                                00006190
236 K=K-1                                                    00006200
240 TYMIN=K                                                  00006210
      TYMIN=YIJ*TYMIN                                         00006220
      TYMAX=TYMIN+YINT*YIJ                                     00006230
      IF (YMAX-TYMAX-TEST) 10, 10, 201                      00006240
10  TT=YINT/10.0                                              00006250
      JY=TT+.000001                                           00006260
      YIJ=YINT*(YIJ/10.0)                                     00006270
      J=TYMIN/ YIJ                                           00006280
      IF (K) 242, 241, 241                                    00006290
242 J=J-1                                                    00006300
241 J=J*JY+JY-K                                             00006310
      JY=J                                                    00006320
      RETURN                                                  00006330
      END                                                    00006340
      SUBROUTINE FORM2(SYMB,XY)                                00006350
C      SUBROUTINE FORM2 FOR PLOTR (IBM 360)                   JUNE 21, 1966 00006360
      INTEGER*2 XY,SYMB,BLANK/' ',TEST(18)/'2 ','3 ','4 ','5 ','6 ', 00006370
1'7 ','8 ','9 ','A ','B ','C ','D ','E ','F ','G ','H ','I ','/' '/' 00006380
      IF (XY.EQ. BLANK) GO TO 50                               00006390
      DO 30 I=1,17                                           00006400
      IF (XY.NE. TEST(I)) GO TO 30                            00006410
C      PUT IN NEXT SYMBOL OF ARRAY FOR MULTIPLE POINTS      00006420
      XY=TEST(I+1)                                           00006430
      GO TO 100                                               00006440
30  CONTINUE                                                 00006450
      IF (XY.EQ. TEST(18)) GO TO 100                         00006460
C      IF OTHER THAN CHARACTERS IN ARRAY TEST PUT IN CHARACTER 2. 00006470
      XY=TEST(1)                                              00006480
      GO TO 100                                               00006490
C      IF BLANK, PUT IN SYMBOL                                00006500
50  XY=SYMB                                                  00006510
100 RETURN                                                  00006520
      END                                                    00006530
      SUBROUTINE REDUCE(KPERM,AMPI,AMPO,Z2I,Z2O,IEND,INHDR,HDR,FMT,
1  SR,JSKIP,KVR,NTAPE,NDATA,NTRI,M,ZO,INS,PUN)
C      SUBROUTINE REDUCE TAKES THE PHASE AND AMPLITUDE OF THE FILTERED INPUT
C      AND OUTPUT SIGNALS WHICH CORRESPOND TO A PARTICULAR TIME AND
C      CALCULATES THE AMPLITUDE RATIO AND THE PHASE DIFFERENCE, AND
C      USES SUBROUTINE CMPLXG TO CALCULATE THE COMPLEX MODULUS.
C      THREE PAGES OF OUTPUT PER TEST (RUN) ARE PRINTED.
C
C      IMIN AND LSEC ARE THE TIME (MINUTES AND SECONDS) WHICH
C      CORRESPOND TO A SET OF DATA.
C      IDATEC IS THE JULIAN DATE THE TEST WAS RUN.
C      ITESTN IS THE NUMBER OF THE TEST BEING PROCESSED.
C      AMP IS THE INPUT OSCILLATION AMPLITUDE (MICRONS) AS MEASURED AT
C      THE TRANSDUCER.
C      W = TEST FREQUENCY (RAD/SEC)
C      RANGEI = AMPLIFIER RANGE SETTING FOR INPUT SIGNAL.
C      RANGE0 = AMPLIFIER RANGE SETTING FOR OUTPUT SIGNAL.
C
      DIMENSION AMPI(1000),AMPO(1000),Z2I(1000),Z2O(1000),RED(50,10),
1  INHDR(4),H5R(9),FMT(180),SDPED(50,3),ICM29(50),DATE(5)
      REAL*8 SQR/'(SQRD)' ' ',BLNK/' '
      IF (IEND) 9, 10, 22
9  IDATE = 0
      ITEST = 0
      IEND = 0

```



```

10 CAVG = 0.0
   SC = 0.0
   AMPAVI = 0.0
   AMPAVO = 0.0
   SAMPI = 0.0
   SAMPO = 0.0
   PI = 3.1415925
   DO 11 I = 1, KPERM
      CN = Z2I(I) - Z20(I)
      IF (CN+3.0*PI/4.0) 15, 15, 16
15  CN = CN + 2.0*PI
16  IF (CN-5.0*PI/4.0) 18, 17, 17
17  CN = CN - 2.0*PI
18  CN = CN*180.0/PI
      CAVG = CAVG + CN
      SC = SC + CN**2
      AMPAVI = AMPAVI + AMPI(I)
      AMPAVO = AMPAVO + AMPO(I)
      SAMPI = SAMPI + AMPI(I)**2
11  SAMPO = SAMPO + AMPO(I)**2
      XKPERM = KPERM
      SC = (XKPERM*SC-CAVG**2)/(XKPERM*(XKPERM-1.0))
      IF (SC.LT.0) GO TO 12
      SC = SQRT(SC)
12  CAVG = CAVG/XKPERM
      SAMPI = (XKPERM*SAMPI-AMPAVI**2)/(XKPERM*(XKPERM-1.0))
      IF (SAMPI.LT.0) GO TO 13
      SAMPI = SQRT(SAMPI)
13  AMPAVI = AMPAVI/XKPERM
      SAMPO = (XKPERM*SAMPO-AMPAVO**2)/(XKPERM*(XKPERM-1.0))
      IF (SAMPO.LT.0) GO TO 14
      SAMPO = SQRT(SAMPO)
14  AMPAVO = AMPAVO/XKPERM
      IMIN = IHDR(1)
      ISEC = IHDR(2)
      IDATEC = IHDR(3)
      ITESTN = IHDR(4)
      W = HDR(1)
      AMP = HDR(2)
      PANGEL = HDR(3)
      RANGE0 = HDR(4)
      MIN = IMIN
      SEC = ISEC
      TIME = MIN + SEC/60.0
      IF (IDATE-IDATEC) 21, 20, 21
21  IF (IDATE) 22, 30, 22
20  IF (ITEST-ITESTN) 22, 35, 22
22  WRITE (6, 104) IDATE, (DATE(I), I=1, 5), ITEST, W2, AMPOLD
104 FORMAT ('IDATE = ', I4//8X, 5X4//) TEST NUMBER ', I3/' FREQUENCY = ',
1    F9.4, 'RAD/SEC'/' OSCILLATION INPUT AMPLITUDE = ', F7.1,
2    ' MICRONS'/'
      WRITE (6, 101)
101 FORMAT (/
1    TIME', 8X, 'C (AVG)', 6X, 'STD', 12X, 'AVG', 5X, 'STD', 12X, 'AVG', 5X,
2    'STD', 10X, 'INPT', 4X, 'OUTPT'/' ', 14X, ' (DEG)', 8X, 'DEV', 8X,
3    'OUT AMP', 5X, 'DEV', 7X, 'INPT AMP', 5X, 'DEV', 9X, 'RANGE', 4X,
4    'RANGE', 6X, 'NO. PTS.'//)
      DO 23 I = 1, KT
      WRITE (6, 102) (RED(I, J), J=1, 10)
102 FORMAT (' ', 3(F8.2, 3X), 6X, 2(F6.3, 2X), 7X, 2(F6.3, 2X), 5X,
1    2(F7.1, 2X), 4X, F6.1)

```

```

WRITE (6,107) (FMT(I),I=1,KVR)
107 FORMAT ('+',48X,18A4/)
36 CONTINUE
RETURN
END
SUBROUTINE CMPLXG (TIME,7,CD,AMPRAT,ISYS,KT,ICMP9,PUN)

C
C SUBROUTINE CMPLXG FOR PARALLEL PLATE GEOMETRY (K. WALTERS AND R. A.
C KEMP, 'RHEOLOGICA ACTA,' VOL. 7, P. 1-8(1968)).
C
C PURPOSE- CALCULATE COMPLEX SHEAR MODULUS FROM AMPLITUDE RATIO
C AND PHASE DIFFERENCE (CALCULATED BY SUBROUTINE REDUCE).
C
C
C XK = TORSION BAR CONSTANT (DYNE-CM) = 10 CM*KT (DYNE-CM/MICRON).
C XI = ROTATIONAL INERTIA OF UPPER ASSEMBLY (DYNE-CM-SEC*2)
C W = FREQUENCY OF OSCILLATION (SEC*(-1))
C A = RADIUS OF PLATENS (CM)
C H = GAP SIZE (MICRONS)
C AMPRAT = AMPLITUDE RATIO OF OUTPUT TO INPUT SIGNALS
C CD = PHASE LAG OF OUTPUT BEHIND INPUT (DEGREES)
C CR = PHASE LAG OF OUTPUT BEHIND INPUT (RADIAN)
C
C G1APPX = REAL PART OF G* THAT NEGLECTS FLUID INERTIA.
C G2APPX = COMPLEX PART OF G* THAT NEGLECTS FLUID INERTIA.
C CG AND CGNEW ARE THE OLD AND NEW (CORRECTED) VALUES OF G*
C THAT DO NOT NEGLECT THE FLUID INERTIA.
C CORCD = ZERO PHASE CORRECTION FOR THE RELEVANT FREQUENCY AND
C AMPLITUDE AND FILTER SETTINGS (CORCD>0 FOR OUTPUT LAGGING INPUT).
C CORAMP = INDICATED AMPLITUDE RATIO FOR A REAL AMPLITUDE RATIO OF 1.0.
C
C DIMENSION CMP(50,9),ICMP9(50)
C COMPLEX CPHDIF,CG,CE,CALSOD, CALPHA,CBO,CEO,CDELE,CGNEW
C IF (KT) 5,4,5
5 IF (ISYS.NE.1) GO TO 3
WRITE (6,101)
101 FORMAT (/
1 40X,'(APPROXIMATE)',12X,9H('EXACT'))//
2106H TIME ANP RAT C G' G''
3 G' G'' MOD(G*) G*/G'//
4 105H (MIN) (DEG)
5 (DN/CM**2) (DN/CM**2) (DN/CM**2) (DN/CM**2) (DN/CM**2)
6 //)
DO 7 I = 1,KT
IF (ICMP9(I).NE.1) GO TO 8
WRITE (6,102)
102 FORMAT ('+',109X,'(INSUFFICIENT DATA)')
8 IF (PUN.EQ.1.) WRITE(7,105) CMP(I,1),CMP(I,6),CMP(I,7)
105 FORMAT (F7.2,1X,F9.3,1X,F9.3)
7 WRITE (6,103) (CMP(I,J),J=1,9)
103 FORMAT (1H+F7.2,1H 1PE10.3,1X, 0PF6.1,9X,4(1PE10.3,2X),2X,
10 11PE10.3,2X,0PF10.5/)
RETURN
4 IF (ISYS-1) 3,1,3
1 READ (5,104) XK,XI,A,H,RHO,CORCD, CORAMP
104 FORMAT (1PE10.3,2X,0PF10.4,2X,F5.2,2X,F8.5,2X,F5.2,3X,F5.2,3X,
2 F6.3)
ISYS=0
C CONVERT H TO CENTIMETERS.
H = H*10.0**(-4)
C

```

```

C      CALCULATE THE CONSTANTS FOR THIS TEST.
C
      S = 2.0*(XK-XI*W**2)/(3.14*W**2*RHO*A**4*H)
      D = S*W**2*RHO*H**2
      IF (CORAMP) -3,2,3
2     CORAMP = 1.0
3     CD=CD - CORCD
      CR = CD*6.28/360.
      IF (AMPRAT.EQ.0.0) GO TO 24
      AMPRAT = AMPRAT/CORAMP
C
      KT=KT+1
      E = 1.0+AMPRAT**2-2.0*AMPRAT*COS(CR)
      IF (E.EQ.0.0) GO TO 24
C
      CALCULATE EXP(IC)/THETA (APPROXIMATE)
C
      CPHDIF = CMPLX(0.0,CR)
      CE = CEXP(CPHDIF)/AMPRAT
C
      CALCULATE COMPLEX G WITH NEGLECT OF FLUID INERTIA.
C
      G1 = D*AMPRAT*(COS(CR)-AMPRAT) /E
      G2 = -D*AMPRAT*SIN(CR)/E
      CG = CMPLX(G1,G2)
      G1APPX=G1
      G2APPX=G2
C
      CALCULATE ALPHA SQUARED.
C
      K = 0
15    CALSQD = W**2*RHO/CG
      IF (K.GT.100) GO TO 16
      CALPHA = CSQRT(CALSQD)
C
      CALCULATE BETA NAUGET.
C
      CBO = CALPHA*R
      CALCULATE CORRESPONDING EXP(IC)/THETA.
      CEO = CCOS(CBO)+S*CBO*CSIN(CBO)
      CDELE = CE-CEO
      CDELB = CDELE/(-CSIN(CBO)+S*(CSIN(CBO)+CBO*CCOS(CBO)))
C
      CALCULATE NEW BETA
      CBO = CBO + CDELB
C
      CALCULATE NEW COMPLEX G
      CGNEW = W**2*RHO*H**2/(CBO**2)
      G1NEW= REAL(CGNEW)
      G2NEW=AIMAG(CGNEW)
C
      CALCULATE AND TEST THE DIFFERENCE BETWEEN OLD AND NEW COMPLEX G.
      ERR1 = ABS((G1NEW-G1)/G1NEW)*100.
      ERR2 = ABS((G2NEW-G2)/G2NEW)*100.
      IF (ERR1.LT.0.1.AND.ERR2.LT.0.1) GO TO 25
      G1 = G1NEW
      G2 = G2NEW
      CG = CGNEW
      K = K+1
      GO TO 15
16    CGNEW = CMPLX(0.0,0.0)
      TANDEL = 0.0
      GO TO 26
24    G1APPX = 0.0

```

```

      IF (ICMP9 (I) .NE. 1) GO TO 23
      WRITE (6,103)
103  FORMAT ('+',111X,'(INSUFFICIENT DATA)')
      23 WRITE (6,110) (SDRED (I,J),J=1,3)
110  FORMAT ('+',30X,A8,19X,A8,18X,A8)
      WRITE (6,104) IDATE,(DATE(I),I=1,5),ITEST,W2,AMPOLD
      IF (PUN.EQ.1.) WRITE(7,111) (DATE(I),I=1,5),ITEST
111  FORMAT (5A4,5X,'RUN NUMBER',2X,I3)
      ISYS = 1
      CALL CMPLXG (TIME,W,CAVG,AMPRAT,ISYS,KT,ICMP9,PUN)
      IF (IEND) 36,30,36
      30 IDATE = IDATEC
      ITEST = ITESTN
      DO 31 I = 1,5
        K = I+4
      31 DATE (I) = HDR(K)
      KT = 0
      W2 = W
      AMPOLD = AMP
      WRITE (6,104) IDATE,(HDR(I),I=5,9),ITEST,W2,AMP
      IF (NTAPE.EQ.5) GO TO 25
      WRITE (6,108)
108  FORMAT (' DATA IS ON TAPE'///)
      GO TO 26
      25 WRITE (6,109)
109  FORMAT (' DATA IS ON CARDS'///)
      26 WRITE (6,105)
105  FORMAT (' TIME SAMPLE RATE FILTER PARAMETERS REC READ FOR
      MAT USED'/11X,'NO./SEC',4X,'DATA TRI RESO WO SKPD'///)
      ISYS = 1
      35 IF (AMPAVI.NE.0.0) GO TO 34
      AMPAVI = 1.0
      AMPAVO = 0.0
      34 AMPRAT = AMPAVO*RANGE0*0.325/(AMPAYI*RANGE1)
      CALL CMPLXG (TIME,W,CAVG,AMPRAT,ISYS,KT,ICMP9,PUN)
      ICMP9(KT) = INS
      INS=0
      RED(KT, 1) = TIME
      RED(KT, 2) = CAVG
      RED(KT, 3) = SC
      RED(KT, 4) = AMPAVO
      RED(KT, 5) = SAMPO
      RED(KT, 6) = AMPAVI
      RED(KT, 7) = SAMPI
      RED(KT, 8) = RANGEI
      RED(KT, 9) = RANGE0
      RED(KT,10) = XPERM
      IF (SC) 40,41,41
      40 SDRED(KT,1) = SQR
      GO TO 411
      41 SDRED(KT,1) = BLNK
      411 IF (SAMPO) 42,43,43
      42 SDRED(KT,2) = SQR
      GO TO 433
      43 SDRED(KT,2) = BLNK
      433 IF (SAMPI) 44,45,45
      44 SDRED(KT,3) = SQR
      GO TO 455
      45 SDRED(KT,3) = BLNK
      455 WRITE (6,106) TIME,SR, NDATA,NTRI,M,WO,JSKIP
106  FORMAT ('+',P8.2,P8.1,5X,I4,1X,I3,1X,I4,P6.3,3X,I3)

```

```

      G2APPX = 0.0
      CGNEW = CMPLX(0.0,0.0)
      TANDEL = 0.0
      GO TO 26
25  TANDEL = AIMAG(CGNEW)/REAL(CGNEW)
26  CMP(KT,1) = TIME
      CMP(KT,2) = AMPHAT
      CMP(KT,3) = CD
      CMP(KT,4) = G1APPX
      CMP(KT,5) = G2APPX
      CMP(KT,6) = REAL (CGNEW)
      CMP(KT,7) = AIMAG (CGNEW)
      CGNEW = CABS(CGNEW)
      CMP(KT,8) = REAL(CGNEW)
      CMP(KT,9) = TANDEL
      RETURN
      END
      SUBROUTINE RDDATA(INFORM,NDATA,FMT,IHDR,HDR,X,LCTJ,JSKIP,SR,INS)
C  SUBROUTINE RDDATA READS THE DATA FROM THE TAPE IN THE APPROPRIATE
C  MANNER FOR BOTH THE UPPER AND LOWER PLATENS.
      DIMENSION HDR(4),IHDR(4),X(5000),XO(5000),FMT(180)
      IF (LCTJ.NE.1) GO TO 5
      DO 25 I = 1,NDATA
      X(I) = 0.0
25  XO(I) = 0.0
      READ (INFORM,103) (IHDR(I),I=1,2),(HDR(J),J=5,9),
1  (IHDR(K),K=3,4),(HDR(L),L=1,4)
103 FORMAT (I3,I3,5A4,I5,I3,F9.4,F7.1,F9.1,F9.1)
      READ (INFORM,102) SR
102 FORMAT (F8.3)
      IF (SR.NE.0.0) GO TO 26
      SR = 1.0
26  SR = 1.0/SR
      READ (5,101) JSKIP
101 FORMAT (I3)
      IF (JSKIP.EQ.0) GO TO 3
      DO 10 I = 1,JSKIP
10  READ (INFORM,FMT,END=15)
3  READ (INFORM,FMT,END=15) (X(I),XO(I),I=1,NDATA)
1  READ (INFORM,FMT,END=2)
      GO TO 1
15  INS=1
      GO TO 2
5  DO 6 I = 1,NDATA
6  X(I) = XO(I)
2  RETUPN
      END

```

/*

APPENDIX C

NON-LINEAR PARAMETER ESTIMATION

To determine values of the parameters in the kinetic model of coagulation, an iterative method for least-square estimation of non-linear parameters was employed (190). This technique employs the method of steepest descent and the Gauss method to obtain a least-squares fit of the model parameters. The FORTRAN program used to estimate the coagulation model parameters is listed in the remainder of this appendix.

```

C      MAIN PROGRAM
C      THIS PROGRAM OBTAINS A LEAST-SQUARES ESTIMATE OF NON-LINEAR
C      PARAMETERS FROM A SET OF DATA USING THE GAUSS METHOD AND THE METHOD
C      OF STEEPEST DESCENT. THE MODEL IS INPUT THROUGH THE SUBROUTINE
C      "MODEL".
      IMPLICIT REAL*8 (A-H,O-Z)
      DIMENSION TH(10),SIGNS(10),DIFF(10),DEP(100)
      COMMON VAR(100,5)
C      ENTER JOB HEADING
      READ(5,20) FNAME1,FNAME2,FNAME3
20      FORMAT(3A7)
      WRITE(6,21) FNAME1,FNAME2,FNAME3
21      FORMAT(/,3A7,/)
C      ENTER NUMBER OF OBSERVATIONS (NOB) AND THE VALUE OF THE EXPONENT IN THE
C      MODEL (XRK1, THE DEPENDENCE ON FIBRINOGEN IN THE RATE EQUATION).
      READ(5,40) NOB,XRK1
40      FORMAT(I4,4E,FS.2)
      IF(NOB.LE.500) GO TO 49
      WRITE(6,50)
50      FORMAT(/,'TOO MANY OBSERVATION POINTS.')
```

```

      GO TO 420
C      ENTER NUMBER OF PARAMETERS (NPAR)
49      READ(5,60) NPAR
60      FORMAT(I2)
      IF(NPAR.LE.10) GO TO 64
      WRITE(6,63)
63      FORMAT(/,'TOO MANY PARAMETERS. SHOULD BE LT. 10')
```

```

      GO TO 420
C      ENTER NUMBER OF VARIABLES (NVAR)
64      READ(5,66) NVAR
66      FORMAT(I3)
      IF(NVAR.LE.11) GO TO 68
      WRITE(6,67)
67      FORMAT(/,'NUMBER OF VARIABLES MUST BE .LT. 11')
```

```

      GO TO 420
68      NVAR=NVAR-1
      DO 100 IKOUNT=1,NPAR
      I=IKOUNT
C      ENTER ESTIMATES OF PARAMETERS (TH), RESTRICTION ON SIGN THE PARAMETER
C      MAY ASSUME (SIGNS(I)=1 IF ITH PARAMETER IS TO BE ONLY POSITIVE),
C      AND THE DIFFERENCE USED IN CALCULATING NEW PARAMETER VALUES (DIFF).
      READ(5,90) TH(I),SIGNS(I),DIFF(I)
90      FORMAT(3F12.5)
100     CONTINUE
C      SUM OF SQUARES CONVERGENCE CRITERION, EPS1=5
      EPS1=.0000001
C      PARAMETER CONVERGENCE CRITERION, EPS2
      EPS2=.0000001
C      LAMBDA VALUE, FLAM
      FLAM=.1
C      NU VALUE, FNU
      FNU=10.
C      MAXIMUM NUMBER OF ITERATIONS, MIT
      MIT=75
      WRITE(6,599) XRK2
599     FORMAT(8H  N = ,FS.2,/)
      WRITE(6,370)
370     FORMAT(/,' LIST OF VARIABLES,')
```

```

      DO 350 IKOUNT=1,NOB
C      ENTER NOB SETS OF DEPENDENT AND INDEPENDENT VARIABLES
      READ(5,300) DEP(IKOUNT),(VAR(IKOUNT),JKOUNT),
```

```
+JKOUNT=1,NVAR)
300  FORMAT(F12.5,5F12.5)
      WRITE(6,300) DEP(IKOUNT),(VAR(IKOUNT,JKOUNT),
+JKOUNT=1,NVAR)
350  CONTINUE
410  CALL HAUS59(1,NOB,DEP,NPAR,TH,DIFF,SIGNS,EPS1,
+EPS2,MIT,FLAM,FNU,NRK1,XRK2)
420  CALL EXIT
      STOP
      END
```



```

C      START OF SUBROUTINE HAUS59
      SUBROUTINE HAUS59(NPROB,NOB,Y,NP,TH,DIFZ,SIGNS,EPS1,EPS2,
+MIT,FLAM,FNU,NRK1,XRK2)
      IMPLICIT REAL*8 (A-H,O-Z)
      DIMENSION TH(10),DIFZ(10),SIGNS(10),Y(100),P(10),
+P(10),PHI(10),TB(10),F(100),R(100),A(100),
+D(100),Q(100),DELZ(5000),YP(100,5),X(100)
      ACOS(X)=DATAN(DSQRT(1.0/X**2-1.0))
      NPSQ=NP*NP
      WRITE(6,1000) NPROB,NOB,NP
      WRITE(6,1001)
      CALL ASS601(NP,TH)
      WRITE(6,1002)
      CALL ASS601(NP,DIFZ)
      IF(MIN0(NP-1,50-NP,NOB-NP,MIT-1,999-MIT)) 99,15,15
15  IF(FNU-1.0) 99,99,16
16  CONTINUE
      DO 19 I=1,NP
      TEMP=DABS(DIFZ(I))
      IF(DMIN1(1.0-TEMP,DABS(TH(I)))) 99,99,19
19  CONTINUE
      GA=FLAM
      NIT=1
      ASSIGN 131 TO LAOS
      ASSIGN 225 TO IRAN
      ASSIGN 265 TO JORDAN
      IF(EPS1) 5,10,10
5    ZPS1=0
10   IF(EPS2) 40,40,30
40   IF(EPS1) 60,60,50
60   ASSIGN 270 TO IRAN
      GO TO 70
50   ASSIGN 265 TO IRAN
      GO TO 70
30   IF(EPS1) 80,80,70
80   ASSIGN 270 TO JORDAN
70   SSQ=0.0
      CALL MODEL(NPROB,TH,F,NOB,NP,NRK1,XRK2)
      DO 90 I=1,NOB
      R(I)=Y(I)-F(I)
90   SSQ=SSQ+R(I)*R(I)
      WRITE(6,1003) SSQ
100  GA=GA/FNU
      INTCNT=0
      WRITE(6,1004) NIT
101  JS=1-NOB
      DO 130 J=1,NP
      TEMP=TH(J)
      P(J)=DIFZ(J)*TH(J)
      TH(J)=TH(J)+P(J)
      Q(J)=0.0
      JS=JS+NOB
      CALL MODEL(NPROB,TH,DELZ(JS),NOB,NP,NRK1,XRK2)
      IJ=JS-1
      DO 120 I=1,NOB
      IJ=IJ+1
      DELZ(IJ)=DELZ(IJ)-F(I)
120  Q(J)=Q(J)+DELZ(IJ)*R(I)
      Q(J)=Q(J)/P(J)
130  TH(J)=TEMP
      GO TO LAOS,(131,414)

```

```

131 DO 150 I=1, NP
    DO 151 J=1, I
        SUM=0.0
        KJ=NOB*(J-1)
        KI=NOB*(I-1)
        DO 160 K=1, NOB
            KI=KI+1
            KJ=KJ+1
160    SUM=SUM+DELZ(KI)*DELZ(KJ)
        TEMP=SUM/(P(I)*P(J))
        JI=J+NP*(I-1)
        D(JI)=TEMP
        IJ=I+NP*(J-1)
151    D(IJ)=TEMP
150    E(I)=DSQRT(D(JI))
666    CONTINUE
    DO 153 I=1, NP
        IJ=I-NP
        DO 153 J=1, I
            IJ=IJ+NP
            A(IJ)=D(IJ)/(E(I)*E(J))
            JI=J+NP*(I-1)
153    A(JI)=A(IJ)
        II=-NP
        DO 155 I=1, NP
            P(I)=Q(I)/E(I)
            PHI(I)=P(I)
            II=NP+1+II
155    A(II)=A(II)+GA
        I=1
        CALL MATIN(A, NP, P, I, DET)
        STEP=1.0
        SUM1=0.0
        SUM2=0.0
        SUM3=0.0
        DO 231 I=1, NP
            SUM1=P(I)*PHI(I)+SUM1
            SUM2=P(I)*P(I)+SUM2
            SUM3=PHI(I)*PHI(I)+SUM3
231    PHI(I)=P(I)
        TEMP=SUM1/DSQRT(SUM2*SUM3)
        TEMP=DEIN1(TEMP, 0.1D+1)
        TEMP=57.295*ACOS(TEMP)
        WRITE(6, 1001) DET, TEMP
170    DO 220 I=1, NP
        P(I)=PHI(I)*STEP/E(I)
        TB(I)=TH(I)+P(I)
220    CONTINUE
        WRITE(6, 7000)
7000    FORMAT(30H01 TEST POINT PARAMETER VALUES )
        WRITE(6, 2006) (TB(I), I=1, NP)
        DO 221 I=1, NP
            IF(SIGNS(I)) 221, 221, 222
222    IF(DSIGN(0.1D+1, TH(I))*DSIGN(0.1D+1, TB(I))) 663, 221, 221
221    CONTINUE
        SUMB=0.0
        CALL MODEL(NPROB, TB, F, NOB, NP, NRK1, XRK2)
        DO 230 I=1, SUB
            Z(I)=F(I)-Z(I)
230    SUMB=SUMB+Z(I)*R(I)
        WRITE(6, 1043) SUMB

```

```

        IF (SUMB - (1.0 + EPS1) * SSQ) 662, 662, 663
663 IF (DEIN1 (TEMP - 30.0, GA)) 665, 665, 664
665 STEP = STEP / 2.0
      INTCNT = INTCNT + 1
      IF (INTCNT - 36) 170, 2700, 2700
664 GA = GA * FNU
      INTCNT = INTCNT + 1
      IF (INTCNT - 36) 666, 2700, 2700
662 WRITE (6, 1007)
      DO 669 I = 1, NP
669 TH (I) = TB (I)
      CALL ASS601 (NP, TH)
      WRITE (6, 1040) GA, SUMB
      GO TO IRAN, (225, 265, 270)
225 DO 240 I = 1, NP
      IF (DABS (P (I)) / (1.0 - 20 * DABS (TH (I))) - EPS2) 240, 240, 241
241 GO TO JORDAN, (265, 270)
240 CONTINUE
      WRITE (6, 1009) EPS2
      GO TO 280
265 IF (DABS (SUMB - SSQ) - EPS1 * SSQ) 266, 266, 270
266 WRITE (6, 1010) EPS1
      GO TO 280
270 SSQ = SUMB
      NIT = NIT + 1
      IF (NIT - NIT1) 100, 100, 280
2700 WRITE (6, 2710)
2710 FORMAT (//116H0$$$$ THE SUM OF SQUARES CANNOT BE REDUCED TO THE SUM
      * OF SQUARES AT THE END OF THE LAST ITERATION - ITERATION STOPS /)
280 WRITE (6, 1011)
      WRITE (6, 1012)
      DO 281 I = 1, NOB
      WRITE (6, 2061) Y (I), F (I), R (I)
281 CONTINUE
      SSQ = SUMB
      IDF = NOB - NP
      WRITE (6, 1015)
      I = 0
      CALL MATIN (D, NP, P, I, DEF)
      DO 7692 I = 1, NP
      II = I + NP * (I - 1)
7692 E (I) = DSQRT (D (II))
      DO 340 I = 1, NP
      JI = I + NP * (I - 1) - 1
      IJ = I + NP * (I - 2)
      DO 340 J = I, NP
      JI = JI + 1
      A (JI) = D (JI) / (E (I) * E (J))
      IJ = IJ + NP
340 A (IJ) = A (JI)
      CALL ASS603 (NP, A)
      WRITE (6, 1016)
      CALL ASS601 (NP, E)
      IF (IDF) 341, 410, 341
341 SDEV = SSQ / IDF
      WRITE (6, 1014) SDEV, IDF
      SDEV = DSQRT (SDEV)
      DO 391 I = 1, NP
      P (I) = TH (I) + 2.0 * E (I) * SDEV
391 TB (I) = TH (I) - 2.0 * E (I) * SDEV
      WRITE (6, 1039)

```

```

CALL ASS602(NP,TB,P)
ASSIGN 414 TO LAOS
GO TO 101
414 DO 415 K=1,NOB
    TEMP=0.0
    DO 420 I=1,NP
    DO 420 J=1,NP
        ISUB=K+NOB*(I-1)
        DEBUG1=DELZ (ISUB)
        ISUB=K+NOB*(J-1)
        DEBUG2=DELZ (ISUB)
        IJ=I+NP*(J-1)
        DEBUG3=0 (IJ)/(DIFZ (I)*TH (I)*DIFZ (J)*TH (J))
420 TEMP=TEMP+DEBUG1*DEBUG2*DEBUG3
    TEMP=2.0*DSQRT (TEMP)*SDEV
    R(K)=F(K)+TEMP
415 F(K)=F(K)-TEMP
    WRITE (6,1008)
    IE=0
    DO 425 I=1,NOB,10
    IE=IE+10
    IF (NOB-IE) 430,435,435
430 IE=NOB
435 WRITE (6,2001) (R(J),J=I,IE)
425 WRITE (6,2006) (F(J),J=I,IE)
410 WRITE (6,1033) NPROB
    RETURN
99 WRITE (6,1034)
    GO TO 410
1000 FORMAT(////,38HNON-LINEAR ESTIMATION, PROBLEM NUMBER,
+I3,/,15,14H OBSERVATIONS,,15,11H PARAMETERS)
1001 FORMAT(/25H0INITIAL PARAMETER VALUES )
1002 FORMAT(/52H0PROPORTIONS USED IN CALCULATING DIFFERENCE QUOTIENTS )
1003 FORMAT(/25H0INITIAL SUM OF SQUARES = ,E12.4)
1004 FORMAT(////,45H,14H ITERATION NO. ,I4)
1007 FORMAT(/32H0PARAMETER VALUES VIA REGRESSION )
1008 FORMAT(////,54H0APPROXIMATE CONFIDENCE LIMITS FOR EACH FUNCTION VAL
+UE )
1009 FORMAT(/62H0ITERATION STOPS - RELATIVE CHANGE IN EACH PARAMETER LE
+SS THAN ,E12.4)
1010 FORMAT(/62H0ITERATION STOPS - RELATIVE CHANGE IN SUM OF SQUARES LE
+SS THAN ,E12.4)
1011 FORMAT(22H FINAL FUNCTION VALUES )
1012 FORMAT(/,48H0DEPENDENT VAR FITTED VALUE RESIDUAL ,/)
1014 FORMAT(/24H0VARIANCE OF RESIDUALS = ,E12.4,1H ,I4,20H DEGREE OF
+ FREEDOM )
1015 FORMAT(////,19H0CORRELATION MATRIX )
1016 FORMAT(////,21H0NORMALIZING ELEMENTS )
1033 FORMAT(/19H0END OF PROBLEM NO. ,I3)
1034 FORMAT(/16H0PARAMETER ERROR )
1039 FORMAT(/71H0INDIVIDUAL CONFIDENCE LIMITS FOR EACH PARAMETER (ON LI
+NEAR HYPOTHESIS) )
1040 FORMAT(/9H0LAMBDA = ,E10.3,40X,33HSUM OF SQUARES AFTER REGRESSION
+ ,E15.7)
1041 FORMAT(14H DETERMINANT = ,E12.4,6X,26H ANGLE IN SCALED COORD.=
+ ,F5.2,8H DEGREES )
1043 FORMAT(28H0TEST POINT SUM OF SQUARES = ,E12.4)
2001 FORMAT(/10E12.4)
2006 FORMAT(10E12.4)
2061 FORMAT(J(2X,1PD12.4))
END

```

```

C      START OF SUBROUTINE MATIN
      SUBROUTINE MATIN(A,NVAR,B,NB,DET)
      IMPLICIT REAL*8 (A-H,O-Z)
      DIMENSION A(NVAR,1),B(NVAR,1)
      COMMON/GASPAR/DUMILS(7),PIVOTM
      PIVOTM=A(1,1)
      DET=1.0
      DO 550 ICOL=1,NVAR
      PIVOT=A(ICOL,ICOL)
      PIVOTM=DMIN1(PIVOT,PIVOTM)
      DET=PIVOT*DET
      A(ICOL,ICOL)=1.0
      PIVOT=DMAX1(PIVOT,1.0-20)
      PIVOT=A(ICOL,ICOL)/PIVOT
      DO 350 L=1,NVAR
350    A(ICOL,L)=A(ICOL,L)*PIVOT
      IF(NB.EQ.0) GO TO 371
      DO 370 L=1,NB
370    B(ICOL,L)=B(ICOL,L)*PIVOT
371    DO 550 L1=1,NVAR
      IF(L1.EQ.ICOL) GO TO 550
      T= A(L1,ICOL)
      A(L1,ICOL)=0.0
      DO 450 L=1,NVAR
450    A(L1,L)=A(L1,L)-A(ICOL,L)*T
      IF(NB.EQ.0) GO TO 550
      DO 500 L=1,NB
500    B(L1,L)=B(L1,L)-B(ICOL,L)*T
550    CONTINUE
      RETURN
      END

```

```

      SUBROUTINE ASS601(NQ,A)
      IMPLICIT REAL*8 (A-H,O-Z)
      DIMENSION A(NQ)
      NP=NQ
      NR=NP/10
      LOW=1
      LUP=10
10    IF(NR) 15,20,30
15    RETURN
20    LUP=NP
      IF(LOW.GT.LUP) RETURN
30    WRITE(6,500) (J,J=LOW,LUP)
      WRITE(6,600) (A(J),J=LOW,LUP)
      LOW=LOW+10
      LUP=LUP+10
      NR=NR-1
      GO TO 10
500    FORMAT(/I8,9I12)
600    FORMAT(10E12.4)
      END

```

```

SUBROUTINE ASS602(NQ,A,B)
IMPLICIT REAL*8 (A-H,O-Z)
DIMENSION A(NQ),B(NQ)
NP=NQ
NR=NP/10
LOW=1
LUP=10
10 IF (NR) 15,20,30
15 RETURN
20 LUP=NP
   IF (LOW.GT.LUP) RETURN
30 WRITE(6,500) (J,J=LOW,LUP)
   WRITE(6,600) (B(J),J=LOW,LUP)
   WRITE(6,600) (A(J),J=LOW,LUP)
   LOW=LOW+10
   LUP=LUP+10
   NR=NR-1
   GO TO 10
500 FORMAT(/I8,9I12)
600 FORMAT(10E12.4)
END

```

```

SUBROUTINE ASS603(NQ,C)
IMPLICIT REAL*8 (A-H,O-Z)
DIMENSION C(NQ,NQ)
NP=NQ
NR=NP/10
LOW=1
LUP=10
10 IF (NR) 15,20,30
15 RETURN
20 LUP=NP
   IF (LOW.GT.LUP) RETURN
30 WRITE(6,500) (J,J=LOW,LUP)
   DO 90 I=LOW,LUP
90  WRITE(6,720) I,(C(J,I),J=LOW,LUP)
   LOW2=LUP+1
   IF (LOW2.GT.NP) GO TO 100
   DO 95 I=LOW2,NP
95  WRITE(6,720) I,(C(J,I),J=LOW,LUP)
100 LOW=LOW+10
   LUP=LUP+10
   NR=NR-1
   GO TO 10
500 FORMAT(/I8,9I12)
720 FORMAT(1H0,I3,1X,F7.4,9F12.4)
END

```

```

SUBROUTINE MODEL(NPROB,TH,F,NOB,WP,XRK1,XRK2)
C   THIS SUBROUTINE CALCULATES THE SHEAR STORAGE MODULUS, G' (F(I)),
C   AS A FUNCTION OF TIME FROM THE TWO-STEP COAGULATION MODEL PRESENTED
C   IN J. P. KIRKPATRICK'S PH.D. THESIS (RICE UNIVERSITY, 1979).
C       TH(1)=K0'
C       TH(2)=K1'
C       TH(3)=G'MAX
C       TH(4)=TI (THE INITIATION TIME)
IMPLICIT REAL*8 (A-H,O-Z)
DIMENSION IH(10),F(100)
COMMON VAR(100,5)
DO 899 IRK=1,NOB
    RHX=VAR(IRK,1)-TH(4)
    IF (RHX.LT.0.0) F(IRK)=0.0
    IF (RHX.LT.0.0) GOTO 899
    CT1=TH(1)*RHX
    IF (CT1.GT.150.) GOTO 789
    CT2=1.-DEXP(-CT1)
    GOTO 790
789    CT2=1.
790    IF (XRK2.GT.1.2.OR.XRK2.LT.0.8) GOTO 888
    CT3=IH(2)*(RHX-CT2/TH(1))
    IF (CT3.GT.150.) GOTO 791
    CT4=DEXP(-CT3)
    GOTO 792
791    CT4=0.
792    F(IRK)=IH(3)*(1.-CT4)
    GOTO 899
888    EX=XRK2
    CT3=TH(2)*(EX-1.)*(RHX-CT2/TH(1))
    CT4=1./(1.+CT3)**(1./(EX-1.))
    F(IRK)=TH(3)*(1.-CT4)
899    CONTINUE
    RETURN
END

```

APPENDIX D

DIFFUSION INTO THE REGION BETWEEN PARALLEL PLATENS

In the dynamic rheological testing of coagulating plasma with the rheogoniometer, a gas mixture is admitted to the test chamber. To determine the effect of this mixture on the dissolved gas concentration in the plasma, a mathematical solution of the radial concentration profile between the platens is obtained.

For a species in low concentration diffusing through a homogeneous medium, the equation of mass continuity in cylindrical coordinates with constant diffusivity is written:

$$D \left[\frac{1}{r} \frac{\partial}{\partial r} \left(r \frac{\partial c}{\partial r} \right) + \frac{1}{r^2} \frac{\partial^2 c}{\partial \theta^2} + \frac{\partial c}{\partial z^2} \right] \\ = \frac{\partial c}{\partial t} + \underline{v} \cdot \nabla c \quad (D.1)$$

where D is the binary diffusion coefficient for the species in the medium, c is the concentration of the species, and r, z , and θ are the radial, axial, and angular coordinates. If axial symmetry is assumed, the dependence on z neglected, and $\underline{v}$ set equal to zero, the above equation may be simplified to yield:

$$\left[\frac{1}{r} \frac{\partial}{\partial r} \left(r \frac{\partial C}{\partial r} \right) \right] = \frac{\partial C}{\partial t} \quad (D.2)$$

There must be no flux of the species at the center of the disc if the axial symmetry assumption is valid. From this assumption, the following boundary condition is obtained

$$\frac{\partial C}{\partial r} = 0 \quad r = 0 \quad (D.3)$$

Since the extra-platen atmosphere in the system is "well-mixed" and the molecular diffusivity of gases in gases is approximately 100 times that of gases in liquids, it is probable that the partial pressure, p , of the diffusing species at the plasma-gas interface is nearly the same as the bulk concentration in the gas. Thus, assuming that the species in the plasma and the gas are in equilibrium, the concentration of the species in the medium at the interface ($r=r_1$) is:

$$C_1 \Big|_{r=-r_1} = kp \Big|_{r=+r_1} \quad r = r_1 \quad (D.4)$$

where k is a partition coefficient for the particular species and medium. This gives the second boundary condition

$$C = C_1 \quad r = r_1 \quad (D.5)$$

Initially, the concentration of the diffusing species is assumed to be constant throughout the disc, yielding the initial condition

$$C = C_0 \quad t = 0 \quad (D.6)$$

At this point, it is useful to place the equations and conditions in nondimensional form. This is done by defining the following dimensionless variables:

$$t^* = \frac{t D}{r_1^2} \quad r^* = \frac{r}{r_1}$$

$$C^* = \frac{C - C_0}{C_1 - C_0}$$

Employing these variables Equations (D.2), (D.3), (D.5), and (D.6) become

$$\frac{1}{r^*} \frac{\partial}{\partial r^*} \left(r^* \frac{\partial C^*}{\partial r^*} \right) = \frac{\partial C^*}{\partial t^*} \quad (D.7)$$

$$\frac{\partial C^*}{\partial r^*} = 0 \quad r^* = 0 \quad (D.8)$$

$$C^* = 1 \quad r^* = 1 \quad (D.9)$$

$$C^* = 0 \quad t^* = 0 \quad (D.10)$$

Butkov (204,p. 370) gives a solution for a similar problem. For this system, the solution found by separation of variables is

$$C^*(r^*, t^*) = 1 - 2 \sum_{n=1}^{\infty} \frac{J_0(\alpha_{on} r^*) e^{-\alpha_{on}^2 t^*}}{\alpha_{on} J_1(\alpha_{on})} \quad (D.11)$$

where J_0 and J_1 are zero and first order Bessel functions of

the first kind respectively, and α_{on} is the nth zero of J_0 .

The average concentration for the species in the region between the platen is found using

$$C_{AV}^*(t^*) = \frac{\int_0^{2\pi} \int_0^1 r^* c^*(r^*, t^*) dr^* d\theta}{\int_0^{2\pi} \int_0^1 r^* dr^* d\theta} \quad (D.12)$$

Equation (E.12) may be evaluated explicitly to yield

$$C_{AV}^*(t^*) = 1 - 4 \sum \frac{e^{-\alpha_{on}^2 t^*}}{\alpha_{on}^2} \quad (D.13)$$

The values of C^* and C_{AV}^* were calculated taking the first ten terms of the series. Graphs of C^* versus r^* for various t^* and C_{AV}^* versus t^* are shown in Figures (D.1) and (D.2), respectively.

From Figure D.2, C_{AV}^* has changed 50 percent when $t^* = 6.4 \times 10^{-2}$. In the test system employed in this study, $r_1 = 2.5$ cm, and at 37°C the diffusivity of O_2 in plasma is approximately 2×10^{-5} cm^2/sec . Therefore, a simple calculation for t yields

$$\begin{aligned} t &= \frac{t^* r_1^2}{D} \\ &= \frac{6.4 \times 10^{-2} (2.5 \text{ cm})^2}{2 \times 10^{-5} \text{ cm}^2/\text{sec}} \\ &= 2 \times 10^4 \text{ sec} \end{aligned}$$

= 5.56 hours

For $t = 5.4 \times 10^3$ seconds (90 minutes), the length of an average run, $t^* = 1.73 \times 10^{-2}$ for which $C_{AV}^* = 0.28$. Thus, in the best case a 28 percent change in the dimensionless O_2 concentration would be found. However, the diffusivity of gas in clots is probably less than in plasma, and as a result the average concentration change would be less. From Figure D.1, it is apparent also that over the length of a normal run, the predominant concentration change occurs near the plasma-gas interface. Therefore, only minor changes in the dissolved gas concentration are expected in the interior of the plasma disc during the course of an experiment.

Figure D-1. Dimensionless radial concentration profiles for a species diffusing into the region between parallel platens.

Figure D-2. Dimensionless bulk average concentration of a species diffusing into the region between parallel platens.

APPENDIX E

SUMMARY OF DYNAMIC RHEOLOGICAL DATA

In this section, the dynamic rheological characteristics of the experiments presented in Chapter 4 are summarized. These characteristics values are:

t_0 = the time (minutes) after recalcification at which G' reaches 15 dynes/cm²

$G'_{\max}$ = the maximum shear storage modulus (dynes/cm²)

$t_{\max}$ = the time (minutes) at which $G'_{\max}$ is attained

G'_f = the shear storage modulus (dynes/cm²) 90 minutes after recalcification.

Because non-lysing PFP samples do not exhibit a decline in G' after $G'_{\max}$ is attained, $t_{\max}$ and G'_f are not given for these experiments.

Donor	Date	DBCAMP conc. (mM)	t _o (min)	G' _{max} (dynes/cm ²)	t _{max} (min)	G' _f (dynes/cm ²)
PN	3-13-78	0	6.0	4930	28	3100
PN	3-13-78	5	7.7	2050	27	1240
PN	3-13-78	5	6.7	2690	24	1410
PN	3-21-78	0	6.8	4760	33	3740
PN	3-21-78	5	7.7	1710	33	1300
JK	3-17-78	0	6.9	5760	30	2250
JK	3-17-78	5	7.2	3410	34	1340

Table B.1. The effect of dibutyryl cyclic AMP on the dynamic rheological characteristics of recalcified PRP (2.0 × 10⁵ platelets/mm³). 9 parts PRP incubated with 1 part DBCAMP solution or PBS 50 minutes prior to recalcification.

Donor	Date	KCN Concentration (M)	2-Deoxy-glucose Concentration (M)	t_o (min)	G'_{max} dynes/cm ²	t_{max} (min)	G'_f dynes/cm ²
PN	3-22-78	0	0	5.7	4250	28	2750
PN	3-22-78	0	10^{-3}	7.4	3600	28	2150
PN	3-22-78	0	10^{-2}	6.4	3270	33	1963
PN	3-27-78	0	0	7.1	4480	33	3270
PN	3-27-78	10^{-3}	0	6.3	5000	48	3607
PN	3-27-78	5×10^{-3}	5×10^{-3}	7.0	1430	45	906
PN	3-27-78	5×10^{-3}	5×10^{-3}	7.3	1130	45	898
PN	3-29-78	0	0	7.9	4070	45	2720
PN	3-29-78	5×10^{-3}	5×10^{-3}	7.2	1070	52	897
EO	6-13-78	0	0	8.2	4950	41	3280
EO	6-13-78	5×10^{-3}	5×10^{-3}	9.2	1370	36	9031
BS	6-14-78	0	0	7.8	4740	32	3020
BS	6-14-78	5×10^{-3}	5×10^{-3}	8.2	882	48	746

Table B-2. The effect of KCN and 2-deoxy-D-glucose on the dynamic rheological characteristics of PRP (2.0×10^5 platelets/mm³). 9 parts PRP incubated with 1 part inhibitor solution or PBS for 60 minutes prior to recalcification.

Donor	Date	Monoiodoacetic Acid Concentration (M)	Platelets/mm ³ × 10 ⁻⁵	t ₀ (min)	G' _{max} (dynes/cm ²)	t _{max} (min)	G' _f (dynes/cm ²)
PN	3-23-78	0	2.0	6.3	4520	33	3460
	3-23-78	2.0 × 10 ⁻⁵	2.0	6.5	3920	33	2227
	3-23-78	2.0 × 10 ⁻⁴	2.0	6.9	1850	39	636
	3-23-78	2.0 × 10 ⁻³	2.0	6.4	795	24	265
	12-14-78	0	2.0	6.0	4110	32	2470
	12-14-78	2.0 × 10 ⁻³	2.0	6.9	682	23	235
	12-14-78	0	0	8.7	601	--	--
	12-14-78	2.0 × 10 ⁻³	0	9.7	236	--	--

Table E-3. The effect of sodium monoiodoacetic acid on the dynamic rheological parameters of PFP or PRP (2.0 × 10⁵ platelets/mm³). 9 parts plasma incubated with 1 part IDA or PBS 15 minutes prior to recalcification.

Donor	Date	Cytochalasin B Concentration (mg/ml)	t ₀ (min)	G _{max} (dynes/cm ²)	t _{max} (min)	G _f (dynes/cm ²)
BS	6-21-78	0	7.9	4860	32	3360
BS	6-21-78	0.01	6.7	3260	32	2140
BS	6-21-78	0.05	7.0	2230	36	1630
BS	6-21-78	0.05	7.2	1890	36	1350
SK	7-17-78	0	7.3	6540	42	4980
SK	7-17-78	0.01	5.5	5000	36	3540
SK	7-17-78	0.1	6.7	2470	42	1950
SK	7-17-78	0.1	6.7	2410	42	1920
BS	7-20-78	0	8.0	5080	34	3560
BS	7-20-78	0.01	6.5	2610	39	2030
BS	7-20-78	0.1	6.9	1930	37	1500
JK	7-21-78	0	7.7	5103	37	3590
JK	7-21-78	0.1	7.6	1983	54	1780
GA	7-24-78	0	6.4	4350	42	3630
GA	7-24-78	0.01	5.9	3160	37	2460
GA	7-24-78	0.05	6.0	1970	48	1690
GA	7-24-78	0.1	5.9	1630	54	1480
AH	9-29-78	0	6.4	5420	32	3970
AH	9-29-78	0.1	6.4	1620	48	1360
AH	9-29-78	0.1	5.9	2060	32	1460

Table E-4. The effect of cytochalasin B on the dynamic rheological parameters of PRP (2.0 × 10⁵ platelets/mm³). 9 parts PRP incubated for 60 minutes with Cytochalasin B or PBS prior to recalcification.

Donor	Date	SK Incubation Period (min)	t_o (min)	G'_{max} (dynes/cm ²)
JG	5-18-77	0	16.0	244
JG	5-18-77	3	15.4	279
JG	5-18-77	10	16.3	183
JG	5-18-77	15	19.8	115
JG	5-19-77	20	17.1	79
JG	5-19-77	30	15.6	122
JG	5-19-77	45	15.8	132
JG	5-19-77	120	19.4	96
JK	4-25-77	0	18.0	192
JK	4-25-77	3	19.7	312
JK	4-26-77	10	19.2	123
JK	4-26-77	15	23.4	89
JK	4-26-77	20	23.8	95
JK	4-26-77	30	21.5	79
JK	4-26-77	45	26.8	79
JK	4-28-77	120	31.2	87
GA	1-18-78	0	16.7	250
GA	1-18-78	3	15.0	304
GA	1-18-78	6	15.8	139
GA	1-18-78	15	18.6	78
GA	1-18-78	20	19.8	63

Table E-5. The dynamic rheological parameters of 1:1 mixtures of fresh PFP and PFP incubated previously with 100 u/ml SK.

Donor	Date	SK Incubation Period (min)	t_0 (min)	$G'_{\max}$ (dynes/cm ²)
JK	9-21-77	0	14.4	272
JK	9-21-77	3	15.8	352
JK	9-21-77	6	12.8	330
JK	9-22-77	10	12.9	250
JK	9-22-77	15	16.3	193
JG	9-22-77	0	13.5	470
JG	9-22-77	3	16.7	760
JG	9-22-77	6	17.4	327
JG	9-22-77	10	17.2	355
JG	9-19-77	15	17.7	373
JG	9-19-77	20	19.0	317

Table E-6. The dynamic rheological characteristics of 1:1 mixtures of fresh PFP and PFP incubated previously with 50 u/ml SK.

Donor	Date	SK Incubation Period (min)	t_0 (min)	G'_{max} (dynes/cm ²)
JG	10- 4-77	0	33.5	446
JG	10- 4-77	50	23.0	470
JG	10- 4-77	100	23.5	481
JG	10- 4-77	150	28.7	417
JK	11-29-77	0	24.3	327
JK	11-29-77	30	29.5	393
JK	11-29-77	60	24.3	318
JK	11-29-77	100	25.8	330
JK	11-29-77	150	25.0	291

Table E-7. The dynamic rheological characteristics of 1:1 mixtures of fresh PFP and PFP incubated previously with 10 u/ml SK.

Table E-8. The dynamic rheological characteristics of 1:1 mixtures of fresh PRP and PFP incubated previously with 100 u/ml SK.

Donor	Date	Platelets/ μm^3 PRP $\times 10^{-5}$	SK Inc. Period (min)	t_0 (min)	G'_{max} (dynes/cm ²)	t_{max} (min)	G'_f (dynes/cm ²)
JG	5-11-77	4.0	0	7.5	2500	31	1420
JG	5-11-77	4.0	3	12.5	1670	35	978
JG	5-12-77	4.0	10	12.0	1460	41	1020
JG	5-12-77	4.0	15	15.0	1110	49	909
JG	5-12-77	4.0	20	12.5	746	30	349
JG	5-12-77	4.0	30	14.5	909	37	620
JG	5-17-77	4.0	45	13.0	1440	41	983
JG	5-17-77	4.0	120	14.0	1280	51	932
PN	8-9-77	4.0	0	11.2	2170	30	731
PN	8-9-77	4.0	3	12.3	1210	30	418
PN	8-12-77	4.0	6	10.8	1390	30	464
PN	8-9-77	4.0	10	10.2	1100	22	138
PN	8-10-77	4.0	15	13.7	1230	38	695
PN	8-10-77	4.0	20	9.8	1120	34	509
PN	8-10-77	4.0	26	11.2	780	34	317
PN	8-11-77	4.0	34	12.8	629	30	318
PN	8-11-77	4.0	45	9.4	1080	30	318
PN	8-11-77	4.0	120	9.9	1220	38	578
GA	1-17-78	3.5	0	9.9	2990	30	1350
GA	1-17-78	3.5	0	9.8	3460	34	1812
GA	1-11-78	3.5	3	8.7	2860	29	729
GA	1-11-78	3.5	6	8.4	1930	26	645
GA	1-11-78	3.5	10		1590		
GA	1-17-78	3.5	15	9.4	1790	38	1140
GA	1-12-78	3.5	20	9.8	1260	26	559
GA	1-12-78	3.5	26	8.9	1280	26	720
GA	1-12-78	3.5	34	10.6	1390	33	1160
GA	1-13-78	3.5	45	9.8	1330	29	623
GA	1-13-78	3.5	120	10.8	1830	33	1180

Donor	Date	Platelets/ μ l PRP $\times 10^{-5}$	SK Incubation Period (min)	Cytochalasin B Conc (ng/ml)	t_0 (min)	$G_{\max}'$ (dynes/cm ²)	$t_{\max}$ (min)	G_f (dynes/cm ²)
PN	8-7-78	4.0	0	0	7.3	3300	39	1720
PN	8-7-78	4.0	3	0	7.4	1310	18	81
PN	8-7-78	4.0	30	0	8.9	406	18	34
PN	8-8-78	4.0	0	0.1	6.3	929	38	655
PN	8-8-78	4.0	3	0.1	7.9	444	56	286
PN	8-8-78	4.0	30	0.1	9.0	233	49	91
PN	8-8-78	4.0	3	0.1	6.8	829	14	122
JG	8-9-78	3.8	0	0	9.1	3110	30	403
JG	8-9-78	3.8	3	0	8.6	2170	22	280
JG	8-9-78	3.8	30	0	8.0	1920	20	194
JG	8-10-78	3.8	0	0.1	9.0	1680	56	1450
JG	8-10-78	3.8	3	0.1	8.7	1660	56	1360
JG	8-10-78	3.8	30	0.1	11.9	625	39	245
JG	8-24-78	3.8	30	0	11.8	1270	25	389
JG	8-24-78	3.8	30	0.1	11.0	760	43	502
DB	8-21-78	4.0	0	0	7.3	3750	29	1830
DB	8-21-78	4.0	3	0	8.2	2590	21	575
DB	8-21-78	4.0	30	0	8.6	750	17	381
DB	8-21-78	4.0	30	0	8.9	1010	19	473
DB	8-23-78	4.0	0	0.1	6.9	1190	33	778
DB	8-23-78	4.0	3	0.1	6.9	818	43	570
DB	8-23-78	4.0	30	0.1	8.0	448	43	251
PN	8-29-78	4.0	0	0	7.2	2260	18	447
PN	8-29-78	4.0	3	0	7.4	858	15	152
PN	8-29-78	4.0	30	0	9.9	287	18	106
PN	8-31-78	4.0	0	0.1	6.5	890	34	458
PN	8-31-78	4.0	3	0.1	6.7	479	44	292
PN	8-31-78	4.0	30	0.1	10.2	244	50	196

Table E-9 (Con't)

Donor	Date	Platelets/ μ l PRP $\times 10^{-5}$	SK Incubation Period (min)	Cytochalasin B Conc (mg/ml)	t_0 (min)	G_{max}' (dynes/cm ²)	t_{max} (min)	G_f' (dynes/cm ²)
GA	8-30-78	3.8	0	0	7.3	2950	23	467
GA	8-30-78	3.8	3	0	6.8	2580	23	450
GA	8-30-78	3.8	30	0	8.4	740	16.5	367
GA	9-1-78	3.8	0	0.1	6.4	1000	44	813
GA	9-1-78	3.8	3	0.1	6.9	1010	39	831
GA	9-1-78	3.8	30	0.1	7.6	713	50	578

Table E-9. The dynamic rheological characteristics of 1:1 mixtures of fresh PRP and PRP incubated previously with 100 u/ml SK. The PRP-PRP-SK mixture was incubated with PBS/EtOH or 0.1 mg/ml cytochalasin B 60 minutes prior to recalcification.

Donor	Date	Platelets/mm ³ × 10 ⁻⁵	NH ₂ OH Conc. (M)	SK Conc. (u/ml)	t ₀ (min)	G _{max} (dynes/cm ²)	t _{max} (min)	G _f (dynes/cm ²)
WK	8-4-77	2.0	0	0	9.0	3720	34	2120
WK	8-4-77	2.0	0	5	9.6	4160	43	2686
WK	8-4-77	2.0	0	20	9.4	506	12	0
WK	8-3-77	0	0	0	10.9	450	--	--
WK	8-3-77	0	0	5	13.7	480	--	--
WK	8-4-77	0	0	10	12.2	423	--	--
WK	8-4-77	0	0	20	11.7	227	18	0
WK	11-22-77	0	0	0	12.6	800	--	--
WK	11-22-77	0	0.01	0	10.2	296	--	--
WK	11-22-77	0	0	20	14.2	219	21	0
WK	11-22-77	0	0.01	20	11.6	64	14.2	0
WK	11-22-77	0	0	10	11.8	603	--	--
WK	11-22-77	0	0.01	10	11.0	155	18	81
WK	11-28-77	0	0	0	11.3	635	--	--
WK	11-28-77	0	0	10	13.3	554	--	--
WK	11-28-77	0	0.1	10	12.4	300	--	--
WK	11-28-77	0	0.1	10	13.4	172	35	115
WK	5-23-78	2.0	0	0	8.7	1900	17	630
WK	5-23-78	2.0	0	10	5.9	2100	16	288
WK	5-23-78	2.0	0	20	8.2	636	12	0
WK	5-23-78	2.0	0	20	7.6	833	12	0
JK	5-25-78	2.0	0	0	8.1	3630	23	755
JK	5-25-78	2.0	0	10	7.7	2630	18	767
JK	5-25-78	2.0	0	0	6.3	1940	18	0

Table E-10. The dynamic rheological characteristics of PRP and PRP (2.0×10^5 platelets/mm³) containing streptokinase in the presence or absence of 0.01 M hydroxylamine.

Donor	Date	t ₀ (min)	G' _{max} (dynes/cm ²)	Thrombin Time (sec)	Prothrombin Time (sec)	Activated Partial Thromboplastin Time (sec)
DB	4-11-78	10.3	931	10.2	11.4	29.7
RB	4-11-78	12.1	816	10.0	10.9	31.0
PJ	4-11-78	13.2	669	10.1	11.2	31.1
ET	4-11-78	12.6	561	10.1	10.9	29.0
DB	4-21-78	24.3	574	10.2	16.2	43.3
RB	4-21-78	19.1	636	10.0	14.8	39.9
PJ	4-21-78	14.6	887	10.1	13.0	34.4
ET	4-21-78	17.0	576	10.1	17.8	42.5
DB	4-28-78	86	313	10.2	22.4	68.1
RB	4-28-78	108	163	10.2	22.3	67.1
PJ	4-28-78	122	250	10.2	20.1	66.6
ET	4-28-78	92	339	10.1	24.9	68.3

Table E-11. The dynamic rheological characteristics and coagulation times of PPP from subjects undergoing warfarin therapy. Therapy initiated on 4-17-78. The plateau values of G' were not attained on 4-28-78; values given are G' at end of run (~ 3 hours).

Donor	Date	Treatment	t_0 (min)	$G'_{\max}$ (dynes/cm ²)
JL	11-10-77	Fresh	8.6	511
JL	11-11-77	Frozen	5.3	344
JL	11-11-77	Lypholised	4.9	325
WK	1-30-78	Fresh	12.7	1115
WK	1-31-78	Frozen	6.4	762
WK	2- 1-78	Frozen	4.8	646
WK	2- 1-78	Lypholised	6.2	523
WK	2-11-78	Lypholised	6.5	596
Pooled	2-17-78	Fresh	9.6	1477
Pooled	2-21-78	Lypholised	6.1	612
Pooled	2-21-78	Lypholised	5.3	626

Table E-12. Dynamic rheological characteristics of fresh, frozen, and lypholised PFP.