INFORMATION TO USERS

This was produced from a copy of a document sent to us for microfilming. While the most advanced technological means to photograph and reproduce this document have been used, the quality is heavily dependent upon the quality of the material submitted.

The following explanation of techniques is provided to help you understand markings or notations which may appear on this reproduction.

1. The sign or "target" for pages apparently lacking from the document photographed is "Missing Page(s)". If it was possible to obtain the missing page(s) or section, they are spliced into the film along with adjacent pages. This may have necessitated cutting through an image and duplicating adjacent pages to assure you of complete continuity.
2. When an image on the film is obliterated with a round black mark it is an indication that the film inspector noticed either blurred copy because of movement during exposure, or duplicate copy. Unless we meant to delete copyrighted materials that should not have been filmed, you will find a good image of the page in the adjacent frame.
3. When a map, drawing or chart, etc., is part of the material being photographed the photographer has followed a definite method in "sectioning" the material. It is customary to begin filming at the upper left hand corner of a large sheet and to continue from left to right in equal sections with small overlaps. If necessary, sectioning is continued again—beginning below the first row and continuing on until complete.
4. For any illustrations that cannot be reproduced satisfactorily by xerography, photographic prints can be purchased at additional cost and tipped into your xerographic copy. Requests can be made to our Dissertations Customer Services Department.
5. Some pages in any document may have indistinct print. In all cases we have filmed the best available copy.

University
Microfilms
International

300 N. ZEEB ROAD, ANN ARBOR, MI 48106
18 BEDFORD ROW, LONDON WC1R 4EJ, ENGLAND

DRAKE, ERIC F.

FATIGUE DAMAGE IN A WC-NICKEL CEMENTED CARBIDE COMPOSITE

Rice University

PH.D.

1980

University
Microfilms
International

300 N. Zeeb Road, Ann Arbor, MI 48106

18 Bedford Row, London WC1R 4EJ, England

Copyright 1980

by

Drake, Eric F.

All Rights Reserved

PLEASE NOTE:

In all cases this material has been filmed in the best possible way from the available copy. Problems encountered with this document have been identified here with a check mark ✓.

1. Glossy photographs ✓
2. Colored illustrations _____
3. Photographs with dark background ✓
4. Illustrations are poor copy _____
5. Print shows through as there is text on both sides of page _____
6. Indistinct, broken or small print on several pages _____ throughout

7. Tightly bound copy with print lost in spine _____
8. Computer printout pages with indistinct print _____
9. Page(s) _____ lacking when material received, and not available
from school or author _____
10. Page(s) _____ seem to be missing in numbering only as text
follows _____
11. Poor carbon copy _____
12. Not original copy, several pages with blurred type _____
13. Appendix pages are poor copy _____
14. Original copy with light type _____
15. Curling and wrinkled pages _____
16. Other _____

RICE UNIVERSITY
FATIGUE DAMAGE IN A WC-NICKEL
CEMENTED CARBIDE COMPOSITE

by

ERIC F. DRAKE

A THESIS SUBMITTED
IN PARTIAL FULFILLMENT OF THE
REQUIREMENTS FOR THE DEGREE

DOCTOR OF PHILOSOPHY

APPROVED, THESIS COMMITTEE:

Aaron D. Krawitz, Adjunct Associate Professor
Thesis Director of Materials Science

William F. Walker, Professor and Chairman
Chairman of Mechanical Engineering

Franz R. Brotzen, Professor of
Materials Science

John E. Merwin, Professor of Civil
Engineering

HOUSTON, TEXAS
MAY 1980

ABSTRACT

"FATIGUE DAMAGE IN A WC-NI CEMENTED CARBIDE COMPOSITE"

by

Eric F. Drake

A model WC-Ni cemented carbide was designed to investigate the response of this type of composite to compressive cyclic loading. The material's monotonic stress-strain behavior was studied in the compressive range, revealing considerable micro-strain plasticity and rapid strain-hardening characteristic of this composite family. Specimens were mechanically conditioned at 20 Hz for one million cycles using a zero-compression-zero sinusoidal program in stress control. Peak stress was varied in increments from zero to 1900 MPa, where failure was observed. Bulk hardness, residual stress state, and fracture toughness were monitored as a function of cyclic stress. Only modest shifts in bulk behavior were observed. On a local scale, fatigue effects on dislocation density and structure were found in the binder phase by transmission electron microscopy. As cyclic stress levels were raised, favorably oriented grain-boundary-ledge dislocation sources were activated, leading to precipitate-free bands of intense slip. These bands broadened at the higher stress levels, saturating entire binder phase regions and triggering a change in dislocation arrangements. At the highest stress levels discontinuous cell structures were observed in some binder regions. It is concluded that fatigue damage in this type of composite accrues in the binder in a characteristic manner dictated by short binder-carbide interaction distances and local stress conditions. The principal roles of fatigue in the fracture behavior of this alloy are concluded to be: a source of incipient defects and a means of stable crack extension.

ACKNOWLEDGEMENTS

The author wishes to express his appreciation to:
Professor Aaron D. Krawitz for his even guidance under difficult circumstances, for his unswerving discipline of the highest moral, ethical, and professional values, and for his ever-poignant humor which is perhaps the largest reflection of his insight and his humanity.

My fellow graduate students in Materials Science at Rice - especially Jay Bhardwaj, Dave Cameron, and Ming-Ming Yang, my colleagues in the "x-ray group" - for the sharing of the facilities, the departmental work burden, and the abundance of ideas that only so heterogeneous an association could produce.

J. "Al" Ehlert for the wealth of his good nature and his know-how.

Drs. R. K. Viswanadham, J. D. Venables, W. L. Wilson, and J. M. Roberts for many helpful discussions and suggestions during the course of this study. Particular thanks is extended to Dr. Viswanadham for his significant contributions in the formulation of this study and for the many personal hours spent in collaboration over the TEM.

Reed Rock Bit Company for the support of this program through a grant to Rice University and by the provision of raw materials, powder facility, testing equipment, and technical assistance, as well as support of the author for the duration. In particular, appreciation is acknowledged to:

D. A. Thiessen and P. W. Schumacher for their instrumental roles in the securing of corporate approval and in the administration of this program.

The staff of the Materials Research Department for their careful cooperation and concern in every phase of material preparation.
Mark Carter for his efficient and artful graphical renderings.
Mrs. Vivian Wright for her patience in the preparation of the manuscript.

And, to Jim Peck, the protagonist - without whose foresight, imagination, initiative, pragmatism, nature, and audacity this effort would not have sallied into reality.

Finally, my wife, Cathy, for her often unspoken, but nevertheless meaningful participation in my work.

To
James A. Peck

TABLE OF CONTENTS

	<u>Page</u>
I. INTRODUCTION	1
A. Evolution of Study.	1
1. Economic context	1
2. Rock drilling application of cemented carbides . . .	3
3. The stress-strain behavior of cemented carbides. . .	5
4. The role of fatigue.	9
B. Objectives.	11
C. Plan of Present Investigation	12
1. Choice of alloy.	12
2. Experimental fatigue parameters.	12
3. Evaluation of fatigue damage	13
II. EXPERIMENTAL	15
A. Preliminary Study of W-C-Ni Ternary	16
B. Alloy Production.	20
C. Characterization.	22
1. Microstructure	22
2. Stress-strain behavior	23
D. Fatigue Loading	31
E. Evaluation of Fatigue Damage.	33
1. Hardness	33
2. Residual stress.	34
3. Fracture toughness	37
4. Microstructure	40
III. RESULTS AND DISCUSSION	45
A. Bulk Properties	45
B. Microstructure.	50
C. Fatigue Effects	57
IV. CONCLUSIONS.	74
REFERENCES	76

LIST OF FIGURES

	<u>Page</u>
Figure 1. Rotary Rock Bit with Cemented Carbide Inserts	2
Figure 2. Hypothetic W-Ni-C Ternary Phase Relations	18
Figure 3. WC-Ni Experimental Alloy Characteristics.	22
Figure 4. Cylindrical and Parallelepiped Stress-Strain Behavior Specimen	24
Figure 5. Compressive Stress-Strain Behavior to Rupture of WC-Ni Composite.	25
Figure 6. Stress-Strain Behavior of WC-Ni Composite in Re-loading.	27
Figure 7. Stress-Strain Behavior of WC-Ni in the Range of Stresses Investigated in Fatigue.. . . .	29
Figure 8. Axial and Poisson Stress-Strain Behavior in the Microstrain Region.	30
Figure 9. Specimen Processing Schematic	32
Figure 10. Allocation of Cylindrical Specimen for Fatigue Analyses.	33
Figure 11. Schematic Diagram of Short Rod Fracture Toughness Specimen.	38
Figure 12. Schematic Diagram of Force - Crack Length Relationship for a Condition of Constant Stress Intensity in the Short Rod Specimen.	38
Figure 13. Short Rod Specimen Tolerances Used in this Study.	41
Figure 14. K_{IC} Loading Fixtures with Short Rod Specimen in Position.	42
Figure 15. Bulk Hardness vs Fatigue Stress Amplitude	46
Figure 16. Residual Stress in WC vs Fatigue Stress Amplitude	47
Figure 17. Fracture Toughness vs Fatigue Stress Amplitude.	48
Figure 18. Typical Fracture Surface of the WC-Ni Cemented Carbide alloy. Secondary Election Images	51
Figure 19. Binder Region. Zero Load	52
Figure 20. Binder Region. Zero Load	52
Figure 21. Binder Region. Zero Load	53

	<u>Page</u>
Figure 22. W C. Grain. Zero Load.	53
Figure 23. Diffraction Patterns of Nickel Binder Cemented Carbides Showing Evidence of β -WC Precipitate	55
Figure 24. WC Grain. 40 KSI Fatigue Level.. . . .	59
Figure 25. WC Grain. 200 KSI Fatigue Level.	59
Figure 26. Binder Region. 40 KSI Fatigue Level.	61
Figure 27. Binder Region. 40 KSI Fatigue Level.	61
Figure 28. Binder Region. 40 SKI Fatigue Level.	62
Figure 29. Binder Region. 120 KSI Fatigue Level	62
Figure 30. Binder Region. 120 KSI Fatigue Level	63
Figure 31. Binder Region. 120 KSI Fatigue Level	63
Figure 32. Binder Region. 120 KSI Fatigue Level	65
Figure 33. Binder Region. 160 KSI Fatigue Level	65
Figure 34. Binder Region. 200 KSI Fatigue Level	66
Figure 35. Binder Region of Figure 34. 200 KSI Fatigue Level. . . .	66
Figure 36. Selected Area Diffraction Patterns from Figure 32 Binder Region	68
Figure 37. Binder Region. 250 KSI Fatigue Level.	68
Figure 38. Binder Region. 250 KSI Fatigue Level.	69
Figure 39. Binder Region. 270 KSI Fatigue Level.	69
Figure 40. Binder Region. 270 KSI Fatigue Level.	71
Figure 41. Binder Region. 270 KSI Fatigue Level.	71
Figure 42. Binder Region. 270 KSI Fatigue Level.	72
Figure 43. Binder Region. 270 KSI Fatigue Level.	72

I. INTRODUCTION

A. Evolution of Study

1. Economic context

Cemented carbides can be defined as composites having a major fraction of transition metal carbide(s) and a minor fraction of metallic binder. In the sixty years since their introduction, cemented carbides or "hard metals" have found widespread application as engineering materials - wherever deformation resistance combined with high toughness was required. Commercial cemented carbide alloys typically contain from 5 to 25 volume percent binder and range from sub-micron to about 5 microns in average grain size. These ranges give rise to hardness values of from 1000 to 1700 kg/mm² and fracture toughness (G_{IC}) values of from 80 to 800 J/m². Many diverse chemistries and often complex compositions have been employed successfully in these materials' history of largely empirical development.⁽¹⁾ For most of their applications, cemented carbides remain unparalleled by any other class of material.

One of these applications is enormously important to global economics: rock drilling. Essentially all energy-related drilling done worldwide relies on cemented carbides in one role or another. Likewise, most mining operations depend on these composites for blast-hole drilling and tunneling. In the past 25 years, the rotary insert bit has emerged in various forms as the predominant tool for rock drilling; (see Fig. 1). So-called "inserts" of cemented carbide form the teeth of these bits, cycling in and out of contact with the hole bottom to produce rock fracture and chip removal. The mechanical behavior of cemented carbide inserts, in particular their fracture behavior, has a strong influence on bit design and performance. Ultimately the physical

behavior of cemented carbides often plays a crucial role in determining overall drilling economics.

Despite considerable incentive, alloy development in rock-drilling cemented carbides has been hindered by an incomplete understanding of the properties which determine insert performance and the inherent difficulty of empirical development of insert materials. This situation reflects a more general lack of complete understanding concerning the mechanical and physical metallurgy of cemented carbides as a class of composites. In the following sections, the application of cemented carbides to rock drilling will be reviewed in light of current understanding to show the significance of fatigue response in these composites.

Figure 1. Rotary Rock Bit with Cemented Carbide Inserts

2. Rock drilling application of cemented carbides

Within the spectrum of cemented carbide technology rock-drilling occupies a distinct niche. The "straight grades" of cemented carbides, comprising only WC and Co, still dominate this application. The straight grades of cemented carbides vary principally in binder fraction and WC grain size. Bulk hardness is manipulated by control of these variables and for some time was the only mechanical property of interest in the specification of insert materials. It has been presumed that wear resistance bore a proportional relationship to hardness while fracture resistance varied inversely with hardness. Therefore, insert hardness has been specified on the basis of bit type to achieve satisfactory wear resistance while minimizing fracture degradation.

Insert performance has been evaluated by a weight-loss measurement under actual drilling conditions. This procedure is both costly and time consuming, and is fraught with statistical uncertainty. Scatter -- introduced by the many variables of drilling which range from rock formation characteristics and drilling fluid chemistry to rig dynamics and operator skill -- precludes any quantitative comparison of inserts run in different bits. "Fracture ratings" obtained from groups of inserts carefully placed in the same bit are regarded as valid comparisons -- though random flaw distributions in the as-manufactured inserts combine with limited sample size to render these ratings rather insensitive. Nonetheless, field testing is still the singular means of evaluation of cemented carbides for rock-drilling applications.

The need for a more analytical approach to the fracture behavior of rock drilling carbides has been recognized for some time; much work has been undertaken to characterize and rationalize the mechanical behavior of

these brittle composites in terms of measurable properties. In addition to hardness, measurements of compressive strength, transverse rupture strength, density, and microstructural parameters traditionally have founded such work. None of these measures has offered more than a crude indication of the integrity exhibited by a given material in actual use.

A significant advance in understanding of failure of cemented carbides has come from the application of fracture mechanics concepts. By separating the parameters of crack initiation from those of propagation, fracture mechanics enables independent evaluation of properties relevant to fracture behavior.

For example, the characterization of crack stability through the use of linear elastic fracture mechanics' parameters G_{IC} or K_{IC} has made possible the accurate prediction of fracture behavior of various WC-Co grades -- for situations in which failure results from the interaction of monotonic loading with the original flaw population⁽²⁻⁸⁾. Furthermore, means of manipulating fracture toughness within a given system have been demonstrated. For example, investigators have reported functional relationships between the microstructural parameter, binder mean free path, and the material property G_{IC} ⁽⁴⁻⁸⁾. Similarly, through experiments with heat treatable (Fe, Ni, Co) binders, the influence of binder microstructure on fracture toughness has been demonstrated⁽⁹⁾.

However, in experiments on a number of WC-Co materials it has been found that no correlation appears to exist between the measured fracture toughness (K_{IC}) values and the fracture resistance observed in drilling tests⁽⁹⁾. This strongly suggests that some type of fatigue mechanism(s) is operating under the influence of the cyclic loading which is

characteristic of a rotary rock bit.

Several means by which fatigue damage may influence fracture behavior can be envisioned. Cyclic strains may give rise to changes in bulk behavior. For example, the development of dislocation networks in the carbide or binder phases could affect the character of plastic accommodation of strain at a crack tip, thereby altering the K_{IC} value of the composite. A similar effect could arise from the redistribution of residual stresses under cyclic strain or from (bulk-scale) strain-induced phase transformation. Another effect of fatigue damage on fracture behavior is local in character. This involves the stable growth of pre-existing flaws into critical-size cracks. Whenever crack extension is necessary to achieve the critical stress intensity under operating stress conditions, the parameters affecting fatigue crack growth can overshadow the role of fracture toughness in determining service life. Local damage phenomena may also constitute a source of defects leading to crack nucleation.

For rock-drilling cemented carbides, there are many implications of fatigue damage for fracture. All of the potential mechanisms of fatigue damage involve the production and movement of dislocations. Since this is the essence of plasticity, it is of interest to review the response of cemented carbides to monotonic load.

3. The stress-strain behavior of cemented carbides

The extraordinary compressive strengths observed in cemented carbides as well as other attractive mechanical properties clearly derive from their composite nature, but the details of how two vastly different phases interact under strain are not known. A number of fundamental stumbling blocks continue to confound this subject.

One unresolved issue concerns the (residual) state-of-stress in the carbide and binder phases. Since the temperature coefficient of expansion of the binder is typically two times that of the carbide while the Young's modulus is less than one-third, it long has been recognized that significant residual stresses are inherent to cemented carbides. Gurland⁽¹⁰⁾, modeling a WC-Co alloy as spheres of WC in a cobalt matrix, predicted hydrostatic compression in the carbide with a more complex (tensile) stress state in the matrix. Numerous investigators have since used x-ray diffraction to measure residual stress in the WC phase of cobalt binder materials⁽¹¹⁻¹⁸⁾. Conflicting results arising from experimental technique, surface preparation, and sizable experimental uncertainties introduced by the high modulus of WC have been largely resolved; the compressive nature of temperature stress in WC and its relative change with such variables as binder fraction and cooling rate have been characterized. French^(12,13) reviews some of the historical problems regarding the theory and practice of these measurements and points out two inherent reasons why x-ray diffraction has not completely resolved the nature of temperature stresses in cemented carbides: x-ray stress measurements on the binder have not been feasible (as a result of intensity considerations); x-ray measurements are surface sensitive and therefore reveal only a partially relaxed (bi-axial) stress state. Both of these problems may be overcome through the application of neutron diffraction⁽¹⁹⁾. At present, however, experimental verification of triaxial stress conditions in cemented carbides is not available.

Uncertainty regarding thermal residual stresses in cemented carbides only augments the difficulty of describing these materials' response to

applied load. Theoretical treatment of the composite behavior has not been feasible due in part to the inability to describe phase shape and distribution. It is felt that the detailed bulk deformation response depends on local spatial arrangements of grains. These irregular arrangements vary (in the average) with grain size distribution and binder fraction, and can change with each increment of deformation. Efforts to generalize this complex interaction have led to two idealized view points which have served as the context for interpretation of nearly all experimental work which has been conducted on the mechanical response of cemented carbides. One concept, set forth by Dawihl⁽²⁰⁾ is that a "continuous carbide skeleton" exists which largely determines deformation behavior. The other view originated with Gurland⁽²¹⁾ and attributes deformation behavior to binder properties. Here the composite is regarded as a dispersion of discrete carbide particles in an essentially continuous matrix.

Experimental data concerning cemented carbide deformation pertains almost exclusively to the WC-Co system. The macroscopic stress-strain response of several WC-Co cemented carbides was established in compression, torsion, and tension by Felgar and Lubahn⁽²²⁾. These measurements showed that deviation from Hookean behavior occurred at very low strains and proceeded very gradually. They attributed the unusual strength of cemented carbides to plasticity effects as reflected in unusually high strain-hardening exponents. More recently, Jaensson⁽¹⁶⁾, working with x-ray diffraction strain measurements from a range of WC-Co alloys has proposed a completely non-linear mechanical model of stress-strain behavior in cemented carbides. He points out that similar behavior occurs in certain cast irons.

The microscopic roles of the carbide and binder phases during deformation have only recently begun to emerge from experimental evidence. Room temperature slip has been documented in WC by a number of investigators⁽²³⁻²⁵⁾. Such plasticity effects have also been observed in the WC phase of deformed cemented carbides, particularly at high deformation⁽²⁶⁻²⁸⁾. Arndt⁽²⁷⁾ reports that the onset of bulk plasticity corresponds to deformation of a WC skeleton.

On the other hand, Doi and co-workers^(29,30) have inferred surprisingly large increases in binder dislocation density from internal friction changes associated with bulk plastic deformations in the microstrain region. They went on to apply (Orowan) dispersion hardening theory to explain the observed strain-hardening behavior in terms of binder dislocation interactions.

However, the precise interpretation of damping measurements in cemented carbides is uncertain if possible loss origins other than dislocation damping are considered. A particular complication of WC-Co concerns the metastable nature of the binder phase in these materials. It has been recognized that the Co binder phase is present in typical cemented carbides in a highly faulted FCC modification, owing to the sluggishness of the low temperature FCC-HCP transformation. Though Doi's work assumes a stable FCC cobalt binder phase, direct observation by transmission electron microscopy (TEM) does not support this view. Sarin and Johannesen⁽²⁸⁾, studying defect structure development in deformed (41%) WC-Co, reported binder deformation by formation of HCP Lamellae in FCC Cobalt. Also, Krawitz⁽¹⁹⁾ has observed this transformation in neutron diffraction studies of rock-drilling inserts.

Other evidence suggesting primarily binder-controlled deformation behavior is found in bulk hardness relationships with temperature, binder fraction, binder structure, and chemistry variation^(4,31,32). From yield strength-binder fraction considerations, Gurland⁽³³⁾ and French⁽³⁴⁾ have been led to apply a Lenel-Ansell formalism to explain the plastic behavior of WC-Co cemented carbide in terms of dislocation pileups in the binder. In the same vein, support for a continuous matrix viewpoint of WC-Co cemented carbides has been provided by recent scanning transmission electron microscopy (STEM) observations of continuous cobalt films in WC-WC grain boundaries⁽³⁵⁾.

Although these observations have been offered at times in support of conflicting viewpoints, a number of consistent conclusions can be drawn. First, the deformation behavior of WC-Co cemented carbides is marked by plastic behavior at very small strains followed by rapid strain hardening. Second, compatibility requirements result in plastic deformation in both phases as strain progresses. The details of this interaction are influenced by microstructural and thermodynamic considerations. Finally, though definitions of yield have been rather arbitrary in these unusual composites, the early plastic strain behavior seems dominated by binder activity.

4. The role of fatigue

The fatigue response of cemented carbides has not been characterized. Dawihl⁽³⁶⁾ reported fatigue bend strength values at two million cycles for two WC-Co alloys. In recent work, Johansson et al⁽³⁷⁾ measured compression fatigue strength of four WC-Co alloys, also at 2 million cycles. Crack propagation under the influence of cyclic loads has been observed in rock drilling carbides under laboratory

conditions and also in association with surface spalls^(9,38). At present, it is not known how fatigue damage contributes to this stable crack growth, nor has there been any study of fatigue damage accumulation in the bulk.

The peculiar monotonic strain response of cemented carbides raises the question of whether fatigue processes similarly reflect the composite nature of cemented carbides. The development of dislocation structure observed in fatigue of pure alloys may be significantly altered in cemented carbide composites as a result of the proximity of interfaces and the image forces arising from extreme property differences of the phases. In particular, the tendency for cemented carbides to accommodate even small strains with palpable plasticity infers that fatigue behavior of cemented carbides composites may play a failure role much different from that of pure metals and alloys.

B. Objectives

It is the principal goal of the present study to characterize the physical and mechanical property changes which occur as a result of cyclic strain in a model cemented carbide composite. In particular, it is of interest to learn the mechanisms of fatigue damage accumulation which affect fracture behavior under conditions of loading resembling those of a rock-drilling insert.

To this end, the main objectives of this study are as follows:

- (i) To design and produce a simplified cemented carbide alloy representative of rock-drilling grades.
- (ii) To characterize the experimental alloy with respect to:
 - a) microstructure
 - b) monotonic stress-strain behavior (compression)
 - c) hardness
 - d) residual stress level in WC
 - e) fracture toughness
 - f) dislocation density and morphology
- (iii) To fatigue condition the experimental alloy in uniaxial compression over a range of stresses for 10^6 cycles.
- (iv) To assess fatigue damage effects on:
 - a) hardness
 - b) residual stress level in WC
 - c) fracture toughness
 - d) dislocation density and morphology

C. Plan of Present Investigation

1. Choice of alloy

A WC+Ni alloy was chosen for this study because it was felt that a nickel binder would most clearly reveal the fatigue behavior associated with the composite nature of cemented carbides. Considerations in this selection include the phase stability of FCC nickel and the relative isotropy of slip in FCC crystals. In addition, the investigation of a binder similar to cobalt except notably in its dislocation behavior was expected to provide perspective for the substantial experimental work already performed on mechanical behavior of WC-Co composites.

The volume fraction of binder and the WC grain size were maximized in the experimental alloy to facilitate binder analysis while remaining within the ranges used in commercial rock-drilling grades. The exact composition of the experimental material was chosen to be within the WC+Ni two phase field as determined by a preliminary study to establish the pertinent boundaries of the W-C-Ni ternary equilibrium diagram.

2. Experimental fatigue parameters

The service requirements of a rock bit insert provided the basis for selection of fatigue parameters where there was no experimental conflict. The frequency and total number of cycles used are reasonable approximations of an actual insert life. The uniaxial sinusoidal compressive load program represents a necessary simplification of the type of loading experienced in practice which is thought to superimpose a reverse-bending component as well. The peak stress was increased in increments determined from the monotonic stress-strain behavior, until fatigue failure was observed in the cylindrical specimens.

3. Evaluation of fatigue damage

In this initial investigation of fatigue behavior of cemented carbides, it was undertaken to establish whether certain bulk properties were affected by cyclic load. This was done to help estimate the cumulative effect of local phenomena as well as to discern among possible origins of fatigue effects. In addition to measurements which averaged over a large volume of the composite, numerous direct observations of local binder and carbide dislocation populations were performed in order to determine the roles of each phase in fatigue and to establish the scale of their interaction under the conditions tested.

Diamond pyramid hardness measurements were made on specimens from each load category. By this technique, only rather large cyclic hardening or softening effects would be observed.

Residual stress measurements were performed on the WC phase. In spite of attempts to enhance the diffracted intensity from the binder phase, no high angle nickel peaks were observable for stress determination. However, it was felt that redistribution of residual stress by plasticity of either phase would be accompanied by a change in WC stress level. The precise characterization of such a redistribution would not be possible by x-ray techniques in any event due to considerations mentioned previously. Thus, the x-ray measurements made in this study serve to establish the scale of residual stress modification resulting from cyclic strain.

Fourier analysis of x-ray data to obtain a quantitative determination of strain in each phase was considered initially but did not prove feasible because neither the binder nor WC phase exhibited palpable peak broadening as a result of fatigue loading. In view of

this, it was hoped to establish at least a maximum limit for strain in the fatigue-active phase (binder). This was prevented by an extreme texture effect associated with the large binder grain size. In this respect, the experimental material was like more typical cemented carbides which exhibit binder grain sizes on the order of millimeters while WC grains are three orders of magnitude smaller.

Fracture toughness measurement was the most sensitive of the "bulk" tests performed. Determination of the property " K_{IC} " was undertaken to establish the influence of fatigue damage processes on crack stability. In conjunction with these measurements, scanning electron fractography was used to monitor possible changes in fracture mode with fatigue parameters.

Transmission electron microscopy of thin foils was used to characterize the nature of dislocation generation and interaction during fatigue. It was of interest to observe dislocation activity in both phases, noting the sources, senses, and density of line defects as a function of fatigue stress level. In particular, a basis for comparison with fatigue behavior in non-composite systems was pursued; the development and scale of dislocation structures served to indicate the nature of plastic inhomogeneity as well as to suggest the steps preceeding fatigue crack nucleation.

Certain experimental difficulties inherent to the TEM study of cemented carbides have imposed limitations on the detail with which dislocations behavior could be characterized. Among these are:

- i) Foil thickness variation due to differential sputtering of phases during final thinning. This limits the number and size of transparent areas and limits accuracy of counting dislocations.
- (ii) Diffuseness of diffracted intensity from binder. This may be attributable to elastic (residual) strains between phases or to magnetic characteristics of the binder. It limits clarity of selected area diffraction patterns.

However, within the scope of this study, the precise character of the dislocations themselves has less relevance than the nature of local aggregate dislocation response which occurs on the scale of the WC grain size. In view of this, the greatest concern regarding interpretation of TEM data has to do with the question of generality of observations rather than questions of small rotations, redistributions or loss of dislocations during thinning. Accordingly, the experiments have been designed to permit evaluation of a large sample population.

Finally, it should be noted that the characterization of nascent material is important to any extrapolations which might be made concerning fatigue response of other cemented carbide materials. The generality of fatigue characterization of the WC-Ni composite depends in large part on the characterization of behavior for which comparable data has been generated in other systems.

II. EXPERIMENTAL

A. Preliminary Study of W-C-Ni Ternary

The experimental alloy of choice was a two-phase WC+Ni composite containing 24 at. % nickel. The lack of published W-C-Ni ternary equilibrium data necessitated an initial study to establish the pertinent boundaries of the phase diagram. From the binary systems⁽³⁹⁾ and knowledge of the three-component intermetallics in the system, a hypothetical isothermal section of the W-C-Ni equilibrium diagram was constructed in accord with thermodynamic principles. This diagram is shown in Fig. 2.

The WC+Ni phase field is bounded on either side by three-phase fields. The most conservative estimate of the extent of this two-phase field results from an assumption of strict stoichiometry; i.e. no compositional range of the WC intermetallic phase. With this simplification and the estimation of the shape of the nickel phase field by analogy to similar ternary systems, the compositional limits of the field of interest were determined (for the case of quasi-equilibrium) by the following experiment.

Five alloys were produced along the 24 at. % nickel isopleth as indicated in Fig. 2. The compositions spanned a range of 2 at. % on either side of the pseudo-binary WC-Ni line.

The materials, designated TD1-5, were produced from powders and vacuum sintered by the same procedures (described in Section B) used for the principal alloy, with the exception of lot size -- which was limited to 1 kg. Impurity levels of the WC, Ni, W and carbon black starting powders were less than 0.01 wt. %, while carbon levels were determined to within ± 0.002 wt. %. Total carbon of each dewaxed material was verified

analytically to within ± 0.02 at. % prior to sintering. Principal contaminants were re-checked at this point by atomic absorption spectroscopy and found to be: 0.02 wt. % Co; 0.07 wt. % Fe; Cr 0.01 wt. %. The materials were vacuum sintered on an alumina tray at 1430°C for 45 minutes and cooled in argon at about $25^{\circ}\text{C}/\text{minute}$ to room temperature.

The five materials were evaluated by x-ray diffraction. $\text{CuK}\alpha$ radiation was used with a Siemens diffractometer equipped with a quartz diffracted beam monochromator. The lattice parameter of the binder phase was determined from the (111) Ni peak and compared with the data in Pearson⁽⁴⁰⁾ to obtain the solute levels of tungsten for each composition. No lattice dilation was attributed to carbon solute atoms due to its low solubility. Verification of phases was obtained by indexing of all peaks from 30° to $150^{\circ} 2\theta$ and metallographically corroborated at 1500X. The results of these determinations are shown in Table 1.

Though the specimens investigated cannot be considered to be at equilibrium, for the purposes of this study a quasi-equilibrium approach was adequate for phase prediction. As shown in Fig. 2 the solute level of tungsten in Ni in the three-phase specimens enabled the establishment of the corners of the tie triangles delineating the phase field of interest. On this basis, the experimental composition was chosen to lie midway in the phase field, coincident with TD-4.

Figure 2. Hypothetic W-Ni-C Ternary Phase Relations

<u>Specimen</u>	<u>at. % C</u>	<u>Phases</u>	<u>Ni(111) 2θ</u>	<u>Ni(111) d($\text{\AA}$)</u>	<u>Ni a₀($\text{\AA}$)</u>	<u>Solute at. % W</u> *
TD1	40	WC+Ni + Graphite	44.4	2.040	3.553	2.3
TD2	39	WC+Ni + Graphite	44.4	2.040	3.553	2.3
TD3	38	WC+Ni + Graphite	44.4	2.040	3.553	2.3
TD4	37	WC+Ni	44.1	2.053	3.556	7.8
TD5	36	WC+Ni+Ni ₂ W ₄ C	43.9	3.571	3.571	11.5

*(from Pearson, 40)

Table 1. X-ray Data from W-C-Ni alloys with 24 at. % Ni

B. Alloy Production

The experimental material was produced by standard powder metallurgy techniques in a single 10 kg batch. The starting powders were:

W - General Electric Lot #V 0.80-4230 (sub-micron)
WC - Wah Chang WC III #3134-A
Ni - Inco 123

The powders were measured to result in a sintered product containing:

15.61 wt. % Ni
4.93 wt. % C
79.46 wt. % W

allowing for 1 wt. % Nickel loss during sintering. The mixed powders were milled for 10 hours in a stainless steel jar with 15 kg of 6 mm diameter WC-Co media and 3.5 l of petroleum ether. The mill was interrupted after 9 hours to add 150g of paraffin dissolved in petroleum ether.

After milling, the mix was screened through a 325 mesh and dried at 90°C under vacuum in a rotating V-blender. The powder was homogenized through a granulator and pulverizer, and then pressed at 50 MPa to form 5 mm thick by 50 mm diameter briquettes. These briquettes were processed through the granulator and pelletized in a V-blender. The pelletized powder was pressed into the final cylindrical configuration at 335 MPa.

As each cylinder was pressed it received an identifying number which was traceable for all ensuing portions of this study. Likewise, orientation of sample in the die was used to identify cylinder top and bottom, which was maintained throughout to ameliorate the experimental influence of any axial textures or gradients which may have developed during pressing and sintering operations.

Each cylinder was weighed (± 0.0001 gm) after pressing and then dewaxed in one batch under vacuum at 600°C . One sample was chemically analyzed at this point to check contamination levels due to processing and to re-verify total carbon present. Specimen weight and dimensions were measured and documented.

Sintering was performed in two batches of 120 each due to furnace capacity limitations. Furnace location of each specimen was documented. After a pressure of less than 25 microns was achieved, the furnace was heated to 1200°C in 50 minutes. The sintering temperature of 1430°C was approached at 3°C per minute and then held for 45 minutes. Cooling was conducted under argon at $25^{\circ}\text{C}/\text{minute}$. Shrinkage and weight were documented for each specimen. Metallographic specimens were reserved. Specimens which lost greater than 1.2 wt. % of the binder (0.2 wt. % total) due to temperature gradients in the furnace were discarded.

Specimens were hot-isostatic-pressed (HIP) to assure full density. HIP'ing was done in one batch at 1288°C under 100 MPa argon pressure for 1 hour. The cooling rate from temperature was about $3^{\circ}\text{C}/\text{minute}$. Weights and densities were documented for each cylinder after HIP'ing.

Finally, specimens were diamond ground to $12.70 \pm .0025$ mm diameter and $18.877 \pm .013$ mm in length. Diametral material removal averaged 0.75 mm; axial excess material condition averaged 0.60 mm. Perpendicularity and flatness of the ends were controlled to within 0.005 mm. To attain these geometrical form tolerances, a removal rate of 0.0025 mm per pass was used as the dimensions were approached.

C. Characterization

1. Microstructure

The experimental material was sectioned through a number of planes and inspected in etched and unetched conditions. No porosity or microstructural inhomogeneity was observed at 250X or 1500X. The microstructure is shown in Fig. 3, along with hardness and density information.

etch: Murakami's Reagent

Ni:	15.61	wt %
C:	4.93	wt %
W:	79.46	wt %
Density:	14.058	g/cm
Binder:	29.5	vol. %
Hardness:	800	DPH

Figure 3. WC-Ni Experimental Alloy Characteristics

2. Stress-strain behavior

The monotonic stress-strain behavior was determined in compression by bonded strain gage techniques. Two specimen configurations were employed. Seven cylindrical specimens (of the same dimensions used for fatigue) were each instrumented by three axial gages spaced at 120° on the circumference. Micro Measurements type WK-06-125Bt-250 strain gages were epoxy-mounted and connected in series for cancellation of bending. One parallelepiped specimen of 8.890 mm square cross-section by 18.80 mm long was gaged on opposite faces with M-M type WK-06-060WT-350 rosette gages as shown in Fig. 4. This specimen was used for simultaneous measurement of axial and Poisson strains. Epoxy mounting was used and series-type connection was again employed. All specimens were true geometrical forms to within 5 microns. Gage alignment was within 0.5° .

The same loading platens were used for monotonic and fatigue testing. These comprised 5 cm diameter by 5 cm thick WC-Co cemented carbide ($91 R_A$) cylinders press-fit in 15 cm diameter S-1 tool steel holders. Flatness and parallelism of load surfaces were within 2.5 microns and .01 degree, respectively. Steel shims 25 microns thick were inserted at both ends of the specimen to minimize end friction effect. These extruded to a few microns in thickness at higher load levels. An MTS #810.14-2 servo-hydraulic test system (4.45×10^5 N capacity) performed all compressive load applications. For monotonic testing, load ramps of approximately 1% per second of the full-scale stress were used.

Reproducibility of stress-strain data among all specimens and configurations was within one percent. Shown in Fig. 5 is the complete compressive behavior of the experimental alloy up to the rupture point.

Figure 4. Cylindrical and Parallelepiped Stress-Strain Behavior Specimens

Figure 5. Compressive Stress-Strain Behavior to Rupture of the WC-Ni Composite

Plotted for comparison are the Young's Moduli of WC⁽⁵²⁾ and Ni⁽⁵³⁾, taken as 7.03×10^5 MPa and 2.07×10^5 MPa, respectively.

Catastrophic compressive failure was observed at 6.29% strain and a stress of 2765 MPa. Both of the specimens which were loaded to fracture failed within 0.2% of the same stress value.

The nature of WC-Ni strain response is similar to that observed in WC-Co. As reported for WC-Co (Section I.A.3), no proper elastic region can be discerned. Plasticity, accompanied by rapid strain hardening occurs from the first increments of strain. Beyond about 1.5% strain, the initial strain hardening characteristic is markedly decreased.

The effect of strain hardening on early stress-strain behavior is depicted in Fig. 6. Here, a specimen was strained to nearly 3.0%, unloaded, then re-loaded. The initial modulus of the nascent and strain-hardened material appears to be the same. Shown on Fig. 6 is the Young's modulus value determined from precision tests such as shown in Fig. 8. In all cases, the observed initial moduli correspond to this value of 4.94×10^5 MPa -- regardless of prior strain. The most restrictive theoretical limits on elastic modulus for an isotropic, two-component mixture have been derived by Haskins and Shtrikman⁽⁴¹⁾:

$$E_{\text{Composite}} = E_b \left[\frac{1 + 2V_a \left(\frac{E_a - E_b}{E_a + 2E_b} \right)}{1 - V_a \left(\frac{E_a - E_b}{E_a + 2E_b} \right)} \right] \quad (1)$$

Where: E is Young's modulus
 V is volume fraction

and: Subscripts a and b refer to WC and Ni for one bound, to Ni and WC for the other bound, respectively.

Figure 6. Stress-Strain Behavior of WC-Ni Composite in Re-loading

It is interesting that the observed initial modulus falls within the lower and upper bounds predicted for this system by equation (1): 4.90×10^5 and 5.27×10^5 MPa.

Noted on Fig. 5 is the range of fatigue stresses tested in this study. Fig. 7 examines this portion of the stress-strain curve in closer detail. This plot extends to slightly beyond 1700 MPa and about 0.6% strain. The unload-reload cycle demonstrates that the early curvature corresponds predominantly to plasticity rather than anelasticity. Although on the initial loading, 0.2% plastic strain and 0.38% elastic strain have accumulated at a stress level of 1730 MPa, the strain hysteresis in the first (unreversed) cycle is only about 0.04% at its maximum extent. As discussed, upon reloading after plastic strain a linear region is observed which has a slope closely approximating the instantaneous initial slope of the first loading.

The same effects are observable in the high-resolution test shown in Fig. 8. At a total strain of only 0.225%, a plastic component of 0.042% has occurred. As in Fig. 7, a linear response is observed for a time until the unloading point is approached. Curvature beyond the unloading point resumes the original trajectory.

Also shown in Fig. 8 is the Poisson response of the experimental alloy. The plots of Poisson's ratio versus (axial) compressive stress were obtained for each loading cycle by taking quotients of total axial strain and total transverse strain. On the first loading, a beginning Poisson's ratio of 0.345 falls continuously to about 0.275. Thereafter, it begins to rise. The behavior on reloading is similar, except Poisson's ratio falls to nearly 0.255 and remains constant at this value until the initial unloading point is approached. Again, the relative

Figure 7. Stress-Strain Behavior of WC-Ni in the Range of Stresses Investigated in Fatigue

Figure 8. Axial and Poisson Stress-Strain Behavior in the Microstrain Region

transverse strain begins to increase as the axial strain resumes a non-linear track.

The peculiar Poisson behavior of this composite may be partially accounted for by plasticity effects. The values of Poisson's ratio for WC⁽⁵²⁾ and pure Ni⁽⁵⁴⁾ are about 0.205 and 0.31, respectively; a ratio of 0.5 is approached in ideal plastic behavior. In the plots of Fig. 8, Hookean behavior would be expected to result in a constant value for Poisson's ratio of between 0.205 and 0.31, while increasing plasticity would displace curves to higher values. These effects are observed. However, the transient behavior between zero and about 300 MPa is of uncertain origin. The possibility that residual elastic strains in the composite may be responsible for variation in the ratio of moduli in this early range of deformation is suggested by the similar magnitude of the residual stress levels in this material (~ 220 MPa). As mentioned earlier, the carbide is in a compressive stress state which is balanced by a tensile condition in the binder. Reversal in the sign of stress occurs in the binder under increasing compressive load. Exactly how the sharing of load is accomplished between phases is not known, but these Poisson data imply that it varies over the course of deformation and that the residual stress state may influence early deformation behavior on a bulk scale.

D. Fatigue Loading

The apparatus for fatigue cycling of the specimen cylinders has been described in the previous section. Fig. 7 shows the first six (designated I-VI) of the seven fatigue levels investigated in relationship to the monotonic stress-strain curve. The highest fatigue level tested was 270 KSI (1862 MPa). Beyond this stress, catastrophic

failure was observed before 10^6 cycles were completed.

The cycling was conducted in stress control using a sinusoidal program at 20 Hz. Great care was taken to avoid accidental overload during setup or shutdown. The amplitude of the applied stress function was controlled within 2%. A 0.5 MPa preload was applied to maintain specimen position on the anvils during the zero-compression-zero cycling. The loading waveform was monitored by oscilloscope. All specimens were subjected to exactly 1×10^6 cycles.

Shown in Fig. 9 is a schematic of the processing steps described in sections III-C, D and E.

Figure 9. Specimen Processing Schematic

E. Evaluation of Fatigue Damage

1. Hardness

Vickers hardness measurements were performed on metallographically polished specimens at 1Kg load. A Shimadzu type M hardness tester was used. Shown in Fig. 10 is a schematic drawing of the specimen indicating the location of sections used for fatigue analysis. In general, measurements were performed on material from the mid-length, near-center region of the cylinders.

Figure 10. Allocation of Cylindrical Specimen for Fatigue Analyses

2. Residual Stress

Residual stress measurements were made by x-ray diffraction on the WC phase of the composite using specially prepared specimens. The scale of surface damage was limited to about 1 micron in view of the effective X-ray penetration of WC of about 28 microns under the experimental conditions.

Surface preparation of x-ray specimens was performed by diamond polishing using the procedure shown in Table 2. A special fixture was designed to maintain flatness and parallelism of the specimen during polishing. The specimen was afixed to the fixture by a thin layer of thermoplastic resin. The approach used to establish the polishing procedure was to remove material to a depth of 3 times the preceeding nominal grit dimension. Polishing rate was monitored by use of a calibrated focus of a metallograph. The efficacy of this procedure in producing a deformation-free surface was checked by monitoring the x-ray peak profile as polishing progressed.

Step #	Cutting Agent (diamond)	Grit Dimension (microns)	Final Specimen Thickness (mm)
1	saw	--	1.52
2	resin-bonded wheel	15	1.38
3	paste on Pellon	10	1.33
4	"	7	1.30
5	"	3	1.28
6	"	1	1.27

Table 2. X-ray Specimen Surface Preparation Procedure

Residual stress measurements were performed by x-ray diffraction using the $\sin^2 \psi$ method⁽⁴²⁾. X-ray measurements were made using a GE XRD-5 diffractometer equipped with a scintillation detector and pulse height analyzer set for 90% acceptance of the CuK_α radiation. The (212) peak of WC residing at about $154^\circ 2\theta$ was utilized for all measurements. In accord with recent work cited by James and Cohen⁽⁴²⁾, the stationary slit technique was adopted for these measurements, sacrificing some intensity due to improper focusing for the benefit of accuracy.

Operating at 50 kV and 16mA with the beam path:

Divergent beam: 1° divergent slits
 Medium Resolution Soller slits

Receiving beam: Medium Resolution Soller slits
 0.2° receiving slits
 25 micron Ni filter for CuK_β

resulted in intensities of about 50 counts per second against a background of about 15 counts per second at $\psi = 0$, on the (212) peak.

Scans were run at 0.1° per minute for $\psi = 0, 45^\circ$, and 60° . Peak traces were manually smoothed. A three-point least squares parabolic curve fitting routine was used to locate peak centroids. A powder standard comprising an unsintered wafer of the experimental material was used throughout to check alignment and ψ rotation. At least two independent sets of measurements were performed on each specimen.

The lattice spacings measured for each material were averaged and plotted versus $\sin^2\psi$ in the form: $\Delta d/d_{\psi=0}$. The slope, m , of the best fit line joining these points indicated the stress state by the relationship:

$$\sigma_{\text{residual}} = m \left(\frac{E}{1+\nu} \right) \quad (2)$$

where the values of Young's modulus and Poisson's ratio for WC were used:

$$E_{\text{WC}} = 7.03 \times 10^8 \text{ MPa}$$

$$\nu_{\text{WC}} = 0.205$$

The uncertainties of the stress values so obtained is estimated to be about $\pm 10\%$.

3. Fracture Toughness

Measurements of the critical stress intensity factor for mode I crack opening, or K_{IC} , were made by the "short rod" method. This test is described by Barker⁽⁴³⁾, but the salient features will be reviewed in the following, along with the special conditions of its application in the present study.

The short rod fracture toughness specimen geometry is depicted schematically in Fig. 11. A crack is initiated at the tip of the "V" at a_0 by "popping in" under monotonic tensile loading. Due to the relationships between crack length, a ; crack width, b ; and specimen compliance, c ; crack extension during tensile loading occurs stably under the influence of the critical stress intensity. This stable growth continues until the position of specimen instability is reached. In Fig. 12, the locus of forces corresponding to a constant K_I is plotted versus crack length. The position of crack instability, a_c , in the short rod configuration is a constant; it does not vary with the K_{IC} of the specimen material.

In an actual test, the value of force required to propagate the crack past the position of instability, a_c , provides a measure of K_{IC} . Thus, the force to fracture the short rod specimen is related to K_{IC} by the proportionality:

$$K_{IC} = \left\{ \frac{AF_c}{(B)^{1.5} (1-\nu^2)^{\frac{1}{2}}} \right\} \quad (3)$$

where

F_c is the maximum force, i.e. the force at a_c ;

B is the specimen diameter;

and

ν is Poisson's ratio.

Figure 11. Schematic Diagram of Short Rod Fracture Toughness Specimen

Figure 12. Schematic Diagram of Force - Crack Length Relationship for a Condition of Constant Stress Intensity in the Short Rod Specimen.

The quantity "A" is the short rod dimensionless constant defined by:

$$A \equiv \left\{ \frac{B}{2b_c} \left[\frac{d(cEB)}{d(a/b)} \right]_{a=a_c} \right\}^{\frac{1}{2}} \quad (4)$$

where a_c is the value of crack length satisfying the relationship:

$$\left[\frac{d(cEB)/d(a/B)}{(a-a_0)} \right] = \left[\frac{d^2(cEB)}{d(a/B)^2} \right] \quad (5)$$

and:

c is the specimen compliance,

E is the Young's Modulus,

all other symbols are geometrical parameters (see Fig. 11).

To date, no analytical solution for the short rod specimen is available, owing to the complexity of the specimen geometry. Barker and Guest ⁽⁴⁴⁾, however, have solved the equations (4) and (5) through an empirical determination of the functional form of the compliance-crack length relationship:

$$cEB = \left\{ 38.80 + 6.531 (a/B) + 7.195 (3.301a/B) \right\} \quad (6)$$

Such that: $a_c = .839(B)$

and: $b_c = .322(B)$

resulting in a value for the constant:

$$A = 24.4 \pm 1.3$$

Subsequent round-robin evaluation ⁽⁴⁵⁾ of the short rod fracture

toughness test has resulted in a revision of the calibration constant to:

$$A = 22.0$$

This is the value used herein.

Plane strain conditions are met for specimen geometries such that:

$$B_{\min} = 2.5(K_{IC}/\sigma_{ys})^2 \quad (7)$$

This condition is readily met by the present study.

In the application of short rod testing for this work, reduced specimen tolerances were developed to minimize the geometrical-form-related uncertainties included in the data. Special fixturing was designed to enable grinding of specimens to these tolerances, which are shown in Fig. 13. Likewise, critical dimensions of the loading fixtures, shown in Fig. 14, were held to within 5 microns. An MTS model 812.11 servo-hydraulic test system was extensively modified and equipped with a non-contacting Class A laser extensometer to perform the fracture toughness testing. Although knowledge of the crack opening was not strictly required to determine the K_{IC} values, the test output was recorded in force versus strain (at the load face). The compliance information so obtained was useful in monitoring crack propagation up to the instability point.

To evaluate the statistical uncertainty of the short rod method as applied herein a 50 specimen test was run using the experimental WC-Ni alloy. Fracture toughness values determined in this test showed a standard deviation of $\sigma = 0.8\%$. On the basis of these results, the uncertainty of any single K_{IC} measurement in the study is taken as $\pm 1.6\%$.

4. Microstructure

Observations of microstructure with particular emphasis on defect structure were performed on thin foils using a JEOL model 100-CX Analytical Transmission Electron Microscope. Accelerating voltages of 100kV and 125kV were utilized. Some experiments used a hot stage accessory with this instrument.

Figure 13. Short Rod Specimen Tolerances Used in this Study

Figure 14. K_{IC} Loading Fixtures with Short Rod Specimen in Position

Specimen preparation included mechanical thinning by the procedure shown in Table 3. The same fixture used for x-ray specimens were utilized. Extreme caution was exercised in the handling of wafers to avoid bending. The 80 micron by 12.7 mm discs were then "cookie cut" to form 3 mm discs by electrical discharge machining. Finally, these were thinned by ion-beam milling in a Technics Mini-Micro Ion Mill. Thinning was achieved by two 100 mA beams of argon ions accelerated through 4-7 kV. The final stages of thinning were always conducted at 5kV or less. In the milling arrangement used, the 3mm specimen was rotated at 15 rpm while inclined at an angle of 15° to the opposing beams.

In all, 30 Foils were evaluated by transmission microscopy in this study.

Step	Cutting Agent	Grit Dimension	Final
#	(diamond)	(microns)	Specimen Thickness (mm)
1	saw	---	.62
2	resin-bonded wheel	15	.40
3	paste on Pellon	10	.45
4	"	7	.42
5	"	3	.40
6	"	1	.39
7	-- specimen remounted on opposite face		
8	resin-bonded wheel	15	.19
9	paste on Pellon	10	.14
10	"	7	.11
11	"	3	.09
12	"	1	.08
13	specimen finished on ion mill --to perforation		

Table 3. TEM Mechanical Thinning Procedure

III. RESULTS AND DISCUSSION

A. Bulk Properties

The bulk hardness level of the WC-Ni experimental alloy was not affected by fatigue on the scale examined. These results are plotted in Fig. 15. However, only rather large changes in hardness would have been detected by the approach used. The scatter characteristic of Diamond Pyramid Hardness measurements on cemented carbides (here, about ± 20 kg/mm²) and the small volume of fatigue-active phase combine to obscure the issue of whether cyclic hardening or softening is occurring in these composites under the conditions of fatigue tested. Strain controlled fatigue experiments would provide greater sensitivity for detection of changes in plastic behavior. For the present, these results suggest that fatigue cycling had little effect on bulk yielding behavior as reflected in hardness.

Similar results are observed in the residual stress data, shown in Fig. 16. The dotted line connecting the residual stress values represents a linear regression fit of these points, indicating a decrease in compressive stress of about 13% at the highest load level. The statistics of such a fit are poor, however. On the scale of interest, no significant change in the residual stress state of WC can be attributed to the fatigue conditioning programs of this study.

The scale of fracture toughness change with fatigue is like that of residual stress, but due to the greater sensitivity of the K_{IC} testing, some significant effects are observable. Plotted in Fig. 17 are the average K_{IC} values from each fatigue level; each point represents 6 to 12 specimens. The error bars shown correspond to the 2σ values of the scatter in each group. It is felt that both the increase in K_{IC} values

Figure 15. Bulk Hardness vs Fatigue Stress Amplitude (10^6 cycles)

Figure 16. Residual Stress in WC vs Fatigue Stress Amplitude (10^6 cycles).

Figure 17. Fracture Toughness vs Fatigue Stress Amplitude. (10^6 cycles)

and the variation in data scatter with fatigue level correspond to real effects. In the following discussion, they are correlated with microstructural changes observed by TEM. In general, the effects of fatigue on structure are very local in character. This localization affects the way transitions in dislocation behavior are observed from specimen to specimen, resulting in increased data scatter at inflections in the curve of Fig. 17. Another indication of the local character of fatigue damage accumulation was obtained from the nature of stable crack growth during K_{IC} testing. For unfatigued specimens, the load vs. crack opening plot exhibited smooth curvature. At the highest fatigue levels, however, very uneven crack propagation was evidenced by a superimposed roughness to this plot. This irregular crack propagation was attributed to fatigue-generated regions of inhomogeneity in the binder phase.

B. Microstructure

The changes in crack propagation behavior indicated by fracture toughness testing were not observable by scanning electron fractography. Fracture surfaces of unfatigued specimens were indistinguishable from those of even the highest level of fatigued material. Shown in Fig. 18 is a typical fracture surface of the WC-Ni composite. Crack propagation is by dimple rupture of the binder with widespread cleavage of the larger WC grains. Also, there is no apparent difference between this fracture mode and that which would be observed in a WC-Co cemented carbide of the same binder fraction and grain size.

Study of the experimental alloy by TEM has revealed microstructural features typical of a cemented carbide. Figures 19-21 show binder areas of the unfatigued material. The nickel binder is not single phase but contains fine precipitates about 100 Å in size. Unambiguous electron diffraction evidence could not be obtained for this particular alloy to establish the identity of the precipitate particles, but it is thought that they are a cubic (high temperature) form of WC stabilized by partial coherency with the nickel lattice. If so, their size may be somewhat smaller than estimated, since the bright field contrast would be attributable in part to coherency strain in the nickel lattice. The interaction of dislocations with these precipitates becomes important in evaluation of fatigue processes, so some further consideration of their identification is called for.

Fine precipitates giving rise to bright field contrast but which lack sufficient volume to be detected in electron diffraction patterns are not uncommon. For example, Krawitz⁽⁴⁶⁾ studying precipitation in

Figure 18. Typical Fracture Surface of the WC-Ni Cemented Carbide alloy. Secondary Electron Images

Figure 19. Binder Region. Zero Load. $[123]$ Zone.

Figure 20. Binder Region. Zero Load. $[112]$ Zone.

Figure 21. Binder Region. Zero Load. $[112]$ Zone.

Figure 22. WC. Grain. Zero Load.

(Fe-Mo-N) and (Fe-V-N) by x-ray diffraction and electron microscopy observed such an effect. In cemented carbide systems, precipitates similar to those visible in Figures 17-19 have been frequently observed. Viswanadham, et.al.⁽⁴⁷⁾ working with (Ti,V)C + Ni cemented carbides have reported semi-coherent precipitates about 200 Å in size and having the same structure (cubic, rocksalt) as the primary (V, Ti)C phase. They were able to determine the orientation relationship of the carbide precipitate with the matrix as:

$$\begin{aligned} (111) \text{ Ni} & \parallel (002) \text{ precipitate} \\ [\bar{1}\bar{1}0] \text{ Ni} & \parallel [\bar{1}\bar{1}0] \text{ precipitate} \end{aligned}$$

In studies with a WC + (Ni, Al) cemented carbide⁽⁹⁾, precipitate spots on electron diffraction patterns have been identified by dark field imaging and indexed as the β -WC (cubic, rocksalt) phase. They were found to bear a relationship with the nickel matrix:

$$\begin{aligned} (111) \text{ Ni} & \parallel (002) \beta\text{-WC precipitate} \\ [110] \text{ Ni} & \parallel [011] \beta\text{-WC precipitate} \end{aligned}$$

Fig. 23 shows a typical pattern from the WC + (Ni, Al) material. (Unindexed spots are from Ni_3Al precipitates).

In the present study, only very limited diffraction information was obtainable for the precipitates. Also shown in Fig. 23 is a very weak selected area diffraction pattern (SADP) of the alleged precipitate in the experimental alloy showing the correspondence with WC + (Ni, Al) material for which clearer diffraction evidence exists. In the following section, other diffraction data from this precipitate phase will be discussed in conjunction with fatigue damage.

Figure 23. Diffraction Patterns of Nickel Binder Cemented Carbides Showing Evidence of β -WC Precipitate:
[$\bar{1}14$] Zone Ni; [011] Zone β -WC. *Left: WC + (Ni, Al), Right: WC + Ni.
(*Courtesy Reed Research)

Though the cited evidence supports the proposed precipitate identification, it should be noted that consideration has been given to the possibility of radiation-damage contrast effects which might have resulted from the ion milling used as a final step in foil thinning. This question has been raised although other investigators have used ion milling to prepare cemented carbide foils with no experience of ion damage effects^(28,35,47). Some quantitative insight into the question can be gained from the data of Brice⁽⁴⁸⁾. He found that 5kV P ions (mass 31) penetrate Si to a depth of 29Å, and 5kV Zn ions (mass 65) to a depth of 20Å. By interpolation, Ar ions (mass 40) should penetrate Si about 25Å. For the case of Ni, the 5kV argon ion beam used herein is therefore expected to penetrate less than 20Å. Moreover, since the angle of incidence is not normal, this value is more realistically about 5-10Å. Thus the damage, if any, comprises a very thin amorphous layer on both surfaces of the specimen. In no manner could such a layer give rise to artifacts which appear as 100Å precipitates and which yield (albeit weak) diffraction patterns. Finally, the interstitialcies associated with ion damage are very mobile. Hot stage experiments with the experimental material revealed no evidence whatever of annealing interstitialcies. Foils were heated to 650°C in the TEM with no precipitate contrast alteration prior to oxidation of the binder areas.

The nascent dislocation structure of the binder and WC phases is also revealed in Figures 19-22. Dislocation densities were estimated from areal counts of surface intersections. Averaged values so obtained were 10^7 - 10^8 cm⁻² for the WC and 10^8 - 10^9 cm⁻² for the binder. Dislocations in the WC phase were probably grown-in or result from HIP'ing, whereas binder dislocations appear in some cases to have

come about from cooling strains, as well as from HIP'ing or solidification. Fig. 19 shows a typical binder region bounded by WC (dark region) and showing precipitate contrast with a scattering of dislocations. Fig. 20 depicts a binder area with ppts. in sharper contrast. The banding of ppts. which is occasionally observed is thought to correspond to solute fluctuations resulting from irregular solidification front motion during sintering. The curvature of these bands conforms to adjacent WC grains (not visible in Fig. 20). Fig. 21 shows another binder area at high magnification with a group of dislocations gliding on parallel slip planes. These dislocations are thought to result from plastic response to cooling or HIPing of the binder.

Finally, Fig. 22 is a WC grain with dislocations and stacking faults. These were likely connected in a nodal structure cut by the foil thinning. This Figure shows relatively more dislocation line than normally viewed in random sampling of WC grains.

C. Fatigue effects

In the following discussion fatigue groups will be designated by level or in thousand pound per square inch units (KSI) for convenience.

The corresponding SI units are given:

<u>Level</u>	<u>KSI</u>	<u>MPa</u>
I	40	276
II	80	552
III	120	827
IV	160	1103
V	200	1379
VI	250	1724
VII	270	1862

No effects of fatigue on the WC phase were detected in this study. Figures 24 and 25 show WC dislocation structures observed in 40 and 200 KSI specimens, respectively. In Fig. 25 the network exists near a WC triple point. However, there is no indication that these dislocation networks were produced by plastic strain, nor was there any noticeable increase in the frequency or extent of such networks with fatigue stress.

In the binder phase, strain effects were evident from the lowest fatigue level, where dislocation density increased by about an order of magnitude, to the highest level which possessed dislocation densities on the order of 10^{11} to 10^{12} per cm^2 . Over the range tested, the character of dislocation structure went through several changes as well. It should also be emphasized that the fatigue response of individual binder areas was not at all homogeneous. The reported characterizations

Figure 24. WC Grain. 40 KSI Fatigue Level.

Figure 25. WC Grain. 200 KSI Fatigue Level

of fatigue levels and trends in behavior are generalizations based on numerous samples and binder areas. In actual practice, stress variations related to local arrangements of grains result in a variety of conditions among binder regions in any proximity.

Binder dislocation observations on specimens from fatigue levels I and II were very similar. Typical binder regions show planar arrays of dislocations gliding on parallel planes. As is evident in Figures 26 and 27, several slip systems are usually active. Internal sources of inclusions are not evident in these composites, but rather as described by Murr⁽⁴⁶⁻⁴⁸⁾ for polycrystals, principal sources of dislocations are grain boundary ledges. Viswanadham⁽⁴⁹⁾, has found evidence for such grain boundary ledge sources in cemented carbides, in studies of (V,Ti)C + (Ni,Mo) alloys. In the WC+Ni alloy of this study, numerous trains of parallel dislocations were observed as shown in Fig. 27. These apparently are omitted from the same ledge or adjacent ledge sources. Fig. 28 shows a WC-Ni grain boundary containing an active source. These arrays are not to be confused with pileups which are not in any event likely in a high stacking fault-energy material such as nickel. Their distinct character is evidenced by a lack of definite spacing exhibited by true pileups.

In fatigue level III (120 KSI) there is a general increase in dislocation debris such as in Fig. 29, usually residing near WC boundaries. Of greater interest, however, is the emergence of a feature which is thought to correspond to the increase in K_{IC} scatter at this level as shown in Fig. 17. These features are local bands of intensified slip. Shown in Fig. 30 is such a band, paralleling the WC grain at the lower right-hand corner of the micrograph. The long slightly curved slip

Figure 26. Binder Region. 40 KSI Fatigue Level. $[\bar{1}23]$ Zone

Figure 27. Binder Region. 40 KSI Fatigue Level. $[\bar{1}23]$ Zone

Figure 28. Binder Region. 40 KSI Fatigue Level. $[123]$ Zone

Figure 29. Binder Region. 120 KSI Fatigue Level. $[011]$ Zone.

Figure 30. Binder Region. 120 KSI Fatigue Level.

Figure 31. Binder Region. 120 KSI Fatigue Level. [011] Zone

traces occupy areas of reduced precipitate population. This characteristic is even more evident in the binder region shown in Fig. 31. In Fig. 32, extended trains of dislocations can be seen in association with these slip traces. The influence of the WC grain (dark contrast) on their morphology is obvious.

These bands of intense slip are the incipient stages of precipitate-free bands which develop more fully at fatigue levels IV and V. The local passage of a large number of dislocations apparently cuts and fragments the precipitates, resulting in re-solution by reduction of precipitate size to below the critical radius and eventual re-precipitation. Though carbon atoms are adequately mobile, for appreciable growth to occur at the temperature of this testing ($<35^{\circ}\text{C}$), transport of W atoms must be assisted by defect motion. The fine, linear contrast of slip traces in Figures 30-32 is thought to be due to compositional inhomogeneity resulting from this process. Also in Fig. 32 is what appears to be some decoration of dislocations by re-precipitation.

The development of precipitate-free bands in fatigue is not an unprecedented observation. A number of investigators have reported this phenomenon in various multiphase materials⁽⁵⁰⁾. Notably, Clark and McEvily⁽⁵¹⁾ working with precipitation-hardening Al-4%Cu found that precipitate-free zones developed when GP-2 zones were present. Thermal treatments resulting in GP-1 zones or θ' precipitation give rise to other dislocation interactions.

At fatigue levels IV and V, the precipitate-free zones become more prevalent, more distinct, broader, and in some instances encompass whole binder regions as more slip systems are activated. Shown in Fig. 33 is an example of re-precipitation along (111) planes where an entire binder

Figure 32. Binder Region. 120 KSI Fatigue Level. $[112]$ Zone

Figure 33. Binder Region. 160 KSI Fatigue Level. $[011]$ Zone.
(111) Traces Indicated.

Figure 34. Binder Region. 200 KSI Fatigue Level. $[013]$ Zone.

Figure 35. Binder Region of Figure 34. 200 KSI Fatigue Level. $[013]$ Zone

region has had its precipitate morphology altered by dislocation activity.

The micrograph of Fig. 34 shows a binder area from a level V (200 KSI) specimen containing a well-developed precipitate-free zone. The adjoining WC grains harbor areas of unperturbed precipitate as well as dislocation debris. Fig. 35 examines the swept zone in closer detail. Dislocations pinned by precipitates are visible in the boundary to the free zone. Selected area diffraction patterns of the precipitate free zone and the adjacent unaffected binder region are compared in Fig. 36. Unlike the area showing precipitate contrast, the precipitate free zone exhibits rings believed to derive from randomly oriented microcrystals of β -WC. An additional subtle difference between these two areas of the same binder grain is that the Ni lattice parameter of the swept zone is about 3% larger than the other, suggesting lattice dilation associated with an increased solute level. Although a difference of 3% would normally be within the uncertainty of an electron diffraction lattice parameter measurement, in this case it is somewhat less tenuous a measurement because of the proximity in time and space, and the unaltered operating conditions of the microscope.

Fatigue level V marks the end of precipitate-free zone phenomena and corresponds to the end of the K_{IC} transition observed in Fig. 17. At level VI (250 KSI), the precipitate morphology has been almost completely transformed and for the first time dislocation dipoles are observed. Figures 37 and 38 depict typical tangles which occur at this level. In the center of Fig. 37 is what appears to be a deformation-produced micro-twin, examples of which were observed in other specimens at this level. Also, in Fig. 38 at the edge of the dark area in the upper-right-hand corner is what seems to be the beginning of

Figure 36. Selected Area Diffraction Patterns from Figure 32 Binder Area: $[013]$ Zone. Left: Precipitate-Free zone, Right: Precipitate contrast area next to WC grain.

Figure 37. Binder Area. 250 KSI Fatigue Level. $[011]$ Zone.

Figure 38. Binder Area. 250 KSI Fatigue Level. [011] Zone.

Figure 39. Binder Area. 270 KSI Fatigue Level. [001] Zone.

dislocation "clumping" normally associated with low-strain fatigue.

Finally, at the highest fatigue level prior to catastrophic failure of the specimen (270 KSI) another development is observed. This is the appearance of long, cross-slipping dislocations occupying relatively open areas between partially developed cell walls. Examples of this are shown in Figures 39-41. In particular, dislocation sub-structure is apparent in Fig. 41 where clumps are organizing into discontinuous cell walls along boundaries of dark contrast.

The effect of the WC grains in limiting cell formation seems rather clear. Cell dimensions are of necessity several tenths of a micron or less and walls are rather discontinuous. In one level VII specimen an uncommonly large binder area of 10-15 microns in size was observed. In this binder pool, a more highly developed cell structure had occurred. Two portions of this region are shown in figure 42 and the high magnification micrograph of Fig. 43. Although it is difficult to estimate from so limited a region, the cell size in this area seem to be on the order of one micron.

In general, the binder dislocation behavior observed in the experimental alloy at the highest stress levels can be said to be representative of low-strain fatigue characteristics in pure metals and alloys. However, the appreciable effect of carbide grains on the plastic response of binder regions seems a serious caution to any direct transfer of phenomenology. It is not clear how the observed development of fatigue damage leads to crack nucleation; the development of persistent slip bands - at least in the form observed in metals and alloys - is not possible in cemented carbides. Rather, the effects of fatigue on these materials are highly localized on a scale of WC-grain size. This study

Figure 40. Binder Region. 270 KSI Fatigue Level. $[112]$ Zone.

Figure 41. Binder Region. 270 KSI Fatigue Level. $[112]$ Zone.

Figure 42. Binder Region. 270 KSI Fatigue Level. $[112]$ Zone.

Figure 43. Binder Region. 270 KSI Fatigue Level. $[112]$ Zone.

further suggests that the damage accumulation events can change character over a relatively small range of stress.

Finally, it is prudent to consider that the results presented here pertain to unreversed stress on a macroscopic scale. While the binder phase - presumed to be in essentially hydrostatic tension - may undergo stress reversal in compressive loading, the narrow hysteresis loops obtained in reloading of strain-gaged specimens suggest that after the initial strain hardening comparatively little plastic work is being absorbed in fatigue. It is possible that the hysteresis loops of fully reversed loading may differ considerably from this situation, reflecting plastic strains on the order of the initial response. If so, fatigue damage accumulation would be more rapid and probably would be dominated by dislocation structures of other types.

IV. CONCLUSIONS

Fatigue damage of the experimental WC+Ni cemented carbide accrues in the binder phase only. Fatigue-induced changes in binder dislocation structure were observed after one million cycles at all stress levels tested. These changes have been generalized by appropriate sampling, but fatigue damage was characteristically local, varying with structure on the scale of the carbide grains. At 40 and 80 KSI levels, dislocation densities were increased from an un-fatigued value of 10^{7-8}cm^{-2} to 10^{8-9}cm^{-2} by grain-boundary-ledge production of planar arrays. Precipitate-dislocation interactions at 120, 160, and 200 KSI levels resulted in the development of regions of intensified slip and precipitate-free-bands which increased in definition and extent with increasing stress. At the 250 KSI level, the binder precipitate structure appeared to be completely modified, and dislocation dipoles and tangles were observed, with some incipient clumping evident. Dislocation densities of 10^{10-11}cm^{-2} had developed progressively up to the 270 KSI level. In this highest stress level, poorly defined cell walls were found whose central regions were often populated by long, cross-slipping screw dislocations.

Throughout the stress range observed, fatigue effects in the binder were peculiar to the composite nature of the material, reflecting the influence of the carbide phase in dislocation production, motion, and development of sub-structure. In instances where composite conditions were relaxed, as in an anomalous binder "pool", dislocation structures more typical of "homogeneous" alloys began to emerge.

The effect of fatigue on bulk properties was minimal. No appreciable effect on bulk hardness or residual stress in the carbide

phase was observed. Small increases in fracture toughness (K_{IC}) were measured on fatigued specimens and correlated with fatigue-induced changes in binder microstructure.

The role of fatigue in fracture of a WC-Ni cemented carbide is thus concluded to be binder-intensive and predominantly local in character: it constitutes a source of incipient defects and a means of stable propagation of flaws -- though in this study, only a few of the mechanisms of these processes have been illuminated. This local view of fatigue is thought to have general applicability to rock-drilling cemented carbides with the following qualification. Cemented carbides possessing meta-stable binders capable of undergoing strain-induced phase transformation may exhibit a significantly different fatigue behavior, including appreciable changes in hardness, residual stress, and fracture toughness. Fatigue damage processes in such systems would retain all of the local aspects cited herein; in fact, as a structural response of a higher order than that of defect arrangement, a martensitic reaction could either ameliorate or exacerbate local mechanical instability, depending on the stress state required for initiation, the magnitude of the dilation, and the plastic behavior of the new phase. In addition, however, fatigue-induced phase transformation of the binder phase has a potential effect on bulk fracture behavior as well. This can occur through long-range stress field modification about a crack by residual stress re-distribution and/or by change in the volume summation over the micro-plastic behavior inherent to cemented carbide composites.

REFERENCES

1. P. Schwarzkopf and R. Kieffer, Cemented Carbides, MacMillan, N.Y., 1960.
2. S. S. Yen, M. S. Thesis, Lehigh University, 1971.
3. J. L. Chermant, A. Deschanvres, and A. Iost, Fracture Mechanics of Ceramics, Volume I, Ed. R. C. Bradt, Plenum Press, 1974, p. 346.
4. R. C. Lueth, PhD Thesis, Michigan State University, 1972.
5. N. Ingelstrom and H. Nordberg, Engineering Fracture Mechanics, 6, 597, (1974).
6. J. L. Chermant and F. Osterstock, Journal of Materials Science, 11, 1939, (1976)
7. J. R. Pickens, PhD Thesis, Brown University, 1977.
8. M. J. Murray, "Fracture of WC-Co Alloys: An Example of Spatially Constrained Crack Tip Opening Displacement", Report of CSIRO Div. of Tribophysics, Melbourne, Australia, 1976.
9. Unpublished research - Reed Tool Company.
10. J. Gurland, Transactions of the ASM, 50, 1063, (1958).
11. S. Öhman, E. Pärnama, and S. Palmqvist, Jernkonterets Annaler, 151 126, (1967).
12. D. N. French, Journal of the American Ceramic Society, 52, 271, (1969).
13. D. N. French, Journal of the American Ceramic Society, 52, 271, (1969).
14. J. Dubois, C. Mai, and R. Rivière, Zeitschrift für Metallkunde, 65, 130, (1974).
15. A. Hara, M. Megata, and S. Yazu, Powder Metallurgy International, 2, 43, (1970).
16. B. O. Jaensson, Materials Science and Engineering, 8, 41, (1971).
17. P. O. Snell and E. Parnama, Planseeberichte für Pulvermetallurgie, 21, 271, (1973).
18. S. I. Spirina, B. M. Sverdlova, and N. I. Spirina, trans from Problem Prochnosti, 9, 60, (1975).
19. A. D. Krawitz, presented at 7th NSF Hard Materials Workshop, (1979), to be published.
20. W. Dawidl and T. Hinnuber, Kolloid, 20, 233, (1943).

21. J. Gurland and J. T. Norton, *Journal of Metals*, 4, 1051, (1952).
22. R. P. Felgar and J. D. Lubahn, *Proceedings ASTM*, 57, 770, (1957).
23. T. Takahashi and E. J. Freise, *Philosophical Magazine*, 12, 1, (1965).
24. D. N. French and D. A. Thomas, *Transactions of the Metallurgical Society of the AIME*, 233, 950, (1965).
25. T. Johanneson and B. Lentinen, *Physica Status Solidi*, 16, 615, (1973).
26. S. B. Luyckx, *Acta Metallurgical*, 16, 535, (1968).
27. R. Arndt, *Zietschrift für Metallkunde*, 63, 274, (1972).
28. V. K. Sarin and T. Johanneson, *Metal Science*, 9, 472, (1975).
29. H. Doi, Y. Fujiwara, and K. Miyake, *Transactions of Japan Inst. Metals*, 9, 616, (1968).
30. H. Doi, Y. Fujiwara, and K. Miyake, *Transactions of the Metallurgical Society of AIME*, 245, 1457, (1969).
31. D. Moskowitz, Modern Developments in Powder Metallurgy, Vol. 10, 543 Princeton, 1977.
32. H. Suzuki, *Transactions of Japan Inst. of Metals*, 7, 112, (1966)
33. J. Gurland, *Transactions of the Metallurgical Society of the AIME*, 227, 1146, (1963).
34. D. N. French, *International Journal of Powder Metallurgy*, 5, 47, (1969).
35. N. K. Sharma and W. S. Williams, presented at 7th NSF Hard Materials Workshop, (1979).
36. W. Dawihl, *Stahl und Eisen*, 40, 909, (1941).
37. I. Johansson, G. Persson, and R. Hiltcher, *Powder Metallurgy*, 13, 440, (1970).
38. C. M. Perrott, research of CSIRO Div. Tribophysics, to be published.
39. M. Hansen, R. P. Elliot, and F. A. Shunk, Constitution of Binary Alloys, 2nd Ed. with Supplements, McGraw-Hill, N.Y., 1969.
40. W. B. Pearson, Handbook of Lattice Spacings and Structure of Metals, Pergamon Press, N.Y., 1958.
41. Z. Hashin and S. Shtrikman, *Journal of Applied Physics*, 33, 3125, (1962).
42. M. R. James and J. B. Cohen, Northwestern University - Dept. of Materials Science Report #21, (1968), to be published in Experimental Methods of Materials Science, Vol 1.

43. L. M. Barker, Engineering Fracture Mechanics, 9, 361, (1977).
44. L. M. Barker and R. V. Guest, "Compliance Calibration of the Short Rod Fracture Toughness Specimen", Report TR 28-20 of Terra Tek to the National Science Foundation, (1978).
45. L. M. Barker and F. I. Baratta, Report on contract #DAAG 46-78-C-0040 for the Army Materials and Mechanics Research Center (1979).
46. L. E. Murr, R. J. Horylev, and W. C. Lin, Philosophical Magazine, 22, 515, (1970).
47. L. E. Murr, Applied Physics Letters, 24, 533, (1974).
48. L. E. Murr, Metallurgical Transactions, 6A, 505, (1975).
49. R. K. Viswanadham, Metallurgical Transactions, 10A, 1631, (1979).
50. W. J. Plumbridge and D. A. Ryder, Metallurgical Reviews, 14, 119, (1969).
51. J. B. Clark and A. J. McEvily, Acta Metallurgica, 12, 1359, (1964).
52. E. Lardner and M. B. McGregor, Journal of the Institute of Metals, 80, 369, (1951).
53. Metals Handbook Vol 1, 1118 American Society for Metals, Metals Park, Ohio, 1961.
54. V. A. Phillips, Philosophical Magazine, 16, 103 (1967).