A high-performance hybrid bismuth/carbon nanotube-based contrast agent for X-ray CT imaging

Mayra Hernández-Rivera^a, Ish Kumar^a, Stephen Y. Cho^a, Benjamin Y. Cheong^b, Merlyn X. Pulikkathara^c, Sakineh E. Moghaddam^a, Kenton H. Whitmire^a, and Lon J. Wilson^{a}*

^aDepartment of Chemistry MS-60, Rice University, P.O. Box 1892, Houston, TX, 77005

^bCHI St. Luke's Health - Baylor St. Luke's Medical Center, 6720 Bertner Ave., MC 2-270
Houston, TX 77030

^cBaylor College of Medicine, 1 Baylor Plaza, Houston, TX, 77030

Keywords: carbon nanotubes, bismuth, X-ray CT, radiocontrast agent

Carbon nanotubes (CNTs) have been used for a plethora of biomedical applications including their use as delivery vehicles for drugs, imaging agents, proteins, DNA, and other materials. Here we describe the synthesis and characterization of a new CNT-based contrast agent (CA) for X-ray computed tomography (CT) imaging. The CA is a hybrid material derived from ultra-short single-walled carbon nanotubes (20-80 nm long, US-tubes) and Bi(III) oxo-salicylate clusters with four Bi(III) ions per cluster (Bi₄C). The element bismuth was chosen over iodine, which is the conventional element used for CT CAs in the clinic today, due to its high X-ray attenuation capability and its low toxicity, which make bismuth a more promising element for new CT CA design. The new CA contains 20% by weight bismuth with no detectable release of bismuth

after a 48 h challenge by various biological media at 37 °C, demonstrating the presence of a strong interaction between the two components of the hybrid material. The performance of the new Bi₄C@US-tubes solid material as a CT CA has been assessed using a clinical scanner and found to possess an X-ray attenuation ability of > 2000 Hounsfield units (HU).

1. Introduction

X-ray computed tomography (CT) is one of the most widely used imaging techniques in diagnostic medicine due to its many advantages, which include cost effectiveness, deep tissue penetration, and high spatial resolution.^{1,2} CT was introduced for the first time in 1972 as the first of the modern slice-imaging modalities.³ Today, true volume imaging of the full body or individual organs can be attained in 5 to 20 seconds with sub-millimeter isotropic resolution.² When using X-ray modalities, hard tissues (bone and cartilage) are easily distinguishable from surrounding soft tissues. However, the difference in contrast between different soft tissues is sometimes very small and contrast agents (CAs) are required to achieve satisfactory detailed images. X-ray CAs (or radiocontrast agents) are used to provide transient contrast enhancement in X-ray-based imaging techniques such as radiography, CT, and fluoroscopy. Contrast enhancement comes largely from the photoelectron effect due to the high atomic number of some elements. As a rule, materials possessing high densities (ρ) and high atomic numbers (Z) absorb X-rays better. The X-ray absorption coefficient (μ) expresses the relationship between the X-ray absorption phenomenon and atomic number,

$$\mu = \frac{\rho Z^4}{AE^3}$$

where A is the atomic mass of the element and E is the incident X-ray energy.^{2,4} Because Z is raised to the fourth power, a small increase in Z will result in a significant increase in μ . Thus, CAs

containing heavier elements have greater μ , which allows for greater X-ray attenuation. The ability of matter to attenuate X-rays is measured in Hounsfield units (HU). By definition, water has a HU value of 0, and air has a value of -1000 HU, with most soft tissues falling between 30 -100 HU. The HU of a material with a linear μ is defined as;⁴

$$\text{HU} = \frac{(\mu - \mu_{\text{water}})}{\mu_{\text{water}}} \times 1000$$

The use of CAs with good X-ray attenuation (high HU values) improves the quality of the images which facilitates the process of distinguishing regions of interest. Currently, there are two types of X-ray CAs approved for human use: barium sulfate suspensions ($Z_{\text{Ba}} = 56$, for gastrointestinal tract imaging) and small, water-soluble iodinated molecules ($Z_{\text{I}} = 53$, for vascular imaging),⁵ however, their X-ray attenuation is far from optimal. The use of barium and iodine as X-ray CAs is mostly based on historical reasons and because they both have proven to have good safety profiles.^{2,4-6} Here we report the use of a new bismuth ($Z_{\text{Bi}} = 83$) nanomaterial as a new X-ray CA. Besides having a high atomic number, bismuth has been used for a number of drug and cosmetic formulation,⁷⁻⁹ and its safety has been extensively evaluated and verified.^{10,11} The new CA is a hybrid material composed of carbon nanotubes (CNTs) and a Bi(III) oxo-salicylate cluster.

CNTs can be described as carbon nanostructures of graphene sheets rolled up in a tubular shape. These materials are of great interest now days because of their novel electrical, optical, mechanical and thermal properties.^{12,13} Single-walled carbon nanotubes (SWCNTs) are derived from one single sheet, while multi-walled carbon nanotubes (MWCNTs) are composed of 2 – 30 concentric SWCNTs. In the biomedical field, both SWCNTs and MWCNTs have been shown to be promising materials as delivery vectors for drugs (therapeutic applications) and imaging agents (diagnostic and tracking applications), among others.¹⁴⁻¹⁶ Many different nanoparticles are being explored for such application, however, the special interest in CNTs is based on their high aspect ratio,

biocompatibility,^{17–19} and the capability to be chemically functionalized,^{20–23} while remaining relatively inert.¹⁶ CNTs have been previously used as CAs for different clinical imaging modalities^{24,25} such as magnetic resonance (MR),^{26–30} ultrasound,^{31,32} fluorescence imaging in the near infrared (NIR) region,^{33–35} Raman scattering,^{36,37} photoacoustic,^{31,38–40} thermoacoustic,^{31,41} CT^{42,43}, positron emission tomography (PET),^{44,45} and single-photon emission computed tomography (SPECT) imaging.^{46,47}

In previous work, Wilson and coworkers reported the first CNT-based CA material for X-ray CT imaging that contained Bi³⁺ ions within the cavities of ultra-short SWCNTs (US-tubes).⁴² That material, designated as Bi@US-tubes, contained only 2 – 3% bismuth by weight. Here we describe the successful synthesis and characterization of a second generation CNT-based CA for CT consisting of US-tubes and Bi(III) oxo-salicylate clusters containing four Bi³⁺ ions/cluster (Bi₄C). The structure of the Bi₄C cluster is shown in Figure S1, and the preparation of the new Bi₄C@US-tubes CA is shown schematically in Figure 1. The new CA formulation contains 20% bismuth by weight, which represent an order-of-magnitude of improvement in X-ray attenuation capability over the first generation material.⁴²

Figure 1. Production of the Bi(III) oxo-salicylate cluster@US-tube ($\text{Bi}_4\text{C@US-tube}$) X-ray CT CA with THF as the solvent.

2. Experimental Methods

2.1 Synthesis of $\text{Bi}_4\text{C@US-tubes}$

US-tubes were produced by first cutting SWCNTs ($> 1 \mu\text{m}$, Carbon Solution, Inc.) via a fluorination/pyrolysis method described elsewhere.⁴⁸ Briefly, 600 mg of SWCNTs were exposed to 2% F_2 in a He gas mixture simultaneously with a flow of H_2 gas, both at a flow rate of $15 \text{ cm}^3/\text{min}$ at 125°C for $\sim 10 \text{ h}$. A 30 to 40% weight increase was obtained after the fluorination process. The fluorinated SWCNTs were then pyrolyzed at 1000°C for 2 h under constant Ar flow. This cutting process reduces the amount of metal impurities (nickel and yttrium catalyst) to $< 3\%$, while creating defect sites along the CNTs sidewalls. The produced ultra-short SWCNTs (US-tubes) were then purified by bath sonication in concentrated $\text{HCl}_{(\text{aq})}$ for 1 h (1:1 ratio of US-tubes

(mg) to $\text{HCl}_{(\text{aq})}$ (mL)) to remove metal impurities and amorphous carbon. The purified US-tubes were then individualized by Na^0 reduction in dried THF (1 h, bath sonication). Finally, the individualized US-tubes were refluxed in 6 M $\text{HNO}_{3(\text{aq})}$ for 10 min to functionalize the ends and defect sites with carboxylate groups. The US-tubes were then extensively washed with distilled water and dried at 120 °C overnight.

Synthesis of the $[\text{Bi}_4(\mu_3\text{-O})_2(\text{HO-2-C}_6\text{H}_4\text{CO}_2)_8]\cdot 2\text{MeCN}$ cluster (Bi_4C , Figure S1), a tetranuclear oxo cluster with a planar Bi_4O_2 core, was performed by mixing $\text{BiPh}_{3(\text{s})}$ with salicylic acid in wet acetonitrile and left under vacuum for 48 h for solvent removal as described elsewhere.⁴⁹ 20 mg of the Bi_4C cluster were dissolved in 20 mL of either dried tetrahydrofuran (THF), ethanol (EtOH), or dimethyl sulfoxide (DMSO), and 20 mg of US-tubes were added to the mixture followed by bath sonication for 1 h. The resulting material was washed with 400 mL of the respective solvent used (THF, EtOH, or DMSO) to remove any free Bi_4C cluster, followed by 1.6 – 2.0 L of distilled water to remove the organic solvent from the material. Lastly, the produced Bi(III) oxo-salicylate cluster@US-tube ($\text{Bi}_4\text{C@US-tube}$) material was dried overnight at 120 °C for characterization.

2.2 Characterization of $\text{Bi}_4\text{C@US-tubes}$

Nuclear magnetic resonance spectra (NMR, Bruker 400 MHz NMR spectrometer) of the Bi_4C cluster was taken before and after sonication in THF for 1 h to determine if sonication modified the structure of the cluster. Samples were sonicated in THF for 1h, followed by removal of the solvent by rotovaporation. NMR spectra were obtained using $\text{d}_6\text{-DMSO}$ as the solvent.

Atomic force microscopy (AFM, Digital Instruments MultiMode AFM-2) was used to evaluate the length of the SWCNTs after the cutting process. Raman spectroscopy was performed using a Renishaw® inVia Raman Microscope equipped with a 633 nm laser.

The presence of Bi^{3+} ions in the $\text{Bi}_4\text{C}@\text{US}$ -tube samples were confirmed by inductively-coupled plasma-optical emission spectrometry (ICP-OES, Optima 4300 from PerkinElmer, Inc.) and by X-ray photoelectron spectroscopy (XPS, PHI Quantera SXMTM). To analyze the material using ICP-OES, the solid was digested in acidic solution. Briefly, the material was weighed, transferred to scintillation vials, digested with two alternate additions of 26% $\text{HClO}_{3(\text{aq})}$ and 70% $\text{HNO}_{3(\text{aq})}$ trace-metal grade, and then diluted with 2% $\text{HNO}_{3(\text{aq})}$ trace-metal grade. A solution of 5 ppm Y^{3+} was used as the internal standard. Prior to this, different acids were used for the digestion of a Bi^{3+} standard to determine which one provides the most complete digestion of the organic matter without affecting the Bi^{3+} concentration (Figure S4). Samples for XPS were prepared by pressing a small amount of the solid material into indium foil.

Thermogravimetric analysis (TGA) was performed using a SDT Q600 instrument. TGA experiments were conducted under a flow of air at 100 mL min^{-1} with a heating rate of $10 \text{ }^\circ\text{C min}^{-1}$ from 50 to $800 \text{ }^\circ\text{C}$. Electron microscopy techniques were utilized to examine the structure of the $\text{Bi}_4\text{C}@\text{US}$ -tubes. High-resolution transmission electron microscopy (HR-TEM) experiments were performed by depositing a drop of a suspension of the material diluted in water, followed by placing a drop of the dispersed material onto a Lacey carbon copper grid. The solvent was evaporated and the sample was analyzed using a JEOL 2100 Field Emission Gun Transmission Electron Microscope. Energy dispersive spectroscopy (EDS) analyzes were collected on the same instrument in scanning transmission electron microscope (STEM) mode. STEM images were obtained using a Hitachi SU8230 scanning electron microscope (SEM) instrument equipped with Brker Flatquad EDS. STEM experiments were performed by depositing a drop of a suspension of the $\text{Bi}_4\text{C}@\text{US}$ -tube material suspended in water onto a TEM Lacey carbon copper grid operated at 30 kV.

2.3 Biological stability studies

The biological stability of the Bi₄C@US-tubes material was explored by challenging the material with biologically-relevant media. Solid samples of Bi₄C@US-tubes were placed in centrifuge filter tubes (MilliporeTM) containing either phosphate-buffered saline (PBS) or α -minimum essential medium (α MEM) with 10% fetal bovine serum (FBS). The samples were kept at 37-40 °C for 24 and 48 h, followed by centrifugation at 1200 rpm for 10 min. The supernatant was analyzed for Bi³⁺ by ICP-OES.

2.4 X-ray computed tomography experiments

The ability of the Bi₄C@US-tubes to attenuate X-rays was examined using a clinical 128-detector CT scanner (Brilliance iCT; Phillips Healthcare, Cleveland, OH, USA) at St. Luke's Baylor Hospital, Houston, TX. Solid samples of: (1) empty US-tubes, (2) Bi@US-tubes (the first generation CNT-material containing 2-3% bismuth by weight)⁴² and (3) Bi₄C@US-tubes were each placed in separate 1.5 mL Eppendorf tubes. Data was acquired using the following scanner parameters: tube voltage = 120 kV, pitch = 0.664, gantry rotation time = 0.33 s, mAs/mA = 150/302, reconstruction slice thickness of 0.625/0.312 cm. For quantitative analysis, three areas per sample were selected as regions of interest (ROI) and measured in Hounsfield units (HU). The reported values are the average measured for axial, sagittal, and coronal views. Analysis was performed using Osirix v. 4.1.2. 32 bit, an open source software.

3. Results and Discussion

3.1 Characterization of Bi₄@US-tubes

Bi₄C@US-tubes is a new X-ray CA material which consists of a hybrid material containing US-tubes and Bi(III) oxo-salicylate clusters (Bi₄C) which are likely located at the defect sites of the US-tubes, which are produced during the chemical cutting process as described in the

Experimental Methods section. The resulting oxidized US-tubes have a length of 20 – 80 nm as confirmed by atomic force microscopy (AFM, Figure S2) and possess defect sites that full-length SWCNTs lack. The presence of defect sites in the US-tubes is confirmed by Raman spectroscopy (Figure S3), where the D band at $\sim 1300\text{ cm}^{-1}$ is significantly larger than that of the full-length SWCNTs. The D band is often referred to as the disorder band or defect band, and it indicates disorder or rupture of the sp^2 hybridization of the full-length SWCNT structure. A small D band is also visible in the Raman spectrum of the full-length SWCNTs which is due to the hybridized vibrational mode associate with the SWCNT edges. For the US-tubes, the D band also exhibits a shoulder around 1200 cm^{-1} which is referred to as the D4 band. This band has been previously reported and attributed to $\text{sp}^2\text{-sp}^3$ bonds.^{50,51}

To synthesize the $\text{Bi}_4\text{C@US}$ -tubes, three different organic solvents were tested: THF, EtOH and DMSO, as described above. The presence of bismuth and its oxidation state (+3) was also established by ICP-OES and XPS, respectively. For ICP-OES analysis, the recovery of Bi^{3+} was first obtained using a bismuth standard solution for validation (Figure S4). The greatest bismuth concentration was obtained using THF as the solvent during the sonication step, with the resulting material containing $\sim 20\%$ bismuth by weight and $\sim 3.5\%$ atomic bismuth relative to carbon (Figure S5). Therefore, for further experiments, THF was used as the solvent of choice for the preparation of $\text{Bi}_4\text{C@US}$ -tubes. Figure 2A shows the high-resolution XPS spectrum for the $\text{Bi}_4\text{C@US}$ -tube solid material, where the two intense bands in the bismuth region are assigned to Bi 4f $7/2$ and Bi 4f $5/2$, which are the distinctive bands for Bi^{3+} .^{52,53} The binding energies acquired by XPS were determined by referencing C 1s to 284.50 eV.

^1H NMR was used to investigate whether the rigorous sonication process used to prepare the $\text{Bi}_4\text{C@US}$ -tubes sample affects the structure of the Bi_4C cluster. For this reason, the ^1H NMR

spectrum of the Bi₄C cluster before and after its sonication in THF was obtained. The two spectra showed no major differences, however, after sonication, the methyl signal of acetonitrile was not observed (Table S1), suggesting that acetonitrile, which is a ligand in the parent cluster, is displaced by another ligand, probably THF or water.

The Raman spectrum of Bi₄C@US-tubes was also obtained and compared to the spectrum of the US-tubes (Figure 2B). The D band is of slightly lower intensity for the Bi₄C@US-tubes, which is probably due to the association of the Bi₄C cluster with the US-tubes sidewall defects, which perturbs the natural vibrational modes associated with the edges and the defect sites of the US-tubes containing sp³ hybridization. The second-order overtone of the D band, the G' band (or 2D band, $\sim 2600\text{ cm}^{-1}$), also differs between the two materials. The G' band is observed for defect-free sp² carbons,⁵⁴ which might be why the intensity of the band increases slightly after the addition of the Bi₄C cluster (crystal structure shown in Figure S1). The Raman spectrum of the Bi₄C@US-tube sample also showed the D4 shoulder (previously attributed to sp²-sp³ bonds^{50,51}), as well as another shoulder around 900 cm^{-1} that the US-tubes do not show. This low intensity band has been associated with C-O-C vibrational modes, which are present in the Bi₄C cluster.^{49,55} The radial breathing mode (RBM) band, which appears around 200 cm^{-1} and can be used to determine the diameter of the CNTs, rises from the natural vibration of the CNT diameter contracting and expanding. As seen in the figure, the RBM band does not differ between the two spectra, which is expected since the nature of the US-tube was not modified by adding the Bi₄C cluster during the synthesis of Bi₄C@US-tubes.

Figure 2: (A) The characteristic XPS signals for Bi^{3+} after using THF as the solvent for the preparation of $\text{Bi}_4\text{C}@$ US-tubes. (B) Raman spectra of US-tubes and $\text{Bi}_4\text{C}@$ US tubes. * Indicates the C-O-C vibrational modes which are present for the Bi(III) oxo-salicylate cluster (Bi_4C).

TGA was used to further analyse the thermochemical and physical properties of the $\text{Bi}_4\text{C}@$ US-tubes. Figure 3 displays the characteristic TGA curve in air of (1) US-tubes, as well as the TGA curves of (2) the Bi_4C cluster alone, (3) the $\text{Bi}_4\text{C}@$ US-tubes and (4) a mixture of equivalent amounts of US-tubes and the Bi_4C cluster. The TGA data shows that US-tubes are thermally stable up to $\sim 500^\circ\text{C}$, where the sample starts to show a significant mass loss. This curve differs from the well-known combustion pattern of the pristine SWCNTs due to the presence of carboxylic groups

and other highly oxidized functional groups at the end and defect sites of the US-tubes. The Bi₄C cluster is stable up to ~160 °C, after which the first loss of mass takes place probably due to the elimination of one of the ligands, whereas the remaining ligands are removed between 250 – 350 °C with complete combustion occurring at ~350 °C. This TGA pattern has been reported before for similar Bi³⁺ compounds synthesized when BiPh₃ is mixed with 3-hydroxy picolinic acid, a derivative of salicylic acid, under different conditions.⁵⁶ In contrast, the Bi₄C@US-tubes sample is thermally stable up to ~340 °C, with just a single mass loss, indicating that the US-tubes and the Bi₄C cluster together oxidized as a single material. The difference in the temperature required to oxidize the US-tubes versus the temperature needed to oxidize the Bi₄C@US-tubes material can be explained by the presence of the high concentration of metal (Bi³⁺) in the hybrid material. Similar results have been reported previously for SWCNTs containing different concentrations of metal catalytic materials, where samples containing higher concentrations of metal impurities showed a decrease of the temperature required to oxidize the sample.^{57,58} Such phenomenon occurs when the energy released in the oxidation of one component of the sample promotes a reaction on the other component(s) in the sample.⁵⁹

For the case of the US-tubes and the Bi₄C cluster being present as a physical mixture, several mass losses were obtained as showed in Figure 4. Sudden mass losses corresponding to the Bi₄C cluster component were observed around 160, 260 and 350 °C, with final combustion occurring around 450-500 °C due to oxidation of the US-tubes component.

Figure 3. TGA curves of empty US-tubes, Bi(III) oxo-salicylate cluster (Bi₄C), and Bi₄C@US-tubes in air. At the top right is the TGA oxidation pattern for a (1:1) physical mixture of the Bi₄C cluster and the US-tubes (Bi₄C / US-tubes*). The first derivative is presented (in blue) to better show where the mass losses occur.

TEM images of Bi₄C@US-tubes showed the characteristic agglomeration of a carbon nanotube material in water which form a fiber-like network. High density spots along the US-tubes are remarkably uniform in diameter (~3-5 nm). The presence of Bi³⁺ ions at these high density spots was confirmed by EDS, as shown in Figure 4B. None of the high dense spots were found outside of the US-tubes network, demonstrating that the Bi₄C clusters are entirely associated with the US-tubes, which is consistent with the above TGA data. However, none the TGA or the TEM data revealed definitive evidence as to whether the Bi₄C clusters are all along the outer surface of the US-tubes or only at the defect sites.

Figure 4. (A) TEM images of the $\text{Bi}_4\text{C}@$ US-tubes. Yellow arrows indicate the Bi_4C clusters as confirmed by EDS. (B) EDS spectrum.

STEM images showed “bumps” on the surface of the US-tubes, suggesting that the Bi_4C clusters agglomerate on the outer surface of the US-tubes (Figure 5A). EDS mapping confirmed that the observed “bumps” contain a high concentration of bismuth, hence, showing that the Bi_4C clusters localize on the outer surface of the US-tubes (Figure 5B-E). Both TEM and STEM techniques confirmed the presence of relatively large agglomerates of bismuth, suggesting that the intact Bi_4C cluster, which is 1.7 nm in length and 0.7 nm in diameter, forms larger agglomerates on the outer surface of the US-tubes. It is possible that the interaction between the Bi_4C cluster and US-tubes is a chemical interaction. The defects sites and ends of the US-tubes contain carboxylic groups and other functional groups thanks to the mild oxidation process performed during the synthesis of the

US-tubes, and the Bi_4C cluster contains salicylic acid groups as ligands, thus hydrogen bonding can be present, as well as Bi-carboxylate covalent bonding.

Figure 5. (A) STEM images of $\text{Bi}_4\text{C}@$ US-tubes tangled in the amorphous carbon film of the sample grid. White arrows point to the Bi_4C clusters. (B) Uncolored image taken with the EDS camera, (C) EDS mapping for C, (D) EDS mapping for Bi, and (E) the overlapped image. Scale bar = 300 nm.

3.2 Biological stability studies

When using $\text{Bi}_4\text{C}@$ US-tubes as an intracellular or extracellular CA label, the material is exposed to different biological microenvironments. For such applications it is essential that the Bi_4C and

the US-tubes remain associated with one another in order to study the localization and biodistribution of the Bi₄C@US-tubes material. To help determine if the Bi₄C clusters remain associated with the US-tubes in biological environments, the material was exposed to two different biological-relevant media (PBS, and α MEM with 10% FBS), as described in the Experimental Methods section. Free bismuth was not detectable in either supernatant by ICP-OES, indicating that the hybrid material is stable in such media for up to 48 h at 37 °C. The supernatant was also analyzed for nickel by ICP-OES, one of the catalyst metals present in the US-tubes. No nickel was found in the supernatant either.

3.3 X-ray CT experiments

CT images were obtained using a clinical scanner to evaluate the ability of the Bi₄C@US-tubes to serve as a CT CA. As a control, the X-ray attenuation of US-tubes was also determined, as well as the attenuation ability of the previously reported first generation Bi@US-tubes CA material.⁴² CT images of solid samples of the three materials are presented in Figure 6, in the conventional black-and-white format, as well as in the colored image mode. As reported in Table 1, the new Bi₄C@US-tubes have an X-ray attenuation performance (HU value) of 8.3 times greater than that of the first generation Bi@US-tubes CA material, which is not unexpected due to the much higher bismuth concentration in the new CA. The US-tubes alone have an HU value of 212 ± 10 , which is probably due to the presence of catalytic metal impurities from the synthesis process, which in this case are nickel and yttrium. The HU values presented in Table 1 are those of solid samples. Thus, it is not possible to make a comparison to commercially-available radiocontrast agents since these agents are in solution and the HU value is dependent on the concentration of the CA. However, we are currently working with the use of the Bi₄C@US-tube material as an intracellular CA for mesenchymal stem cells, and preliminary results have shown that Bi₄C@US-tube-labeled

cells exhibit an HU value of around 215, which is within the range of HU values reported for soft tissue CAs available in the clinic (from 100 to 300 HU).⁶⁰

Figure 6. CT images (coronal and axial views) of solid samples of (A) US-tubes, (B) Bi@US-tubes, and (C) Bi₄C@US-tubes. Both black and white images (top) and color images (bottom) are presented to better demonstrate performance.

Table 1. Comparative HU values for solid samples of US-tubes, Bi@US-tubes, and Bi₄C@US-tubes.

Material	US-tubes	Bi@US-tubes	Bi ₄ C@ US-tubes
HU value	188 ± 12	227 ± 24	2178 ± 309

4. Conclusion

This work reports the successful synthesis and full characterization of a new hybrid material consisting of US-tubes and Bi(III) oxo-salicylate clusters (Bi₄C), abbreviated as Bi₄C@US-tubes. The hybrid material contains 20% bismuth by weight with the potential to perform as a CA for X-ray-based imaging techniques such as radiography, CT, and fluoroscopy. Its ability to attenuate X-rays has been evaluated using a clinical CT scanner and compared to empty US-tubes and a first

generation CA material, Bi@US-tubes, which contained only ~2.6 wt.% of Bi³⁺. The X-ray attenuation ability of the new Bi₄C@US-tubes is nearly 10 times greater than that of the first generation material. The stability of the Bi₄C@US-tubes material has been firmly established using biological relevant media challenges (PBS and α -MEM containing 10% FBS), which revealed no leaking of Bi³⁺ from the hybrid material for up to 48 h at 37 °C.

The present work continues to demonstrate that the pairing of Bi³⁺ and CNT materials can produce new hybrid materials with extremely high X-ray attenuation capabilities. These materials offer the opportunity to develop a new technology to internally label cells with a high concentration of Bi³⁺ for the purpose of cellular imaging (as previously assessed⁴²) and potentially *in vivo* cellular tracking by X-ray CT. The labeling and tracking of stem cells by CT would seem to be a desirable application of this new technology since the lack of intracellular radiocontrast agents is one of the limitation of using X-ray-based imaging modalities to track cells. Ongoing work is focusing on the use of Bi₄C@US-tubes as an intracellular CT CA for mesenchymal stem cells. For such studies, Bi₄C@US-tubes are well-dispersed with Pluronic®-108, a non-ionic and biocompatible surfactant that is commonly used to suspend CNTs and other nanomaterials for biological applications.^{61–63} Preliminary results have shown that Bi₄C@US-tubes can cross the cellular membrane and enter mesenchymal stem cells by simply adding a Bi₄C@US-tubes suspension to the culture medium, without the need of a transfection agent. These results have also showed that Bi₄C@US-tubes are not cytotoxic to stem cells, and that the viability, proliferation, and differentiation properties of the cells were not affected by the agent. Future studies will evaluate the potential of the Bi₄C@US-tubes as a new tool to track mesenchymal stem cells *in vivo* in real time by CT imaging.

5. Associated Content

Additional data (crystal structure of $[\text{Bi}_4(\mu_3\text{-O})_2(\text{HO-2-C}_6\text{H}_4\text{CO}_2)_8]\cdot 2\text{MeCN}$ (Bi_4C cluster), AFM of the US-tubes, Raman spectrum of the SWCNTs, percent of recovery for the digestion of a Bi^{3+} -ion standard solution, ^1H NMR data for the Bi(III) oxo-salicylate cluster, and the concentration of Bi^{3+} in the $\text{Bi}_4\text{C@US}$ -tubes by ICP-OES and XPS) can be found on the Supporting Information free of charge via the Internet at <http://pubs.acs.org>.

6. Author Information

Corresponding Author

* Lon J. Wilson. Email: durango@rice.edu; Tel: (713) 348-3476; Chemistry Department, Rice University, Houston, TX, USA

Author Contributions

All authors have given approval to the final version of the manuscript.

7. Acknowledgments

We gratefully acknowledge The Welch Foundation (Grants C-0627; LJW, C-0976; KHW) for support of this work.

8. Abbreviations

AFM; atomic force microscopy; Bi_4C , Bi(III) oxo-salicylate cluster; EDS, energy dispersive spectroscopy; CT, computed tomography; RBM, radial breathing mode; STEM, transmission scanning electron microscopy; TEM, transmission electron microscopy; TGA, thermogravimetric analysis; XPS, X-ray photoelectron spectroscopy; US-tubes, ultra-short carbon nanotubes

9. References

- (1) Schwenzer, N. F.; Springer, F.; Schraml, C.; Stefan, N.; Machann, J.; Schick, F. Non-Invasive Assessment and Quantification of Liver Steatosis by Ultrasound, Computed Tomography and Magnetic Resonance. *J. Hepatol.* **2009**, *51* (3), 433–445.
- (2) Kalender, W. A. X-Ray Computed Tomography. *Phys. Med. Biol.* **2006**, *51* (13), R29–R43.

- (3) Hounsfield, G. N. Computerized Transverse Axial Scanning (tomography). 1. Description of System. *Br. J. Radiol.* **1973**, *46* (552), 1016–1022.
- (4) Lusic, H.; Grinstaff, M. W. X-Ray-Computed Tomography Contrast Agents. *Chem. Rev.* **2013**, *113* (3), 1641–1666.
- (5) Yu, S. B.; Watson, A. D. Metal-Based X-Ray Contrast Media. *Chem. Rev.* **1999**, *99* (9), 2353–2378.
- (6) Guo, R.; Wang, H.; Peng, C.; Shen, M.; Pan, M.; Cao, X.; Zhang, G.; Shi, X. X-Ray Attenuation Property of Dendrimer-Entrapped Gold Nanoparticles. *J. Phys. Chem. C* **2010**, *114* (1), 50–56.
- (7) Udalova, T. A.; Logutenko, O. A.; Timakova, E. V.; Afonina, L. I.; Naydenko, E. S.; Yukhin, Y. M. Bismuth Compounds in Medicine. In *Third International Forum on Strategic Technologies, IFOST*, **2008**; 137–140.
- (8) Tsang, C.-N.; Ho, K.-S.; Sun, H.; Chan, W.-T. Tracking Bismuth Antiulcer Drug Uptake in Single Helicobacter Pylori Cells. *J. Am. Chem. Soc.* **2011**, *133* (19), 7355–7357.
- (9) Briand, G. G.; Burford, N. Bismuth Compounds and Preparations with Biological or Medicinal Relevance. *Chem. Rev.* **1999**, *99* (9), 2601–2658.
- (10) Gordon, M. F.; Abrams, R. I.; Rubin, D. B.; Barr, W. B.; Correa, D. D. Bismuth Subsalicylate Toxicity as a Cause of Prolonged Encephalopathy with Myoclonus. *Mov. Disord.* **1995**, *10* (2), 220–222.
- (11) Reynolds, P. T.; Abalos, K. C.; Hopp, J.; Williams, M. E. Bismuth Toxicity: A Rare Cause of Neurologic Dysfunction. *Int. J. Clin. Med.* **2012**, *03* (01), 46–48.
- (12) Bianco, A.; Kostarelos, K.; Prato, M. Applications of Carbon Nanotubes in Drug Delivery. *Curr. Opin. Chem. Biol.* **2005**, *9* (6), 674–679.
- (13) Volder, M. F. L. D.; Tawfick, S. H.; Baughman, R. H.; Hart, A. J. Carbon Nanotubes: Present and Future Commercial Applications. *Science* **2013**, *339* (6119), 535–539.
- (14) Sinha, N.; Yeow, J. T. W. Carbon Nanotubes for Biomedical Applications. *IEEE Trans. Nanobioscience* **2005**, *4* (2), 180–195.
- (15) He, H.; Pham-Huy, L. A.; Dramou, P.; Xiao, D.; Zuo, P.; Pham-Huy, C.; He, H.; Pham-Huy, L. A.; Dramou, P.; Xiao, D.; Zuo, P.; Pham-Huy, C. Carbon Nanotubes: Applications in Pharmacy and Medicine. *BioMed Res. Int. BioMed Res. Int.* **2013**, *2013* (2013), e578290.
- (16) Wu, H.-C.; Chang, X.; Liu, L.; Zhao, F.; Zhao, Y. Chemistry of Carbon Nanotubes in Biomedical Applications. *J. Mater. Chem.* **2010**, *20* (6), 1036–1052.
- (17) Smart, S. K.; Cassidy, A. I.; Lu, G. Q.; Martin, D. J. The Biocompatibility of Carbon Nanotubes. *Carbon* **2006**, *44* (6), 1034–1047.
- (18) Wang, J.; Xu, Y.; Yang, Z.; Huang, R.; Chen, J.; Wang, R.; Lin, Y. Toxicity of Carbon Nanotubes. *Curr. Drug Metab.* **2013**, *14* (8), 891–899.
- (19) Al Faraj, A.; Fauvelle, F.; Luciani, N.; Lacroix, G.; Levy, M.; Crémillieux, Y.; Canet-Soulas, E. In Vivo Biodistribution and Biological Impact of Injected Carbon Nanotubes Using Magnetic Resonance Techniques. *Int. J. Nanomedicine* **2011**, *6*, 351–361.
- (20) Ashcroft, J. M.; Hartman, K. B.; Mackeyev, Y.; Hofmann, C.; Pheasant, S.; Alemany, L. B.; Wilson, L. J. Functionalization of Individual Ultra-Short Single-Walled Carbon Nanotubes. *Nanotechnology* **2006**, *17* (20), 5033–5037.
- (21) Banerjee, S.; Hemraj-Benny, T.; Wong, S. S. Covalent Surface Chemistry of Single-Walled Carbon Nanotubes. *Adv. Mater.* **2005**, *17* (1), 17–29.
- (22) Marangon, I.; Ménard-Moyon, C.; Kolosnjaj-Tabi, J.; Béoutis, M. L.; Lartigue, L.; Alloeyau, D.; Pach, E.; Ballesteros, B.; Autret, G.; Ninjbadgar, T.; Brougham, D. F.; Bianco,

- A.; Gazeau, F. Covalent Functionalization of Multi-Walled Carbon Nanotubes with a Gadolinium Chelate for Efficient T1-Weighted Magnetic Resonance Imaging. *Adv. Funct. Mater.* **2014**, *24* (45), 7173–7186.
- (23) Richard, C.; Doan, B.-T.; Beloeil, J.-C.; Bessodes, M.; Toth, E.; Scherman, D. Noncovalent Functionalization of Carbon Nanotubes with Amphiphilic Gd³⁺ Chelates: Toward Powerful T-1 and T-2 MRI Contrast Agents. *Nano Lett.* **2008**, *8* (1), 232–236.
 - (24) Hernández-Rivera, M.; Zaibaq, N. G.; Wilson, L. J. Toward Carbon Nanotube-Based Imaging Agents for the Clinic. *Biomaterials* **2016**, *101*, 229–240.
 - (25) Liu, Z.; Yang, K.; Lee, S.-T. Single-Walled Carbon Nanotubes in Biomedical Imaging. *J. Mater. Chem.* **2011**, *21* (3), 586.
 - (26) Avti, P. K.; Talukdar, Y.; Sirotkin, M. V.; Shroyer, K. R.; Sitharaman, B. Toward Single-Walled Carbon Nanotube–gadolinium Complex as Advanced MRI Contrast Agents: Pharmacodynamics and Global Genomic Response in Small Animals. *J. Biomed. Mater. Res. B Appl. Biomater.* **2013**, *101B* (6), 1039–1049.
 - (27) Gizzatov, A.; Hernández-Rivera, M.; Keshishian, V.; Mackeyev, Y.; Law, J. J.; Guven, A.; Sethi, R.; Qu, F.; Muthupillai, R.; Cabreira-Hansen, M. da G.; Willerson, J. T.; Perin, E. C.; Ma, Q.; Bryant, R. G.; Wilson, L. J. Surfactant-Free Gd³⁺-Ion-Containing Carbon Nanotube MRI Contrast Agents for Stem Cell Labeling. *Nanoscale* **2015**.
 - (28) Liu, Y.; Hughes, T. C.; Muir, B. W.; Waddington, L. J.; Gengenbach, T. R.; Easton, C. D.; Hinton, T. M.; Moffat, B. A.; Hao, X.; Qiu, J. Water-Dispersible Magnetic Carbon Nanotubes as T2-Weighted MRI Contrast Agents. *Biomaterials* **2014**, *35* (1), 378–386.
 - (29) Peci, T.; Dennis, T. J. S.; Baxendale, M. Iron-Filled Multiwalled Carbon Nanotubes Surface-Functionalized with Paramagnetic Gd (III): A Candidate Dual-Functioning MRI Contrast Agent and Magnetic Hyperthermia Structure. *Carbon* **2015**, *87*, 226–232.
 - (30) Liu, Y.; Muir, B. W.; Waddington, L. J.; Hinton, T. M.; Moffat, B. A.; Hao, X.; Qiu, J.; Hughes, T. C. Colloidally Stabilized Magnetic Carbon Nanotubes Providing Mri Contrast in Mouse Liver Tumors. *Biomacromolecules* **2015**, *16* (3), 790–797.
 - (31) Ke, H.; Erpelding, T. N.; Jankovic, L.; Liu, C.; Wang, L. V. Performance Characterization of an Integrated Ultrasound, Photoacoustic, and Thermoacoustic Imaging System. *J. Biomed. Opt.* **2012**, *17* (5), 0560101–0560106.
 - (32) Delogu, L. G.; Vidili, G.; Venturelli, E.; Ménard-Moyon, C.; Zoroddu, M. A.; Pilo, G.; Nicolussi, P.; Ligios, C.; Bedognetti, D.; Sgarrella, F.; Manetti, R.; Bianco, A. Functionalized Multiwalled Carbon Nanotubes as Ultrasound Contrast Agents. *Proc. Natl. Acad. Sci. U. S. A.* **2012**, *109* (41), 16612–16617.
 - (33) Chen, B.; Zhang, H.; Zhai, C.; Du, N.; Sun, C.; Xue, J.; Yang, D.; Huang, H.; Zhang, B.; Xie, Q.; Wu, Y. Carbon Nanotube-Based Magnetic-Fluorescent Nanohybrids as Highly Efficient Contrast Agents for Multimodal Cellular Imaging. *J. Mater. Chem.* **2010**, *20* (44), 9895–9902.
 - (34) Welsher, K.; Liu, Z.; Daranciang, D.; Dai, H. Selective Probing and Imaging of Cells with Single Walled Carbon Nanotubes as near-Infrared Fluorescent Molecules. *Nano Lett.* **2008**, *8* (2), 586–590.
 - (35) Welsher, K.; Liu, Z.; Sherlock, S. P.; Robinson, J. T.; Chen, Z.; Daranciang, D.; Dai, H. A Route to Brightly Fluorescent Carbon Nanotubes for near-Infrared Imaging in Mice. *Nat. Nanotechnol.* **2009**, *4* (11), 773–780.

- (36) Liu, Z.; Davis, C.; Cai, W.; He, L.; Chen, X.; Dai, H. Circulation and Long-Term Fate of Functionalized, Biocompatible Single-Walled Carbon Nanotubes in Mice Probed by Raman Spectroscopy. *Proc. Natl. Acad. Sci.* **2008**, *105* (5), 1410–1415.
- (37) Liu, Z.; Li, X.; Tabakman, S. M.; Jiang, K.; Fan, S.; Dai, H. Multiplexed Multicolor Raman Imaging of Live Cells with Isotopically Modified Single Walled Carbon Nanotubes. *J. Am. Chem. Soc.* **2008**, *130* (41), 13540–13541.
- (38) De La Zerda, A.; Zavaleta, C.; Keren, S.; Vaithilingam, S.; Bodapati, S.; Liu, Z.; Levi, J.; Smith, B. R.; Ma, T.-J.; Oralkan, O.; Cheng, Z.; Chen, X.; Dai, H.; Khuri-Yakub, B. T.; Gambhir, S. S. Carbon Nanotubes as Photoacoustic Molecular Imaging Agents in Living Mice. *Nat. Nanotechnol.* **2008**, *3* (9), 557–562.
- (39) Zerda, A. de la; Liu, Z.; Bodapati, S.; Teed, R.; Vaithilingam, S.; Khuri-Yakub, B. T.; Chen, X.; Dai, H.; Gambhir, S. S. Ultrahigh Sensitivity Carbon Nanotube Agents for Photoacoustic Molecular Imaging in Living Mice. *Nano Lett.* **2010**, *10* (6), 2168–2172.
- (40) Xiang, L.; Yuan, Y.; Xing, D.; Ou, Z.; Yang, S.; Zhou, F. Photoacoustic Molecular Imaging with Antibody-Functionalized Single-Walled Carbon Nanotubes for Early Diagnosis of Tumor. *J. Biomed. Opt.* **2009**, *14* (2), 021008–021008 – 7.
- (41) Pramanik, M.; Swierczewska, M.; Green, D.; Sitharaman, B.; Wang, L. V. Single-Walled Carbon Nanotubes as a Multimodal-Thermoacoustic and Photoacoustic-Contrast Agent. *J. Biomed. Opt.* **2009**, *14* (3), 034018–034018 – 8.
- (42) Rivera, E. J.; Tran, L. A.; Hernández-Rivera, M.; Yoon, D.; Mikos, A. G.; Rusakova, I. A.; Cheong, B. Y.; Cabreira-Hansen, M. da G.; Willerson, J. T.; Perin, E. C.; Wilson, L. J. Bismuth@US-Tubes as a Potential Contrast Agent for X-Ray Imaging Applications. *J. Mater. Chem. B* **2013**, *1* (37), 4792–4800.
- (43) Ashcroft, J. M.; Hartman, K. B.; Kissell, K. R.; Mackeyev, Y.; Pheasant, S.; Young, S.; Van der Heide, P. a. W.; Mikos, A. G.; Wilson, L. J. Single-Molecule I2@US-Tube Nanocapsules: A New X-Ray Contrast-Agent Design. *Adv. Mater.* **2007**, *19* (4), 573–576.
- (44) Huang, X.; Zhang, F.; Sun, X.; Choi, K.-Y.; Niu, G.; Zhang, G.; Guo, J.; Lee, S.; Chen, X. The Genotype-Dependent Influence of Functionalized Multiwalled Carbon Nanotubes on Fetal Development. *Biomaterials* **2014**, *35* (2), 856–865.
- (45) Ruggiero, A.; Villa, C. H.; Holland, J. P.; Sprinkle, S. R.; May, C.; Lewis, J. S.; Scheinberg, D. A.; McDevitt, M. R. Imaging and Treating Tumor Vasculature with Targeted Radiolabeled Carbon Nanotubes. *Int. J. Nanomedicine* **2010**, *5*, 783–802.
- (46) Hong, S. Y.; Tobias, G.; Al-Jamal, K. T.; Ballesteros, B.; Ali-Boucetta, H.; Lozano-Perez, S.; Nellist, P. D.; Sim, R. B.; Finucane, C.; Mather, S. J.; Green, M. L. H.; Kostarelos, K.; Davis, B. G. Filled and Glycosylated Carbon Nanotubes for in Vivo Radioemitter Localization and Imaging. *Nat. Mater.* **2010**, *9* (6), 485–490.
- (47) Wu, W.; Wieckowski, S.; Pastorin, G.; Benincasa, M.; Klumpp, C.; Briand, J.-P.; Gennaro, R.; Prato, M.; Bianco, A. Targeted Delivery of Amphotericin B to Cells by Using Functionalized Carbon Nanotubes. *Angew. Chem. Int. Ed.* **2005**, *44* (39), 6358–6362.
- (48) Gu, Z.; Peng, H.; Hauge, R. H.; Smalley, R. E.; Margrave, J. L. Cutting Single-Wall Carbon Nanotubes through Fluorination. *Nano Lett.* **2002**, *2* (9), 1009–1013.
- (49) Boyd, T. D.; Kumar, I.; Wagner, E. E.; Whitmire, K. H. Synthesis and Structural Studies of the Simplest bismuth(III) Oxo-Salicylate Complex: [Bi4(μ₃-O)2(HO-2-C6H4CO₂)8]·2Solv (Solv = MeCN or MeNO₂). *Chem. Commun.* **2014**, *50* (27), 3556–3559.

- (50) Dippel, B.; Jander, H.; Heintzenberg, J. NIR FT Raman Spectroscopic Study of Flame Soot. *Phys. Chem. Chem. Phys.* **1999**, *1* (20), 4707–4712.
- (51) Ji, Z.; Dai, R.; Zhang, Z. Characterization of Fine Particulate Matter in Ambient Air by Combining TEM and Multiple Spectroscopic Techniques--NMR, FTIR and Raman Spectroscopy. *Environ. Sci. Process. Impacts* **2015**, *17* (3), 552–560.
- (52) Song, J.-M.; Mao, C.-J.; Niu, H.-L.; Shen, Y.-H.; Zhang, S.-Y. Hierarchical Structured Bismuth Oxychlorides: Self-Assembly from Nanoplates to Nanoflowers via a Solvothermal Route and Their Photocatalytic Properties. *CrystEngComm* **2010**, *12* (11), 3875–3881.
- (53) Zhao, Z.; Liu, F.; Zhao, L.; Yan, S. Preparation and XPS Study of X-Ray Photochromic Transparent BiOI/nylon11 Composite Film. *Appl. Phys. Mater. Sci. Process.* **2011**, *103* (4), 1059–1065.
- (54) Dresselhaus, M. S.; Dresselhaus, G.; Saito, R.; Jorio, A. Raman Spectroscopy of Carbon Nanotubes. *Phys. Rep.* **2005**, *409* (2), 47–99.
- (55) Socrates, G. *Infrared and Raman Characteristic Group Frequencies: Tables and Charts*; John Wiley & Sons, 2001.
- (56) Anjaneyulu, O.; Maddileti, D.; Kumara Swamy, K. C. Structural Motifs in Phenylbismuth Heterocyclic Carboxylates--Secondary Interactions Leading to Oligomers. *Dalton Trans. Camb. Engl. 2003* **2012**, *41* (3), 1004–1012.
- (57) Chiang, I. W.; Brinson, B. E.; Smalley, R. E.; Margrave, J. L.; Hauge, R. H. Purification and Characterization of Single-Wall Carbon Nanotubes. *J. Phys. Chem. B* **2001**, *105* (6), 1157–1161.
- (58) Ballesteros, B.; Tobias, G.; Ward, M. A. H.; Green, M. L. H. Quantitative Assessment of the Amount of Material Encapsulated in Filled Carbon Nanotubes. *J. Phys. Chem. C* **2009**, *113* (7), 2653–2656.
- (59) Rinzler, A. G.; Liu, J.; Dai, H.; Nikolaev, P.; Huffman, C. B.; Rodríguez-Macías, F. J.; Boul, P. J.; Lu, A. H.; Heymann, D.; Colbert, D. T.; Lee, R. S.; Fischer, J. E.; Rao, A. M.; Eklund, P. C.; Smalley, R. E. Large-Scale Purification of Single-Wall Carbon Nanotubes: Process, Product, and Characterization. *Appl. Phys. A* **1998**, *67* (1), 29–37.
- (60) De Vos, W.; Casselman, J.; Swennen, G. R. J. Cone-Beam Computerized Tomography (CBCT) Imaging of the Oral and Maxillofacial Region: A Systematic Review of the Literature. *Int. J. Oral Maxillofac. Surg.* **2009**, *38* (6), 609–625.
- (61) Mejia, J.; Tichelaar, F.; Saout, C.; Toussaint, O.; Masereel, B.; Mekhalif, Z.; Lucas, S.; Delhalle, J. Effects of the Dispersion Methods in Pluronic F108 on the Size and the Surface Composition of MWCNTs and Their Implications in Toxicology Assessment. *J. Nanoparticle Res.* **2011**, *13* (2), 655–667.
- (62) Bardi, G.; Tognini, P.; Ciofani, G.; Raffa, V.; Costa, M.; Pizzorusso, T. Pluronic-Coated Carbon Nanotubes Do Not Induce Degeneration of Cortical Neurons in Vivo and in Vitro. *Nanomedicine Nanotechnol. Biol. Med.* **2009**, *5* (1), 96–104.
- (63) Wang, X.; Xia, T.; Duch, M. C.; Ji, Z.; Zhang, H.; Li, R.; Sun, B.; Lin, S.; Meng, H.; Liao, Y.-P.; Wang, M.; Song, T.-B.; Yang, Y.; Hersam, M. C.; Nel, A. E. Pluronic F108 Coating Decreases the Lung Fibrosis Potential of Multiwall Carbon Nanotubes by Reducing Lysosomal Injury. *Nano Lett.* **2012**, *12* (6), 3050–3061.

TOC